

Habib Tabatabai Al Ghorbanpoor Matthew D. Pritzl Department of Civil Engineering and Mechanics University of Wisconsin Milwaukee

> October 2009 WHRP 09-04

WISCONSIN HIGHWAY RESEARCH PROGRAM #0092-06-06

EVALUATION OF SELECT METHODS OF CORROSION CONTROL, CORROSION PREVENTION, AND REPAIR IN REINFORCED CONCRETE BRIDGES

FINAL REPORT

Habib Tabatabai

Al Ghorbanpoor

Matthew D. Pritzl

University of Wisconsin-Milwaukee

College of Engineering and Applied Science

Department of Civil Engineering and Mechanics

Submitted the Wisconsin Department of Transportation

October 2009

ACKNOWLEDGEMENTS

The project team expresses its appreciation to Mr. Travis McDaniel and Mr. Scott Becker of Wisconsin Department of Transportation as well as the Structures Technical Oversight Committee of the Wisconsin Highway Research Program for their support, guidance, and input.

The research team would like to thank Ambassador Steel of Waukesha, WI for donating the steel reinforcement used in test specimens. We also want to thank Masonry Restoration, Inc. of Milwaukee, WI for lending their concrete demolition equipment.

The research team wishes to acknowledge UWM students Aaron Coenen, John Condon, Chin Wei-Lee, and Cory Schultz for their help during the concrete pour. We would also like to give recognition to Rahim Reshadi for his help during the concrete pour, setting up the wiring, and helping with the placement of the patch repair materials. We would also like to thank Dr. Tracy Pritzl for her assistance with chloride testing of the concrete powders.

DISCLAIMER

This research was funded through the Wisconsin Highway Research Program by the Wisconsin Department of Transportation and the Federal Highway Administration under Project 0092-06-06. The contents of this report reflect the views of the authors who are responsible for the facts and the accuracy of the data presented herein. The contents do not necessarily reflect the official views of the Wisconsin Department of Transportation or the Federal Highway Administration at the time of publication.

This document is disseminated under the sponsorship of the Department of Transportation in the interest of information exchange. The United States Government assumes no liability for its contents or use thereof. This report does not constitute a standard, specification, or regulation.

The United States Government does not endorse products or manufacturers. Trade and manufacturers' names appear in this report only because they are considered essential to the object of the document.

TECHNICAL REPORT DOCUMENTATION PAGE

1. Report No. WHRP 09-04	2. Govern No	nment Accession	3. Recipient's Ca	talog No
4. Title and Subtitle	•		5. Report Date: Oc	tober 2009
Evaluation of Select Methods of Corros Control, and Repair in Reinforced Cond			6. Performing Orga	anization Code
7. Authors Habib Tabatabai, Al Ghorbanpoor, and Matthew D. Pritzl			8. Performing Or Report No.	ganization
9. Performing Organization Name			10. Work Unit No.	(TRAIS)
University of Wisconsin - Milwaukee Department of Civil Engineering & Mechanics 3200 N Cramer Street Milwaukee, WI 53211			11. Contract or Gra WisDOT SPR # 00	
12. Sponsoring Agency Name and Address Wisconsin Department of Transportation Division of Business Services			 Type of Report Covered Final Report, 2005 	
Research Coordination Section 4802 Sheboygan Ave. Rm 104 Madison, WI 53707			14. Sponsoring Ag	
15. Supplementary Notes				
16. Abstract The objective of this study was to evaluate the effectiveness of selected techniques for corrosion prevention, control, and repair of reinforced concrete bridges. Thirty laboratory specimens were subjected to six months of accelerated corrosion testing that consisted of cyclic wet/dry cycles and an applied regulated voltage. The use of galvanic thermal sprayed zinc, galvanic embedded anodes, sealers, coatings, and epoxy repair mortar was evaluated. The long-term effectiveness of some admixtures and sealers was evaluated on nine different bridge decks across Wisconsin through an extensive analysis of chloride ingress.				
reinforcement, sacrificial anodes public t Informa 5285 Pe			. This document is h the National Tech	
19. Security Classif.(of this report) Unclassified19. Security Classif. (of this page) Unclassified			20. No. of Pages 370	21. Price

EXECUTIVE SUMMARY

This project aimed to investigate new or promising techniques to improve the repair and maintenance of reinforced concrete bridges in Wisconsin by providing controlled accelerated testing and evaluation on selected techniques and products.

Thirty laboratory specimens were subjected to six months of accelerated corrosion testing that consisted of cyclic wet/dry cycles and an applied regulated voltage. The use of galvanic thermal sprayed zinc, galvanic embedded anodes, sealers, coatings, and epoxy repair mortar was evaluated. Sixteen of the specimens received treatment prior to exposure to accelerated corrosion while the remaining fourteen specimens were cast with mixed-in chlorides and subjected to patch repair treatments after 3 months of accelerated corrosion testing. After repairs, these fourteen specimens were subjected to an additional 3 months of testing. Each treatment in question was applied to two specimens. The specimens were evaluated with respect to corrosion currents, chloride ingress, half-cell potential readings, extent of cracking, rust staining, and condition of the reinforcing steel after the conclusion of testing.

The effectiveness of admixtures and sealers was evaluated on nine different bridge decks across Wisconsin through an extensive analysis of chloride ingress. Two of the bridge decks were cast with admixtures, four of the bridge decks were treated with surface sealers at various times of exposure, and three of the bridge decks were untreated.

In the laboratory, it was found that surface applied sealers and the conjoint use of galvanic thermal sprayed zinc and coatings were much more effective in preventing the onset of corrosion than the galvanic anode cathodic protection systems alone. Specimens

v

with embedded anodes resulted in a non-uniform chloride distribution along the top bar. When used in a patch repair application, the galvanic thermal sprayed zinc and conjoint use of galvanic thermal sprayed zinc and coatings was shown to be the most effective in controlling corrosion.

In the field, it was discovered that the application of sealer at the time of construction, without any reapplication in later years, was not as effective in reducing chloride ingress. In contrast, periodic reapplication proved to be an effective means of reducing chloride ingress, even when the initial application was not made at the time of construction. The use of admixtures had varied results based on the type of admixture used.

TABLE OF CONTENTS

ACKNC	WLED	OGEMENTS	ii
TECHN	ICAL F	REPORT DOCUMENTATION PAGE	iv
EXECU	TIVE S	SUMMARY	v
		RES	
LIST OI	F TABL	ES	xxiii
CHAPT		INTRODUCTION	
1.1		al	
1.2	-	round	
1.3		em Statement	
1.4	Object	tives and Scope	
СНАРТ	ER 2: 1	LITERATURE REVIEW	
2.1		sion Induced Deterioration of Reinforced Concrete Structures	
	2.1.1	Chloride Ingress	
	2.1.2	Carbonation	
	2.1.3	Chloride Ingress and Carbonation	
2.2	Assess	sment of Deteriorated Reinforced Concrete Structures	
	2.2.1	Sounding	
	2.2.2	Chloride Ion Content	
	2.2.3	Depth of Carbonation	
	2.2.4	Half-Cell Potential Testing	
	2.2.5	Impact Echo and Ultrasonic Pulse Velocity Methods	19
2.3	Repair	r of Deteriorated Reinforced Concrete Structures	
2.4	Corros	sion Management Strategies	
	2.4.1	Corrosion Prevention	
		2.4.1.1 Coatings and Sealers	
		2.4.1.2 Admixed Corrosion Inhibitors	
		2.4.1.3 Cathodic Protection	
	2.4.2	Corrosion Control	
		2.4.2.1 Coatings and Sealers	
		2.4.2.2 Surface Applied Corrosion Inhibitors	
		2.4.2.3 Cathodic Protection	
		2.4.2.3.1 Impressed Current Cathodic Protection	
		2.4.2.3.1.1 Discrete Anode ICCP	
		2.4.2.3.1.2 Mesh Anode ICCP	
		2.4.2.3.1.3 Conductive Coating ICCP	
		2.4.2.3.1.4 Thermal Sprayed ICCP	
		2.4.2.3.2 Galvanic Cathodic Protection	
		2.4.2.3.2.1 Discrete Anode GCP	
		2.4.2.3.2.2 Thermal Sprayed GCP	

		2.4.2.3.3 Galvanic Cathodic Protection with Coatings	. 48
		2.4.2.3.3.1 Discrete Anode GCP with Coatings	. 49
		2.4.2.3.3.2 Thermal Sprayed GCP with Coatings	. 50
		2.4.2.3.4 Comparison of Cathodic Protection Systems	. 53
	2.4.3	Corrosion Passivation	. 54
		2.4.3.1 Electrochemical Chloride Extraction	. 55
		2.4.3.2 Re-alkalization	. 60
		EXPERIMENTAL APPROACH	
3.1		1	
3.2	Produc	ts/Techniques Used for Experimental Program	
	3.2.1	Embedded Galvanic Anodes	
		3.2.1.1 EA-A	
		3.2.1.2 EA-A w/A-C	
		3.2.1.3 EA-B	. 68
	3.2.2	Thermal Sprayed Galvanic Metals	. 69
		3.2.2.1 TSZ	
		3.2.2.2 TSZ w/EP-C	. 71
	3.2.3	T-SS	. 72
	3.2.4	EM	. 73
	3.2.5	Conventional Patch Repair Material	. 73
3.3	Experi	mental Plan	. 75
	3.3.1	Setup of Concrete Specimens	. 75
	3.3.2	Composition of Concrete	. 76
	3.3.3	Concrete Pour	. 79
	3.3.4	Wetting/Drying Cycles and Galvanostatic Electrical Current	. 81
	3.3.5	Monitoring	
	3.3.6	Patch Repairs	. 86
		3.3.6.1 Patch Repair Process	. 86
		3.3.6.2 Conventional Patch Material Application	. 89
		3.3.6.3 EM Application	
CHAPT	ER 4: E	EXPERIMENTAL RESULTS AND DISCUSSION	. 93
4.1	Genera		
	4.1.1	Concrete Material Data	. 93
	4.1.2	Current Monitoring	. 94
		4.1.2.1 Current Monitoring for CoP Specimens	. 95
		4.1.2.2 Current Monitoring for CoC Specimens	. 99
	4.1.3	Steel Loss	102
	4.1.4	Chloride Contents	105
		4.1.4.1 Base-Line (Virgin Concrete)	106
		4.1.4.2 CoP Specimens after 6-Months	108
		4.1.4.3 CoC Specimens at 0-Months	
		4.1.4.4 CoC Specimens after 3-Months	
		4.1.4.5 Base-Line Chlorides for Patch Repair Materials	124

		4.1.4.6 CoC Specimens after 6-Months	124
		4.1.4.6.1 Substrate Concrete	
		4.1.4.6.2 Patch Repair Materials	129
	4.1.5	Corrosion of Reinforcing Steel and Concrete Staining	132
		4.1.5.1 CoP Specimens after 6-Months	
		4.1.5.2 CoC Specimens after 3-Months	134
		4.1.5.3 CoC Specimens after 6-Months	
	4.1.6	Half-Cell Potential Data	
	4.1.7	Summary of Specimen Monitoring	138
		4.1.7.1 Summary of CoP Specimen Monitoring	138
		4.1.7.2 Summary of CoC Specimen Monitoring after 3-Months	140
		4.1.7.3 Summary of CoC Specimen Monitoring after 6-Months	141
4.2	Condit	ion Observations for CoP Specimens	
	4.2.1	Specimen #1 – TSZ (1)	143
	4.2.2	Specimen #2 – TSZ (2)	
	4.2.3	Specimen #3 – TSZ w/EP-C (1)	
	4.2.4	Specimen #4 – TSZ w/EP-C (2)	
	4.2.5	Specimen #5 – EA-A w/A-C (1)	
	4.2.6	Specimen #6 – EA-A w/A-C (2)	
	4.2.7	Specimen #7 – EA-A (1)	
	4.2.8	Specimen #8 – EA-A (2)	
	4.2.9	Specimen #9 – EA-B (1)	
		Specimen #10 – EA-B (2)	
		Specimen #11 – T-SS (1)	
		Specimen #12 – T-SS (2)	
		Specimen #13 – A-C	
		Specimen #14 – EP-C	
		Specimen #15 – Control (1)	
		Specimen #16 – Control (2)	
		CoP Discussion	
4.3		ion Observations for CoC Specimens	
		Specimen $\#17 - \text{Control}(1)$	
	4.3.2	Specimen #18 – Control (2)	
	4.3.3	Specimen #19 – TSZ w/EP-C (1)	
	4.3.4	Specimen #20 – TSZ w/EP-C (2)	
	4.3.5	Specimen $#21 - TSZ(1)$	
	4.3.6	Specimen $#22 - TSZ(2)$	
	4.3.7	Specimen #23 – EA-A (1)	
	4.3.8	Specimen #24 – EA-A (2)	
	4.3.9	Specimen #25 – EA-A w/A-C (1)	
	4.3.10	1	
		Specimen $#27 - EA-B(1)$.	
		Specimen #28 – EA-B (2)	
		Specimen #29 – EM (1) Specimen #30 – EM (2)	
		CoC Discussion	
	4.3.13		1//

CHAPT	ER 5: 1	FIELD TESTING OF BRIDGE DECKS	179
5.1		al	
5.2	Bridge	Decks Tested	
	5.2.1	Bridge B-14-0110	
	5.2.2	Bridge B-14-0115	
	5.2.3	Bridge B-14-0119	
	5.2.4	Bridge B-14-0129	
	5.2.5	Bridge B-14-0133	
	5.2.6	Bridge B-47-0110	
	5.2.7	Bridge B-47-0118	
	5.2.8	Bridge B-47-0120	
	5.2.9	Bridge B-47-0141	
5.3	Result	S	
5.4	Discus	sion	
CHAPT	ER 6: (CONCLUSIONS AND RECOMMENDATIONS	
6.1	Conclu	usions	
	6.1.1	Laboratory Specimens	
	6.1.2	Field Testing of Bridge Decks	199
	6.1.3	Overall Conclusions and Recommendations	
6.2	Recon	mendations for Future Research	
REFERI	ENCES		
APPENI	DIX A:	Reinforcing Steel and Concrete Data	
		Cylinder Breaks and Baseline Chlorides	
		CoP Chlorides	
		CoC Chlorides at 0-Months	
		CoC Chlorides at 3-Months	
		CoC Chlorides at 6-Months	
		Bridge Deck Chlorides	
IMPLEN	MENTA	TION PLAN	

LIST OF FIGURES

Figure 1: Corrosion cell	8
Figure 2: Corrosion "microcell"	8
Figure 3: Corrosion "macrocell"	9
Figure 4: Delamination of concrete	10
Figure 5: Spalling of concrete	10
Figure 6: Hammer sounding	16
Figure 7: Chain-drag sounding	16
Figure 8: Profile of chloride content vs. depth	17
Figure 9: Concrete sample displaying depth of carbonation	18
Figure 10: Half-cell potential test	18
Figure 11: Corrosion cell in concrete	21
Figure 12: Patch-accelerated corrosion in concrete	21
Figure 13: Surface applied corrosion inhibitor	30
Figure 14: Protection of reinforcing steel	30
Figure 15: Discrete Anode ICCP	33
Figure 16: Discrete anode ICCP	35
Figure 17: Conductive coating ICCP	35
Figure 18: Discrete anode GCP	38
Figure 19: Thermal sprayed GCP	40
Figure 20: Application of a top-coating to thermal sprayed zinc	50
Figure 21: Electrochemical chloride extraction	55
Figure 22: Installation of steel mesh	56
Figure 23: Application of cellulose fibers	57
Figure 24: Operational ECE system	57
Figure 25: Re-alkalization	60
Figure 26: Cut-through of EA-A	66
Figure 27: Installation of individual EA-A in CoP specimens	67
Figure 28: Placement of EA-A in CoP specimens	67
Figure 29: Application of A-C to specimen with EA-A	67
Figure 30: Close-up of EA-B	68
Figure 31: Installation of individual EA-B in CoP specimens	68

Figure 32:	Placement of EA-B in CoP specimens	68
Figure 33:	Grit blasting of the concrete surface	70
Figure 34:	Application of the thermal spray	70
Figure 35:	Check for electrical continuity	70
Figure 36:	Application of humectant activator	70
Figure 37:	Application of epoxy coating to TSZ	71
Figure 38:	Application of polyurethane coating to epoxy coating	71
Figure 39:	Application of T-SS	72
Figure 40:	Preparation of EM	73
Figure 41:	Low resistivity ionic bridge between anode and substrate concrete	74
Figure 42:	Cross section of concrete specimen	75
Figure 43:	Layers of prepared reinforcement	76
Figure 44:	Clear cover to reinforcement	76
Figure 45:	Setup of laboratory specimens for concrete pour	76
Figure 46:	Calculated chloride content profile used for mixed-in chlorides	78
Figure 47:	Pouring the bottom 5" of the CoC specimens	80
Figure 48:	Finishing the CoP specimens	80
Figure 49:	Placing the bottom layer of concrete with mixed-in chlorides	80
Figure 50:	Placement of the middle layer of concrete with mixed-in chlorides	80
Figure 51:	Corrosion cell for laboratory specimens	81
Figure 52:	Wiring/data acquisition setup	82
Figure 53:	Setup of resistors	82
Figure 54:	Project setup	83
Figure 55:	Positioning of specimens per Table 11	83
Figure 56:	Location of laboratory concrete powders	85
Figure 57:	Concrete removal	87
Figure 58:	Discoloration of concrete discovered during concrete removal	87
Figure 59:	Condition after concrete removal	87
Figure 60:	"Finger-gap" below reinforcing steel	87
Figure 61:	Cleaning of the reinforcing steel by wire brush	87
Figure 62:	Loss of ribs on reinforcing steel	87
Figure 63:	Presence of cracking exposed through routing	88

Figure 64:	Application of epoxy resin to fill cracks on horizontal face of CoC specimens	88
Figure 65:	Existing cracks on the sides of the CoC specimens	88
Figure 66:	Application of silicone sealant to routed cracks	88
Figure 67:	Application of anti-corrosion coating to reinforcing steel	89
Figure 68:	Application of bonding agent to substrate (not applied on or directly below anodes)	89
Figure 69:	Placing the conventional patch repair material	91
Figure 70:	Scoring of the conventional patch repair material after the first lift had reached final set	91
Figure 71:	Applying the concrete primer for EM	91
Figure 72:	Applying the EM	91
Figure 73:	Average corrosion currents of CoP specimens	97
Figure 74:	Individual corrosion currents of CoP Specimens	98
Figure 75:	Average corrosion currents of CoC specimens	100
Figure 76:	Individual corrosion currents of CoC specimens	101
Figure 77:	Collecting the concrete powders	105
Figure 78:	Mixing concrete powders with the extraction liquid (far) & reading potentials (near)	105
Figure 80:	Chloride contents of CoP specimens	109
Figure 81:	Agreement of actual and theoretical chlorides for Specimen #16	110
Figure 82:	Chloride profiles for Locations 7E(1), 9D(1), 9E(1), and 10D(1)	114
Figure 83:	Location of additional chloride tests for Specimen #9	114
Figure 84:	Location of additional chloride tests for Specimen #10	114
Figure 85:	Chloride contents near Location 9E	115
Figure 86:	Presence of cracking on exterior of Specimen #9.	116
Figure 87:	Presence of significant concrete staining on dissected concrete of Specimen #9	116
Figure 88:	Location of "near anode" chloride tests for EA-B	117
Figure 89:	Comparison of initial theoretical, initial, and regression chlorides for Specimen #17	120
Figure 90:	Comparison of initial theoretical, initial, 3-month, and 3-month regression chlorides for Specimen #17	
Figure 91:	CoC substrate chloride contents of Specimens #17 through #22 after 6- months	126

Figure 92: Comparison of substrate chloride contents of Specimens #17, #18, #24, and #30 after 6-months	.127
Figure 93: Horizontal cracking on exterior of Specimen #24	.127
Figure 94: Horizontal cracking on exterior of Specimen #30	.127
Figure 95: Comparison of initial theoretical, initial, 3-month, 6-month, and 6-month regression chlorides for Specimen #17	.129
Figure 96: Discoloration in EM (Location D) of Specimen #30	.131
Figure 97: CoP specimens after dissection	.133
Figure 98: CoC specimens following concrete removal after 3-months	.134
Figure 99: CoC specimens after dissection after 6-months	.135
Figure 100: Half-cell potential measurement	.136
Figure 101: Condition of CoP specimens after 3-months	.142
Figure 102: Condition of CoP specimens after 6-months	.142
Figure 103: Condition of TSZ(1) at 0-months	.143
Figure 104: Crack-mapping of TSZ(1) at 0-months	.143
Figure 105: Condition of TSZ(1) after 3-months	.143
Figure 106: Crack-mapping of TSZ(1) after 3-months	.143
Figure 107: Condition of TSZ(1) after 6-months	.143
Figure 108: Crack-Mapping of TSZ(1) after 6-months	.143
Figure 109: Dissection of TSZ(1) after 6-months	.143
Figure 110: Close-up of TSZ(1) exposed rebar	.143
Figure 111: Condition of TSZ(2) at 0-months	.144
Figure 112: Crack-Mapping of TSZ(2) at 0-months	.144
Figure 113: Condition of TSZ(2) after 3-months	.144
Figure 114: Crack-mapping of TSZ(2) after 3-months	.144
Figure 115: Condition of TSZ(2) after 6-months	.144
Figure 116: Crack-mapping of TSZ(2) after 6-months	.144
Figure 117: Dissection of TSZ(2) after 6-months	.144
Figure 118: Close-up of TSZ(2) exposed rebar	.144
Figure 119: Condition of TSZ w/EP-C(1) at 1.5-months	.145
Figure 120: Crack-mapping of TSZ w/EP-C(1) at 0-months	.145
Figure 121: Condition of TSZ w/EP-C(1) after 3-months	.145
Figure 122: Crack-mapping of TSZ w/EP-C(1) after 3-months	.145

Figure 123:	Condition of TSZ w/EP-C(1) after 6-months	145
Figure 124:	Crack-mapping of TSZ w/EP-C(1) after 6-months	145
Figure 125:	Dissection of TSZ w/EP-C(1) after 6-months	145
Figure 126:	Close-up of TSZ w/EP-C(1) exposed rebar	145
Figure 127:	Condition of TSZ w/EP-C(2) at 1.5-months	146
Figure 128:	Crack-mapping of TSZ w/EP-C(2) at 0-months	146
Figure 129:	Condition of TSZ w/EP-C(2) after 3-months	146
Figure 130:	Crack-mapping of TSZ w/EP-C(2) after 3-months	146
Figure 131:	Condition of TSZ w/EP-C(2) after 6-months	146
Figure 132:	Crack-mapping of TSZ w/EP-C(2) after 6-months	146
Figure 133:	Dissection of TSZ w/EP-C(2) after 6-months	146
Figure 134:	Close-up of TSZ w/EP-C(2) exposed rebar	146
Figure 135:	Condition of EA-A w/A-C(1) at 1.5-months	147
Figure 136:	Crack-mapping of EA-A w/A-C(1) at 0-months	147
Figure 137:	Condition of EA-A w/A-C(1) after 3-months	147
Figure 138:	Crack-mapping of EA-A w/A-C(1) after 3-months	147
Figure 139:	Condition of EA-A w/A-C(1) after 6-months	147
Figure 140:	Crack-mapping of EA-A w/A-C(1) after 6-months	147
Figure 141:	Dissection of EA-A w/A-C(1) after 6-months	147
Figure 142:	Close-up of EA-A w/A-C(1) exposed rebar	147
Figure 143:	Condition of EA-A w/A-C(2) at 1.5-months	148
Figure 144:	Crack-mapping of EA-A w/A-C(2) at 0-months	148
Figure 145:	Condition of EA-A w/A-C(2) after 3-months	148
Figure 146:	Crack-mapping of EA-A w/A-C(2) after 3-months	148
Figure 147:	Condition of EA-A w/A-C(2) after 6-months	148
Figure 148:	Crack-mapping of EA-A w/A-C(2) after 6-months	148
Figure 149:	Dissection of EA-A w/A-C(2) after 6-months	148
Figure 150:	Close-up of EA-A w/A-C(2) exposed rebar	148
Figure 151:	Condition of EA-A(1) at 0-months	149
Figure 152:	Crack-mapping of EA-A(1) at 0-months	149
Figure 153:	Condition of EA-A(1) after 3-months	149
Figure 154:	Crack-mapping of EA-A(1) after 3-months	149
Figure 155:	Condition of EA-A(1) after 6-months	149

Crack-mapping of EA-A(1) after 6-months	149
Dissection of EA-A(1) after 6-months	149
Close-up of EA-A(1) exposed rebar	149
Condition of EA-A(2) at 0-months	150
Crack-mapping of EA-A(2) at 0-months	150
Condition of EA-A(2) after 3-months	150
Crack-mapping of EA-A(2) after 3-months	150
Condition of EA-A(2) after 6-months	150
Crack-mapping of EA-A(2) after 6-months	150
Dissection of EA-A(2) after 6-months	150
Close-up of EA-A(2) exposed rebar	150
Condition of EA-B(1) at 0-months	151
Crack-mapping of EA-B(1) at 0-months	151
Condition of EA-B(1) after 3-months	151
Crack-mapping of EA-B(1) after 3-months	151
Condition of EA-B(1) after 6-months	151
Crack-mapping of EA-B(1) after 6-months	151
Dissection of EA-B(1) after 6-months	151
Close-up of EA-B(1) exposed rebar	151
Condition of EA-B(2) at 0-months	152
Crack-mapping of EA-B(2) at 0-months	152
Condition of EA-B(2) after 3-months	152
Crack-mapping of EA-B(2) after 3-months	152
Condition of EA-B(2) after 6-months	152
Crack-mapping of EA-B(2) after 6-months	152
Dissection of EA-B(2) after 6-months	152
Close-up of EA-B(2) exposed rebar	152
Condition of T-SS(1) at 0-months	153
Crack-mapping of T-SS(1) at 0-months	153
Condition of T-SS(1) after 3-months	153
Crack-mapping of T-SS(1) after 3-months	153
Condition of T-SS(1) after 6-months	153
Crack-mapping of T-SS(1) after 6-months	153
	Dissection of EA-A(1) after 6-months

Figure 189:	Dissection of T-SS(1) after 6-months	.153
Figure 190:	Close-up of T-SS(1) exposed rebar	.153
Figure 191:	Condition of T-SS(2) at 0-months	.154
Figure 192:	Crack-mapping of T-SS(2) at 0-months	.154
Figure 193:	Condition of T-SS(2) after 3-months	.154
Figure 194:	Crack-mapping of T-SS(2) after 3-months	.154
Figure 195:	Condition of T-SS(2) after 6-months	.154
Figure 196:	Crack-mapping of T-SS(2) after 6-months	.154
Figure 197:	Dissection of T-SS(2) after 6-months	.154
Figure 198:	Close-up of T-SS(2) exposed rebar	.154
Figure 199:	Condition of A-C at 0-months	.155
Figure 200:	Crack-mapping of A-C at 0-months	.155
Figure 201:	Condition of A-C after 3-months	.155
Figure 202:	Crack-mapping of A-C after 3-months	.155
Figure 203:	Condition of A-C after 6-months	.155
Figure 204:	Crack-mapping of A-C after 6-months	.155
Figure 205:	Dissection of A-C after 6-months	.155
Figure 206:	Close-up of A-C exposed rebar	.155
Figure 207:	Condition of EP-C at 1.5-months	.156
Figure 208:	Crack-mapping of EP-C at 0-months	.156
Figure 209:	Condition of EP-C after 3-months	.156
Figure 210:	Crack-mapping of EP-C after 3-months	.156
Figure 211:	Condition of EP-C after 6-months	.156
Figure 212:	Crack-mapping of EP-C after 6-months	.156
Figure 213:	Dissection of EP-C after 6-months	.156
Figure 214:	Close-up of EP-C exposed rebar	.156
Figure 215:	Condition of Control(1) at 0-months	.157
Figure 216:	Crack-mapping of Control(1) at 0-months	.157
Figure 217:	Condition of Control(1) after 3-months	.157
Figure 218:	Crack-mapping of Control(1) after 3-months	.157
Figure 219:	Condition of Control(1) after 6-months	.157
Figure 220:	Crack-mapping of Control(1) after 6-months	.157
Figure 221:	Dissection of Control(1) after 6-months	.157

Figure 222:	Close-up of Control(1) exposed rebar	157
Figure 223:	Condition of Control(2) at 0-months	158
Figure 224:	Crack-mapping of Control(2) at0-months	158
Figure 225:	Condition of Control(2) after 3-months	158
Figure 226:	Crack-mapping of Control(2) after 3-months	158
Figure 227:	Condition of Control(2) after 6-months	158
Figure 228:	Crack-mapping of Control(2) after 6-months	158
Figure 229:	Dissection of Control(2) after 6-months	158
Figure 230:	Close-up of Control(2) exposed rebar	158
Figure 231:	Rust staining on CoC specimens after 3-months	161
Figure 232:	Location of CoC specimens after replacement	161
Figure 233:	Condition of CoC specimens after completion of patch repairs	162
Figure 234:	Condition of CoC specimens after 6-months	162
Figure 235:	Condition of Control(1) after 3-months	
Figure 236:	Crack-mapping of Control(1) after 3-months	163
Figure 237:	Condition of Control(1) exposed rebar after 3-months	163
Figure 238:	Close-up of Control(1) exposed rebar after 3-months	163
Figure 239:	Condition of Control(1) after patch repairs	163
Figure 240:	Condition of Control(1) after 6-months	
Figure 241:	Dissection of Control(1) after 6-months	163
Figure 242:	Close-up of Control(1) exposed rebar after 6-months	163
Figure 243:	Condition of Control(2) after 3-months	164
Figure 244:	Crack-mapping of Control(2) after 3-months	164
Figure 245:	Condition of Control(2) exposed rebar after 3-months	164
Figure 246:	Close-up of Control(2) exposed rebar after 3-months	164
Figure 247:	Condition of Control(2) after patch repairs	164
Figure 248:	Condition of Control(2) after 6-months	164
Figure 249:	Dissection of Control(2) after 6-months	164
Figure 250:	Close-up of Control(2) exposed rebar after 6-months	164
Figure 251:	Condition of TSZ w/EP-C(1) after 3-months	165
Figure 252:	Crack-mapping of TSZ w/EP-C(1) after 3-months	165
Figure 253:	Condition of TSZ w/EP-C(1) exposed rebar after 3-months	165
Figure 254:	Close-up of TSZ w/EP-C(1) exposed rebar after 3-months	165

Figure 255:	Condition of TSZ w/EP-C(1) after patch repairs	.165
Figure 256:	Condition of TSZ w/EP-C(1) after 6-months	.165
Figure 257:	Dissection of TSZ w/EP-C(1) after 6-months	.165
Figure 258:	Close-up of TSZ w/EP-C(1) exposed rebar after 6-months	.165
Figure 259:	Condition of TSZ w/EP-C(2) after 3-months	.166
Figure 260:	Crack-mapping of TSZ w/EP-C(2) after 3-months	.166
Figure 261:	Condition of TSZ w/EP-C(2) exposed rebar after 3-months	.166
Figure 262:	Close-up of TSZ w/EP-C(2) exposed rebar after 3-months	.166
Figure 263:	Condition of TSZ w/EP-C(2) after patch repairs	.166
Figure 264:	Condition of TSZ w/EP-C(2) after 6-months	.166
Figure 265:	Dissection of TSZ w/EP-C(2) after 6-months	.166
Figure 266:	Close-up of TSZ w/EP-C(2) exposed rebar after 6-months	.166
Figure 267:	Condition of TSZ(1) after 3-months	.167
Figure 268:	Crack-mapping of TSZ(1) after 3-months	.167
Figure 269:	Condition of TSZ(1) exposed rebar after 3-months	.167
Figure 270:	Close-up of TSZ(1) exposed rebar after 3-months	.167
Figure 271:	Condition of TSZ(1) after patch repairs	.167
Figure 272:	Condition of TSZ(1) after 6-months	.167
Figure 273:	Dissection of TSZ(1) after 6-months	.167
Figure 274:	Close-up of TSZ(1) exposed rebar after 6-months	.167
Figure 275:	Condition of TSZ(2) after 3-months	.168
Figure 276:	Crack-mapping of TSZ(2) after 3-months	.168
Figure 277:	Condition of TSZ (2) exposed rebar after 3-months	.168
Figure 278:	Close-up of TSZ(2) exposed rebar after 3-months	.168
Figure 279:	Condition of TSZ(2) after patch repairs	.168
Figure 280:	Condition of TSZ(2) after 6-months	.168
Figure 281:	Dissection of TSZ (2) after 6-months	.168
Figure 282:	Close-up of TSZ(2) exposed rebar after 6-months	.168
Figure 283:	Condition of EA-A(1) after 3-months	.169
Figure 284:	Crack-mapping of EA-A(1) after 3-months	.169
Figure 285:	Condition of EA-A(1) exposed rebar after 3-months	.169
Figure 286:	Close-up of EA-A(1) exposed rebar after 3-months	.169
Figure 287:	Condition of EA-A(1) after patch repairs	.169

Figure 288:	Condition of EA-A(1) after 6-months	169
Figure 289:	Dissection of EA-A(1) after 6-months	169
Figure 290:	Close-up of EA-A(1) exposed rebar after 6-months	169
Figure 291:	Condition of EA-A(2) after 3-months	170
Figure 292:	Crack-mapping of EA-A(2) after 3-months	170
Figure 293:	Condition of EA-A(2) exposed rebar after 3-months	170
Figure 294:	Close-up of EA-A(2) exposed rebar after 3-months	170
Figure 295:	Condition of EA-A(2) after patch repairs	170
Figure 296:	Condition of EA-A(2) after 6-months	170
Figure 297:	Dissection of EA-A(2) after 6-months	170
Figure 298:	Close-up of EA-A(2) exposed rebar after 6-months	170
Figure 299:	Condition of EA-A w/A-C(1) after 3-months	171
Figure 300:	Crack-mapping of EA-A w/A-C(1) after 3-months	171
Figure 301:	Condition of EA-A w/A-C(1) exposed rebar after 3-months	171
Figure 302:	Close-up of EA-A w/A-C(1) exposed rebar after 3-months	171
Figure 303:	Condition of EA-A w/A-C(1) after patch repairs	171
Figure 304:	Condition of EA-A w/A-C(1) after 6-months	171
Figure 305:	Dissection of EA-A w/A-C(1) after 6-months	171
Figure 306:	Close-up of EA-A w/A-C(1) exposed rebar after 6-months	171
Figure 307:	Condition of EA-A w/A-C(2) after 3-months	172
Figure 308:	Crack-mapping of EA-A w/A-C(2) after 3-months	172
Figure 309:	Condition of EA-A w/A-C(2) exposed rebar after 3-months	172
Figure 310:	Close-up of EA-A w/A-C(2) exposed rebar after 3-months	172
Figure 311:	Condition of EA-A w/A-C(2) after patch repairs	172
Figure 312:	Condition of EA-A w/A-C(2) after 6-months	172
Figure 313:	Dissection of EA-A w/A-C(2) after 6-months	172
Figure 314:	Close-up of EA-A w/A-C(2) exposed rebar after 6-months	172
Figure 315:	Condition of EA-B(1) after 3-months	173
Figure 316:	Crack-mapping of EA-B(1) after 3-months	173
Figure 317:	Condition of EA-B(1) exposed rebar after 3-months	173
Figure 318:	Close-up of EA-B(1) exposed rebar after 3-months	173
Figure 319:	Condition of EA-B(1) after patch repairs	173
Figure 320:	Condition of EA-B(1) after 6-months	173

Figure 321:	Dissection of EA-B(1) after 6-months	.173
Figure 322:	Close-up of EA-B(1) exposed rebar after 6-months	.173
Figure 323:	Condition of EA-B(2) after 3-months	.174
Figure 324:	Crack-mapping of EA-B(2) after 3-months	.174
Figure 325:	Condition of EA-B(2) exposed rebar after 3-months	.174
Figure 326:	Close-up of EA-B(2) exposed rebar after 3-months	.174
Figure 327:	Condition of EA-B(2) after patch repairs	.174
Figure 328:	Condition of EA-B(2) after 6-months	.174
Figure 329:	Dissection of EA-B(2) after 6-months	.174
Figure 330:	Close-up of EA-B(2) exposed rebar after 6-months	.174
Figure 331:	Condition of EM(1) after 3-months	.175
Figure 332:	Crack-mapping of EM(1) after 3-months	.175
Figure 333:	Condition of EM(1) exposed rebar after 3-months	.175
Figure 334:	Close-up of EM(1) exposed rebar after 3-months	.175
Figure 335:	Condition of EM(1) after patch repairs	.175
Figure 336:	Condition of EM(1) after 6-months	.175
Figure 337:	Dissection of EM(1) after 6-months	.175
Figure 338:	Close-up of EM(1) exposed rebar after 6-months	.175
Figure 339:	Condition of EM(2) after 3-months	.176
Figure 340:	Crack-mapping of EM(2) after 3-months	.176
Figure 341:	Condition of EM(2) exposed rebar after 3-months	.176
Figure 342:	Close-up of EM(2) exposed rebar after 3-months	.176
Figure 343:	Condition of EM(2) after patch repairs	.176
Figure 344:	Condition of EM(2) after 6-months	.176
Figure 345:	Dissection of EM(2) after 6-months	.176
Figure 346:	Close-up of EM(2) exposed rebar after 6-months	.176
Figure 347:	Bridge B-14-0110	.180
Figure 348:	Bridge B-14-0115	.181
Figure 349:	Bridge B-14-0119	.181
Figure 350:	Bridge B-14-0129	.182
Figure 351:	Bridge B-14-0133	.183
Figure 352:	Bridge B-47-0110	.184
Figure 353:	Bridge B-47-0118	.184

Figure 354:	Bridge B-47-0120	185
Figure 355:	Bridge B-47-0141	185
Figure 356:	Obtaining chloride powders from bridge deck	186
Figure 357:	Individual Chloride Content of Locations of Bridge B-14-110	189
Figure 358:	Average Chloride Content of Locations for Bridge B-14-110	189
Figure 359:	Average chloride content of Pierce County bridge decks	190
Figure 360:	Calculated depth at which chlorides would not be present	191
Figure 361:	Bridge B-14-0110 Regression Comparison	194
Figure 362:	Bridge B-47-0110 Regression Comparison	194
Figure 363:	Comparison of chloride contents of tested admixtures	195
Figure 364:	Comparative regression analysis of tested admixtures	195

LIST OF TABLES

Table 1: Radii of penetrating ions
Table 2: Chloride limits for new construction 12
Table 3: Corrosion management strategies 23
Table 4: Chloride ion content for Bridge B-14-012927
Table 5: Chloride ion content for Bridge B-14-013327
Table 6: Polarization requirements as a function of chloride concentration at the steel surface
Table 7: Partial galvanic series of metals in seawater
Table 8: Comparison of characteristics of thermally sprayed zincs
Table 9: Characteristics of cathodic protection systems
Table 10: Products used for experimental program64
Table 11: Table of products used and application to which specimens
Table 12: Evaluation of WisDOT approved rapid setting concrete patch materials74
Table 13: State corrosion testing results 77
Table 14: Level of chlorides to be mixed into the CoC specimens 79
Table 15: Concrete Mix Design
Table 16: Steel loss of CoP Specimens after 6-months of exposure103
Table 17: Steel loss of CoC specimens after 3-months and 6-months exposure104
Table 18: Base-line chloride content of specimens 107
Table 19: Average acid-soluble chloride content of CoP specimens after 6-months108
Table 20: Calculated chloride diffusion coefficients for CoP specimens after 6- Months
Table 21: Revised chloride diffusion coefficients and top 1" chlorides for CoP specimens after 6-Months
Table 22: "Near anode" chloride contents for E.AB
Table 23: Average acid-soluble chloride contents of CoC specimens at 0-months118
Table 24: Comparison of initial theoretical and average acid-soluble chloride contents of CoC specimens at 0-months
Table 25: Calculated chloride diffusion coefficients for CoC Specimens at 0-months120
Table 26: Average acid-soluble chloride contents of CoC Specimens after 3-months 121
Table 27: Comparison of average acid-soluble chloride contents of CoC Specimens at 0- and after 3-months 122

Table 28:	Calculated chloride diffusion coefficients for CoC specimens after 3- months	.122
Table 29:	Chloride contents of conventional patch repair material	.124
Table 30:	Average acid-soluble chloride contents of CoC substrate concrete after 6- months	.125
Table 31:	Calculated chloride diffusion coefficients for substrate concrete of CoC specimens after 6-months	.128
Table 32:	Average acid-soluble chloride contents of patch materials for CoC specimens after 3-months	.130
Table 33:	Acid-soluble chloride contents of EM for Specimen #30	.131
Table 34:	Calculated chloride diffusion coefficients for patch materials of CoC specimens after 3-months	.131
Table 35:	Rating of concrete staining and reinforcing steel for CoP Specimens after 6-months	.133
Table 36:	Rating of concrete staining and exposed reinforcing steel for CoC specimens after 3-months	.134
Table 37:	Rating of concrete staining and reinforcing steel for CoC specimens after 6-months	.136
Table 38:	Half-cell potential readings of uncoated CoP specimens after 3-months	.137
Table 39:	Half-cell potential readings of uncoated CoC specimens after 3-months	.137
Table 40:	Half-cell potential readings of uncoated CoP specimens after 6-months	.138
Table 41:	Condition summary of CoP specimens after 6-months	.139
Table 42:	Condition summary of CoC specimens after 3-months	.140
Table 43:	Condition summary of CoC specimens after 6-months	.141
Table 44:	Description of bridge decks tested	.180
Table 45:	Compressive strength results of Bridge B-14-0129	.182
Table 46:	Compressive strength results of Bridge B-14-0133	.183
Table 47:	Chloride content of Dodge and Pierce County bridge decks	.187
Table 48:	Chloride content comparison of Bridge B-14-0129 at 2"	.187
Table 49:	Chloride content comparison of Bridge B-14-0133 at 2"	.188
Table 50:	Diffusion coefficients and surface chloride concentrations for each bridge deck	.190
Table 51:	Relative regression analysis for bridge decks	.192
Table 52:	Comparative regression analysis for bridge decks	.193

CHAPTER 1

INTRODUCTION

1.1 General

The expensive and on-going subject of reinforced concrete bridge maintenance and repair is a national concern. In northern deicing states such as Wisconsin, the ingress of chlorides from deicing salts continues to cause considerable deterioration that requires periodic maintenance and repair. While the associated costs are considerable and continue to rise, the inconvenience placed on society when such work is conducted is also significant.

1.2 Background

The cost of bridge maintenance and repair is a well documented issue. The U.S. Department of Transportation reports that an estimated \$78 billion to \$112 billion is required to address all structural and functional bridge deficiencies nationwide. In order to maintain current bridges through 2011, an estimated \$5.2 billion per year is needed. ⁽¹⁾

Even though the percentage of structurally deficient bridges decreased from 18% in 1995 to 15% in 1999, replacement costs had increased 12% during the same period of time. Yunovich et al. report that "...significant maintenance, repair, rehabilitation, and replacement activities for the nation's highway bridge infrastructure are foreseen over the next few decades before current construction practices begin to reverse the trend." ⁽²⁾

A 2007 report by the American Society of Civil Engineers (ASCE) gave Wisconsin a grade of "C" for the conditions of its bridges. The report also noted that Wisconsin needs \$1.75 billion for state and local bridge projects. There is also concern

in the engineering community that there is insufficient funding to keep up with the age of infrastructure. ⁽³⁾

While the cost of bridge maintenance and repair is high, the burden placed on society when a bridge is repaired or replaced is also substantial. As reported by the Federal Highway Administration (FHWA), "...when traffic impact is considered, the importance of bridges...cannot be understated."⁽⁴⁾

The reason bridges are so important is that they are key elements in the transportation system. When a bridge is taken out of service, restrictions on the system cause detours, increased travel times, and increased fuel expenses. ⁽⁵⁾

1.3 Problem Statement

While many products and techniques claim to be effective for the maintenance and repair of reinforced/prestressed/precast concrete bridge elements, not all products can perform adequately in severe field conditions over the long-term. By providing controlled accelerated testing and evaluation, this project aimed to investigate new or promising techniques to improve the repair and maintenance of reinforced concrete bridges in Wisconsin.

1.4 Objectives and Scope

After a thorough review of the available literature, a laboratory experimental program was initiated to:

• Evaluate the effectiveness of selected corrosion prevention products in new concrete construction

- Evaluate the effectiveness of selected corrosion control products in concrete members already containing chlorides
- Conduct testing of promising products not yet approved by the Wisconsin Department of Transportation

Accelerated corrosion testing was conducted on 30 small specimens that represent typical bridge deck sections. Two identical specimens were tested for each method in question (except for surface coatings) so that the validity of the tests could be confirmed. Testing included weekly wetting/drying cycles of 6% salt solution and an imposed 9V electrical charge. Corrosion currents, half-cell potential readings, crack-mapping, rust staining, and chloride ingress were analyzed. After testing, all specimens were dissected to inspect and evaluate the condition of the embedded reinforcing steel.

Sixteen (16) specimens were prepared to test various corrosion prevention methods (hereafter referred to as CoP). Testing was performed for six (6) continuous months. The CoP methods tested include:

- Activated thermal sprayed zinc (galvanic)
- Activated thermal sprayed zinc (galvanic) in conjunction with coatings
- Two (2) types of embedded anodes (galvanic)
- Embedded anodes (galvanic) in conjunction with coatings
- Tri-silane penetrating sealer
- An epoxy and polyurethane coating
- An acrylic coating

Fourteen (14) specimens were created to test various corrosion control methods (hereafter referred to as CoC). Chlorides were mixed-in to the concrete prior to

exposure. Testing was performed for three (3) months, patch repairs were made, and testing was continued for an additional three (3) months. The CoC methods tested include:

- Activated thermal sprayed zinc (galvanic)
- Activated thermal sprayed zinc (galvanic) in conjunction with coatings
- Two (2) types of embedded anodes (galvanic)
- Embedded anodes (galvanic) in conjunction with coatings
- An epoxy patch repair material

To determine the effectiveness of admixtures and sealers in reducing the ingress of chlorides, field testing of nine (9) bridge decks was performed. By removing and testing concrete powders taken at $\frac{1}{4}$ " increments to a depth of 2", the ingress of chlorides was measured and evaluated at selected locations on each bridge deck.

CHAPTER 2

LITERATURE REVIEW

2.1 Corrosion Induced Deterioration of Reinforced Concrete Structures

Design and construction faults have contributed to the defects found in R/C structures. Design faults include inadequate drainage in horizontal members, insufficient concrete cover that protects the reinforcing steel, and inappropriate concrete mixes. Construction faults include insufficient concrete cover, inadequate consolidation, improper placement techniques, and improper/insufficient joints. ⁽⁶⁾

While concrete seems like a solid material, it is not impervious. "Excess water, not required for hydration," according to Chrest et al., "eventually dries, leaving behind an interconnected network of capillary pores." ⁽⁷⁾ The diameter of these pores range from 15 to 1,000 angstrom (one angstrom equals 1×10^{-10} m). However, various ions, such as chlorides, are able to penetrate concrete and reach the reinforcing steel as their diameters are less than the capillary pores (Table 1). ⁽⁷⁾

Attacking Substance	Atomic Radius	Ionic Radius
Cl	0.99 A	1.18 A
Ca^+	1.97 A	0.99 A
Na ⁺	1.86 A	0.95 A

Table 1: Radii of penetrating ions ⁽⁷⁾

To decrease concrete permeability, materials such as pozzolans (microsilica, fly ash, silica-fume, etc.) or polymer-modified concrete can be used. Pozzolans make concrete stronger, denser, less permeable, and more cohesive. Although pozzolans can be used as a replacement for some of the cement in a concrete mix, their dosage must be controlled. When concentrations of pozzolans are too high, the concrete can suffer from plastic shrinkage cracking and reduced alkalinity as the $Ca(OH)_2$ may be used in the pozzolanic reaction. Additionally, curing must be monitored as pozzolans reduce bleed water. ^{(8), (9)}

As a repair material, polymer-modified concrete (latex-modified, acrylic, polyvinyl acetate (PVA), etc.) both reduces permeability and increases bond strength with the substrate. Polymer-modified concrete also has a better chemical resistance to alkalis and diluted acids than plain concrete. However, latex additives increase flexural creep in high humidity, reduce the modulus of elasticity of the repair material, and require prompt finishing and curing. ⁽⁸⁾

Permeability can also be reduced by specifying concrete with a low water to cementitious material ratio (w/cm). In addition, provisions for adequate concrete cover will further protect the reinforcing steel by increasing the time it takes for ions to reach it. Today, ACI 201.2R recommends a maximum w/cm of 0.40 with a minimum 2 inch clear cover for concrete exposed to deicing salts. It also reports that a design cover of 2.6 inches should be specified because of construction tolerances. ⁽¹⁰⁾

However, high concrete permeability may be an issue with older structures that were built in accordance to earlier design standards. Chrest et al. report that structures built prior to the 1977 ACI Building Code were constructed with concrete containing w/cm of 0.53 or greater, and a cover of 1.5 inches. $^{(7)}$

Nevertheless, a low w/cm alone does not automatically ensure a low permeability concrete. In addition, the concrete must be properly proportioned, well consolidated, and allowed to cure properly. ⁽¹⁰⁾

High-quality concrete is an ideal environment for reinforcing steel. When water is added to cement, the process of hydration creates a gel that binds the concrete matrix. The cement hydration process also produces calcium hydroxide $[Ca(OH)_2]$. This provides a highly alkaline (basic) environment, pH of 12 to 13, which affords protection to the reinforcing steel. ⁽⁷⁾

The highly alkaline environment afforded by the concrete leads to the formation of a passive layer on the steel surface. El-Reedy writes that "A passive layer is a dense, impenetrable film that, if fully established and maintained, prevents further corrosion of the steel. The layer formed on steel in concrete is probably part metal oxide/hydroxide and part minerals from the cement. A true passive layer is a very dense, thin layer of oxide that leads to a very slow rate of oxidation (corrosion)." ⁽¹¹⁾


"For steel in concrete," as reported by ACI Committee 222, "the passive corrosion rate is typically 0.1 μ m/yr; without the passive film, the steel will corrode at rates at least three orders of magnitude higher than this." ⁽⁹⁾

If the alkalinity of the concrete is lowered to pH 11.5, the protective oxide film will become unstable and will no longer be able to prevent the initiation of corrosion on the reinforcing steel. ⁽⁷⁾ The two main causes of the reduction in alkalinity and the associated destabilization of the oxide film are chloride attack and carbonation.

Unlike a chemical attack on concrete (sulfate attack for example, where the integrity of the concrete is destroyed), chloride ingress and carbonation do not attack the integrity of the concrete. Instead, they penetrate through the pores of the concrete, without damaging it, and attack the reinforcing steel. The associated corrosion by-products cause distress in the concrete. ⁽¹¹⁾

According to Newman, "Corrosion of reinforcement embedded in concrete is an electrochemical reaction, involving both chemical processes and the flow of electricity between various areas of steel and concrete." (8) The corrosion process is influenced by chloride-ion content, pH levels, concrete permeability, moisture, oxygen, etc. To complete a corrosion cell, an anode, a cathode, a metallic connection between the anode and cathode, an ionic path, moisture, and oxygen are required. ⁽¹²⁾

At the anode, corrosion occurs through the process of oxidation, a chemical reaction where an electron is lost. A reduction, chemical reaction where



an electron is gained, occurs at the non-corroding cathode (Figure 1). The metallic connection is provided by the reinforcing steel and the ionic path is provided by the concrete matrix (electrolyte). However, there must be sufficient moisture in the concrete matrix so that conductivity can be provided. ⁽¹²⁾

The driving force of corrosion is the difference in potential between the anode and the cathode. When this potential occurs on the same element (Figure 2), a corrosion cell termed a "microcell" is created. This potential may be created by ⁽¹⁾:

> 1. Differences in the surface of the steel bars. Since steel is an alloy created




Figure 2: Corrosion "microcell"

from various elements (most notably iron and carbon), its surface area has sites of differing electrochemical potentials.

- 2. Differences in electrolytes. These include differences in the concentration of chlorides, oxygen, moisture, hydroxides, etc.
- 3. Presence of cracks. Cracks allow the more rapid ingress of deteriorating chemicals and moisture.

When the difference in potential occurs between the upper and lower mats of reinforcing steel in a concrete slab, such as a bridge deck, a "macrocell" can be formed (Figure 3). In this case, the difference in potential occurs because of the difference in chloride ion concentrations along the reinforcement



and the amount of chloride ions reaching the upper and lower mats of reinforcing steel. Since the upper mat is more chloride contaminated, it will become anodic in regards to the lower mat when the two layers are electrically connected. The metallic connection can be provided by bent bars or chairs. "Macro-cell" corrosion, which is more widespread than "microcell" corrosion, promotes a more rapid deterioration of the structure. ⁽⁷⁾

However, the deterioration of most R/C structures can be attributed to instances of both "microcell" and "macro-cell" corrosion. ⁽⁷⁾

As corrosion occurs, the cross section of the steel is reduced and the bond between the steel and concrete is damaged. This loss of section and bond loss could reduces the strength of the R/C member. As the cross section of the steel bar is reduced, the corrosion byproducts occupy a greater volume than the original steel. ⁽¹⁾ This increase can be up to 7 times the original volume of the steel. ⁽⁹⁾ The expansion causes tensile stresses to be exerted on the surrounding concrete. As concrete is weak in




Figure 4: Delamination of concrete



Figure 5: Spalling of concrete

tension, the tensile forces cause local delamination (Figure 4, planes of cracking within the concrete), and eventually, spalling (Figure 5). ⁽¹⁾

At the anode, iron is oxidized to a ferrous state and electrons are released. ⁽¹⁾

$$2Fe \rightarrow 2Fe^{+2} + 4e^{-1}$$
 (Eq. 1)

At this time, the iron atom has lost electrons and has become a positively charged ion. ⁽¹⁾ These ions are then dissolved in the electrolyte. At the cathode, the lost electrons travel through the steel and combine with oxygen and moisture to form hydroxyl ions. ⁽⁸⁾

$$O_2 + 2H_2O + 4e^- \rightarrow 4OH^-$$
 (Eq. 2)

The ferrous ions from the anode then combine with the hydroxyl ions from the cathode to produce ferrous hydroxide. ^{(1), (8)}

$$2Fe^+ + 4OH^- \rightarrow Fe(OH)_2$$
 (Eq. 3)

Further oxidation, with the presence of oxygen and moisture, produces ferric oxide (i.e. the stable state of iron). ⁽¹⁾

$$4Fe(OH)_2 + 2H_2O + O_2 \rightarrow 4Fe(OH)_3$$
 (Eq. 4)

$$2Fe(OH)_3 \rightarrow Fe_2O_3 + 3H_2O \qquad (Eq. 5)$$

"The rate of corrosion," according to Newman, "depends on the speed of the ions traveling back from the cathode to the anode, which is a function of the electric potential of the reinforcing bars and the electrical resistance of concrete." A high current can be achieved with a high potential and low resistance. Lower levels of resistance occur when the pores of the concrete contain a lot of electrolyte (moisture and chlorides). ⁽⁸⁾

2.1.1 Chloride Ingress

The presence of chlorides not only destroys the protective oxide layer, but also fuels the corrosion process. ⁽¹³⁾ Chlorides can be introduced to concrete during mixing or service. Calcium chloride (CaCl₂) has been used as an accelerant at the time of mixing. This facilitates the casting of concrete in cold conditions and provides higher early strength concrete. Chlorides may also be found in the aggregates and mixing water. Service chloride contamination occurs because of deicing salts, proximity to sea water, and ground water salts. ⁽⁶⁾

Bohdanowicz writes that "…iron chloride hydrolysis leads to acidification of the environment and liberation of chloride ions." ⁽¹³⁾ Generally speaking, this means that the pH will be reduced as hydrogen ions, which are acidic, are produced (Eq. 6 and Eq. 7).

$$Fe + 2Cl^- \rightarrow FeCl_2 + 2e^-$$
 (Eq. 6)

$$FeCl_2 + 2H_2O \rightarrow Fe(OH)_2 + 2H^+ + 2Cl^-$$
 (Eq. 7)

The equations above show that pitting corrosion can occur even without the presence of oxygen. ⁽⁸⁾ They also show that chloride ions are not consumed and are further able to contribute to the corrosion process. In the presence of oxygen and moisture, the ferrous hydroxide produced in Eq. 7 will turn into ferric oxide (see Eq. 4 and Eq. 5).

Although it is accepted that the amount of chloride ions needed to initiate corrosion is relatively small, accepted limits on chloride ion content are not universal. Committees within the American Concrete Institute, ACI 318 and ACI 222, differ on accepted limits of chlorides (Table 2). ⁽⁹⁾

Table 2:	Chloride	limits	for	new	construction	(9))
----------	----------	--------	-----	-----	--------------	-----	---

	(Percent Chloride Ions (Cl) by mass of cement)				
Type of Structure	ACI 318-05	ASTM C 1152	ASTM C 1218		
	water soluble	acid soluble	water soluble		
Prestressed Concrete	0.06	0.08	0.06		
R/C exposed to chloride in	0.15	0.10	0.08		
service	0.15	0.10	0.08		
R/C that will be dry or protected	1.00	0.20	0.15		
from moisture in service	1.00	0.20	0.15		
Other R/C construction	0.30				

ACI 222R-01 recommends the chlorides limits specified in ASTM C1152 and ASTM C 1218. It also emphasizes "...that these are recommended limits for new construction and are not thresholds for electrochemical corrosion." ⁽⁹⁾

ACI 222R-01 also writes that it "…has taken a more conservative approach (than ACI 318) because of the serious consequences of corrosion, the conflicting data on corrosion-threshold values, and the difficulty of defining the service environment

throughout the life of a structure." ⁽⁹⁾

In Table 2 above, the levels of chlorides are presented in terms of water or acid soluble chlorides. Water-soluble chlorides are the "free" chloride ions. That is, they are the chloride ions that are not bound and are extractable in water. Acid-soluble means that all chloride ions, both bound and unbound, are measured. The amount of water-soluble chlorides is approximately 75%-80% of the acid-soluble chlorides. ⁽⁹⁾

For electrochemical corrosion, the acid-soluble corrosion threshold for reinforcing steel in concrete, in the United States, is generally considered to be 1.0 to 1.5 lb chloride ions/yd³ of concrete (0.6 to 0.9 kg/m³). ⁽⁹⁾ At 3.0 lb/yd³, severe rusting of the steel and spalling of the concrete occurs as accelerated corrosion takes place. At 7.0 lb/yd³, a major loss of steel cross section and significant distress of the concrete occurs. ⁽⁸⁾

As with chloride limits, the electrochemical corrosion threshold differs from country to country as well. According to ACI 222R-01, a threshold of 0.4% Cl⁻ by mass of cement (2.4 lb/yd³ of concrete or 1.4 kg/m^3) was proposed by the CEB (Comité Euro-International du Béton). ⁽⁹⁾

2.1.2 Carbonation

The other process that causes the corrosion of reinforcing steel is carbonation. While carbonation initially increases concrete's compressive strength, modulus of elasticity, surface hardness, and resistance to frost and sulphate attack, it has the detrimental effect of reducing the alkalinity of the concrete. ⁽¹⁴⁾ Carbonation occurs when carbon dioxide and other gases from the atmosphere penetrate through the surface pores and capillaries of concrete. When these gases react with water, carbonic acid is formed

(Eq. 8). The carbonic acid then reacts with the calcium hydroxide of the hydrated cement paste to produce calcium carbonate (Eq. 9). $^{(6)}$

$$CO_2 + H_2O \rightarrow H_2CO_3$$
 (Eq. 8)

$$H_2CO_3 + Ca(OH)_2 \rightarrow CaCO_3 + 2H_2O$$
 (Eq. 9)

A reduction in pH occurs as the calcium carbonate does not have a high alkalinity. Over time, carbonation will drop the pH levels to 8 - 9, and the passive film will start to break down as the lower alkaline concrete is not able to support the protective oxide layer. ^{(10), (12)}

Carbonation progresses inwards from the outer surface of the concrete. Initially, the outer zone of concrete is affected and over time, the depth of carbonation increases. While the rate of carbonation depends on the permeability of the concrete, it also depends on the relative humidity (RH). According to Hansson et al., "...the penetration of the CO_2 into the concrete is highest at low RH but the reaction with the $Ca(OH)_2$ takes place in solution and is, therefore, highest in saturated concrete." ⁽¹⁵⁾ Because of this, carbonation is most likely to occur at RH of 50% to 70%. In dry environments, there is not enough moisture to initiate the process. When too much moisture is present, the concrete pores are filled with water and the ingress of carbon dioxide is restricted. ⁽⁸⁾

A common problem in older structures occurs when the depth of carbonation is greater than the concrete cover provided for the reinforcing steel. When this occurs, the protective layer is destroyed and the reinforcing steel no longer has protection against moisture and oxygen.

Carbonation becomes less of an issue when higher quality (less permeable concrete) concrete with sufficient concrete cover is specified.

2.1.3 Chloride Ingress and Carbonation

In summary, the most common causes of corrosion are "a localized breakdown of the passive film on the steel by the chloride ions and a general breakdown of passivity by neutralization of the concrete from carbon dioxide." ⁽¹⁶⁾

However, chlorides and carbonation can work together. Since carbonation lowers the pH of concrete, even less chloride ions are required to initiate corrosion. ⁽⁸⁾ The carbonation process can also release bound chlorides, which means that higher concentrations of chlorides will be found in the carbonated zone. ⁽¹⁴⁾

Nevertheless, chloride ingress and carbonation do not alone cause corrosion. "While chlorides are directly responsible for the initiation of corrosion," according to ACI 222R, "they appear to play only an indirect role in determining the rate of corrosion after initiation. The primary rate-controlling factors are the availability of oxygen, the electrical resistivity, the relative humidity, all of which are interrelated, and the pH and the temperature...the chlorides can influence the pH, electrical conductivity, and the porosity. Similarly, carbonation destroys the passive film but does not influence the rate of corrosion." ⁽⁹⁾

This is evidenced by the fact that piles immersed in salt water rarely corrode. Although significant levels of water and chlorides are present, there isn't enough oxygen to support the reaction. In contrast, portions of the piles that are located in the "splashzone" often deteriorate rapidly because of the wet/dry cycles and availability of both water and oxygen. ⁽⁸⁾

Assessment of Deteriorated Reinforced Concrete Structures

To assess the condition of the reinforced concrete, many testing techniques can be utilized. Some of the more common techniques may include: sounding, chloride ion content, depth of carbonation, and half-cell potential testing. Additionally, the impact echo and ultrasonic pulse velocity methods can be used to locate voids in the concrete.

2.2.1 Sounding

Sounding techniques, utilizing a hammer (Figure 6) or a chain-drag (Figure 7), are simple and effective non-destructive techniques used to locate areas of delaminated concrete. While both techniques require a trained ear, hammer sounding requires only a rock hammer and chain-drag sounding requires a chain. The idea behind these techniques is that a change in pitch is heard when an area of delaminated concrete is encountered. By impacting the concrete through the striking of the hammer on a surface or dragging of the chain on a horizontal surface, a pitch that sounds hollow



Figure 6: Hammer sounding




Figure 7: Chain-drag sounding

can be heard. The perimeter of the delaminated area is then marked out. It should also be noted that the actual area of corrosion activity may be larger than the discovered area of delamination. ⁽¹⁷⁾

2.2.2 Chloride Ion Content

The chloride ion content of the concrete can be found in a few ways. First, a core can be taken from the concrete in question and subsequently taken back to the laboratory where a portion of the core is ground into a powder. The powder is then mixed with an extraction liquid to determine the amount of chlorides. The second way is to take concrete powders directly. This can be accomplished by drilling into the concrete in question and collecting the powders that are brought up. As before, the powder is mixed with an extraction liquid to determine the chloride content. ⁽¹⁷⁾

As discussed previously, chlorides can be introduced into concrete during mixing or service. If the powders are taken in regular intervals of depth, a profile of chloride content vs. depth can



be made (Figure 8). If the chloride content is fairly uniform, it can be concluded that the chlorides were premixed. If the chloride content displays a curve with high levels of chlorides at the surface and levels diminishing with depth, it can be concluded that the chlorides were introduced during service. $^{(6)}$

2.2.3 Depth of Carbonation

The depth of carbonation can be determined by spraying a phenolphthalein indicator onto a freshly fractured or cut concrete sample. Noncarbonated concrete (pH greater than 10) is found where areas of concrete have changed to a red or




Figure 9: Concrete sample displaying depth of carbonation

purple color while carbonated concrete remains colorless (Figure 9). ⁽¹⁷⁾ Although the phenolphthalein solution will not give the exact pH value, other solutions are able to display a gradient of colors so that a range of pH value can be indicated. ⁽¹⁸⁾

2.2.4 Half-Cell Potential Testing

Half-cell potential testing is one method used to estimate the corrosion activity of the reinforcing steel. During the corrosion process, differences in electric potential occur between the anodic half-cells




Figure 10: Half-cell potential test ⁽⁶⁾

and the cathodic half-cells. By connecting a high-impedance voltmeter between a reference electrode and exposed reinforcing steel, a full electric cell is completed and the potential can be measured (Figure 10). By taking readings in a grid pattern, a potential gradient map is produced and the extents of probable corrosion can be displayed. ^{(17), (19)}

In order to have valid readings, the continuity of the reinforcing steel should be confirmed. If continuity is not achieved, steps should be taken to provide it.

The reference electrode can either be a copper-copper sulfate (Cu-CuSo₄) or a silver-silver chloride (Ag-AgCl). The Cu-CuSo₄ electrodes have been around longer than the Ag-AgCl electrodes. Although both electrodes work well, the Cu-CuSo₄, when compared to the Ag-AgCl, has a slower response time, less stability with respect to time and temperature, and uses a liquid electrolyte. Additionally, the Cu-CuSo₄ electrodes have been known to leak. ^{(19), (20)}

If using the Cu-CuSo₄ electrode, potential readings more negative than -350mV indicate a 90% probability of corrosion activity, readings between -200mV and -350mV indicated an unknown probability of corrosion activity, and readings more positive than - 200mV indicate a 90% probability of no corrosion activity. ⁽¹⁷⁾ The Ag-AgCl electrode produces readings approximately 100mV less than the Cu-CuSo₄ electrode. ⁽²⁰⁾

2.2.5 Impact Echo and Ultrasonic Pulse Velocity Methods

In order to locate voids, cracks, and honeycombs within the concrete, the impact echo and ultrasonic pulse velocity methods can be used. By impacting the concrete surface and analyzing the pulse that is reflected from defects and boundaries, the impact echo method can predict the probability and depth of defects. By measuring the velocity (distance over time) of ultrasonic pulses between a transmitter and a receiver, the ultrasonic pulse velocity method can compare the uniformity of the concrete. If voids or cracks are present, the velocity of the pulse will be reduced. ⁽¹⁷⁾

2.3 Repair of Deteriorated Reinforced Concrete Structures

As mentioned previously, corrosion of the reinforcing steel can lead to cracking, delamination, and spalling of concrete. When spalling occurs, repairs need to be undertaken. A typical patch repair will include the following:

- saw cutting of the perimeter of the patch area (patch area should be square or rectangular in shape)
- removal of deteriorated concrete to a distance of ³/₄" to 1" behind the reinforcing steel (essentially, a finger gap)
- cleaning of the reinforcing steel by grit blasting (preferred) or wire brush (not as effective)
- coating the reinforcing steel with a corrosion-inhibiting primer
- proper preparation of the substrate to receive the patch material
- application of a bonding agent to improve bond between patch and existing concrete
- installation of patching materials
 - patch material should have very low shrinkage and have compatible coefficient of thermal expansion with substrate
- application of a protective sealer or membrane to prevent further ingress of harmful chemicals. ^{(6), (8), (21)}

Even if the aforementioned steps are followed, failure of patches can and do frequently occur. Moulzolf writes that, "...although the design may have addressed all of the critical factors necessary for a successful repair scenario, work and quality control practices associated with the various steps will control the outcome of the repair." Failures of patches can occur because of a bond failure between the substrate and repair material, poor consolidation of the repair material, damage to the substrate concrete from over-impact during demolition, and/or improper curing which can lead to plastic shrinkage cracking. ⁽²¹⁾

Even when installed properly, it is not uncommon for patch repairs to fail, or even increase in size, after only 2-5 years when utilized in chloride-contaminated concrete. This phenomena, known as patch accelerated corrosion, occurs when the once "sound" area that surrounds the initial patch repair now requires repair itself. ⁽¹²⁾

Using traditional "chip and patch" procedures, a sudden change is created in the concrete surrounding the reinforcing steel (Figures 11 and 12). This occurs when new concrete, which is chloride-free and has a high pH, is placed adjacent to old concrete, which is chloride-contaminated and has a low pH. The concrete itself creates zones of significantly

different corrosion potentials. "This

 $F_{e} \xrightarrow{2C1} \rightarrow F_{e}CI_{2} \xrightarrow{+2e}$ Anode (Corroding Area) $F_{e}CI_{2} \xrightarrow{+2OH} \rightarrow F_{e}(OH)_{2} \xrightarrow{+2C1}$ $F_{e}CI_{2} \xrightarrow{+2OH} \xrightarrow{-2OH}$ 2OH $1_{2}O_{2} \xrightarrow{+}H_{2}O \xrightarrow{+2e} \xrightarrow{-2OH}$ $Cathode (Non-Corroding Area) \xrightarrow{-1} \xrightarrow{+}$ Figure 11: Corrosion cell in concrete (12)

horide Contaminated Concrete Chloride-Free Patch $1/_2O_2 + H_2O + 2e^- \rightarrow 2OH$ Cathode node # 2e Fe - Fe2 + 20 Fe²⁺ + 2Cl → FeCl₂ $FeCl_2 + 2OH^- \rightarrow Fe(OH)_2 + 2Ch^-$ Fe2O3 + 2H2O 2Fe(OH), + 1/, O, →

Figure 12: Patch-accelerated corrosion in concrete ⁽¹²⁾

difference in corrosion potential," according to Ball and Whitmore, "is the driving force for new corrosion sites to form in the surrounding chloride-contaminated concrete." ⁽¹²⁾ The "ring anode" or "halo effect" occurs as the new concrete acts as an accelerant for corrosion. The steel bar within the new concrete acts as a cathode while the bar in the old concrete acts as an anode. Evidence of this can be seen when spalls appear next to previously completed patch repairs. ⁽¹²⁾

If significant areas of distressed and chloride-contaminated concrete exist, it may be more effective, in terms of time, cost, and duration of repair, to remove and replace. ⁽⁸⁾

One method of repair that should not be used with cracks caused by corrosion is epoxy injection. While this method works effectively on dormant cracks, it is not effective on corrosion induced cracks since it does not address the underlying corrosion issue. ^{(8), (17)}

2.4 Corrosion Management Strategies

The management of corrosion can be handled in many ways. According to Vector Corrosion Technologies (VCT), factors including "...the level of chloride contamination and carbonation, amount of concrete damage, location of corrosion activity (localized or widespread), the cost and design life of the corrosion protection system, and the expected service life of the structure" determine which corrosion management strategy to use. ⁽²²⁾

Various corrosion management strategies, such as corrosion prevention, corrosion control, and corrosion passivation, are shown in Table 3.

Corrosion Prevention	Corrosion Control	Corrosion Passivation			
Coatings	Coatings	Electrochemical Chloride			
Sealers	Sealers	Extraction			
Admixed Corrosion	Surface Applied				
Inhibitors	Corrosion Inhibitors	Re-alkalization			
Cathodic Protection	Cathodic Protection				

Table 3: Corrosion management strategies

2.4.1 Corrosion Prevention (CoP)

CoP intends that the initiation of corrosion be prevented, even in concrete containing chlorides. Some of these methods include coatings, sealers, admixed corrosion inhibitors, and cathodic protection.

2.4.1.1 Coatings and Sealers

Ball and Whitmore report that the application of protective sealers and coatings helps to prevent the initiation of corrosion. Properly applied sealers and coatings do offer a significant increase in life expectancy when installed before contamination of the concrete. ⁽¹²⁾

Sealers work by chemically reacting with the components of concrete to fill the pores; thus, making it difficult for water to penetrate the concrete surface. However, this also inhibits water vapor from exiting the concrete. Today's sealers keep water from penetrating the concrete and are now formulated to allow water vapor to exit. Coatings, meanwhile, provide barrier protection by creating a physical barrier between the concrete and the environment. ⁽²³⁾

Using a sealer or coating depends on the project requirements and service environment. Sealers are, according to Helsel, suggested "…in a moderate climate with limited freeze/thaw cycles, moisture, and salt exposure" while coating/membrane systems are suggested "...in harsher climates with subfreezing temperatures, a good deal of precipitation, and significant salt exposure..." ⁽²³⁾

Tabatabai et al. found that surface treatments (coatings) applied to the end of concrete bridge girders prior to installation in the field and before the onset of corrosion would successfully prevent beam end corrosion. ⁽²⁴⁾

As part of this project, concrete powders from four candidate bridge decks in Wisconsin that utilized a surface applied tri-siloxane masonry water repellent at various increments of time were taken from the field and analyzed in the lab. Two of the bridges were located in Dodge County and two were located in Pierce County. The bridge decks were chosen because of their frequency in sealer application. Untreated bridge decks (one in Dodge County and two in Pierce County) were also tested for comparison. A detailed discussion can be found in Section 5 of this report.

2.4.1.2 Admixed Corrosion Inhibitors

Admixed corrosion inhibitors, which are added to the concrete at the time of mixing, are used to prevent the onset of corrosion in R/C. While this section gives a brief summary of corrosion inhibitors, in general, its primary focus is on admixed corrosion inhibitors. Section 2.4.2.2 focuses on surface applied corrosion inhibitors.

Corrosion inhibitors, according to Brown, "...function by one or both of two mechanisms: by increasing the threshold concentration for aggressive species necessary for corrosion to occur or by reducing the rate of corrosion once corrosion has begun." ⁽²⁵⁾

Corrosion inhibitors, whether admixed or surface applied, exist in three basic forms: anodic inhibitors, cathodic inhibitors, and mixed inhibitors. Anodic inhibitors

minimize the anodic component of the corrosion process while cathodic inhibitors minimize the cathodic component. Mixed inhibitors prevent both the anodic and cathodic reactions. ⁽²⁶⁾ By forming a film on the steel, coating the surface of the steel, or by reacting with the chloride ions, the interaction between the chloride ions and steel will be prevented. ⁽²⁵⁾

Anodic inhibitors work by stabilizing the protective film of the concrete. It does so by interfering with the conversion of the ferrous oxide to ferric oxide. The most commonly used anodic inhibitor is calcium nitrate. By reacting with chlorides, higher concentrations of chlorides are necessary for the initiation of corrosion. ⁽¹¹⁾ When using anodic inhibitors, using too low of a concentration in aqueous environments has a possibility of producing pitting corrosion. ⁽²⁶⁾

Cathodic inhibitors work by reducing the amount of oxygen in the concrete. However, cathodic inhibitors require a large amount of material and are therefore impractical for use in concrete. Furthermore, some cathodic inhibitors slow the setting time of concrete. ^{(11), (26)} Mixed inhibitors generally work by coating the entire steel surface with a protective layer. ⁽²⁶⁾

Corrosion inhibitors can also be distinguished as passivation inhibitors, organic inhibitors, or precipitation inhibitors. ⁽²⁵⁾

The benefits of admixed corrosion inhibitors are that they slow the ingress of chlorides and may increase the level of chlorides required to initiate the corrosion process. Brown writes that admixtures slow the ingress of chloride ions "...by "clogging" the internal pore structure of the concrete, to deter movement of foreign substances by absorption or diffusion" or by ""scavenging", in which aggressive species

or oxygen in pore solution are chemically combined or adsorbed, rendering them inert in the concrete environment." ⁽²⁵⁾

In a 1999 thesis by Brown, a comparison of DCI-S by W.R Grace, Rheogard 222 by Master Builders, Inc., FerroGard 901 by Sika Corp., Catexol 1000 by Axim, MCI 2005 by Cortec, Corporation, and a control was performed. Brown concluded that "...all of the inhibitors extended the average initial time to corrosion, when compared to control concrete..." ⁽²⁵⁾

In December 2002, a report by Balaguru and Nazier compared DCI-S, Xypex C-1000, Rheocrete 222, and Ferrogard 901. The authors "…recommend the use of Xypex in decks with no cracks. The admixture provides a more dense and impermeable concrete that reduces the ingress of chemicals." ⁽²⁷⁾

Several bridges cast with various admixtures were constructed in Dodge County, WI. Specifically, Bridges B-14-0129 and B-14-0133 were used as test bridges for the Wisconsin Department of Transportation (Wis DOT).⁽²⁸⁾

In 2001, chloride testing was performed by the Wis DOT on cores that were taken from the bridge decks in 2000. ⁽²⁹⁾ The testing only examined the chloride ion content at the top steel level. ⁽³⁰⁾

Bridge B-14-0129, constructed in 1994, utilized a complex alkaline earth silicate admixture (referred to as Admix A) on the northern 1/3 of the bridge deck, an untreated control on the center 1/3, and an organic corrosion inhibiting admixture with a water-based combination of amines and esters (referred to as Admix B) on the southern 1/3 of the bridge deck. Chloride ion content for bridge B-14-0129 is shown in Table 4. ⁽³⁰⁾

Core Label	Pounds of Cl per yd ³ of concrete	Average	Rating	Product Used
P5	1.80	2.52	Good	Admix-A
P6	3.24	2.32	Poor	Aumix-A
P3	2.66	2.38	Good	Control
P4	2.09	2.30	Good	Control
P1	1.91	2.75	Good	Admix-B
P2	3.59	2.75	Poor	Auiiiix-D

 Table 4: Chloride ion content for Bridge B-14-0129⁽³⁰⁾

Bridge B-14-0133, constructed in 1995, utilized a crystalline producing admixture (referred to as Admix C) on the support structure and one-half of the bridge deck. The other half of the bridge deck was used as a control section and did not contain an admixture. Chloride ion content for Bridge B-14-0133 is shown in Table 5.⁽³⁰⁾

Core Label	Pounds of Cl per yd ³ of concrete	Average	Rating	Product Used
G1 G2	3.13 2.55	2.84	Fair Good	Admix-C
G3 G4	3.53 9.04	6.285	Poor Bad	Control

 Table 5: Chloride ion content for Bridge B-14-0133 (30)

The age and construction of these bridges ideally lent themselves to additional testing. As such, testing was performed in this study to establish chloride concentration profiles, to calculate a chloride diffusion coefficient for each section in which admixtures were used, and to determine the surface chloride concentration for each bridge. A more detailed discussion on these bridge decks can be found in Section 5.

Another commercially available admixture is Hycrete. The water-based product is reportedly hydrophobic and reacts within the concrete matrix to fill in cracks and capillaries to provide a polar monomolecular barrier that protects the steel. ⁽³¹⁾

In a 2000 study at the University of Connecticut, Goodwin et al. reported that adding the DAS (ammonium form of Hycrete) or DSS (Hycrete admixture) prototype chemicals to the concrete "…produced significant improvements in corrosion protection compared with the control concrete and with the two commercial inhibitors. After about 24 months of corrosion monitoring, specimens with the two prototype chemicals showed no sign of corrosion. For specimens with a saw-cut or preformed crack, the chemicals produced greatly reduced amounts of reinforcement corrosion." ^{(32), (33)}

The two commercial inhibitors in the study were DCI-S and Rheocrete 222. The study also concluded that the DSS prototype chemical performed slightly better than the DAS prototype chemical. ^{(32), (33)}

A 2007 Virginia Transportation Research Council (VTRC) research report by Sharp and Ozyildirim stated that the conjoint use of fly ash and Hycrete DSS in concrete "considerably restricted" chloride ingress. Furthermore, the report stated that, "If the field performance confirms the laboratory test results of this study, the use of Hycrete DSS is expected to lead to extended service life and to aid in minimizing maintenance costs." ⁽³⁴⁾

2.4.1.3 Cathodic Protection

The basis of corrosion theory is that a measurable difference in potential exists between the anodic and cathodic areas. Cathodic protection (CP) makes use of an externally applied potential, which acts as the anode, to shift all of the reinforcing steel into a cathodic and protected state. ⁽⁶⁾

When used in new construction or structures in which the initiation of corrosion has not yet occurred, low levels of applied current are needed to prevent the initiation of

corrosion. When used in structures where corrosion is on-going, higher levels of current are required. ⁽³⁵⁾

In order to prevent the initiation of corrosion, current levels significantly less than 0.5mA/m^2 of steel surface are required. When chloride levels reached 6 lb/yd³, current levels of 0.5mA/m^2 were able to mitigate the on-going corrosion. Using current levels of $0.5 \text{ to } 2.0 \text{mA/m}^2$ were effective in preventing the initiation of corrosion when chloride concentrations of 10 times the corrosion threshold were used. ⁽³⁵⁾

A more detailed discussion of CP can be found in Section 2.4.2.3.

2.4.2 Corrosion Control (CoC)

CoC strategies, according to VCT, are intended to "...stop on-going corrosion activity or provide a significant reduction in the corrosion rate and an increased service life of the rehabilitated structure." Coating, sealers, surface applied corrosion inhibitors, and cathodic protection systems are examples of corrosion control. ⁽²²⁾

2.4.2.1 Coatings and Sealers

Although coatings and sealers work well for corrosion prevention, Tabatabai et al. found that surface applied treatments offered limited effectiveness when applied after the onset of corrosion. ⁽²⁴⁾ Once contamination begins and signs of corrosion distress appear, Whitmore and Ball report that "...barrier systems will generally have a limited impact on the service life of the structure." ⁽¹²⁾

2.4.2.2 Surface Applied Corrosion Inhibitors

As mentioned previously, surface applied and admixed corrosion inhibitors act much alike. The difference is that surface applied corrosion inhibitors are applied on the concrete surface after the concrete has been placed and cured.

Surface applied corrosion inhibitors work by migrating through the pores of the concrete to seek out and protect the reinforcing bars (Figures 13 and 14) from the ingress of harmful chemicals. ⁽³⁶⁾




Figure 13: Surface applied corrosion inhibitor ⁽³⁶⁾




Figure 14: Protection of reinforcing steel ⁽³⁶⁾

While much research and testing has been performed on surface applied corrosion inhibitors, the results have varied. Newman writes that, "...the only practical method of applying them in concrete repair is to coat the concrete surface and hope that the chemicals migrate deep enough to reach the steel." ⁽⁸⁾

A 2004 VTRC report by Sharp investigated the use of FerroGard 903 by Sika, Corp. and TPS-II by Surtreat International. The study by Sharp concluded that "The topical application of inhibitor for corrosion mitigation is ineffective" and that "The vacuum/pressure injection method shows promise, but the methodology requires refinement." ⁽³⁷⁾ It should be noted, however, that the experimental program utilized 15 lb/yd³ of NaCl around the top layer of reinforcing and none in the bottom layer. A 2004 thesis by Cook investigated the use of Aquron-7000/CPT 2000 by Aquron, AXIM Post III by Axim, MCI 2020M/MCI 2022 by Cortec, Postrite by Grace, Sonocrete-Corrosion Inhibitor by Master Builders, and FerroGard 903 by Sika. Cook concluded that the products tested "...did initially help delay and slow the corrosion process. As would be expected, none of these products totally stopped or reversed the corrosion process..." It also concluded that "...there is no significant benefit in applying any of the tested corrosion inhibitors to the surface of reinforced concrete when the chloride contamination levels are above 0.5% by weight of cement..." ⁽³⁸⁾

Projects both in the United States and the United Kingdom by C-Probe Systems Limited have utilized surface applied corrosion inhibitors when half-cell potentials (Cu-CuSo₄) were more negative than -200mV and chloride content was less than 1.0% by weight of cement. ⁽³⁹⁾

Reportedly, the amino-alcohol (Ferrogard 903) and amine carboxylate (MCI 2020) technologies can be used when the chloride content at the reinforcing steel was measured up to 6 lbs/yd^3 . ⁽⁴⁰⁾

2.4.2.3 Cathodic Protection

"Based on extensive Government and private industry research, the Federal Highway Administration (FHWA) concluded that CP is the only rehabilitation technique that has been proven to stop corrosion is salt-contaminated bridge decks regardless of the chloride content of the concrete."⁽⁴¹⁾

CP provides a high level of corrosion management by using electrical current to shift the potential of the reinforcing steel in the negative direction. Corrosion can be

mitigated if the potential is shifted far enough so that the reinforcement becomes cathodic and is unable to lose electrons. In the absence of the anodic reaction of iron, the electrochemical cell will not exist. ⁽⁴²⁾

CP is predominantly used when corrosion of the reinforcement is caused by the presence of chlorides. It is not generally used with carbonated concrete, according to Kay, "…because of the increase in electrical resistivity which occurs with carbonation and also because damage is often limited to a small portion of the surface where cover is low. Conventional repair techniques can provide a durable and economical solution in such situations." ⁽⁶⁾

As a repair method, Kepler et al. stated that cathodic protection is advantageous as "...only spalls and detached concrete need to be repaired. Chloride contaminated concrete that is still sound can remain in place because the cathodic protection system will prevent further corrosion, and, in fact, reduce the concentration of chloride ions adjacent to protected reinforcing bars..." ⁽⁴²⁾

In order to inhibit the anodic (corrosive) reactions of corroding steel in normal conditions, the National Association of Corrosion Engineers (NACE) uses a 100 mV polarization criterion. This polarization is measured by estimating "off potential." This "off potential" is measured from the potential decay of the steel that occurs after the protective current is turned off. The initial potential, otherwise known as "instant off" or "IR-free," should be taken 100 to 1,000 msec after the protective current is shut off. The ioff potential" is calculated from the difference between the "IR-free" potential and the potential found four hours later. ⁽⁴³⁾


As displayed in Table 6, the 100 mV polarization criterion may be excessive in low corrosive environments and insufficient in severely corrosive environments. ⁽⁴³⁾

Chloride (Concentration	Polarization Needed	
$(lb/yd^3 \text{ concrete})$	(kg/m ³ concrete)	(mV)	
<1	<0.6	0	
1-2	0.6-1.2	60	
2-5	1.2-3.0	80	
5 - 10	3.0 - 6.0	100	
10 - 20	6.0 - 12.0	150	

CP systems are divided into two categories: impressed current cathodic protection (ICCP) and galvanic cathodic protection (GCP).

2.4.2.3.1 Impressed Current Cathodic Protection

ICCP systems (Figure 15) use an external power source that provides the necessary current, $5 - 20 \text{ mA/m}^2 (0.5 - 1.9 \text{ mA/ft}^2)$, to mitigate corrosion activity. ⁽³⁵⁾ An ICCP system consists of "the reinforcement to be protected, an anode, a power source, concrete



surrounding the steel, a monitoring system, and cabling to carry the system power and monitoring signals." ⁽⁴²⁾

In an ICCP system, anodes are permanently installed and connected to the positive (+) charge from the AC/DC rectifier. The steel is connected to the negative (-) terminal of the rectifier. Thus, the steel is forced into a cathodic and protective condition

through this connection to the negative charge. ⁽¹²⁾ The current flows through the electrolyte that contains alkalis and allows the transfer of current from the anode to the steel reinforcement. ⁽⁴²⁾ Since the driving voltage of an ICCP system is supplied by the DC power source, the anode does not have to be more active than the steel it protects. ⁽⁴⁴⁾ Therefore, the anode used is non-consumable, and should not corrode. ⁽⁴⁵⁾

Because the system is connected to an outside power source, its voltage and current are adjustable. Thus, ICCP can be used on any sized structure or in almost any resistivity environment. ⁽⁴²⁾

However, one requirement of the ICCP system is that power always needs to be supplied. Since the system is based on DC power to supply the driving voltage, protection will be lost if the system breaks down or loses it power.

Although the upfront material and application cost is high, a low cost per square foot of protection can be achieved by spreading the cost over the life of the project. ⁽¹²⁾ If properly maintained and monitored, ICCP systems are believed to provide 25+ years of protection. ⁽⁴⁶⁾

ICCP is generally not recommended for use with prestressed or post-tensioned concrete because of concerns of hydrogen embrittlement. The impressed current can cause the hydrogen produced by the cathodic reaction to migrate into the steel rather than into the surrounding concrete environment. The formation of hydrogen makes the steel brittle and may cause premature failure. Nevertheless, Kepler reported that it may "…be avoided through careful monitoring and control of the amount of steel polarization." ⁽⁴²⁾

Today, a few ICCP system installation techniques are used: a discrete anode system, a mesh anode system, a conductive coating system, and a thermal sprayed metal

system. The discrete anode system provides local protection, while the mesh anode, conductive coating, and thermal (or arc) sprayed metal systems provide global protection.

2.4.2.3.1.1 Discrete Anode ICCP

The discrete anode system utilizes anodes that are permanently embedded in the concrete structure (Figure 16). The individual anodes are connected to one another by titanium feed wire and then connected to the DC power source. ⁽⁴⁶⁾




Figure 16: Discrete anode ICCP⁽⁴⁶⁾


2.4.2.3.1.2 Mesh Anode ICCP

In the mesh anode system, a metallic mesh with integrated anodes is attached to the exposed concrete surface and connected to a rectifier. A thin layer of concrete (i.e. shotcrete) is applied over the mesh and embeds the anodes into the system. Many state and local transportation agencies have accepted the conjoint use of a titanium mesh anode with a concrete overlay as "…a durable anode for use in impressed current CP of reinforced concrete bridge decks." ⁽¹⁾

2.4.2.3.1.3 Conductive Coating ICCP

The conductive coating system utilizes conductive fillers in the coating itself (Figure 17). The conductive coating is applied to the concrete surface and connected to the rectifier by means of





feed-wires. The conductive coatings can be over-coated for performance and aesthetic reasons. ⁽⁶⁾

2.4.2.3.1.4 Thermal Sprayed ICCP

The thermal or arc sprayed metal application includes the melting of a metal or alloy wire and the spraying of the molten metal to the concrete with compressed air. To provide cathodic protection, a connection is made between the rectifier and the thermal sprayed metal by means of a stainless steel or copper plate that is secured to the concrete surface prior to spraying. The plate is secured with an epoxy. ⁽¹⁾ The sprayed metal is either a zinc or catalyzed titanium. ⁽⁴⁷⁾

2.4.2.3.2 Galvanic Cathodic Protection

In a GCP system, a connection is made between two dissimilar metals. One of the metals has a higher potential for corrosion (i.e. more electronegative) while the other metal is more noble and has a lower potential for corrosion (i.e. more electropositive). The reinforcing steel, having a lower corrosion potential, is protected as the metal with a higher corrosion potential will sacrifice itself by corroding in preference to the reinforcing steel. As the sacrificial anode now supplies the electrons and thus corrodes, an electrical current is produced. This effectively makes the reinforcing steel a protected cathode. ^{(12), (45)}

While the use of GCP is relatively new to reinforced concrete, the idea behind galvanic cathodic protection is not. Its first use is credited to Sir Humphrey Davy in

1824. Davy successfully protected the copper sheeting of navy ship hulls from corrosion in seawater by attaching iron anodes to them. ⁽¹⁾

To understand the performance of sacrificial anodes, a partial galvanic series of metals in seawater is presented in Table 7.

Table 7: Partial galvanic series of metals in seawater ⁽⁴⁵⁾				
Electropositive				
(lower corrosion potential)				
Platinum				
Titanium				
Stainless Steel				
Monel				
Copper				
Lead				
Iron, Cast Iron, or Steel				
Cadmium				
Zinc				
Aluminum				
Magnesium				
Electronegative				
(higher corrosion potential)				

While the voltage of galvanic system is fixed, the amount of current supplied is dependent on the surrounding environment. Since the current output changes with the corrosiveness of the environment, a higher current is expected in more corrosive or conductive environments. This means that "...current output will likely exhibit a daily and seasonal variation based on moisture and temperature changes." Because of the fixed voltage, galvanic systems may not reach the accepted 100mV depolarization criteria for cathodic protection. However, "...a significant level of corrosion protection is nevertheless provided to the steel." Additionally, less current is needed as time goes on since "...hydroxyl ions are generated at the steel (thus increasing the pH), chloride ions migrate away from the steel, and passivity develops over time." ⁽¹²⁾

The advantages of GCP systems are that they are self-powered and require little to no monitoring and maintenance. Moreover, the low current provided by the sacrificial anodes allows them to be used on prestressed and post-tensioned concrete. The problem with GCP systems is that they have a limited life of 10-20 years because the anode is being sacrificed and consumed.⁽⁴⁸⁾

The use of two types of galvanic cathodic protection systems has been studied: discrete (embedded) anodes and thermal sprayed metals.

2.4.2.3.2.1 Discrete Anode GCP

Discrete (embedded) anode GCP systems provide local protection and have been used in patch repair to stop the "ring anode" or "halo" effect. The discrete sacrificial anodes are intended to function because of the differing




Figure 18: Discrete anode GCP ⁽¹²⁾

electric potentials between the steel and the anode. When attached to the newly cleaned steel at the perimeter of the patched area, the sacrificial anode, being more electronegative, will corrode in preference to the steel in the adjacent, non-patched area (Figure 18). Because of this, the "ring anode" or "halo" effect is supposed to be mitigated. ⁽¹²⁾

Since the anodes are an addition to the patch, normal repair techniques can still be used. ⁽⁴⁹⁾ In 2001, the Concrete Innovations Appraisal Service (CIAS) reported that

embedded anodes have "... considerable promise as a strategy to increase the life of concrete repairs" and "...provide an economical method to perhaps eliminate a repair cycle for projects with corrosion related problems." ⁽⁵⁰⁾

The CIAS also reported that the embedded anodes are "...a viable and costeffective means of extending the longevity of concrete repairs necessitated by chlorideinduced corrosion in reinforced concrete structures...This technology seems to offer the best alternative at a low cost to extend the life of concrete repairs." ⁽⁵⁰⁾

The use of sacrificial anodes have also been studied by the Vermont Agency of Transportation (VAOT). Between July 2, 2001 and November 15, 2002, "Anodes were installed in all bridges of the Middlesex-Bolton AC IM 089-2(26) project where new concrete was placed next to existing concrete to provide protection against corrosion to the reinforcing steel. No significant difficulties were encountered with the installation of the anodes." In all, 817 anodes and 20 test kits were installed. ⁽⁵¹⁾

In early 2005, Jerry McMahan of the VAOT released a report on the results. The report evaluated the test kits, which were monitored for approximately 2 years. McMahan concluded that "There are wide differences in monitored current, and presumably in corrosion rates and the amount of protection provided. Applying the 'weakest link' concept would indicate that the ... devices will really only provide significant protection to concrete for 5 to 7 years." ⁽⁵²⁾

In the Midwest, the use of discrete anodes has already been approved by some states. The Michigan Department of Transportation (MDOT) has included several embedded anodes in its "Qualified Products List." ⁽⁵³⁾ In addition, the Illinois Department of Transportation (IDOT) has included a commercial embedded anode in its "Products

Evaluation Circular." ⁽⁵⁴⁾ Field tests installed in June, 2001 were evaluated by IDOT in 2007. Joe Vespa, Development Studies Engineer for the IDOT, responded that, as of the inspections conducted in late 2007, all of the patches, control and with embedded anodes, were in very good condition. ⁽⁵⁵⁾

The concrete patch materials should have a resistivity below 15,000 ohm-cm. Additionally, the repair materials should have limited polymer modification and silica fume content. ⁽⁴⁹⁾ These provisions are made as polymers are electric insulators and silica fume increases the resistivity of the concrete, thereby reducing the available current.

The spacing of the anodes, found in the supplier's guidelines, depends on the chloride content of the concrete and the amount of reinforcement. According to the manufacturers, the service life of sacrificial embedded anodes is estimated to be 10 to 20 years. ^{(48), (56)} The cost of each anode ranges from \$25-\$29. ^{(57), (58)}

2.4.2.3.2.2 Thermal Sprayed GCP

Another form of sacrificial cathodic protection is metalizing. Metalizing, or thermal spraying, is a method where a metal is melted and sprayed onto a prepared substrate (Figure 19). The most common method is the wire arc method because of its reported




Figure 19: Thermal sprayed GCP⁽⁵⁹⁾

efficiency and low cost. This procedure uses two wires of metal that are energized to an opposing polarity using DC power and are brought together at the gun. A short circuit is created as the wires get close, which causes an arc. The high temperature created at the

arc melts the wires while high-pressurized air atomizes and applies the melted metal as a coating to the substrate. (47)

Thermally sprayed galvanic coatings can be used for repair in two ways:

- 1. Without Reprofiling: "In this system, concrete excavations in which the reinforcing steel is partially uncovered are not filled with repair mortar and the initial concrete surface is not restored. With this method, the zinc layer is directly sprayed onto the exposed steel and on to the concrete surfaces."
- 2. With Reprofiling: "...the application of zinc coating is possible when either no spalling of the concrete has occurred or spalls have been repaired." A thermal spray coating is applied to the surface of the concrete and an electrical connection is made to the rebar embedded in the concrete. ⁽⁶⁰⁾

(60)

ī

Table 8 summarizes the different characteristics of thermally sprayed zincs.

Characteristics of Thermally Sprayed Zinc	Galvanic Without Reprofiling	Galvanic with Reprofiling	Impressed Current
Reprofiling Required	No	Yes	Yes
Current Measurable	No	Yes	Yes
Protective Capacity Detectable	No	Yes	Yes
Current Adjustable	No	Conditional	Yes
Installation in dry environment	No	No	Yes
Installation in humid environment	Yes	Yes	Possible, but not required

Reportedly, "The entire coating process, blast cleaning, metal spraying, and sealing is completed in one work day. Metalizing can be applied virtually year round and in nearly any shop or field environment." This means that metalized coatings can be applied in both warm and cold temperatures and because it is spray applied, the process

can be used on structures of any size or shape. Additionally, the metals used do not contain volatile organic compounds (VOCs). ⁽⁶¹⁾

For reinforced concrete structures, the most commonly used thermal sprayed anodes are pure zinc and an aluminum-zinc-indium alloy (Al-Zn-In). The Al-Zn-In alloy consists of 80% aluminum, 20% zinc, and 0.2% indium. ⁽⁶²⁾ According to a report, a 20-year life can be expected by using a thickness of 300-500 μ m (12 mils). ⁽⁶⁰⁾ Another thermal sprayed metal is the 85/15-alloy (85% zinc and 15% aluminum) ⁽⁶³⁾

When applied, thermal sprayed zinc has a bright silver gray color. Over time, the color dulls and approaches the color of the concrete. The bond strength between the zinc and the concrete reportedly ranges from 170 to 300 psi. The corrosion product is a white zinc oxide and has "little effect" on the appearance. ⁽⁶⁴⁾ The Al-Zn-In alloy also has a gray-silver color when applied to the concrete. Its corrosion products are also white. ⁽⁶²⁾

Some investigators believe that the melted metals also act as a barrier coating and improve aesthetic appearance. ⁽¹³⁾ When scratched, the metalized coating reportedly continues to give cathodic protection as long as any metal remains in the area. ⁽⁶⁴⁾

When comparing zinc and the Al-Zn-In alloy, zinc is more malleable, inexpensive, and can be obtained from several sources. ⁽⁶⁵⁾ However, the open circuit potential of the Al-Zn-In alloy is higher than zinc. ⁽⁶⁶⁾

To have maximum efficiency, the zinc should have the highest purity possible. "For CP," according to Costa, President of Electro Tech CP, "it is important to select the purest alloy available with iron (Fe) content less than 14 ppm. Higher iron contamination could lead to passivation of the anode." ⁽⁶⁶⁾

Alloys of zinc and aluminum combine the benefits of both pure zinc and pure aluminum. ⁽⁶¹⁾ Although pure zinc is electrochemically active and provides a high level of cathodic protection, its high electrochemical activity also means that the zinc will corrode, thus depleting the coating. Aluminum coatings, on the other hand, are more passive and act as a barrier. ⁽⁶⁷⁾ Alloys of zinc and aluminum are, according to Butler, "…somewhat more chloride and sulfur dioxide resistant than pure zinc, while still retaining the greater electro-chemical activity of pure zinc." ⁽⁶¹⁾

The problem with thermal sprayed metals is that environmental conditions will affect the levels of cathodic protection and current densities. Moisture content at the anode/concrete interface and temperature are environmental conditions that affect the current output. ⁽⁶²⁾

In a dry environment, zinc will not work effectively as the resistivity of the concrete will be high. In comparison, the Al-Zn-In alloy will deliver more current than the pure zinc in the same high resistivity environment. ⁽⁶⁶⁾ This happens because the indium keeps the anode active in the drier conditions. ⁽⁶²⁾

In extremely cold temperatures, the current output of thermal sprayed metals may be insignificant. When both low temperature and dry concrete are present, the level of protection supplied by the thermal sprayed metals will be greatly reduced. However, the corrosion rate of reinforcing steel in this environment may be negligible. ⁽⁶²⁾

Although pure zinc may not work effectively in a high resistivity (i.e. low moisture) concrete environment, a chemical treatment can be added to increase the moisture content of the pure zinc. An alkaline humectant is one such chemical that increases the moisture content at the interface, thereby reducing the resistivity of the

concrete. The humectant helps to lower the resistivity by forming soluble Zn(OH)₂, thus leaving the surface of zinc available for continued reaction and current output by holding moisture in the pores of the metal. ⁽⁶⁵⁾ Holcomb et al. reported that humectants were effective in "…raising the long-term galvanic current density is GCP (galvanic cathodic protection)" and that "Humectant treatment increased the protection current in GCP. Spot application of humectants would prolong the useful life of GCP zones that were not achieving sufficient galvanic current." ⁽⁶⁸⁾

A problem with using humectants on zinc, according to Costa, is the reapplication of the humectant activator. Costa's experience with activated zinc in cold climates is that the humectant loses its effectiveness and needs to be reapplied every two years. ⁽⁶⁹⁾ When asked about the reapplication of the humectant, Sandron, Business Development Manager of VCT, responded that, "...By monitoring these results (current and polarization) over time, one can decide on reapplication if current throw is insufficient to maintain adequate polarization. We do not recommend a scheduled reapplication of humectant but only suggest that reapplication is required if current drops below acceptable levels." ⁽⁷⁰⁾

Testing by Corrpro has reportedly shown that the Al-Zn-In alloy has a higher current density, a higher depolarization (it can actually meet the 100 mV depolarization criterion), and similar adhesion strength to that of pure zinc. ⁽⁶²⁾

The success of a thermal sprayed system, according to Daily and Green, "...is greatly influences by several factors including adequate concrete surface preparation, electrical continuity of the reinforcing steel, a degree of moisture at the anode/concrete interface to improve overall conductivity, and finally an experienced thermal spray

operator who can successfully apply the system to provide adequate bonding in accordance with the project specifications." ⁽⁶²⁾

Electrical continuity should be checked at 5 locations per every 1000 ft² of concrete and among all exposed steel. Continuity can be achieved by welding the reinforcing bars together or by wrapping and tightening uncoated steel wire ties. ⁽⁶²⁾ This check should also be performed for half-cell potential testing and all other forms of cathodic protection.

According to Miltenberger, the problem with the Al-Zn-In alloy is that it is "…available only from one supplier and is patented. The alloy is brittle, causing the wire to break inside the metalizing equipment. This increases wear and tear on the equipment and (gives) less efficient work." ⁽⁶⁵⁾

However, Clem Firlotte, Senior Project Manager of North American Concrete Services for Corrpro Companies, Inc., replied:

"When we first developed this wire (Al-Zn-In alloy), in 1995, some of the early applications had a few problems with the wire jamming up in the lines that feed to the spray gun. This is not because the wire is brittle, but just the opposite, it is a cored (an aluminum sheath wrapped around zinc and indium powder) wire and is soft. The first applications had the equipment set for solid wire such as zinc or aluminum and some problems occurred. We made some adjustments, and with an experienced operator, the wire actually sprays faster and with better efficiency than zinc or aluminum." ⁽⁷¹⁾

In 2003, Whitney et al. released a Project Summary Report on Research Project 7-2945, Performance Evaluation of Cathodic Protection Systems for Queen Isabella

Causeway in Texas. The project studied the use of cathodic protection on substructure elements in the splash zone. The report stated that the non-impressed sprayed zinc and aluminum-zinc alloy systems both performed reasonably well. The report also noted that although the zinc was less expensive, the aluminum-zinc alloy appeared to perform more effectively in dryer conditions and provided more uniform protection. ⁽⁷²⁾

In an experiment by Bohdanowicz, when a zinc protection layer was applied to reinforced concrete specimens completely immersed in aqueous sodium chloride solutions, a gradual increase of reinforcement cathodic polarization was found. Complete cathodic protection was achieved after two months of polarization. During the experiment, no significant consumption, delamination, or blistering of the zinc layer occurred. A 100% adhesion to the concrete was also found. ⁽¹³⁾

Sagues and Powers reported in 1994 that sprayed zinc galvanic systems "…have continued to show physical integrity after up to 4.5 years of service in a harsh marine environment…Field current density measurements over 4.5 years indicate that typically 0.5mA/ft² has been maintained on structures containing corroded epoxy-coated rebar. On the order of 1.0 mA/ft² was maintained over two years on structures containing corroded ordinary rebar…Rebar probe measurements consistently showed typical steel polarization decay values that exceeded 100mV in as little as one hour." ⁽⁷³⁾

Laboratory and field investigations of thermal sprayed zincs in deicing salt environments were conducted by the Transport Ministry of Quebec, in cooperation with the Institute for Research in Construction and the Industrial Materials Institute. In 1993, seven reinforced concrete columns of a bridge were flame-sprayed and the zinc continued to protect the columns when tested 20 months later. In another field test, researchers

from the National Research Council (NRC) of Canada used zinc to metalize driving surfaces in an Ottawa parking garage. "High levels of protection were provided by the metalizing, although in extremely wet areas the zinc sacrificed itself more rapidly than in the dry areas, indicating that more zinc needs to be applied in areas where water collects." ⁽⁷⁴⁾

The NRC is also studying metalized alloys (zinc in combination with other materials). The researchers believed that these materials would be more effective than pure zinc in dry environments. ⁽⁷⁴⁾

Although the life of thermal sprayed metals is limited, Andrews-Phaedonos et al. write that "…The life of the system can be extended by simply whip blasting the surface and spraying additional molten zinc. A longer life system is possible by increasing the coating thickness."⁽⁷⁵⁾

Although thermal sprayed metals are normally used on bridge substructures or the underside of bridge decks, the Missouri Department of Transportation is currently researching the use of the Al-Zn-In alloy in a bridge deck application. A 0.060" thick alloy 3003 aluminum expanded mesh, with 1" x 2.75" diamond pattern openings, was thermally sprayed. The anode mesh was installed to the existing deck and a 2-1/4" thick low slump concrete overlay was then installed. Installed in July 2005, initial depolarization tests performed in September 2005 showed that the anode was working and was producing sufficient current to protect the rebar. ⁽⁷⁶⁾

A 2002 report by the Illinois Department of Transportation evaluated thermally sprayed pure zinc, an 85/15% blend of zinc and aluminum, and a zinc/aluminum/indium alloy on prestressed concrete bridge girders. They concluded that "...the systems do not

offer any improved amount of protection to the pre-stressing strands when compared to beams not treated. Results from the corrosion potential surveys indicate that the systems are not protecting the steel. It appears that the anodes do not develop enough current necessary to drive the ion exchange to arrest the corrosion process." ⁽⁷⁷⁾

However, the results were only based on corrosion potentials. Because the tests were performed in the field, the girders were not dissected to see if the strands were indeed being protected.

When asked to further comment on the report, Gawedzinski replied, "No additional work was performed on the metalized beams after the study was concluded. The cause for the "poor" performance (as described by industry reps) was that the concrete was too "dry," in that it could not conduct enough current to drive the ion transfer between the rebars/strands and sprayed on anodes." ⁽⁷⁸⁾

From projects quoted in 2008, the cost of humectant-activated thermal sprayed zinc was approximately \$30 per square foot while the cost of the Al-Zn-In alloy was approximately \$35 per square foot. ^{(79), (80)}

2.4.2.3.3 Galvanic Cathodic Protection with Coatings

To increase the useful life of the sacrificial anodes, the method of using coatings in addition to sacrificial cathodic protection has been researched. Francis writes:

"The provision of an insulating coating to the structure will greatly reduce the current demand for cathodic protection...The conjoint use of coatings and cathodic protection takes advantage of the most attractive features of each method...the bulk of the protection is provided by the coating and cathodic

protection provides protection to flaws in the coating...A combination of coating and cathodic protection will normally result in the most economic protection system." ⁽⁴⁵⁾

2.4.2.3.3.1 Discrete Anode GCP with Coatings

The Interstate Route 480 Viaduct substructure in Omaha, Nebraska utilized discrete (embedded) galvanic anodes in patch repairs of piers with limited chloride contamination and electrochemical chloride extraction on the piers with the highest chloride levels. Fallaha and Whitemore wrote that the anodes "...would address future 'hot spots' which are likely to occur outside of the repair zone." After treatment, the entire substructure was coated with a flexible, breathable acrylic coating to prevent future chloride contamination. ^{(81), (82)} As of 2006, Whitmore reported that the treatments seemed to be working well. ⁽⁸³⁾

However, Costa explained that coatings should not have an effect on the life of the discrete anodes:

"I don't see any added benefit nor detriment to this type of anode by using an external coating...In my opinion this should not affect the life of the anode. The life of the anode is directly proportional to its current output. Current output is controlled by anode geometry, concrete resistivity and driving voltage between the anode material and the steel. The only variables here are concrete resistivity and driving voltage (which will change as the steel polarizes, if it does). If there is corrosion activity in concrete (enough to warrant the use of discrete anodes), then it follows that the resistivity of the concrete is low. Although chlorides affect the

resistivity, moisture and humidity are the dominant factors, not chlorides. Chlorides primary role in the corrosion process is the removal of the passive film that is created on the steel in alkaline environments. So, coating the exterior of a concrete structure with the objective of preventing further chloride ingress will not affect concrete resistivity, therefore anode current output (and hence anode life) will not be affected by this. Further, exterior coatings will not isolate the concrete matrix from the environment such that no moisture and humidity can penetrate." ⁽⁶⁶⁾

2.4.2.3.3.2 Thermal Sprayed GCP with Coatings

To increase the life of melted metals, coatings can be placed on top of the metal to further protect it (Figure 20). Melted metals also give excellent adhesion to top-coatings. ⁽⁶⁴⁾ Costa commented that, "It is important to use coatings that will allow vapor diffusion




Figure 20: Application of a top-coating to thermal sprayed zinc⁽⁶⁰⁾

(not sealers) to permit moisture to migrate both back and forth from the concrete. This will allow zinc oxides to migrate out and prevent accumulation at the interface of the anode and the concrete, which could lead to debonding of the anode." ⁽⁶⁶⁾

David Whitmore, President of VCT, remarked that "The top coat will significantly reduce self corrosion of the galvanic coating especially in conditions where it is exposed to splash and spray." However, top coats should not be used in all situations. He also commented, "I would not recommend it where the concrete is never exposed to moisture or splash and the concrete is not in contact with moisture or humidity (such as the underside of a deck)." ⁽⁸⁴⁾

As described by Costa, inorganic zinc primers, such as zinc silicate, have reportedly been used successfully with thermal sprayed zinc in Florida. In other environments, latex coatings have been used with success. ⁽⁶⁶⁾ According to Firlotte, coatings can be used with the Al-Zn-In alloy provided that the coatings are breathable. ⁽⁸⁵⁾

According to Spriestersbach et al., the application of organic top coatings helps to protect and prolong the life of arc-sprayed zinc. Because of the organic top coating, "...the zinc coating is not in direct contact with the atmosphere and thus is not longer subject to self corrosion. Therefore, zinc consumption only takes place at the interface between the zinc coating and the concrete. It is calculated that the zinc consumption can be reduced to 50%..." This calculation is based on Faraday's 2nd law. ⁽⁶⁰⁾

After six months of laboratory testing using NaCl contaminated concrete and the salt spray test, the sprayed zinc coated concrete specimens with organic top-coating satisfied the 100mV off-potential (NACE criterion) after only one hour. ⁽⁶⁰⁾ As discussed previously, sufficient protection is provided when a potential decay greater than 100mV is found after four hours.

The study also examined the use of the arc-sprayed zinc with an organic topcoating as a repair method for severely corroded concrete structures in the Persian Gulf. The repair included the removal of loose concrete, grit blasting of the corroded steel reinforcement, installation of reference cells and electrical contacts, reprofiling of the

concrete structure, arc spraying of the zinc anode, and application of the organic topcoating $^{(60)}$

More than a year-and-a-half after field installation of the arc sprayed zinc and organic top-coating, Spriestersbach et al reported that "...no sign of rebar corrosion could be observed...The obtained values of static potential measurements indicate that there is no sign of corrosion..." ⁽⁶⁰⁾

The paper by Spriestersbach et al. concluded as follows:

"Sprayed zinc coatings do not present any significant limitations with regard to their applicability in comparison with other cathodic protection variants for concrete... Thermally sprayed zinc anodes can be renewed very easily after being consumed... The anode can be easily replaced by spraying a new zinc coating on the concrete surface... By applying organic top-coatings to the sprayed zinc coating, the lifetime can be enhanced considerably." ⁽⁶⁰⁾

2.4.2.3.4 Comparison of Cathodic Protection Systems

Table 9 compares and contrasts the characteristics of impressed current and galvanic cathodic protection systems.

Impressed Current	Galvanic Anode
External power required	External power not required
Driving voltage can be varied	Driving voltage is fixed
Current can be varied	Current is limited
Can be designed for almost any current	Usually used where current requirements
requirement	are small
Can be used in any level of resistivity	Usually used in low-resistivity electrolytes
High \$/unit cost	Low \$/unit cost
Low \$/sq. ft. of metal protected	High \$/sq. ft. of metal protected

Table 9: Characteristics of cathodic protection systems ⁽⁴²⁾

As ICCP systems are more expensive and complex (requires an outside power source, a rectifier, monitoring, and maintenance), their use is not pursued in this project. For this project, the use of galvanic (sacrificial) cathodic protection is pursued because of its simplicity (does not require monitoring or maintenance) and lower initial cost.

According to a 2004 article by the Ontario Ministry of Transportation (MTO), "The implementation of new sacrificial anode systems could dramatically improve and simplify the rehabilitation or some structures suffering from corrosion." The MTO also writes that, "Based on their potential to reduce the costs of long-term monitoring and system maintenance and to enhance the durability of Ontario's bridges, sacrificial anode systems may eventually replace impressed current systems as the standard for cathodic protection." ⁽⁸⁶⁾

2.4.3 Corrosion Passivation

Corrosion passivation makes use of electrochemical treatments to address and remove the underlying cause(s) of corrosion. While the electrochemical chloride extraction (ECE) process removes chlorides and the re-alkalization process restores the alkalinity of carbonated concrete, both processes are intended to restore the passivity of all reinforcing steel within the treated area. Operated for a short amount of time, dismantled and then removed, these electrochemical treatments are supposed to provide long-term mitigation benefits without the need for future maintenance and monitoring. (22), (87), (88)

In order to use either technique, the following steps need to be performed: ^{(87), (88)}

- 1. All existing surface finishes must be removed
- 2. All cracks, spalls, and delaminations should be located and repaired using an approved cementitious mortar
- All metallic features on concrete surface should be located and insulated, or removed
- Thickness of concrete cover should be determined and built up to a minimum of 3/8" (10mm), if necessary
- 5. The continuity of the reinforcement should be checked and provided if it does not exist.

2.4.3.1 Electrochemical Chloride Extraction

Used mostly on bridges and parking garages, the ECE process (Figure 21) is supposed to remove chlorides from chloride contaminated concrete and regenerate the passivity of the reinforcing steel. ⁽²²⁾ This occurs as the positively




Figure 21: Electrochemical chloride extraction ⁽¹²⁾

charged external anode attracts the negatively charged chloride ions. In turn, all of the rebar becomes a negatively charged cathode and passivity is reinstated as hydroxyl ions are formed at the rebar. ⁽⁸⁹⁾

"...the ECE process," according to Donald Jackson of the Federal Highway Administration (FHWA), "has become nationally recognized as a promising technology that can benefit the owners of thousands of concrete structures." ⁽⁹⁰⁾ Additionally, James Cheatham writes that "ECE offers benefits over conventional means of bridge rehabilitation or replacement because this technology requires less disruptive and expensive rehabilitation work, can extend the service life of the structure by as much as 12 to 15 years or more, and can save construction time." ⁽⁹⁰⁾

The success of the ECE process depends on three facets that will be discussed in the following paragraphs:

- 1. Site utilities and services
- 2. Anode, electrolyte, and electrolyte media
- 3. System operation

The requirements for site utilities and services are a temporary power supply, availability of water for the electrolyte solution, and site access. Although the rectifiers require 240V AC input, the applied voltage ranges from 10 to 40V DC while the current density is normally $1A/m^2$ of concrete surface. ^{(87), (89)}

The proper selection of anode, electrolyte, and electrolyte media is paramount to the success of ECE.

The anode can be either a catalyzed titanium or steel mesh (Figure 22). While the titanium is inert and does not corrode, the catalyzed coating is



Figure 22: Installation of steel mesh ⁽⁹¹⁾

consumed over time. Whitmore writes that the "Titanium mesh may require the use of a buffered electrolyte or regular electrolyte replacement since chlorides will concentrate in the electrolyte resulting in acidification of the electrolyte over time." In contrast, steel mesh is not inert, will be consumed during the ECE process, and will produce rust stains on the concrete. However, the stains can be taken off with light sandblasting. The cost of the catalyzed titanium mesh is 6 times that of the steel mesh. ⁽⁸⁹⁾

The electrolyte can be water, calcium hydroxide (lime) solution, or "lithium borate" solution. The advantages of using water are that it is the most efficient, inexpensive, more readily available, and does not require environmental protection or containment. However, its disadvantage is that water does not have buffering ability. Whitmore writes that, "If water is used as an electrolyte with an inert anode in a closed system, electrolyte acidification will occur if the water is not regularly replaced." Although calcium hydroxide solutions provide some buffering capability, they are more expensive than water, require time to prepare and maintain, and have somewhat less efficiency than water. "Lithium borate" is a mixture of lithium hydroxide and boric acid. This electrolyte is highly buffered and has been specified for concrete suffering from alkali-silicate reactivity. Whitmore also writes that the "Disadvantages of lithium electrolyte solutions include their relatively high cost and the need for re-circulating systems which are often installed to minimize the quantity of electrolyte required." ⁽⁸⁹⁾

The electrolyte media holds the electrolyte solution to the concrete and provides separation between the anode and concrete surface. Sprayed cellulose fibers (Figure 23), used for vertical surfaces, synthetic felt mats, used for horizontal ponding, and surface mounted tanks, used



Figure 23: Application of cellulose fibers ⁽⁹

for vertical ponding, are the three types of electrolyte media used.⁽⁸⁹⁾

During the treatment (Figure 24), which lasts for six to eight weeks on average, the system must be monitored and maintained. Daily wetting, by a person or by a wetting system, is required for cellulose and synthetic felt installations. The electrolyte of a tank or a ponding



Figure 24: Operational ECE system ⁽⁹¹⁾

system, which is usually buffered, requires periodic circulation, topping, and regular replacement. ⁽⁸⁹⁾

A problem with ECE is that when it is used on bridge decks, the traffic must be rerouted so that the system is not disturbed. When the system is used on bridge piers, traffic rerouting is not required. ⁽⁹²⁾

Additionally, ECE should not be used with structures containing epoxy coated rebar and pre-stressed or post-tensioned steels. The epoxy coating insulates the steel, thus "…preventing electrical continuity, and effective chloride removal." The high applied voltages may cause hydrogen embrittlement of the high strength steel wires used in pre-stressed and post-tensioned concrete. ⁽⁹³⁾

Although FHWA reported that "Various studies have demonstrated ECE is a promising bridge restoration alternative to CP for chloride-contaminated concrete bridges," it also states that ECE "...data from field and laboratory experiments indicate certain regions in concrete appear to lead to inefficient chloride extraction." ⁽⁹²⁾

The University of Minnesota conducted a study using ECE on the substructure of reinforced concrete bridges in Minneapolis, Minnesota. The study found that "...the effectiveness of the treatment process varied greatly by location, sample depth, and original chloride content. In general, ECE reduced the average chloride concentrations the most near the concrete surface, and the effectiveness decreased slightly with depth into the structure." However, it was also determined that several locations possessed "...chloride concentrations in excess of the established threshold for corrosion, of 2000 ppm by weight of cement, at multiple sample depths...following ECE treatment."


Therefore, it was concluded that "...corrosion can potentially reoccur once chloride ions migrate back to the reinforcing steel level..." ⁽⁹⁴⁾


The Michigan Department of Transportation (MDOT) also evaluated ECE on the substructure of M60 over I-94 in Jackson, MI. The project treated one pier cap and four columns. Kahl concluded that:

"Passivity of the reinforcing steel was regenerated; eighty-one percent of the readings after the ECE treatment were more positive than -200 mV, the region characteristic of very little corrosion. Chloride levels were reduced at locations above the steel reinforcement, with no adverse effects to the structural integrity of the concrete. At the reinforcement, chloride levels were redistributed, except one location where chlorides were completely removed. However, it was expected that all chloride contamination at the reinforcement depth would be reduced below the corrosion threshold. Despite the incomplete removal of chloride contamination from around the reinforcement, ECE has reduced the ability of the remaining chlorides to initiate corrosion by repassivating the steel. Electrochemical chloride extraction appears to work well, given the resources available at a remote location. Because of the variability in chloride removal at the steel reinforcement, it is recommended that ECE be studied further with additional field trials. More substructure units should be treated with ECE and evaluated before adoption as a standard alternative substructure rehabilitation method in Michigan." (91)

2.4.3.2 **Re-alkalization**

Used primarily on carbonated building facades, ⁽²²⁾ the re-alkalization process (Figure 25) "...restores the alkalinity of carbonated concrete and reinstates the passivity of the steel reinforcement." (88)





During this process, an electric field is applied between the reinforcing steel and an externally mounted anode mesh. A reservoir of electrolytes provides a connection between the concrete and the embedded anode mesh. The electric field produces a high pH environment at the steel surface as electrolysis occurs. Simultaneously, the electrolyte is transported into the concrete and increases the alkalinity of the concrete. ⁽⁹⁵⁾

The anode mesh is made of steel or platinized titanium. The alkaline electrolyte, usually a sodium carbonate solution, conducts electricity and provides alkalis to the carbonated concrete. The reservoir may be sprayed-on cellulose fiber, felt cloth, or coffer tanks. (95)

Prior to applying the cellulose fiber, wooden battens are attached to the concrete. The anode mesh is attached to the wooded battens, which provides separation between the concrete surface and the anode mesh. The cellulose fiber is saturated with electrolyte and sprayed onto the concrete surface to a thickness that coats the mesh. Although regular wetting is required, cellulose fiber can be used on most concrete structures. ^{(22), (95)}

Felt cloths are used primarily on concrete decks. With this application, the anode mesh is sandwiched between two layers of felt cloth. Constant wetting is required.⁽⁹⁵⁾

Coffer tanks are made of plastic sheets with sealing edge strips and a built-in anode mesh. The coffer tanks are then attached to the concrete and filled with electrolyte. This application is used on smaller, separated areas. ⁽⁹⁵⁾

Using an applied voltage between 10 and 40V DC and a current density of 1 A/m^2 of concrete surface, the procedure usually takes a week to complete. To assess the effectiveness of the treatment, cores are taken after a few days and tested to determine the extent of re-alkalization. The treatment continues until sufficient levels of re-alkalization are achieved. When the treatment is stopped, the pH of the concrete is at a value greater than 10.5. At this level, the passivity of the reinforcement can be maintained. The system is dismantled and the concrete surface is washed with water. Finally, all core holes and cavities are repaired. ⁽⁹⁵⁾

(Page left blank intentionally)

CHAPTER 3

EXPERIMENTAL APPROACH

3.1 General

In previous sections of this report, an overview of a few recently developed technologies that could be used for the prevention and repair of corrosion in concrete bridges was presented.

While many products and techniques may appear to be effective for the maintenance and repair of reinforced/prestressed/precast concrete bridge elements, not all effective claims will hold true under field conditions. By providing controlled accelerated testing and evaluation, this project aimed to investigate new or promising techniques to improve the repair and maintenance of reinforced concrete bridges in Wisconsin.

3.2 Products/Techniques Used for Experimental Program

Based on the literature information discussed previously, three galvanic products, one penetrating sealer, two coatings, and two patch repair materials were evaluated experimentally. Additionally, the use of coatings in conjunction with the galvanic anode cathodic protection systems was studied (Table 10). Table 11 details the use of the products for this project.

Product	Produced By	Referred to As
Disk-Shaped Embedded Galvanic Anode	Supplier A	EA-A
Box-Shaped Embedded Galvanic Anode	Supplier B	EA-B
Humectant activated Thermal-Sprayed Zinc Galvanic Anode	Zinc was not a proprietary product. Humectant activator from Supplier A	TSZ
Tri-Silane Penetrating Sealer	Supplier C	T-SS
Epoxy/Polyurethane Coating	Supplier D	EP-C
Acrylic Coating	Supplier E	A-C
Epoxy Repair Mortar	Supplier F	EM

 Table 10:
 Products used for experimental program

	Table 11:	Table of products used	and application to	specimens
--	-----------	------------------------	--------------------	-----------

Specimen Number	Туре	General Referred to As		CoP/CoC	
01 and 02	Thermal sprayed galvanic anode	Humectant activated zinc	TSZ		
03 and 04	Thermal sprayed galvanic anode with coating	Humectant activated zinc with epoxy/polyurathane coating	ated zinc with y/polyurathane TSZ w/EP-C		
05 and 06	Embedded galvanic anode with coating	Disk-shaped anode with acrylic coating	EA-A w/A-C		
07 and 08	Embedded galvanic anode	Disk-shaped anode	EA-A	СоР	
09 and 10	Embedded galvanic anode	Box-shaped anode	EA-B		
11 and 12	Penetrating Sealer	Alkylalkoxysilane	T-SS		
13	Coating	Acrylic Coating	A-C		
14	Coating	Epoxy/polyurethane coating EP-C			
15 and 16	Control	No treatment	Control		
17 and 18	Control	No treatment	Control		
19 and 20	Thermal sprayed galvanic anode with coating	Humectant activated zinc with epoxy/polyurethane coating	TSZ w/EP-C		
21 and 22	Thermal sprayed galvanic anode	Humectant activated zinc	TSZ		
23 and 24	Embedded galvanic anode	Disk-shaped anode	EA-A	CoC	
25 and 26	Embedded galvanic anode with coating	Disk-shaped anode with acrylic coating EA-A w/A-C			
27 and 28	Embedded galvanic anode	Box-shaped anode	EA-B		
29 and 30	Epoxy Repair mortar	Epoxy resins and polyamino amine adducts			

3.2.1 Embedded Galvanic Anodes

As discussed earlier in this report, some previous research reportedly showed that embedded anodes provided an effective means of locally protecting the reinforcing steel in patched concrete. Because the anodes are an addition to the patch, their installation would be relatively quick and easy and would not require special equipment or training.

3.2.1.1 EA-A

EA- A (Figure 26) was chosen because of the reportedly positive results from previous applications of the product. EA-A, used primarily for patch repair and bridge widening, is disk shaped and is comprised of a zinc core encased in an activated cementitious mortar that reportedly




Figure 26: Cut-through of EA-A⁽⁴⁸⁾

activated cementitious mortar that reportedly provides high capacity, high current output performance. The pH of the mortar is 14 or greater. ⁽⁴⁸⁾ The number of anodes needed, as reported in the manufacturer's guidelines, depends on the chloride content of the concrete and the amount of reinforcement. The placement and locations of the anodes for this project was confirmed with Supplier A (Figures 27 and 28). ⁽⁹⁶⁾



Figure 27: Installation of individual EA-A in CoP specimens



Figure 28: Placement of EA-A in CoP specimens

3.2.1.2 EA-A w/A-C

The use of the A-C, in conjunction with the EA-A, (Figure 29) was pursued to determine the effectiveness of a coating with embedded anodes. The use of this product was endorsed by Supplier A. ⁽⁸²⁾ The acrylic coating was used as it is an "elastomeric, crackbridging, anti-carbonation, acrylic protective



Figure 29: Application of A-C to specimen with EA-A

coating." The coating reportedly offers resistance against the ingress of carbon dioxide and other aggressive gases, as well as chlorides and waterborne salts. In addition, it does not act as a vapor barrier. Specified by Supplier E, a coating dry film thickness of 8 mils (16 wet mils applied in two-8 wet mil layers) was applied. ⁽⁹⁷⁾ The applied thickness of the coatings were measured with a coating thickness gauge.

3.2.1.3 EA-B

EA-B (Figure 30) utilizes a zinc core, two corrosion inhibitors, and a Vnotch configuration with insulating barrier and is designed to extend the life of patch repairs in parking decks and bridge




Figure 30: View of EA-B⁽⁹⁸⁾

structures by preventing the "anode ring effect." The insulating barrier reportedly prevents current "dumping" into the attachment bar. The V-notch configuration is also designed to assist in an "…efficient placement on any sized reinforcing bar." ^{(56), (98)} The manufacturer offers guidelines for spacing of the anodes that are similar to that of EA-A. The placement and locations of the anodes for this project was confirmed with Supplier B (Figures 31 and 32). However, they expressed some concerns about the level of voltage, and associated amount of current, that would be used for accelerating corrosion in this project. ⁽⁹⁹⁾ Nonetheless, the research team evaluated the expressed concerns and decided that the accelerated corrosion setup was not incompatible with the anode, and would represent long-term consumption and depletion of the anode properly.



Figure 31: Installation of individual EA-B in CoP specimens



Figure 32: Placement of EA-B in CoP specimens

3.2.2 Thermal Sprayed Galvanic Metals

As discussed previously, there are a few metals that could have been used for thermal spraying. The use of Supplier A's humectant–activated metalized zinc was pursued because it is more readily available compared to the Al-Zn-In proprietary alternative. At the time we were ready to apply the humectant–activated metalized zinc, circumstances would not allow Supplier A to apply their product to our concrete specimens. With approval from Supplier A, a local metalizing company was able to apply pure zinc to our specimens. The humectant solution, supplied by Supplier A, was then applied to the specimens.

3.2.2.1 TSZ

The use of the thermal sprayed pure zinc with the humectant activator solution, supplied by Supplier A, was tested. Supplier A's humectant–activated metalized zinc application usually utilizes a 3/16" diameter high purity zinc wire at a thickness of 20 mils. ⁽¹⁰⁰⁾ The local metalizing company, however, did not have the equipment to use that thickness of wire. Instead, a 1/8" diameter zinc wire was used and sprayed to a thickness of 15 mils as the reduced thickness wire produced smaller droplets and would create less voids. This procedure was confirmed with Supplier A. ⁽¹⁰¹⁾ The application of thermal sprayed zinc was as follows:

- 1) Grit blast the entire concrete surface (Figure 33)
- 2) Spray a layer of 6" x 6" area of 6-mil thickness around connection to rebar
- 3) Apply zinc mesh and secure with galvanized nut
- 4) Check for electrical continuity between the thermal spray and embedded rebar

- 5) Apply a uniform thermal spray thickness of 15 mils (Figure 34)
- Check for electrical continuity between the thermal spray and embedded rebar (Figure 35)
- 7) Apply humectant activator (Figure 36)

As specified by Supplier A, a second rebar connection was made for redundancy. In the CoP specimens, only one of the connections was used. Because of the small surface area, we did not feel that both connections would be necessary and the second connection was covered. However, the second rebar connection was used in the patch repair for the CoC specimens because of the apparent failure of one of the single connections in the CoP specimens.



Figure 33: Grit blasting of the concrete surface



Figure 34: Application of the thermal spray



Figure 35: Check for electrical continuity



Figure 36: Application of humectant activator

3.2.2.2 TSZ w/EP-C

The conjoint use of a coating with the thermal sprayed zinc was tested as previous research showed this to be a promising means of extending the life of the thermal sprayed zinc. Supplier A specifies the use of a zinc coating by Supplier D with its humectant–activated metalized zinc. ⁽¹⁰⁰⁾ However, technical support from Supplier D stated that there is "no advantage of putting zinc on zinc" and suggested using an epoxy/polyurethane topcoat. ⁽¹⁰²⁾ The United States Army Corps of Engineers (USACE) also specifies the use of an epoxy primer/polyurethane topcoat in conjunction with thermal spray coatings. ⁽¹⁰³⁾ The use of this coating system was also confirmed with Supplier A. ⁽¹⁰⁴⁾

As such, recommendations of coating thickness by the manufacturer $^{(105)}$ and the USACE $^{(103)}$ were followed (a coating thickness gauge was used):

- The epoxy coating was applied with a 3/8" woven roller at a dry film thickness of 3 to 4 mils (75 to 100 μm) (Figure 37)
- The polyurethane coating was applied with a 3/8" woven roller at a dry film thickness of 3 mils (75 μm) (Figure 38)



Figure 37: Application of epoxy coating to TSZ



Figure 38: Application of polyurethane coating to epoxy coating

3.2.3 T-SS

The T-SS (Figure 39) was used as a corrosion prevention product based on recommendations from the Wisconsin Highway Research Program (WHRP) Technical Oversight Committee during a proposal meeting for this project. A previous product



Figure 39: Application of T-SS

from Supplier C, a tri-siloxane masonry water repellent, has been widely used by the WisDOT. A newer version of the product (T-SS) from Supplier C has recently (effective April 26, 2007) been listed within WisDOT Approved Lists under Concrete Protective Surface Treatment. ⁽¹⁰⁶⁾

The T-SS is an alkylalkoxysilane and is described as a "…one component, deep penetrating, invisible, non-darkening treatment for concrete." Reportedly, the concrete becomes hydrophobic as the silanol groups chemically bond themselves to the concrete by using the moisture present in the concrete. This reportedly "…eliminates the ever present moisture that had previously engulfed the cementitious material" and prevents the intrusion of water and waterborne salts. ⁽¹⁰⁷⁾

3.2.4 EM

An epoxy repair mortar product identified by WisDOT personnel and the research team appeared to offer some promise for patch repairs. The EM (Figure 40) is a three component, solventfree, high performance epoxy mortar.



Figure 40: Preparation of EM

According to the manufacturer's data sheet, it is "...based on a blend of solvent free epoxy resins and polyamino amine adducts reinforced with a special blend of silica quartz minerals and lightweight fillers..." The repair system reportedly does not have shrinkage or volume changes. ⁽¹⁰⁸⁾

3.2.5 Conventional Patch Repair Material

When selecting options for a repair material for this project, the WisDOT Approved Products List was first examined. We considered fast-setting materials with a low resistivity and limited silica/polymer modification for compatibility with galvanic anodes. In searching for an acceptable material, we discovered that the resistivity value was not a readily available property. According to Cheney, "…resistivity is not a typical property for evaluation for state DOT's APL's (approved products lists) for road repair materials…" ⁽¹⁰⁹⁾ We had initially planned on using commonly-used patch materials, but those products could not be used because of their relatively high resistivity (incompatible with anodes) (Table 12).

Product	Composition	Resistivity (ohm-cm)
Five Star Highway Patch	One component, contains cementitious material and crystalline silica ⁽¹¹⁰⁾	40,386 (109)
Set 45	One-component, magnesium phosphate- based ⁽¹¹¹⁾	192,359 (air cured) 22,925 (saturated) ⁽¹¹²⁾

Table 12: Evaluation of WisDOT approved rapid setting concrete patch materials

We then contacted Supplier A to inquire about a repair material to use with EA-A. Supplier A provided a long list of approved products and informed us that a repair material with a high resistivity could be used, provided that there was an ionic bridge between the anode and the substrate concrete (Figure 41). This ionic




Figure 41: Low resistivity ionic bridge between anode and substrate concrete ⁽¹¹³⁾

bridge could be provided by using a low-resistivity mortar, <5,000 ohm-cm.⁽¹¹³⁾

Supplier B also provided a list of approved patch materials for use with EA-B. However, they do not recommend the use of an ionic bridge. ⁽¹¹⁴⁾

As expected, none of the products listed by the two suppliers overlapped. After evaluating available information on the products, we chose a product from Suppler B's approved list. The product is a"…cement based, ready to use, rapid strength gain, patching and repair mortar containing a migratory corrosion inhibitor" and is also "Compatible with galvanic anodes." ⁽¹¹⁵⁾

3.3 Experimental Plan

To meet the objectives of the project, "salt-ponding" and electrochemical aging were used to accelerate chloride migration and corrosion. While only 14 of the 30 concrete specimens included mixed-in chlorides, all specimens were subjected to wetting/drying cycles of chloride (salt) laden water and an imposed electrical charge.

3.3.1 Setup of Concrete Specimens

To represent typical bridge deck thickness and reinforcing patterns, concrete specimens that measured 28" in width, 28" in length, and 8" in thickness were cast with two layers of #5 reinforcing bars placed at 6" on center (Figure 42). Although the specimen thickness and reinforcement spacing reflect a typical bridge deck, the repair and prevention approaches studied in this project are not limited to bridge decks alone, and can be applied to all parts of concrete bridges.




Figure 42: Cross section of concrete specimen

To quicken chloride diffusion and accelerate corrosion, the top layer of reinforcement utilized a 1" clear cover (instead of a more standard 2" clear cover). A standard 2" clear cover was used for the bottom layer of reinforcement. PVC pipe (34" diameter) was caulked to the perimeter of the top surface of the concrete specimens to create the reservoir or "pond" that periodically held the salt laden water.

The setup of the specimens is depicted in Figures 43 through 45.



Figure 43: Layers of prepared reinforcement



Figure 44: Clear cover to reinforcement



Figure 45: Setup of laboratory specimens for concrete pour

3.3.2 Composition of Concrete

The CoP specimens, which represented new construction, did not contain mixedin chlorides. The CoC specimens, which represented members already containing chlorides, were cast with pre-mixed chlorides.

For all concrete specimens, a conventional 4000 psi concrete mix was used. For the CoC specimens, the bottom 5" of the specimens was cast without chlorides and the upper 3" were cast according to chloride level profiles found in normal bridge conditions. To represent approximately 10 years of chloride exposure, Fick's 2nd law of diffusion (Eq. 10) was used to determine the appropriate chloride profile.

Fick's Second Law can be written as:

$$C_{(x,t)} = C_o \left(1 - erf \frac{x}{2\sqrt{D t}} \right)$$
(Eq. 10)

where: $C_{(x,t)}$ = chloride concentration at depth *x* and time *t*

 C_0 = surface chloride diffusion (lb/yd³ or kg/m³)

erf = error function

D = chloride diffusion coefficient (in²/yr or cm²/yr)

Weyers et al. released a Strategic Highway Research Program (SHRP) report in 1994 that provided chloride diffusion coefficient (D) and surface chloride concentration (C_0) values for sixteen states. ⁽¹¹⁶⁾ Table 13 presents their findings, based on results from 321 bridges and 2764 samples.

State	Number Of Bridges	Number of Samples	D (mean, in ² /yr)	C_{θ} (mean, lb/yd ³)
Arkansas	10	80	0.03	1.81
California	49	252	0.25	3.23
Delaware	3	14	0.05	8.67
Florida	15	52	0.33	5.98
Indiana	6	43	0.09	8.97
Iowa	27	183	0.05	8.09
Kansas	28	275	0.12	3.64
Maryland	59	1069	0.36	4.89
Michigan	13	35	0.15	4.83
Minnesota	59	521	0.05	6.54
Nevada	2	9	0.08	3.01
New York	15	45	0.13	14.63
Pennsylvania	9	6	-	7.26
Virgina	6	57	0.12	6.29
West Virginia	8	48	0.07	8.54
Wisconsin	12	75	0.11	10.10

Table 13:	State chloride	testing	results	(116)
-----------	----------------	---------	---------	-------

As mentioned previously, the top 3" of the CoC specimens were profiled according to a 10-year exposure to chlorides. This profile replicates conditions typically seen in bridge decks. To accomplish this, chloride content values at 0.5", 1.5", and 2.5" from the concrete surface were used. Based on the results of the SHRP-S-668 study, a chloride diffusion coefficient (*D*) of 0.11 in²/yr (as suggested by the study) and a surface chloride concentration (C_0) of 5.985 lb/yd³ (representative of the mean of all of the collected data) were used.

When these values were inserted into Fick's 2^{nd} Law of diffusion, a chloride content nearly 4.5 times greater than the corrosion threshold was found at a depth of 0.5", a chloride content 2.0x greater than the corrosion threshold was found a depth of 1.5" (the level of reinforcing steel in this project), and a chloride content approximately 0.5x the corrosion threshold was found a depth of 2.5". The anticipated chloride profile for a bridge deck with 10 years of exposure can be seen in Figure 46.




Figure 46: Calculated chloride content profile used for mixed-in chlorides

Table 14 presents the values of the 10 year chloride profile that were used in the CoC specimens for this project. The percentage assumes a concrete unit weight of 145.0 lb/ft³.

Table 14. Level of emolides to be mixed into the coc specificity				
Donth	% Chlorides by	Chloride Content by		
Depth	Mass of Concrete	Volume of Concrete		
0.5"	0.113 %	4.41 lb/yd^3		
1.5"	0.048 %	1.87 lb/yd^3		
2.5"	0.014 %	0.55 lb/yd^3		

Table 14: Level of chlorides to be mixed into the CoC specimens

3.3.3 Concrete Pour

The slump of the concrete was first measured. After acceptance, the bottom 5" of the CoC specimens was poured (Figure 47). Next, the CoP specimens were completely poured and finished (Figure 48). During this time, the mixed-in chlorides for the CoC specimens were begun.

In order to mix the chlorides into the concrete, a 9-cubic-foot concrete mixer and table salt were used. Levels of chlorides, as presented in Table 14, were mixed into the concrete. Since salt was used, the amount of Cl⁻ in NaCl was calculated and used in measuring the amount of chlorides to be mixed-in. After the first 5" of the CoC specimens were poured, the bottom profile level was added (Figure 49). After the bottom profile level was completed, the middle profile level was added (Figure 50). Finally, the top profile level was completed.

Since the levels were only 1" thick, the mechanical vibrator was used internally in a horizontal direction to consolidate the concrete. The use of the mechanical vibrator also aided in some blending of the profile levels. When the pour was completed, all of the specimens were covered with a sheet of plastic.



Figure 47: Pouring the bottom 5" of the CoC specimens



Figure 48: Finishing the CoP specimens



Figure 49: Placing the bottom layer of concrete with mixed-in chlorides



Figure 50: Placement of the middle layer of concrete with mixed-in chlorides

3.3.4 Wetting/Drying Cycles and Galvanostatic Electrical Current

To further accelerate the corrosion process, the specimens were subjected to wetting/drying cycles and a galvanostatic electrical current. Cycles of one week wet, using a 6% NaCl solution, and one week dry were performed. A reverse cathodic protection system was created by continuously applying a regulated voltage of 9V from the positive terminal of the regulated power supply to the top layer of reinforcement (the anode). Between the positive terminal and the anode, a 1 Ω resistor was used to calculate the difference in current. By connecting the positive terminal to the upper level of reinforcement, a faster than normal rate of chloride diffusion could be found as the negatively charged chloride ions were attracted to the positively charged reinforcing steel. The bottom steel layer (cathode) was attached to the negative terminal. See Figures 51 to 55.

Even though each layer of reinforcement had electrical continuity, the two layers were not electrically connected. This forced the current to travel through the concrete. The accelerated corrosion test regime is similar to the one used for an earlier WHRP Project (No. 0092-01-06). ⁽²⁴⁾




Figure 51: Corrosion cell for laboratory specimens



Figure 52: Wiring/data acquisition setup




Figure 53: Setup of resistors



Figure 54: Project setup




Figure 55: Positioning of specimens per Table 11

3.3.5 Monitoring

The monitoring system was setup so that corrosion current data could be collected and recorded with a data acquisition system. However, due to software issues, manual readings of all of the corrosion currents were taken on a daily basis.

At first, the manual readings were taken across the data acquisition modules. After two-months of testing, however, we realized that the readings were being affected by the resistance of a "jumper" in the circuit. To account for this, the resistance across each "jumper" was determined and used to correct the previously taken readings. Subsequently, all manual readings were taken directly across the resistors, without a need for adjustment.

The chloride content of all specimens was determined by analyzing pulverized concrete samples at various depths. See Figure 56 for the location of the tests. The base-line chlorides for the specimens were initially determined at 6 locations, at depths of $\frac{1}{2}$ " and 1", for a total of 12 chloride tests.

The chloride content of each of the 14 CoC specimens (i.e. those containing mixed-in chlorides) were evaluated at depths of $\frac{1}{4}$, $\frac{1}{2}$, $\frac{3}{4}$, 1", 1- $\frac{1}{4}$, 1- $\frac{1}{2}$, 2", 2- $\frac{1}{2}$ ", and 3" from the concrete surface prior to accelerated corrosion exposure. Three locations were analyzed per specimen (Locations A, B, and C). Therefore, the total number of chloride tests per specimen was 27 for this stage. Each drilled hole was filled with concrete filler after drilling.

After 3-months of accelerated testing, the chloride content of the 14 CoC specimens were re-evaluated at depths of $\frac{1}{4}$, $\frac{1}{2}$, $\frac{3}{4}$, 1", 1- $\frac{1}{4}$ ", $1-\frac{1}{2}$ ", $1-\frac{3}{4}$ ", and 2". Three locations (Locations D, E, and F), for a total of 24 chloride tests per specimen,

84

were analyzed per specimen for this stage. For Specimen #23, location E was reevaluated at location G.

After 6-months of accelerated testing, the chloride content of the 16 CoP specimens were evaluated at depths of $\frac{1}{4}$, $\frac{1}{2}$, $\frac{3}{4}$, 1", $1-\frac{1}{4}$ ", $1-\frac{1}{2}$ ", $1-\frac{3}{4}$ ", and 2". Three locations (Locations D, E, and F), for a total of 24 chloride tests per specimen, were analyzed per specimen for this stage.

After an additional 3-months of exposure to accelerated corrosion after patch repairs, chloride content of the 14 CoC specimens were evaluated at two locations per specimen at depths of $\frac{1}{4}$, $\frac{1}{2}$, $\frac{3}{4}$, 1", $1-\frac{1}{4}$ ", $1-\frac{1}{2}$ ", $1-\frac{3}{4}$ ", and 2". One location was tested inside the patched area (Location B), and one location was tested outside the patch area (Location H). Because of inconsistencies, additional testing was performed at Locations D, E, G, and I to verify the original results.




Figure 56: Location of laboratory concrete powders

Periodically, half-cell potential readings were taken. Readings were taken at sixteen locations per specimen. Each recorded location represents a "grid" within the rebar spacing (See Figure 56). The readings were only taken on specimens that did not contain coatings.

In addition, the specimens were monitored for cracking. Detailed crack maps were created at periodic increments. The widths of the cracks were measured using a standard crack width comparator.

3.3.6 Patch Repairs

To test the various corrosion control techniques, patch repairs were completed on the 14 CoC specimens after 3 months of exposure. Repairs were performed in accordance with the International Concrete Repair Institute (ICRI) standards.

3.3.6.1 Patch Repair Process

The patches were sized at 16" by 16". After sizing, the perimeter of the patches was saw cut and concrete removal commenced (Figure 57). Note the discoloration of the concrete at the rebar locations (Figures 58). The concrete was removed to a depth of $\frac{3}{4}$ " below the top layer of reinforcing steel (Figures 59 and 60). The reinforcing steel was then cleaned with a grinder (Figure 61). Note the loss of ribs (due to corrosion) on the reinforcing steel in Figure 62.



Figure 57: Concrete removal



Figure 58: Discoloration of concrete discovered during concrete removal



Figure 59: Condition after concrete removal



Figure 61: Cleaning of the reinforcing steel by wire brush



Figure 60: "Finger-gap" below reinforcing steel



Figure 62: Loss of ribs on reinforcing steel

Prior to application of patches, the existing cracks on the top of the slab were routed out with a hand-held grinder and diamond blade (Figure 63). After the application of the repair material, the cracks were gravity-fed with an epoxy resin so that further corrosion of the reinforcing steel would not be caused by the presence of existing cracks outside of the patched area (Figure 64).



Figure 63: Presence of cracking exposed through routing



Figure 64: Application of epoxy resin to fill cracks on horizontal face of CoC specimens

In addition, the existing cracks on the sides of the CoC specimens were also

addressed (Figure 65). After routing, these cracks were sealed with a silicone sealant

(Figure 66).



Figure 65: Existing cracks on the sides of the CoC specimens



Figure 66: Application of silicone sealant to routed cracks

3.3.6.2 Conventional Patch Material Application

Prior to placement of the repair material, the substrate concrete and reinforcing were prepared. The electrical continuity of the reinforcing bars was also checked. If continuity was not achieved, rebar ties or welding was used to provide it.

As specified by the conventional patch material data sheet ⁽¹¹⁵⁾, a water based and epoxy modified portland cement bonding agent and corrosion resistant coating was used. ⁽¹¹⁷⁾ Once continuity was achieved, the first coat of the corrosion resistant coating was applied to the steel (Figure 67). Care was taken not to coat the points of electrical continuity, the connections of the anodes to the reinforcing steel, or the anodes themselves. After the corrosion resistant coating had cured for the specified amount of time, the epoxy modified portland cement bonding agent was applied to the substrate concrete (Figure 68). However, the bonding agent was not applied directly below the anodes. During this time, the second coat of the corrosion resistant coating was applied to the steel.



Figure 67: Application of anti-corrosion coating to reinforcing steel



Figure 68: Application of bonding agent to substrate (not applied on or directly below anodes)

Although epoxy bonding agents are not generally recommended for use with galvanic anodes ^{(48), (56)}, epoxy bonding agents can be used if the metallic path and the ionic path are maintained. Since the metallic path had already been confirmed, the ionic

path from the anode to the cathode had to be provided as well. This could be accomplished by dry-packing below the anode or not creating a barrier between the anode and the substrate. In the case of using epoxy bonding agents with thermal sprayed metals, the ionic path will still reach the bars in the patch and the areas outside the patch; however, the ionic path may not be able to get to the bars immediately below the patched area because the bonding agent effectively creates a barrier between lower layer of reinforcing steel and the ionic path. ⁽¹¹⁸⁾

Since the conventional patch material recommended the use of an epoxy bonding agent and the epoxy repair material specified a concrete primer, we chose to use the epoxy bonding agent for consistency. However, an ionic path between the galvanic anodes and the substrate concrete was provided.

After the steel and substrate concrete were prepared, the repair material was placed. As per specifications, the repair material was placed in two, $1\frac{1}{2}$ " lifts. Care was taken to ensure that an ionic path was provided by placing the repair material below the embedded anodes (Figure 69). After the first lift was placed and allowed to reach final set (which took approximately 30 minutes), the surface was scored and the second lift was placed (Figure 70). After allowing the 2^{nd} lift to reach final set, the surface was broom finished.

90



Figure 69: Placing the conventional patch repair material



Figure 70: Scoring of the conventional patch repair material after the first lift had reached final set

3.3.6.3 EM Application

As per recommendations from Supplier F, a liquid epoxy coating was applied to the exposed and cleaned reinforcing steel. After this, the concrete primer was mixed and applied to the substrate concrete (Figure 71). The repair material was then mixed and hand-applied to the still tacky primed area (Figure 72). The repair material was packed under and around the reinforcing steel. It was then finished smooth with the supplied trowel.



Figure 71: Applying the concrete primer for EM



Figure 72: Applying the EM

(Page left blank intentionally)

CHAPTER 4

EXPERIMENTAL RESULTS AND DISCUSSION

4.1 General

Based on the aforementioned experimental program, the experiments were broken into two categories: "corrosion prevention" and "corrosion control." The CoP specimens were treated prior to exposure to accelerated corrosion testing and evaluated after 6months of exposure. The CoC specimens were cast with mixed-in chlorides and were first exposed to accelerated corrosion testing for 3-months. Subsequently, they were subjected to concrete patch repairs, treated with various corrosion control products, subjected to an additional 3-months of accelerated corrosion testing, and evaluated at the conclusion of the testing.

The corrosion current was monitored at regular intervals throughout the duration of the accelerated corrosion program. Extensive laboratory testing and analyses of chloride ingress were also performed. In addition, half-cell potential readings were periodically taken. Detailed crack-maps were generated at 0-months, 3-months, and 6months exposure. At the conclusion of testing, the extent of rust-staining on the concrete surface was evaluated. Finally, the specimens were dissected and the embedded reinforcing steel was evaluated for extent of corrosion.

4.1.1 Concrete Material Data

The slump of the concrete was measured at 4.75". See Table 15 for a mix design (as submitted by the supplier).

93

Product	Amount
Cement	450 lb
Fly Ash	100 lb
Sand	1370 lb
³ / ₄ " Aggregate	1830 lb
Water Reducer	4 ounce

The average 28-day compressive strength of three, 6"x12" cylinders was measured at 5,839 psi. The concrete delivery sheet and mil certification for the reinforcing steel can be found in Appendix A. The concrete cylinder strength results can be found in Appendix B.

4.1.2 Current Monitoring

A regulated 9V potential was applied between the anode and cathode of the specimens over the duration of the exposure cycles to facilitate accelerated corrosion and to increase the rate of chloride intrusion. Plots of corresponding corrosion current versus time for the CoP specimens are shown in Section 4.1.2.1 and plots for the CoC specimens are shown in Section 4.1.2.2. As expected, the corrosion currents increased during the wet cycles (shaded region) and decreased during the dry cycles.

When examining the corrosion current vs. time graphs, it is important to note that the area under curve is proportional to the amount of steel lost due to corrosion. Accordingly, the specimens that exhibit the least area below the curve experience less steel loss and thereby provide more corrosion protection.

4.1.2.1 Current Monitoring for CoP Specimens

When comparing the "average" (Figure 73) and "individual" (Figure 74) CoP graphs, one can see a reasonable agreement between "identical" specimens. That is, specimens with the same treatment behaved in a reasonably similar fashion.

From the initiation of testing until approximately 60 days, all specimens appeared to exhibit a decrease in monitored current. Tabatabai et al. reported that this phenomenon is common in such experiments as the corrosion products increase electrical resistance around the bar, thereby decreasing current when a fixed voltage is applied. ⁽²⁴⁾

After 60 days, the T-SS, EP-C, TSZ w/EP-C, A-C, TSZ, and EA-A w/A-C specimens continued to display a decrease in corrosion current with respect to time. Meanwhile, the corrosion currents for the EA-A and Control specimens remained relatively constant. However, the EA-B specimens displayed an increase in current. It is believed that a non-uniform chloride ingress caused more severe anodic and cathodic reactions on the rebar, thus increasing the corrosion current. The presence of chloride "hot spots" around the anodes was later verified through chloride testing. The chloride "hot spots" are believed to have contributed to the increased corrosion current.

When comparing the conjoint use of coatings with galvanic anodes (whether they be embedded or thermal sprayed), it was found that the coatings helped reduce corrosion currents. While the corrosion currents for the EP-C and TSZ w/EP-C were similar, the specimens with TSZ alone exhibited higher corrosion currents. In regards to the use of coatings with or without embedded anodes, the A-C alone exhibited a lower corrosion current than the EA-A w/A-C. However, the specimens with the EA-A alone exhibited higher corrosion currents than that of the specimens with EA-A w/A-C

95

Based on the results of the current monitoring for the laboratory CoP specimens, it can be concluded that the tri-silane sealer (T-SS), epoxy/polyurethane coating (EP-C), and thermal sprayed zinc with epoxy/polyurethane coating (TSZ w/EP-C) were most effective.





Figure 73: Average corrosion currents of CoP specimens






4.1.2.2 Current Monitoring for CoC Specimens


When comparing the "average" (Figure 75) and "individual" (Figure 76) CoC graphs from Day 1 to 3-months, there appears to be reasonable agreement among all specimens (as expected). Therefore, it was concluded that the laboratory CoC specimens were in an approximately similar condition after the first 3-months of testing.

When comparing the "average" and "individual" CoC graphs from 3-months to 6months, reasonable agreement can be seen among individual specimens belonging to TSZ, TSZ w/EP-C, EA-A w/A-C, and EM treatments. However, there were significant discrepancies among specimens belonging to the Control, EA-A, and EA-B treatments. The following discussion is based on the "average" graph.

The TSZ, EA-A w/A-C, and TSZ w/EP-C treatments all displayed a decrease in corrosion current while the Control and EM specimens increased initially, then decreased. It is believed the rapid increase in corrosion current for the EM was due to its widely dissimilar material properties compared with the surrounding concrete. Meanwhile, EA-A and EA-B exhibited an increase in corrosion current over time, after treatment.









4.1.3 Steel Loss

By utilizing the aforementioned corrosion currents, the amount of steel loss could be calculated through the use of Equation 11: ⁽¹¹⁹⁾

$$m = \frac{A^{tm}C}{Fz}$$
(Eq. 11)

where
$$m = \text{loss of mass}$$

 $A^{tm} = \text{atomic mass of the reaction ion (55.85 g/mol for iron)}$
 $C = \text{total charge that has passed through the circuit}$
 $= \int I(t)dt$
 $F = \text{Faraday's constant (96485 C/mol)}$
 $z = \text{valence of reaction (assumed to be 2)}^{(24), (119)}$

Numerical integration was used to calculate the total charge. This was done by summing the products of each current reading by the time increment between readings. For Specimens #13 through #16, there were some sporadic readings during a two-week period. The problem was identified and corrected subsequently.

The results of the steel loss calculations (Tables 16 and 17) were indexed according to a scale of 0 to 4. The indices were determined using Eq. 12:

Index =
$$\frac{(actual value) - (minimum value)}{(maximum value) - (minimum value)} x 4$$
 (Eq. 12)

Specimen #	Treatment	Theoretical Steel Loss (g)	Index
1	TSZ	483.8	1.0
2	152	500.2	1.1
3	TSZ w/EP-C	406.7	0.3
4	ISZ W/EF-C	397.4	0.3
5	EA-A w/A-C	506.7	1.2
6	LA-A W/A-C	500.2	1.1
7	EA-A	605.8	2.0
8	LA-A	586.2	1.9
9	EA-B	734.4	3.1
10	LA-D	839.8	4.0
11	T-SS	370.0	0.0
12	1-36	365.2	0.0
13	A-C	420.5	0.5
14	EP-C	396.1	0.3
15	Control	610.0	2.1
16	Control	576.6	1.8

 Table 16:
 Steel loss of CoP Specimens after 6-months of exposure

For the CoP specimens, the T-SS, EP-C, TSZ w/EP-C and A-C specimens gave the lowest theoretical steel loss index values. In contrast, the EA-B, EA-A, and Control specimens had the highest index values. When comparing these index values to the corrosion currents of Figures 73 and 74, a direct comparison can be seen.

To present the theoretical steel loss values for the CoC specimens over the duration of testing, Table 17 includes the steel loss and associated index values for the following time intervals: 0-3 months, 3-6 months, and 0-6 months. The indices were determined for each data subset using Eq. 11. Specimens #17 through #28 utilized the conventional patch repair material, while Specimens #29 and #30 utilized the EM.

Specimen #	Future Treatment	0 - 3 Month Steel Loss (g)	3 - 6 Month Steel Loss (g)	3 - 6 Month Index	0-6 Month Steel Loss (g)	0 – 6 Month Index
17	Control	348.3	101.4	0.5	449.7	1.9
18	Control	366.0	196.0	2.1	562.0	3.7
19	TSZ w/EP-C	341.9	71.1	0.0	413.0	1.3
20	ISZ W/LF-C	330.9	76.0	0.1	406.9	1.2
21	T 07	333.0	105.0	0.6	438.0	1.7
22	TSZ	293.7	76.2	0.1	369.8	0.5
23	EA-A	381.6	149.7	1.3	531.4	3.2
24	EA-A	294.6	201.9	2.2	496.5	2.6
25	EA-A w/A-C	288.5	87.7	0.3	376.2	0.7
26	EA-A W/A-C	267.9	68.8	0.0	336.7	0.0
27	EA-B	299.6	206.9	2.3	506.5	2.8
28	EA-D	291.3	131.5	1.0	422.7	1.4
29	EM	310.5	239.5	2.8	550.1	3.5
30		267.5	311.2	4.0	578.7	4.0

Table 17: Steel loss of CoC specimens after 3-months and 6-months exposure

For the 0-3 month data, it may at first appear that there is a wide range of index values; however, the average steel loss was calculated to be 315.4g with a standard deviation of 35.4g. Based on the steel loss values, it appears that the CoC specimens were in a reasonably similar condition after the first 3-months of laboratory testing.

For the 3-6 month steel loss data, the Index values can be used to compare the specimens as there is significant variation among the steel loss results. For this period of data, the TSZ w/EP-C, EA-A w/A-C, and TSZ produced the lowest indices.

When looking at the 0-6 month Index, EA-A w/A-C, TSZ, and TSZ w/EP-C had the lowest Index values. Therefore, it can be concluded that these laboratory CoC treatments performed better with regard to theoretical steel loss due to corrosion. It is interesting to note that each of these treatments is essentially a coating.

4.1.4 Chloride Contents

The chloride content of the concrete was determined by analyzing pulverized concrete at various depths using the Rapid Chloride Test method (RCT 1029). This method has been shown to be in excellent agreement with the AASHTO T-260 potentiometric titration. ⁽¹²⁰⁾ The RCT 1029 method measures the acid soluble chlorides as a percentage of concrete mass. After the concrete powders were extracted from the specimens with a hammer drill (Figure 77), a 1.5g sample was weighed and mixed with a vial that contained 10 mL of an extraction liquid. A potential reading of each sample was taken using the RCT readout device and electrode (Figure 78). Readings were taken 5-minutes after mixing, and then again after 24-hours. The 24-hour test gives higher acid-soluble chloride content. Therefore, it is believed to be closer to the total chloride content in the concrete powder. After testing, the potential results were converted to a chloride content in percent of concrete mass using the supplied calibration chart. Although the calibration chart was initially used to calculate the chloride contents, a spreadsheet equation derived from the calibration chart was later used.

Unless otherwise noted, all values of chloride content presented in the remainder of this work are the 24-hour tests in terms of "percent chlorides by mass of concrete."



Figure 77: Collecting the concrete powders



Figure 78: Mixing concrete powders with the extraction liquid (far) & reading potentials (near)

This same approach was followed for determining the chloride content of virgin concrete, concrete with pre-mixed chlorides in the CoC specimens, concrete after 3-months exposure in CoC specimens, concrete after 6-months exposure in both CoC and CoP specimens, and the bridge decks tested in the field. In all, approximately 2,000 concrete powders were analyzed for this project (Figure 79).



Figure 79: Tested concrete powder samples

4.1.4.1 Base-Line (Virgin Concrete)

The virgin chloride content (taken prior to accelerated corrosion exposure) was taken at two locations in three separate specimens (Table 18). See Appendix B for detailed results. At each location, samples were taken at two different depths from the concrete surface. Powder samples were taken from depths of $0^{"}$ - $\frac{1}{2}^{"}$ and $\frac{1}{2}^{"}$ - 1".

Sample Location	Depth of Testing	%Cl by concrete weight	lbs Cl/ yd ³ concrete
11B	$0" - \frac{1}{2}"$	0.037	1.449
11B	$\frac{1}{2}"-1"$	0.034	1.331
11C	$0" - \frac{1}{2}"$	0.046	1.801
11C	$\frac{1}{2}"-1"$	0.040	1.566
13B	$0" - \frac{1}{2}"$	0.035	1.370
13B	$\frac{1}{2}"-1"$	0.033	1.292
13C	$0" - \frac{1}{2}"$	0.048	1.879
13C	$\frac{1}{2}"-1"$	0.046	1.801
15B	$0" - \frac{1}{2}"$	0.050	1.958
15B	$\frac{1}{2}"-1"$	0.048	1.879
15C	$0" - \frac{1}{2}"$	0.049	1.918
15C	$\frac{1}{2}"-1"$	0.039	1.527

Table 18: Base-line chloride content of specimens

The average measured chloride content of the virgin concrete was 0.042% by concrete weight, or approximately 1.648 lb/yd^3 of concrete. This measured chloride content was relatively high. Using a 6:1 cement to concrete ratio, the chloride content equals 0.252% chlorides by weight of cement. This is approximately 2.5 times greater than the acid-soluble limit recommended by ACI 222 (see Table 2).

An earlier project, WHRP Project 0092-01-06, discovered a similar chloride content in its virgin concrete. ⁽²⁴⁾ The average chloride content of virgin concrete in that study was measured at 0.053% by concrete weight. To find the source of chlorides, they performed a number of tests to determine chloride contents of the mix water, as well as the coarse and fine aggregates. ⁽²⁴⁾

Based on their findings, it was determined that coarse aggregates (limestone) were the source of the high chloride levels found in the virgin concrete. ⁽²⁴⁾ It was not clear from the tests performed whether the acid-soluble chlorides were bound within the aggregates, or if they could enter the cement paste.

4.1.4.2 CoP Specimens after 6-Months

To determine the effectiveness of the CoP products in reducing the ingress of chlorides into the concrete, chloride analyses were performed after the completion of 6-months of accelerated testing (Table 19). As mentioned previously, three concrete powder locations per specimen, with powders taken at ¹/₄" increments of depth, were used to calculate average chloride contents. Thus, each listed value of chlorides is based on the average of three separate concrete powders. The locations selected for testing were consistent in each specimen tested (See Appendix C for complete results).

		Chloride Content (% Chlorides by Mass of Concrete)								
	T	SZ	TSZ w	TSZ w/EP-C EA-A w/A-C		w/A-C	EA-A			
Depth \Specimen	#1	#2	#3	#4	#5	#6	# 7	#8		
0" to $\frac{1}{4}$ "	0.197	0.331	0.096	0.197	0.484	0.479	0.416	0.388		
$\frac{1}{4}$ " to $\frac{1}{2}$ "	0.107	0.169	0.040	0.057	0.361	0.290	0.405	0.282		
$\frac{1}{2}$ " to $\frac{3}{4}$ "	0.062	0.055	0.043	0.053	0.163	0.147	0.330	0.165		
³ / ₄ " to 1"	0.035	0.040	0.045	0.035	0.057	0.067	0.268	0.092		
1" to $1\frac{1}{4}$ "	0.019	0.032	0.043	0.033	0.052	0.034	0.138	0.050		
$1\frac{1}{4}$ " to $1\frac{1}{2}$ "	0.028	0.028	0.037	0.045	0.048	0.023	0.044	0.031		
$1\frac{1}{2}$ " to $1\frac{3}{4}$ "	0.030	0.022	0.023	0.029	0.028	0.019	0.023	0.019		
$1^{3}/4$ " to 2"	0.030	0.017	0.033	0.036	0.033	0.025	0.015	0.022		
	EA	А-В	T-SS		A-C EP-C		Control			
Depth \Specimen	#9	#10	#11	#12	#13	#14	#15	#16		
0" to $\frac{1}{4}$ "	0.445	0.555	0.076	0.115	0.415	0.040	0.344	0.372		
¹ / ₄ " to ¹ / ₂ "	0.418	0.481	0.034	0.034	0.250	0.034	0.292	0.284		
$\frac{1}{2}$ " to $\frac{3}{4}$ "	0.322	0.421	0.027	0.022	0.125	0.028	0.166	0.161		
³ / ₄ " to 1"	0.385	0.380	0.026	0.019	0.062	0.026	0.094	0.079		
1" to $1\frac{1}{4}$ "	0.447	0.349	0.020	0.020	0.032	0.022	0.078	0.055		
$1\frac{1}{4}$ " to $1\frac{1}{2}$ "	0.407	0.306	0.020	0.031	0.027	0.023	0.076	0.034		
$1\frac{1}{2}$ " to $1\frac{3}{4}$ "	0.304	0.171	0.025	0.034	0.038	0.019	0.069	0.021		
1 ³ / ₄ " to 2"	0.160	0.107	0.017	0.028	0.042	0.019	0.045	0.033		

Table 19: Average acid-soluble chloride content of CoP specimens after 6-months


To more fully understand the results in Table 19, Figure 80 has been developed to visualize the average chloride content of the CoP specimens at 6-months.

As expected, the chloride content was highest at the concrete surface and

decreased with the distance from the surface. The testing also revealed that the

epoxy/polyurethane coating (EP-C) was most effective in reducing the ingress of chlorides. This was followed by the tri-silane sealer (T-SS) and thermal sprayed zinc with epoxy/polyurethane coating (TSZ w/EP-C).

One type of specimen shows markedly different chloride profiles. As discussed later, the presence of embedded anodes affected the distribution of chlorides in the horizontal plane.



To further analyze the chloride content, regression analyses were performed. These analyses involved finding the parameters for Fick's 2^{nd} Law of diffusion (Eq. 10) such that they best-fit the experimental data. The parameters are the diffusion coefficients (*D*) and the surface chloride concentration (*C*₀). This optimization effort utilized Microsoft Excel's "solver" function and involved minimizing the sum of squares of errors between the experimental data and Fick's Law predictions.

Prior to regression analysis, the virgin chloride content was subtracted from the values shown in Table 19. By doing so, only the chlorides that penetrated the concrete during exposure would be considered. If the actual level of calculated chlorides was less than the base-level chlorides (0.042% by concrete weight), a value of "0" was given.

By utilizing a time of 0.5 years in the regression analysis, a uniform surface chloride concentration of 0.476% chlorides by mass of concrete (18.648 lb/yd³) was calculated. An example of the agreement between the actual 6-month chlorides and chloride regression plus base-line chlorides is shown in Figure 81. Table 20 presents the calculated diffusion coefficients for each specimen and the average of each treatment.




Figure 81: Agreement of actual and theoretical chlorides for Specimen #16

Specimen #	Treatment	C ₀ (% Cl)	D _{Specimen} (in ² /yr)	D _{Treatment} (in ² /yr)
1	T07		0.017	054
2	TSZ		0.091	.054
3	TSZ w/EP-C		0.006	.011
4	ISZ W/EF-C		0.016	.011
5	EA-A w/A-C		0.353	.320
6	EA-A W/A-C		0.286	.520
7	EA-A		See Note B	See Note B
8	EA-A	0.476	0.283	See Note D
9	EA-B	0.470	See Note C	See Note C
10	EA-D		See Note C	See Note C
11	T-SS		0.005	.002
12	1-55		0.000	.002
13	A-C		0.215	.215
14	EP-C		0.000	.000
15	Control		0.295	.282
16	Control		0.269	.202

Table 20: Calculated chloride diffusion coefficients for CoP specimens after 6-Months

NOTE A: For Specimen #2, a failure occurred at the connection between the thermal spray zinc and reinforcing steel.

NOTE B: For Specimen #7, the diffusion coefficient was found to be $0.890 \text{ in}^2/\text{yr}$. This high value can be attributed to the level of chlorides found at Location 7E. Using this calculated diffusion coefficient, an average value of $0.586 \text{ in}^2/\text{yr}$ was calculated for EA-A. Because of the unusually high value of Location 7E, it was removed for the revised analysis (Table 21). Location 7E was adjacent to an anode and points to the presence of chloride "hot spots."

NOTE C: For Specimen #9, there were inconsistencies with the chloride contents of Locations D and E. For Specimen #10, there were also indications of chloride "hot spots" at Location D. The diffusion coefficient for Specimen #9 was calculated to be $6.192 \text{ in}^2/\text{yr}$ while the value for Specimen #10 was $3.470 \text{ in}^2/\text{yr}$. This gave an average of $4.831 \text{ in}^2/\text{y}$ for EA-B. Because this chloride distribution was not compatible with Fick's 2^{nd} Law, Specimens #9 and #10 were removed in the revised analysis (Table 21).

From Table 20 above, it was found that the EP-C, T-SS, and TSZ w/EP-C were

most effective in preventing the ingress of chlorides. To account for the noted

inadequacies of Specimens #7, #9, and #10, a revised regression analysis was performed

(Table 21).

To create an Index value for Specimens #9 and #10, their diffusion coefficients

were assumed to be $0.50 \text{ in}^2/\text{yr}$ so that they could be compared to the other specimens.

As an additional criterion, the chloride content of the top 1" of concrete for all specimens

was compared (Table 21). This was then used as the primary rating criteria for the CoP chlorides at 6-months since the regression analysis using Fick's 2nd Law could not be used to directly compare all of the specimens.

Specimen #	Treatment	C ₀ . revised (% Cl)	$\begin{array}{c} \mathbf{D}_{\text{Specimen-}} \\ \text{revised} \\ (\text{in}^2/\text{yr}) \end{array}$	D _{Treatment} - revised (in ² /yr)	Index for "D"	%Cl ⁻ in Top 1"	Index for %Cl ⁻ in Top 1"
1	TSZ		0.017	0.055	0.1	0.100	0.6
2	152		0.092	0.033	0.7	0.149	1.1
3	TSZ		0.006	0.011	0.0	0.056	0.2
4	w/EP-C		0.016	0.011	0.1	0.085	0.5
5	EA-A		0.357	0.324	2.9	0.266	2.2
6	w/A-C		0.290		2.3	0.246	2.0
7	EA-A	0.472	0.362	0.324	2.9	0.355	3.0
8	EA-A		0.287		2.3	0.232	1.9
9	EA-B	0.472	-	_ *	4.0	0.393	3.4
10	EA-D		-		4.0	0.459	4.0
11	T-SS		0.005	0.002	0.0	0.041	0.1
12	1-55		0.000	0.002	0.0	0.047	0.1
13	A-C		0.218	0.218	1.7	0.213	1.7
14	EP-C		0.000	0.000	0.0	0.032	0.0
15	Control		0.300	0.287	2.4	0.224	1.8
16		• 1	0.273	0.207	2.2	0.224	1.8

Table 21: Revised chloride diffusion coefficients and top 1" chlorides for CoP specimens after 6-Months

* - assumed to be $0.50in^2/yr$ to provide a comparison

As seen in Table 21, the surface chloride concentration and diffusion coefficients for the treatments that were not affected by the chloride "hot spots" contents did not change appreciably. However, by removing Location 7E from the regression analysis, the diffusion coefficient for Specimen #7 dropped from 0.890 in²/yr to 0.362 in²/yr.

When comparing the Index values for the diffusion coefficients and chloride content of the top 1" of concrete, there is reasonable agreement. Based on these indices, it can be concluded that the EP-C, T-SS, and TSZ w/EP-C were most effective in reducing the ingress of chlorides. In contrast, EA-A and EA-B were least effective in reducing chloride ingress. From the results, it appears that the embedded anodes actually attracted chlorides to their vicinity.

For Specimens #1 - #4, the "before" and "after" calibration numbers varied considerably. To check the validity of chloride testing, the chloride testing equipment were checked against calibration liquids with known chloride contents before and after each set of tests (See Appendix C). In contrast, the "before" and "after" calibration values for the 0-month and 3-month CoC specimens and the bridge decks, all of which will be discussed later, had little variation.

After some experimentation with the 5-minute tests, we discovered that the calibration values changed as soon as a vial containing chloride powders from the TSZ specimens was tested. This experimentation involved the cleaning of the RCT electrode after some tests, replacement of the electrode wetting agent, and retesting of the calibration liquids. When this assessment was completed, the calibration values returned to normal. As soon as a vial with TSZ powder was tested, the calibration values again dropped. After further evaluations and inquiry from the chloride test equipment supplier, we concluded that the zinc from the thermal spray may have an adverse effect on the testing procedure, which is based on potential readings. Therefore, chloride contents for Specimens #1 - #4 were determined from the calibration numbers at the conclusion of testing and not the average of the "before" and "after" calibrations.

In regards to Specimens #7, #9, and #10, Locations 7E, 9D, 9E, and 10D produced chloride profiles that were not consistent with Fick's 2nd Law of Diffusion (Figure 82). Because of these inconsistent values, 2 to 4 additional locations were tested near each area in question (Figures 83 and 84).

113




Figure 82: Chloride profiles for Locations 7E(1), 9D(1), 9E(1), and 10D(1)



Figure 83: Location of additional chloride tests for Specimen #9



Figure 84: Location of additional chloride tests for Specimen #10

Similar to the TSZ specimens, the calibration values for Specimens #7, #9, and #10 varied significantly, albeit much more dramatically (See Appendix C). To determine the extent of the change of calibration values, numerous checks were taken during the course of the retests for locations 7E, 9D, 9E, and 10D as the calibration values immediately dropped after the first few tests and continued to drop throughout the testing. To correctly measure the chlorides, the spreadsheet equation was adjusted for each set of calibration checks. As with the TSZ, we feel that the zinc from the embedded anodes may have had an effect on these values.

Because of the variation in chloride contents at similar locations (Figure 85), we concluded that the chloride penetration in these specimens was not one-dimensional and did not conform to Fick's 2nd Law.




Figure 85: Chloride contents near Location 9E

The most significant variation of chlorides occurred at the level of reinforcing, which was 1" from the concrete surface. As seen in Figure 86, horizontal cracks were present at the level of the reinforcing steel. In addition, significant staining was found on the dissected concrete at the level of the reinforcing steel (Figure 87). Detailed condition observations can be found in Section 4.2.



Figure 86: Presence of cracking on exterior of Specimen #9.



Figure 87: Presence of significant concrete staining on dissected concrete of Specimen #9

To determine where the variation in chlorides occurred, additional testing was performed on the specimens containing EA-B. Two samples were taken near the anode, (i.e. Location A), and two sets of two samples were taken from concrete outside the "anode grid" (i.e. Locations E and W, Figure 88). When referring to the concrete powders locations of Figure 56, tests for Specimen #9 were taken near Location D while tests for Specimen #10 were taken near Location C. The tests revealed that chloride "hot spots" could be found near the anodes (Table 22). Additionally, corrosion staining was more severe in the vicinity of the anodes.




Figure 88: Location of "near anode" chloride tests for EA-B

Location	%Cl by concrete weight	Average %Cl by concrete weight
9W ¼"	0.039	0.026
9W ½"	0.013	0.020
9A ¼"	0.078	0.065
9A ½"	0.053	0.003
9E ¼"	0.035	0.026
9E ½"	0.016	0.020
10W ¼"	0.023	0.022
10W ½"	0.021	0.022
10A ¼"	0.027	0.026
10A ½"	0.025	0.026
10E ¼"	0.026	0.023
10E ½"	0.021	0.025

Table 22: "Near anode" chloride contents for E.A.-B

4.1.4.3 CoC Specimens at 0-Months

The mixed-in chloride content of the CoC specimens was evaluated prior to exposure to accelerated corrosion so that confirmation of the actual chloride contents of the specimens could be made.

Chloride testing (see Appendix D) revealed that the actual chloride content (Table 23) was in reasonable agreement with the initial theoretical chloride content (see Table 13), once the virgin chloride content was added to the theoretical chlorides. For clarification, subsequent treatments for each specimen have been indicated in Table 23.

Donth Specimon	Con	trol	TSZ w	/ ЕР-С	TS	SZ	EA	-A
Depth \Specimen	#17	#18	#19	#20	#21	#22	#23	#24
0" to $\frac{1}{4}$ "	0.177	0.201	0.183	0.183	0.190	0.181	0.194	0.177
$\frac{1}{4}$ " to $\frac{1}{2}$ "	0.200	0.207	0.169	0.172	0.139	0.173	0.192	0.174
$\frac{1}{2}$ " to $\frac{3}{4}$ "	0.143	0.159	0.127	0.144	0.129	0.140	0.183	0.163
³ ⁄ ₄ " to 1"	0.139	0.131	0.120	0.103	0.142	0.139	0.143	0.136
1" to $1\frac{1}{4}$ "	0.137	0.128	0.120	0.124	0.111	0.120	0.121	0.119
$1\frac{1}{4}$ " to $1\frac{1}{2}$ "	0.126	0.110	0.115	0.111	0.099	0.121	0.111	0.094
$1\frac{1}{2}$ " to 2"	0.097	0.081	0.089	0.080	0.092	0.101	0.094	0.078
2" to $2\frac{1}{2}$ "	0.069	0.068	0.067	0.085	0.076	0.076	0.070	0.075
$2^{1/2}$ " to 3"	0.043	0.072	0.066	0.062	0.073	0.062	0.045	0.050
	EA-A	EA-A w/A-C		EA-B		EM		
Depth\Specimen	#25	#26	#27	#28	#29	#30		
0" to $\frac{1}{4}$ "	0.176	0.189	0.162	0.191	0.174	0.179		
$\frac{1}{4}$ " to $\frac{1}{2}$ "	0.150	0.174	0.161	0.143	0.161	0.178		
$\frac{1}{2}$ " to $\frac{3}{4}$ "	0.151	0.144	0.131	0.120	0.112	0.141		
$\frac{3}{4}$ " to 1"	0.137	0.133	0.132	0.124	0.114	0.106		
74 to 1	0.157	0.155	0.152	0.121	0.11.	0.1 - 0.0		
$\frac{74}{1^{\circ}}$ to $1^{1/4}$	0.137	0.133	0.132	0.098	0.111	0.124		
1" to $1\frac{1}{4}$ "	0.112	0.124	0.117	0.098	0.111	0.124		
$\frac{1" \text{ to } 1\frac{1}{4}"}{1\frac{1}{4}" \text{ to } 1\frac{1}{2}"}$	0.112 0.093	0.124 0.113	0.117 0.099	0.098 0.101	0.111 0.112	0.124 0.115		

Table 23: Average acid-soluble chloride contents of CoC specimens at 0-months

To further quantify the effectiveness of the addition of chlorides to the concrete

mix, Table 24 displays the average chloride content and standard deviation within the top

three inches of concrete.

Table 24: Comparison of initial theoretical and average acid-soluble chloride contents of CoC specimens at 0-months

Depth	Theoretical plus Virgin Chlorides	Average of Actual Chlorides per Increment of Depth	Standard Deviation	Average of Actual Chlorides per Inch
0" to $\frac{1}{4}$ "		0.183	0.010	
$\frac{1}{4}$ " to $\frac{1}{2}$ "	.155	0.171	0.020	.156
$\frac{1}{2}$ " to $\frac{3}{4}$ "		0.142	0.018	.130
³ ⁄ ₄ " to 1"		0.129	0.013	
1" to $1\frac{1}{4}$ "		0.119	0.009	
$1\frac{1}{4}$ " to $1\frac{1}{2}$ "	.090	0.109	0.010	.106
$1\frac{1}{2}$ " to 2"		0.089	0.009	
2" to $2\frac{1}{2}$ "	050	0.073	0.007	065
$2^{1}/2$ " to 3"	.056	0.057	0.010	.065

By utilizing the aforementioned regression analysis, the agreement between the intended initial theoretical chloride content (mixed-in chlorides) and experimental data could be further verified. Using a time of 10 years (assumed for calculating the amount of mixed-in chlorides), C_0 was found to equal 0.149% chlorides by concrete weight (5.83 lb/yd³) and D_{avg} was found to equal 0.150 in²/yr, with a standard deviation of 0.026 (Table 25). These values are in excellent agreement with the values of $C_0 = 0.153\%$ (5.985lb/yd³) and D = 0.11 in²/yr that were used initially to determine the mixed-in chlorides. Figure 89 shows the initial theoretical chlorides, initial chlorides, and initial regression plus base-line chlorides. Because the regression analyses did not include the base-line chlorides, the plot includes the addition of the base-line chlorides to the values obtained from the regression analysis. By doing so, one can see a direct comparison of the data.

Because of the excellent agreement of the diffusion coefficients, an Index rating was not used to compare the specimens.

Specimen #	Subsequent Treatment	C0 (% by concrete weight)	D _{Specimen} (in ² /yr)	$\mathbf{D}_{\mathbf{Treatment}}$ (in ² /yr)	
17	Control		0.185	0.181	
18	Collutor		0.177	0.181	
19	TSZ w/EP-C		0.143	0.143	
20	152 w/Ei -C		0.144	0.145	
21	TSZ		0.143	0.163	
22	152		0.184	0.105	
23	EA-A	0.149	0.180	0.160	
24	LA-A	0.149	0.140	0.100	
25	EA-A w/A-C		0.130		
26	EA-A W/A-C		0.154	0.142	
27	EA-B		0.121	0.111	
28	LA-D		0.101	0.111	
29	EM		0.128	0.148	
30			0.168	0.140	

Table 25: Calculated chloride diffusion coefficients for CoC Specimens at 0-months




Figure 89: Comparison of initial theoretical, initial, and regression chlorides for Specimen #17

4.1.4.4 CoC Specimens after 3-Months

Prior to removing parts of the CoC specimens for patch repair, the specimens were again evaluated for chlorides after 3-months of accelerated corrosion testing (Table 26). Chloride testing (see Appendix E) revealed that the chlorides were effectively drawn into the concrete. In Table 26, the various treatments shown refer to subsequent treatments since the CoC specimens were not treated within the first 3-months of exposure.

Donth Specimon	Con	trol	TSZ w	/EP-C	TS	SZ	EA	-A
Depth\Specimen	#17	#18	#19	#20	#21	#22	#23	#24
0" to $\frac{1}{4}$ "	0.492	0.427	0.465	0.468	0.617	0.617	0.467	0.453
$\frac{1}{4}$ " to $\frac{1}{2}$ "	0.410	0.365	0.398	0.427	0.465	0.422	0.414	0.295
$\frac{1}{2}$ " to $\frac{3}{4}$ "	0.238	0.255	0.298	0.299	0.365	0.242	0.235	0.187
³ ⁄ ₄ " to 1"	0.158	0.275	0.184	0.220	0.279	0.157	0.171	0.143
1" to $1\frac{1}{4}$ "	0.151	0.183	0.130	0.134	0.215	0.112	0.109	0.096
$1\frac{1}{4}$ " to $1\frac{1}{2}$ "	0.133	0.157	0.117	0.136	0.156	0.099	0.090	0.084
$1\frac{1}{2}$ " to $1\frac{3}{4}$ "	0.113	0.129	0.117	0.119	0.104	0.102	0.094	0.087
$1\frac{3}{4}$ " to 2"	0.123	0.099	0.093	0.112	0.082	0.079	0.090	0.094
Depth\Specimen	EA-A	w/A-C	EA	-B	E	Μ		
Deptil/Specillell	#25	#26	#27	#28	#29	#30		
0 " to $\frac{1}{4}$ "	#25 0.477	#26 0.452				1		
			#27	#28	#29	#30		
0 " to $\frac{1}{4}$ "	0.477	0.452	#27 0.603	#28 0.503	#29 0.527	#30 0.460		
$\frac{0" \text{ to } \frac{1}{4}"}{\frac{1}{4}" \text{ to } \frac{1}{2}"}$	0.477 0.330	0.452 0.297	#27 0.603 0.341	#28 0.503 0.321	#29 0.527 0.348	#30 0.460 0.304		
$\frac{0" \text{ to } \frac{1}{4}"}{\frac{1}{4}" \text{ to } \frac{1}{2}"}$ $\frac{1}{2"} \text{ to } \frac{3}{4}"$	0.477 0.330 0.233	0.452 0.297 0.211	#27 0.603 0.341 0.244	#28 0.503 0.321 0.197	#29 0.527 0.348 0.204	#30 0.460 0.304 0.199		
$ \begin{array}{c} 0" to \frac{1}{4}" \\ \frac{1}{4}" to \frac{1}{2}" \\ \frac{1}{2}" to \frac{3}{4}" \\ \frac{3}{4}" to 1" \end{array} $	0.477 0.330 0.233 0.138	0.452 0.297 0.211 0.164	#27 0.603 0.341 0.244 0.148	#28 0.503 0.321 0.197 0.133	#29 0.527 0.348 0.204 0.137	#30 0.460 0.304 0.199 0.136		
$ \begin{array}{r} 0" \text{ to } \frac{1}{4}" \\ \frac{1}{4}" \text{ to } \frac{1}{2}" \\ \frac{1}{2}" \text{ to } \frac{3}{4}" \\ \frac{3}{4}" \text{ to } 1" \\ 1" \text{ to } \frac{1}{4}" \end{array} $	0.477 0.330 0.233 0.138 0.104	0.452 0.297 0.211 0.164 0.123	#27 0.603 0.341 0.244 0.148 0.111	#28 0.503 0.321 0.197 0.133 0.128	#29 0.527 0.348 0.204 0.137 0.109	#30 0.460 0.304 0.199 0.136 0.128		

Table 26: Average acid-soluble chloride contents of CoC Specimens after 3-months

For further assessment, Table 27 compares the chloride content at 0-months and

the chloride content and associated standard deviation of chlorides at 3-months.

Depth	Average of 0-Month Chlorides	Average of 0-Month Chlorides per Inch	Average of 3- Month Chlorides	Standard Deviation of 3-Month Chlorides	Average of 3- Month Chlorides per Inch	
0" to $\frac{1}{4}$ "	0.183		0.502	0.064		
¹ / ₄ " to ¹ / ₂ "	0.171	0.150	0.367	0.055	0.322	
$\frac{1}{2}$ " to $\frac{3}{4}$ "	0.142	0.156	0.243	0.049		
³ ⁄ ₄ " to 1"	0.129		0.174	0.049		
1" to $1\frac{1}{4}$ "	0.119		0.131	0.033		
$1\frac{1}{4}$ " to $1\frac{1}{2}$ "	0.109	0.106	0.113	0.025	0.100	
$1\frac{1}{2}$ " to $1\frac{3}{4}$ "	0.089	0.106	0.099	0.016	0.108	
$1\frac{3}{4}$ " to 2"	0.089		0.088	0.017		

Table 27: Comparison of average acid-soluble chloride contents of CoC Specimens at 0- and after 3-months

From Table 27, it is clearly shown that the chlorides were effectively drawn into top 1" of the concrete. More explicitly, the average amount of chlorides in the top 1-inch of concrete more than doubled in the 3-months of accelerated corrosion testing.

A regression analysis using the 3-month chloride content data, minus the initial chloride content, with a time of 0.25 years (3 months) revealed that $C_0 = 0.514\%$ by concrete weight (20.12 lb/yd³) and that $D_{avg} = 1.375 \text{ in}^2/\text{yr}$, with a standard deviation of 0.565. Table 28 displays the chloride diffusion coefficient values calculated at 3-months.

Specimen	Subsequent	C ₀	D _{Specimen}	D _{FutTreat.}	
#	Treatment	(% by concrete weight)	(in ² /yr)	(in ² /yr)	
17	Control		1.522	1.792	
18	Collutor		2.062	1.792	
19	TSZ w/EP-C		1.610	1.757	
20	152 w/Ei-C		1.905	1.737	
21	TSZ		2.793	2.093	
22	152		1.393	2.075	
23	EA-A	0.514	1.267	1.016	
24	LA-A	0.314	0.765	0.972	
25	EA-A w/A-C		0.991		
26	EA-A W/A-C		0.954	0.972	
27	EA-B		1.155	1.059	
28	EA-D		0.964	1.039	
29	EM		0.973	0.938	
30	EIVI		0.904	0.938	

 Table 28:
 Calculated chloride diffusion coefficients for CoC specimens after 3-months

Figure 90 shows a representative graph comparing the initial theoretical, initial, 3month, and 3-month regression plus base-line chloride levels.




Figure 90: Comparison of initial theoretical, initial, 3-month, and 3-month regression chlorides for Specimen #17

4.1.4.5 Base-Line Chlorides for Patch Repair Materials

To evaluate the virgin chloride content of the conventional patch repair material, concrete powders were taken from a sample of repair material that was made at the time of patch repair (Appendix F). The powders were taken at depths of $\frac{1}{2}$ " and 1" in two locations (Table 29).

T 4	Denth	Chloride Cont	ent
Location	Depth	(% Cl by concrete weight)	(lb/yd^3)
•	1/2"	0.010	0.378
A	1"	0.007	0.264
Ъ	1/2"	0.012	0.470
В	1"	0.005	0.214

Table 29: Chloride contents of conventional patch repair material

Testing revealed that the average chloride content of the conventional repair mortar was 0.008% by concrete weight (0.331 lb/yd^3). This level of chlorides is well within the accepted limits.

The virgin chloride content of the EM was found to be 0.001% chlorides by weight.

4.1.4.6 CoC Specimens after 6-Months

After exposure to an additional three months of accelerated corrosion testing, the CoC specimens were tested for chloride ingress. As before, testing examined the concrete powders at increments of ¹/₄" to a depth of 2". Section 4.1.3.6.1 examines the chloride content of the original concrete while Section 4.1.3.6.2 examines the chloride content of the patch repair materials.

4.1.4.6.1 Substrate Concrete


The chloride contents of the substrate concrete for the CoC specimens after 6months of accelerated corrosion testing can be found in Table 30 (see Appendix F). In order to achieve viable data for the substrate concrete, several locations were tested to confirm results that seemed incompatible with Fick's 2nd Law. Specimens #19 through #22 had non-conforming chloride levels at a depth of ¹/₄" only. The substrate concrete of Specimens #24 had a spike in chloride content at a depth corresponding to the level of reinforcing steel. The substrate concrete of Specimen #30 produced chloride contents that were inconsistent with Fick's 2nd Law (i.e. showing high chloride levels at deeper test locations).


	Con	trol	TSZ w	/ EP-C	TS	SZ	EA	-A
Depth\Specimen	#17	#18	#19	#20	#21	#22	#23	#24
0" to $\frac{1}{4}$ "	0.542	0.576	0.496	1.077	1.270	1.313	0.448	0.607
$\frac{1}{4}$ " to $\frac{1}{2}$ "	0.438	0.387	0.518	0.515	0.330	0.464	0.409	0.541
$\frac{1}{2}$ " to $\frac{3}{4}$ "	0.338	0.363	0.236	0.464	0.208	0.458	0.310	0.381
³ / ₄ " to 1"	0.243	0.247	0.156	0.434	0.145	0.258	0.211	0.321
1" to $1\frac{1}{4}$ "	0.168	0.174	0.148	0.204	0.095	0.192	0.105	0.402
$1\frac{1}{4}$ " to $1\frac{1}{2}$ "	0.130	0.150	0.100	0.176	0.080	0.110	0.122	0.330
$1\frac{1}{2}$ " to $1\frac{3}{4}$ "	0.140	0.116	0.074	0.113	0.058	0.067	0.105	0.227
$1\frac{3}{4}$ " to 2"	0.128	0.088	0.058	0.083	0.047	0.069	0.132	0.126
Donth Specimon	EA-A	w/A-C	EA	ч-В	E	Μ		
Depth\Specimen	#25	#26	#27	#28	#29	#30		
	π43	π 4 0	$\pi \Delta I$	#40		π 30		
0" to $\frac{1}{4}$ "	0.521	0.490	0.528	0.493	0.558	0.437		
$\frac{0" \text{ to } \frac{1}{4}"}{\frac{1}{4}" \text{ to } \frac{1}{2}"}$								
	0.521	0.490	0.528	0.493	0.558	0.437		
$\frac{1}{4}$ " to $\frac{1}{2}$ "	0.521 0.473	0.490 0.414	0.528 0.458	0.493 0.411	0.558 0.526	0.437 0.345		
$\frac{\frac{1}{4} \text{ to } \frac{1}{2}}{\frac{1}{2} \text{ to } \frac{3}{4}}$	0.521 0.473 0.312	0.490 0.414 0.304	0.528 0.458 0.402	0.493 0.411 0.346	0.558 0.526 0.495	0.437 0.345 0.347		
¹ / ₄ " to ¹ / ₂ " ¹ / ₂ " to ³ / ₄ " ³ / ₄ " to 1"	0.521 0.473 0.312 0.173	0.490 0.414 0.304 0.189	0.528 0.458 0.402 0.213	0.493 0.411 0.346 0.250	0.558 0.526 0.495 0.181	0.437 0.345 0.347 0.314		
1/4" to 1/2" 1/2" to 3/4" 3/4" to 1" 1" to 11/4"	0.521 0.473 0.312 0.173 0.119	0.490 0.414 0.304 0.189 0.097	0.528 0.458 0.402 0.213 0.206	0.493 0.411 0.346 0.250 0.222	0.558 0.526 0.495 0.181 0.114	0.437 0.345 0.347 0.314 0.293		

 Table 30:
 Average acid-soluble chloride contents of CoC substrate concrete after 6-months

As mentioned, Specimens #19 through #22 (i.e. those that were treated with the TSZ) had non-conforming chloride contents at a depth of $\frac{1}{4}$ ". To confirm the accuracy of the results, the measurement equipment were calibrated frequently, and steps were made to take out measurement errors due to the presence of zinc ions in the concrete.

It is believed that the TSZ (zinc anode) attracts and retains neagatively-charged chloride ions near the surface, thus causing deviation from Fick's 2^{nd} Law. Figure 91 compares the chloride contents of the control specimens and those treated with thermal sprayed zinc. As can be seen, the chloride contents at a depth of ¹/₄" for Specimens #20 through #22 are much greater than the control specimens.





For Specimens #24 (EA-A) and #30 (EM), the substrate chloride contents did not entirely agree with Fick's 2nd Law either. To verify the results, additional tests were taken at two locations. After the retests were completed, results from each increment of depth were averaged. Figure 92 displays the non-conformity of Ficks's 2nd Law in regards to the average substrate chloride contents of Specimens #24 and #30. The substrate chloride contents of the Control specimens have also been provided.




Figure 92: Comparison of substrate chloride contents of Specimens #17, #18, #24, and #30 after 6-months

In assessing the profile of chloride contents for Specimen #24 in Figure 92, it can be seen that a sudden increase in chloride content can be found at the depth of reinforcing steel.

When looking at the sides of Specimens #24 and #30, significant horizontal cracking of the substrate concrete is evidence that corrosion of the embedded reinforcing has occurred (Figures 93 and 94). It seems that the presence of cracks may be cause for the higher level of chlorides found in the substrate concrete of Specimens #24 and #30. The embedded anodes in Specimen #24 may have also caused some of this distress.



Figure 93: Horizontal cracking on exterior of Specimen #24



Figure 94: Horizontal cracking on exterior of Specimen #30

With this information, an additional regression analysis was performed to calculate the surface chloride concentration and diffusion coefficients for the substrate concrete of the CoC specimens after 6-months of exposure (Table 31). The chloride contents at a depth of ¹/₄" for Specimens #19 through #22 were not used in this regression analysis (to take out the localized TSZ effect). In addition, Specimen #30 was not included in the analysis.

Specimen #	Subsequent Treatment	C ₀ (% by concrete weight)	$\begin{array}{c} \mathbf{D}_{\mathbf{Specimen}}\\ (\mathrm{in}^2/\mathrm{yr}) \end{array}$	$\begin{array}{c} \mathbf{D}_{\mathbf{Treatment}}\\ (\mathrm{in}^2/\mathrm{yr}) \end{array}$	Index
17	Control		.993	.982	1.1
18	Collutor		.971	.982	1.0
19	TSZ w/EP-C		.649	1.147	0.5
20	ISZ W/EF-C		1.645	1.147	2.2
21	TSZ		.379	.727	0.0
22	152		1.075	.121	1.2
23	EA-A	0.570	.701	1.704	0.6
24	LA-A	0.370	2.707	1.704	4.0
25	EA-A w/A-C		.714	.652	0.6
26		_	.590	.052	0.4
27	EA-B		1.117	1.053	1.3
28	LA-D		.990	1.033	1.0
29	EM		1.091	1.091	1.2
30			-	1.071	-

 Table 31: Calculated chloride diffusion coefficients for substrate concrete of CoC specimens after

 6-months

It should be noted, however, that the chloride contents of the substrate concrete were not used in evaluating the performance of the treatments within the patch repair materials. The chloride testing of the substrate concrete was performed merely to show that chlorides have continued to penetrate the concrete and that an environment representative of a patch repair in the field was simulated. Figure 95 shows the ingress of chlorides over the course of the 6 months of testing for the substrate concrete of a Control specimen. Chloride levels increased significantly over the course of testing. Furthermore, the actual chloride content and regression plus base-line chlorides at 6-months have excellent agreement.




Figure 95: Comparison of initial theoretical, initial, 3-month, 6-month, and 6-month regression chlorides for Specimen #17

4.1.4.6.2 Patch Repair Materials

Analysis of the chloride testing data, Table 32, revealed that chlorides were only drawn into the top ¹/₄" of the patch repair materials, except for Specimens #27 and #30 (See Appendix F). While chlorides were found to have penetrated to a depth of 1" for the conventional patch repair material of Specimen #27, irregular chloride contents were found in the epoxy patch material of Specimen #30. To verify the results, additional testing was performed in the patched areas of Specimens #27 and #30.

Depth\Specimen	Con	trol	TSZ w	/ EP-C	TS	SZ	EA	-A
Deptii\Specimen	#17	#18	#19	#20	#21	#22	#23	#24
0" to $\frac{1}{4}$ "	0.183	0.085	0.065	0.025	0.008	0.030	0.044	0.041
$\frac{1}{4}$ " to $\frac{1}{2}$ "	0.009	0.009	0.007	0.005	0.005	0.008	0.010	0.015
$\frac{1}{2}$ " to $\frac{3}{4}$ "	0.008	0.008	0.006	0.007	0.006	0.005	0.007	0.009
³ / ₄ " to 1"	0.008	0.007	0.008	0.007	0.005	0.006	0.008	0.007
1" to $1\frac{1}{4}$ "	0.008	0.007	0.006	0.006	0.005	0.005	0.009	0.007
$1\frac{1}{4}$ " to $1\frac{1}{2}$ "	0.008	0.008	0.006	0.006	0.015	0.005	0.007	0.008
$1\frac{1}{2}$ " to $1\frac{3}{4}$ "	0.009	0.013	0.007	0.006	0.009	0.006	0.007	0.008
$1\frac{3}{4}$ " to 2"	0.010	0.008	0.006	0.007	0.005	0.005	0.008	0.014
Donth Snooimon	EA-A	w/A-C	EA	-В	EM			
Depth\Specimen	#25	#26	#27	#28	#29	#30		
0" to $\frac{1}{4}$ "	0.013	0.012	0.136	0.067	0.001	0.003		
$\frac{1}{4}$ " to $\frac{1}{2}$ "	0.005	0.007	0.035	0.007	0.001	0.001		
$\frac{1}{2}$ " to $\frac{3}{4}$ "	0.007	0.006	0.016	0.006	0.001	0.011		
³ ⁄ ₄ " to 1"	0.006	0.006	0.010	0.006	0.001	0.043		
1" to $1\frac{1}{4}$ "	0.006	0.005	0.007	0.006	0.001	0.055		
$1\frac{1}{4}$ " to $1\frac{1}{2}$ "	0.006	0.006	0.008	0.006	0.001	0.037		
$1\frac{1}{2}$ " to $1\frac{3}{4}$ "	0.006	0.007	0.008	0.006	0.001	0.023		
$1\frac{3}{4}$ " to 2"	0.005	0.006	0.007	0.007	0.002	0.013		

Table 32: Average acid-soluble chloride contents of patch materials for CoC specimens after 3-months

In Specimen #30, the measured chloride values were found to be approximately zero at the concrete surface and increased to a depth of 1¹/4", where they then decreased towards a depth of 2." To locate the discrepancy, further testing was performed. The results of the additional testing (Table 33) revealed that a high level of chlorides was found at Location D and approximately zero chlorides were found at Location E. In addition, a line of discoloration was found approximately ³/₄" from the surface in Location D (Figure 96), which later was found to be rust staining.

#30				
Depth	Location B/C	Location D	Location E	Average
0.125	0.003	0.004	0.002	0.003
0.375	0.001	0.001	0.001	0.001
0.625	0.004	0.028	0.001	0.011
0.875	0.018	0.110	0.001	0.043
1.125	0.056	0.108	0.001	0.055
1.375	0.046	0.064	0.001	0.037
1.625	0.027	0.041	0.001	0.023
1.875	0.029	0.009	0.001	0.013

Table 33: Acid-soluble chloride contents of EM for Specimen#30



Figure 96: Discoloration in EM (Location D) of Specimen #30

A regression analysis was performed on the chloride results (Table 34). Because of the unusual profile of chloride levels for Specimen #30, it was not included in the regression. Using a time of 0.25 years, $C_{0-patch}$ was found to equal 0.445 % chlorides by concrete weight (17.421 lb/yd³).

Table 34: Calculated chloride diffusion coefficients for patch materials of CoC specimens after 3	3-
months	

Specimen #	Patch Treatment		C ₀ (% Cl by concrete weight)	D _{Specimen} (in ² /yr)	D _{Treatment} (in ² /yr)	Index
17	Control	(0.042	0.030	4.0
18	control	rial		0.017	0.050	1.6
19	TSZ w/EP-C	material)		0.013	0.010	1.2
20	ISZ W/EP-C			0.007	0.010	0.6
21	TSZ	epa		0.001	0.004	0.0
22		patch repair		0.008	0.004	0.7
23	EA-A		0.445	0.010	0.010	0.9
24	EA-A	(Conventional	0.445	0.010		0.9
25	EA-A w/A-C	ntio		0.005	0.005	0.4
26	LA-A W/A-C	nve		0.005	0.005	0.4
27	EA-B	Co		0.028	0.021	2.6
28	LA-D)		0.014	0.021	1.3
29	EM			0.001	0.001	0.0
30				-	0.001	

As displayed in Table 34, EM, TSZ and EA-A w/A-C had the lowest effective coefficients of diffusion.

4.1.5 Corrosion of Reinforcing Steel and Concrete Staining

To provide a quantitative measure of the condition of the specimens after exposure to accelerated corrosion testing, a visual examination of the rust staining on the concrete surface and exposed reinforcing steel was performed so that a numerical rating could be assigned to each of the specimens. Based on a rating scale of 0 to 4, with 0 being the best condition and 4 being the worst condition, rust staining on the surface of the specimens and the level of section loss in the reinforcing steel were each evaluated. The two ratings were then added together to determine a combined rating.

The rating scale for staining was based purely on visual examination; the more severe the staining, the higher the grade. The rating scale for the condition of the exposed reinforcing steel was based on the loss of ribs. If no corrosion by-products were present, a grade of 0 was given. If it appeared that all of the ribs were lost, a grade of 4 was given.

4.1.5.1 CoP Specimens after 6-Months

The dissected CoP specimens are displayed in Figure 97 while Table 35 presents the individual and combined ratings for each of the CoP specimens after 6-months of accelerated corrosion testing. In Table 35, Rebar A denotes the top mat reinforcing steel on the west end of the specimens while Rebar E denotes the reinforcing steel on the east end of the specimens. Detailed condition observations of the CoP specimens can be found in Section 4.2.

132



Figure 97: CoP specimens after dissection

Specimen	Treatment	I	ndivi	dual	Reb	ar	Dohon	Surface	Combined
#	1 reatment	Α	В	С	D	Ε	Rebar _{Avg.}	Staining	Rating
1	TSZ	0	1	1	2	0	0.8	0	0.8
2	152	0	4	4	3	1	2.4	4	6.4
3	TSZ w/EP-C	0	2	1	1	0	0.8	0	0.8
4	ISZ W/EF-C	1	2	0	1	0	0.8	0	0.8
5	EA-A w/A-C	4	3	2	3	3	3.0	4	7.0
6	EA-A W/A-C	3	3	4	2	2	2.8	3	5.8
7	EA-A	3	4	3	4	4	3.6	4	7.6
8	LA-A	4	4	4	4	3	3.8	4	7.8
9	EA-B	4	4	4	4	4	4.0	4	8.0
10	LA-D	4	4	4	4	4	4.0	4	8.0
11	T-SS	0	1	1	1	1	0.8	0	0.8
12	1-55	0	0	0	0	0	0.0	0	0.0
13	A-C	4	2	2	2	2	2.4	3	5.4
14	EP-C	4	1	1	2	1	1.8	2	3.8
15	Control	4	4	4	4	4	4.0	4	8.0
16	Colltroi	4	4	4	4	4	4.0	4	8.0

 Table 35: Rating of concrete staining and reinforcing steel for CoP Specimens after 6-months

Based on the above ratings, T-SS (#11 and #12) and TSZ w/EP-C (#3 and #4) provided the best protection against corrosion. The specimens with the embedded anodes (#7 - #10) did not perform better than the control (#15-#16).

4.1.5.2 CoC Specimens after 3-Months

Figure 98 displays the dissected CoC specimens and Table 36 presents the individual grades and final rating for each of the specimens after the initial 3-months of exposure. In Table 36, Rebar B denotes the reinforcing steel on the west end of the patch area while Rebar D denotes the reinforcing steel on the east end of the patch area. Detailed condition observations of the CoC specimens can be found in Section 4.3.



Figure 98: CoC specimens following concrete removal after 3-months

Specimen	Subsequent	Indiv	vidual I	Rebar		Surface	Combined
- #	Treatment	В	D	D	Rebar _{Avg.}	Staining	Rating
17	Control	3	2	3	2.7	3	5.7
18	Control	3	2	3	2.7	3	5.7
19	TSZ w/EP-C	3	2	4	3.0	3	6.0
20	ISZ W/EF-C	4	3	4	3.7	3	6.7
21	TSZ	3	2	4	3.0	2	5.0
22		3	3	3	3.0	3	6.0
23		4	2	4	3.3	2	5.3
24	EA-A	3	2	3	2.7	4	6.7
25	EA-A w/A-C	4	3	4	3.7	2	5.7
26	EA-A W/A-C	4	2	4	3.3	4	7.3
27	EA-B	4	1	4	3.0	3	6.0
28		3	2	4	3.0	4	7.0
29	EM	3	2	4	3.0	3	6.0
30	ENI	3	1	3	2.3	3	5.3

Table 36: Rating of concrete staining and exposed reinforcing steel for CoC specimens after 3-months

The average rating for the exposed reinforcing steel was 3.0 with a standard

deviation of 0.4. The average rating for the staining was 3.0 with a standard deviation of

0.7. The average combined rating for the CoP after 3-months of exposure was 6.0 with a standard deviation of 0.7.

4.1.5.3 CoC Specimens after 6-Months

Figure 99 displays the dissected CoC specimens and Table 37 presents the individual grades and combined rating for each of the specimens after 6-months of exposure. In Table 37, Rebar A denotes the reinforcing steel on the west end of the specimens while Rebar E denotes the reinforcing steel on the east end of the specimens. Detailed condition observations of the specimens can be found in Section 4.3.



Figure 99: CoC specimens after dissection after 6-months

In Table 37, all exposed rebar has been rated; however, only the rebars that were exposed, cleaned, and used "in" the patch repairs counted toward the combined rating. The rebar "out" of the patch area did not count toward the combined rating.

Snaaiman			Indi	vidu	al Re	bar			"in"	Surface	Combined
Specimen #	Α		B		С		D	Е	Rebar	Staining	Rating
π	A	in	out	in	out	in	out	Ľ	Average	Stanning	Kating
17	4	3	4	3	3	3	4	4	3.0	1	4.0
18	4	3	4	3	4	3	4	4	3.0	0	3.0
19	2	3	4	3	3	4	4	4	3.3	0	3.3
20	4	4	4	3	4	4	4	4	3.7	0	3.7
21	4	4	4	3	4	4	4	3	3.7	0	3.7
22	4	3	4	3	4	4	4	4	3.3	0	3.3
23	4	4	4	3	3	4	4	4	3.7	1	4.7
24	4	4	4	2	3	4	4	4	3.3	1	4.3
25	4	4	4	3	4	4	4	4	3.7	0	3.7
26	3	4	4	3	4	4	4	2	3.7	0	3.7
27	2	4	4	2	3	4	4	4	3.3	3	6.3
28	4	3	4	3	4	4	4	4	3.3	1	4.3
29	4	3	4	3	4	4	4	4	3.3	3	6.3
30	3	3	4	3	4	3	4	4	3.0	3	6.0

Table 37: Rating of concrete staining and reinforcing steel for CoC specimens after 6-months

4.1.6 Half-Cell Potential Data

Half-cell measurements utilizing a copper-copper sulfate electrode were obtained for each of the concrete specimens that did not contain coatings (Figure 100). Prior to measurement during the dry cycle, the accelerated corrosion system was



Figure 100: Half-cell potential measurement

turned off for a day and the slabs were moistened with tap-water. Readings were made after 3-months (Table 38 and 39) and 6-months (Table 40). Since the readings were generally uniform, contour plots were not made. Additionally, positive values were obtained since the polarity of experimental setup is reversed from the standard method.

Speci	imen #	Treatment	Specimen _{Avg} (mV)	Specimen _{StDev} (mV)	Treatment _{Avg} (mV)	Treatment _{StDev} (mV)
	7	EA-A	616.7	22.5	608.9	26.9
JS	8	8	601.1	29.3	000.7	
Specimens	9	EA-B	636.0	24.3	637.5	21.1
ecin	10	EA-D	639.0	17.9	037.5	
$\mathbf{S}\mathbf{p}$	11	TCC	375.9	5.6	2546	22.1
CoP	12	T-SS	333.3	3.7	354.6	
Ŭ	15	Control	639.2	20.5	604.4	36.2
	16	– Control	582.7	24.9	004.4	

Table 38: Half-cell potential readings of uncoated CoP specimens after 3-months

Table 39: Half-cell potential readings of uncoated CoC specimens after 3-months

_

Speci	men #	Future Treatment	Specimen _{Avg} (mV)	Specimen _{StDev} (mV)	Treatment _{Avg} (mV)	Treatment _{StDev} (mV)
	17	Control	535.2	25.0	()	(
	18		547.0	30.2		
	19	TSZ w/EP-C	533.0	30.0		
	20	15Z W/EP-C	548.1	22.8		28.4
Su	21	22 TSZ 23 FA-A	550.3	12.5		
me	22		515.1	28.5		
eci	23		569.4	20.2	546.1	
$\mathbf{S}\mathbf{p}$	Similar 21 22 TSZ 23 EA-A 24 EA-A 25 EA-A 26 w/A-C		516.4	18.2		
Ŋ		EA-A	564.2	22.0		
ŭ	26	w/A-C	544.2	19.1		
	27	EA-B	569.8	24.9		
	28 EA-B	EA-D	543.8	34.2		
	29	EM	561.8	19.7		
	30	ENI	546.9	13.2		

Based on criteria discussed in Section 2.4.4, the readings from Table 38 indicated that corrosion was occurring in the CoP specimens containing EA-A and EA-B, as well as the Control after 3-months of exposure. However, the specimens with the T-SS were at the threshold of unknown probability after 3-months of exposure. In contrast, all of the readings from Table 39 for the CoC specimens indicated a 90% probability of corrosion after 3-months of exposure.

Speci	imen #	Treatment	Specimen _{Avg} (mV)	Specimen _{StDev} (mV)	Treatment _{Avg} (mV)	Treatment _{StDev} (mV)
	7	EA-A	582.9	17.0	579.1	17.9
Su	8		575.4	18.4		
me	9	EA-B	585.3	26.4	582.4	28.1
Specimens	10	LA-D	579.5	30.2	502.4	
$\mathbf{S}\mathbf{p}$	11	TCC	190.4	2.0	1967	4.1
CoP	12	T-SS	182.9	1.2	186.7	
C	15	Control	618.4	21.2	594.5	29.7
	16	Control	570.6	12.4	594.5	

 Table 40:
 Half-cell potential readings of uncoated CoP specimens after 6-months

The 6-month half-cell readings for the CoP specimens containing EA-A and EA-B, as well as the Control, indicated that corrosion was occurring. However, the readings for the T-SS specimens indicated that no corrosion was occurring.

4.1.7 Summary of Specimen Monitoring

In the previous sections, the rating criteria for the specimens was presented. Section 4.1.7.1 provides a summary of the CoP Specimens while Sections 4.1.7.2 and 4.1.7.3 provide a summary of the CoC Specimens. Since half-cell potential readings were not performed on all of the CoP specimens, they are not included in the final ratings.

4.1.7.1 Summary of CoP Specimen Monitoring

As the previously discussed chloride regression analysis for the CoP specimens would not warrant a direct comparison of all the specimens based on Fick's 2nd Law, the chloride content rating in Table 41 was based on a chloride content index rating of the top 1" of the concrete, and not the regression analysis index rating.

		<u> </u>	T. A. I		
Specimen #	Treatment	Steel Loss	Chloride Content	Rebar Corrosion and Staining	Total (out of 16)
1	TSZ	1.0	0.6	0.8	2.4
2	152	1.1	1.1	6.4	8.6
3	TSZ w/EP-C	0.3	0.2	0.8	1.3
4	152 W/EF-C	0.3	0.5	0.8	1.6
5	EA-A	1.2	2.2	7.0	10.4
6	w/A-C	1.1	2.0	5.8	8.9
7	EA-A	2.0	3.0	7.6	12.6
8		1.9	1.9	7.8	11.6
9	EA-B	3.1	3.4	8.0	14.5
10	EA-D	4.0	4.0	8.0	16.0
11	T-SS	0.0	0.1	0.8	0.9
12	1-55	0.0	0.1	0.0	0.1
13	A-C	0.5	1.7	5.4	7.6
14	EP-C	0.3	0.0	3.8	4.1
15	Control	2.1	1.8	8.0	11.9
16	Control	1.8	1.8	8.0	11.6

Table 41: Condition summary of CoP specimens after 6-months

Based on the summary of laboratory results for the CoP Specimens in Table 41, the T-SS and TSZ w/EP-C treatments offered the most effective means of preventing corrosion from initiating. Treatments that coated or sealed the concrete surface prior to exposure offered the most protection. As stated earlier, the connection for Specimen #2 had failed; therefore, it is anticipated that performance similar to Specimen #1 may have been observed if a failure of the connection had not occurred.

The embedded anodes do not appear to offer a benefit in preventing the onset of corrosion in the laboratory specimens. In fact, Specimens #7 thru #10 had less favorable total ratings than the control specimens. The embedded anodes appear to attract more chlorides to their vicinity. This created variable chloride concentrations and non-uniform chloride penetrations in the laboratory specimens containing the embedded anodes.

When comparing the EA-A and EA-A w/A-C, the addition of the acrylic coating improves the performance. However, the A-C alone was more effective in preventing corrosion than the EA-A or EA-A w/A-C laboratory specimens.

4.1.7.2 Summary of CoC Specimen Monitoring after 3-Months

Since the steel loss was similar for each of the CoC specimens prior to patch repairs, it was not included in this evaluation. Additionally, as half-cell potential readings for all of the CoC specimens indicated a high probability of corrosion, a rating of 4.0 was given to each of the specimens (Table 42).

		3.			
Specimen #	Subsequent Treatment	Chloride ContentRebar Corrosion and Staining		Half-cell Potential Testing	Total (out of 16)
17	Control	1.5	5.7	4.0	11.2
18	Control	2.6	5.7	4.0	12.3
19	TSZ w/EP-C	1.7	6.0	4.0	11.7
20	ISZ W/EP-C	2.2	6.7	4.0	12.9
21	TSZ	4.0	5.0	4.0	13.0
22		1.2	6.0	4.0	11.2
23		1.0	5.3	4.0	10.3
24	EA-A	0.0	6.7	4.0	10.7
25		0.4	5.7	4.0	10.1
26	EA-A w/A-C	0.4	7.3	4.0	11.7
27		0.8	6.0	4.0	10.8
28	EA-B	0.4	7.0	4.0	11.4
29	EM	0.4	6.0	4.0	10.4
30	ENI	0.3	5.3	4.0	9.6

Table 42: Condition summary of CoC specimens after 3-months

With an average value of 11.2 and a standard deviation of 1.01, the CoC specimens appeared to be in a similar condition after the first 3-month of testing. Therefore, it can be concluded that the addition of chlorides to the concrete mix, "ponding" of salt-water, and application of electric current were properly controlled.

4.1.7.3 Summary of CoC Specimen Monitoring after 6-Months

As mentioned previously, the chloride content of the substrate concrete was not used in evaluating the effectiveness of the treatments within the patch repair. In addition, only the "in" patch reinforcing steel was used for the rating (Table 43).

		6-M	Ratings		
Specimen #	Treatment	Steel Loss	Patch Chloride Content	Rebar Corrosion and Staining	Total (out of 16)
17	Control	1.9	4.0	4.0	9.9
18	Control	3.7	1.6	3.0	8.3
19	TSZ w/EP-C	1.3	1.2	3.3	5.8
20		1.2	0.6	3.7	5.5
21	TSZ	1.7	0.0	3.7	5.4
22		0.5	0.7	3.3	4.5
23	EA-A	3.2	0.9	4.7	8.8
24	EA-A	2.6	0.9	4.3	7.8
25		0.7	0.4	3.7	4.8
26	EA-A w/A-C	0.0	0.4	3.7	4.1
27	EA-B	2.8	2.6	6.3	11.7
28		1.4	1.3	4.3	7.0
29	EM	3.5	0.0	6.3	9.8
30		4.0	_*	6.0	10.0*

Table 43: Condition summary of CoC specimens after 6-months

* Patch chloride content assumed to be zero from data conforming to Fick's 2nd Law

Based on the results of Table 43, EA-A w/A-C, TSZ, and TSZ w/EP-C appeared to be the most effective in controlling corrosion. It is interesting to note that these treatments were effectively coatings. We did not have a specimen with A-C alone to evaluate the relative contributions of EA-A and A-C. However, it should also be noted that the EA-A (without coating) and EA-B specimens did not perform any better than the Control specimens.

In regards to the EM, the high initial corrosion currents and associated steel loss appear to be the result of the dissimilar material properties. As will be seen in Section 4.3, a "ring-anode" effect was visible at the interface of the patch and substrate concrete.

Condition Observations for CoP Specimens

4.2

As seen in Figure 101, visible signs or corrosion, in the form of rust staining on the concrete surface, were present on the CoP specimens that did not contain coatings after only 3-months of exposure. After 6-months of exposure (Figure 102), a majority of the specimens, excluding those with the T-SS and TSZ w/EP-C, displayed signs of rust staining. Sections 4.2.1 through 4.2.16 display the surface condition and associated crack mapping of the CoP specimens at 0-months, 3-months, and 6-months of exposure, as well as the dissected specimens with their rebar ratings. All of the figures in the following sections are oriented with "North" towards the top of the page (Figures 103 to 230). The numbers in parentheses are representative of the specimens for each treatment.




Figure 101: Condition of CoP specimens after 3-months



Figure 102: Condition of CoP specimens after 6-months



Figure 103: Condition of TSZ(1) at 0-months



Figure 105: Condition of TSZ(1) after 3-months



Figure 107: Condition of TSZ(1) after 6-months



Figure 109: Dissection of TSZ(1) after 6-months




Figure 104: Crack-mapping of TSZ(1) at 0-months



Figure 106: Crack-mapping of TSZ(1) after 3-months




Figure 108: Crack-Mapping of TSZ(1) after 6-months



Figure 110: Close-up of TSZ(1) exposed rebar

4.2.2 Specimen #2 – TSZ (2)



Figure 111: Condition of TSZ(2) at 0-months




Figure 113: Condition of TSZ(2) after 3-months



Figure 115: Condition of TSZ(2) after 6-months




Figure 117: Dissection of TSZ(2) after 6-months




Figure 112: Crack-Mapping of TSZ(2) at 0-months




Figure 114: Crack-mapping of TSZ(2) after 3-months




Figure 116: Crack-mapping of TSZ(2) after 6-months



Figure 118: Close-up of TSZ(2) exposed rebar




Figure 119: Condition of TSZ w/EP-C(1) at 1.5-months



Figure 121: Condition of TSZ w/EP-C(1) after 3-months



Figure 123: Condition of TSZ w/EP-C(1) after 6-months



Figure 125: Dissection of TSZ w/EP-C(1) after 6-months




Figure 120: Crack-mapping of TSZ w/EP-C(1) at 0-months



Figure 122: Crack-mapping of TSZ w/EP-C(1) after 3-months




Figure 124: Crack-mapping of TSZ w/EP-C(1) after 6-months



Figure 126: Close-up of TSZ w/EP-C(1) exposed rebar



Figure 127: Condition of TSZ w/EP-C(2) at 1.5-months



Figure 129: Condition of TSZ w/EP-C(2) after 3-months



Figure 131: Condition of TSZ w/EP-C(2) after 6-months



Figure 133: Dissection of TSZ w/EP-C(2) after 6-months




Figure 128: Crack-mapping of TSZ w/EP-C(2) at 0-months




Figure 130: Crack-mapping of TSZ w/EP-C(2) after 3-months




Figure 132: Crack-mapping of TSZ w/EP-C(2) after 6-months



Figure 134: Close-up of TSZ w/EP-C(2) exposed rebar



Figure 135: Condition of EA-A w/A-C(1) at 1.5-months



Figure 137: Condition of EA-A w/A-C(1) after 3-months



Figure 139: Condition of EA-A w/A-C(1) after 6-months




Figure 141: Dissection of EA-A w/A-C(1) after 6-months




Figure 136: Crack-mapping of EA-A w/A-C(1) at 0-months




Figure 138: Crack-mapping of EA-A w/A-C(1) after 3-months




Figure 140: Crack-mapping of EA-A w/A-C(1) after 6-months



Figure 142: Close-up of EA-A w/A-C(1) exposed rebar



Figure 143: Condition of EA-A w/A-C(2) at 1.5-months



Figure 145: Condition of EA-A w/A-C(2) after 3-months



Figure 147: Condition of EA-A w/A-C(2) after 6-months



Figure 149: Dissection of EA-A w/A-C(2) after 6-months




Figure 144: Crack-mapping of EA-A w/A-C(2) at 0-months



Figure 146: Crack-mapping of EA-A w/A-C(2) after 3-months




Figure 148: Crack-mapping of EA-A w/A-C(2) after 6-months



Figure 150: Close-up of EA-A w/A-C(2) exposed rebar



Figure 151: Condition of EA-A(1) at 0-months



Figure 153: Condition of EA-A(1) after 3-months



Figure 155: Condition of EA-A(1) after 6-months



Figure 157: Dissection of EA-A(1) after 6-months




Figure 152: Crack-mapping of EA-A(1) at 0-months




Figure 154: Crack-mapping of EA-A(1) after 3-months




Figure 156: Crack-mapping of EA-A(1) after 6-months



Figure 158: Close-up of EA-A(1) exposed rebar




Figure 159: Condition of EA-A(2) at 0-months



Figure 161: Condition of EA-A(2) after 3-months



Figure 163: Condition of EA-A(2) after 6-months




Figure 165: Dissection of EA-A(2) after 6-months




Figure 160: Crack-mapping of EA-A(2) at 0-months




Figure 162: Crack-mapping of EA-A(2) after 3-months




Figure 164: Crack-mapping of EA-A(2) after 6-months



Figure 166: Close-up of EA-A(2) exposed rebar



Figure 167: Condition of EA-B(1) at 0-months



Figure 169: Condition of EA-B(1) after 3-months



Figure 171: Condition of EA-B(1) after 6-months



Figure 173: Dissection of EA-B(1) after 6-months




Figure 168: Crack-mapping of EA-B(1) at 0-months




Figure 170: Crack-mapping of EA-B(1) after 3-months




Figure 172: Crack-mapping of EA-B(1) after 6-months



Figure 174: Close-up of EA-B(1) exposed rebar

4.2.10 Specimen #10 – EA-B (2)



Figure 175: Condition of EA-B(2) at 0-months



Figure 177: Condition of EA-B(2) after 3-months



Figure 179: Condition of EA-B(2) after 6-months



Figure 181: Dissection of EA-B(2) after 6-months




Figure 176: Crack-mapping of EA-B(2) at 0-months




Figure 178: Crack-mapping of EA-B(2) after 3-months



Figure 180: Crack-mapping of EA-B(2) after 6-months



Figure 182: Close-up of EA-B(2) exposed rebar

4.2.11 Specimen #11 – T-SS (1)



Figure 183: Condition of T-SS(1) at 0-months



Figure 185: Condition of T-SS(1) after 3-months



Figure 187: Condition of T-SS(1) after 6-months



Figure 189: Dissection of T-SS(1) after 6-months




Figure 184: Crack-mapping of T-SS(1) at 0-months



Figure 186: Crack-mapping of T-SS(1) after 3-months




Figure 188: Crack-mapping of T-SS(1) after 6-months



Figure 190: Close-up of T-SS(1) exposed rebar

4.2.12 Specimen #12 – T-SS (2)



Figure 191: Condition of T-SS(2) at 0-months



Figure 193: Condition of T-SS(2) after 3-months



Figure 195: Condition of T-SS(2) after 6-months



Figure 197: Dissection of T-SS(2) after 6-months




Figure 192: Crack-mapping of T-SS(2) at 0-months




Figure 194: Crack-mapping of T-SS(2) after 3-months




Figure 196: Crack-mapping of T-SS(2) after 6-months



Figure 198: Close-up of T-SS(2) exposed rebar

4.2.13 Specimen #13 – A-C



Figure 199: Condition of A-C at 0-months



Figure 201: Condition of A-C after 3-months



Figure 203: Condition of A-C after 6-months



Figure 205: Dissection of A-C after 6-months




Figure 200: Crack-mapping of A-C at 0-months




Figure 202: Crack-mapping of A-C after 3-months




Figure 204: Crack-mapping of A-C after 6-months



Figure 206: Close-up of A-C exposed rebar

4.2.14 Specimen #14 – EP-C



Figure 207: Condition of EP-C at 1.5-months



Figure 209: Condition of EP-C after 3-months



Figure 211: Condition of EP-C after 6-months



Figure 213: Dissection of EP-C after 6-months






Figure 208: Crack-mapping of EP-C at 0-months








Figure 212: Crack-mapping of EP-C after 6-months



Figure 214: Close-up of EP-C exposed rebar

4.2.15 Specimen #15 – Control (1)



Figure 215: Condition of Control(1) at 0-months



Figure 217: Condition of Control(1) after 3-months



Figure 219: Condition of Control(1) after 6-months



Figure 221: Dissection of Control(1) after 6-months




Figure 216: Crack-mapping of Control(1) at 0-months




Figure 218: Crack-mapping of Control(1) after 3-months




Figure 220: Crack-mapping of Control(1) after 6-months



Figure 222: Close-up of Control(1) exposed rebar

4.2.16 Specimen #16 – Control (2)



Figure 223: Condition of Control(2) at 0-months



Figure 225: Condition of Control(2) after 3-months



Figure 227: Condition of Control(2) after 6-months




Figure 229: Dissection of Control(2) after 6-months




Figure 224: Crack-mapping of Control(2) at0-months




Figure 226: Crack-mapping of Control(2) after 3-months




Figure 228: Crack-mapping of Control(2) after 6-months



Figure 230: Close-up of Control(2) exposed rebar

4.2.17 CoP Discussion

The TSZ treatment appeared to offer some protection against the initiation and progression of corrosion. Because of the failed connection of Specimen #2, the condition observations did not accurately portray the effectiveness of the treatment. However, this failure did emphasize the importance of providing redundant connections. In addition, crack-mapping showed that cracks initiated, and increased in width over time. Furthermore, the zinc was indeed "used up" as the color of the zinc turned to a white at the conclusion of accelerated corrosion testing.

In comparison to the TSZ, the TSZ w/EP-C was more effective in preventing the initiation and progression of corrosion. When looking at the crack-map plots, there was no appreciable difference in the cracking over time. When dissected, it is interesting to note that the reinforcing bars with the most corrosion damage were the ones with the connection to the thermal sprayed zinc.

The EA-A w/A-C treatment did not prevent the initiation and progression of corrosion. Although cracking was not prevalent on the concrete surface, rust-staining was.

The EA-A (without coating) treatment was not effective in preventing the initiation and progression of corrosion. Although minor cracking was present at the onset of testing, numerous cracks initiated and grew in size over the duration of accelerated testing. When compared to the Control laboratory specimens, the condition of the exposed EA-A rebar was similar.

159

Crack initiation, crack growth, and rust-staining were prevalent in the EA-B specimens. The exposed reinforcing steel appeared to be in a visually worse condition than the Control specimens.

The T-SS treatment was effective in preventing the initiation and progression of corrosion. Over the course of testing, only minimal cracks had initiated. When dissected, the condition of the reinforcing steel was in a good state. Only minor surface rust could be found on the exposed reinforcing steel for the T-SS specimens.

The A-C treatment provided some protection against the initiation and progression of corrosion. Although the width of cracks did not appear to increase over time, the presence of rust-staining was evidence that corrosion of reinforcing steel was occurring. When dissected, the rebar was in a better condition compared to the Control specimens. However, the A-C approach was not more effective than the EP-C and T-SS treatments.

The EP-C treatment appeared to be effective in preventing the initiation and progression of corrosion. Although some crack growth and rust-staining occurred, it was limited to a small area on the rebar at the perimeter of the specimens.

As expected, the Control specimens had prevalent crack initiation and growth, as well as extensive rust-staining.

160

4.3 Condition Observations for CoC Specimens

The initial 3-months of accelerated corrosion testing on the CoC specimens was effective in producing extensive cracking and corrosion of the embedded reinforcing steel. This can be seen with the amount of rust-staining present on the concrete surface (Figure 231).



Figure 231: Rust staining on CoC specimens after 3-months

After the previously discussed patch repairs were completed, the CoC specimens were re-positioned (Figure 232) and the second phase of accelerated corrosion testing for the CoC specimens was commenced (Figures 233 and 234).




Figure 232: Location of CoC specimens after patch repairs



Figure 233: Condition of CoC specimens after completion of patch repairs



Figure 234: Condition of CoC specimens after 6-months

Sections 4.3.1 through 4.3.14 display the surface condition and associated crack mapping of the CoC specimens at 3-months, the condition of the specimen and exposed reinforcing steel prior to patching, the condition of the specimens after patching, the condition of the specimens after exposure to an additional three months of testing, and the final dissection. Since the initial crack-mapping did not show cracking for any of the CoC specimens, the surface condition and crack-mapping at 0-months were not provided. As before, all of the figures in the following sections are oriented with "North" towards the top of the page (Figures 235 to 346).



Figure 235: Condition of Control(1) after 3-months



Figure 237: Condition of Control(1) exposed rebar after 3-months



Figure 239: Condition of Control(1) after patch repairs



Figure 241: Dissection of Control(1) after 6-months




Figure 236: Crack-mapping of Control(1) after 3-months



Figure 238: Close-up of Control(1) exposed rebar after 3-months



Figure 240: Condition of Control(1) after 6-months



Figure 242: Close-up of Control(1) exposed rebar after 6-months



Figure 243: Condition of Control(2) after 3-months



Figure 245: Condition of Control(2) exposed rebar after 3-months



Figure 247: Condition of Control(2) after patch repairs



Figure 249: Dissection of Control(2) after 6-months




Figure 244: Crack-mapping of Control(2) after 3-months



Figure 246: Close-up of Control(2) exposed rebar after 3-months



Figure 248: Condition of Control(2) after 6-months



Figure 250: Close-up of Control(2) exposed rebar after 6-months



Figure 251: Condition of TSZ w/EP-C(1) after 3-months



Figure 253: Condition of TSZ w/EP-C(1) exposed rebar after 3-months



Figure 255: Condition of TSZ w/EP-C(1) after patch repairs



Figure 257: Dissection of TSZ w/EP-C(1) after 6-months




Figure 252: Crack-mapping of TSZ w/EP-C(1) after 3-months



Figure 254: Close-up of TSZ w/EP-C(1) exposed rebar after 3-months



Figure 256: Condition of TSZ w/EP-C(1) after 6-months



Figure 258: Close-up of TSZ w/EP-C(1) exposed rebar after 6-months



Figure 259: Condition of TSZ w/EP-C(2) after 3-months



Figure 261: Condition of TSZ w/EP-C(2) exposed rebar after 3-months



Figure 263: Condition of TSZ w/EP-C(2) after patch repairs



Figure 265: Dissection of TSZ w/EP-C(2) after 6-months




Figure 260: Crack-mapping of TSZ w/EP-C(2) after 3-months



Figure 262: Close-up of TSZ w/EP-C(2) exposed rebar after 3-months



Figure 264: Condition of TSZ w/EP-C(2) after 6-months



Figure 266: Close-up of TSZ w/EP-C(2) exposed rebar after 6-months



Figure 267: Condition of TSZ(1) after 3-months



Figure 269: Condition of TSZ(1) exposed rebar after 3-months



Figure 271: Condition of TSZ(1) after patch repairs



Figure 273: Dissection of TSZ(1) after 6-months




Figure 268: Crack-mapping of TSZ(1) after 3-months



Figure 270: Close-up of TSZ(1) exposed rebar after 3-months



Figure 272: Condition of TSZ(1) after 6-months



Figure 274: Close-up of TSZ(1) exposed rebar after 6-months



Figure 275: Condition of TSZ(2) after 3-months



Figure 277: Condition of TSZ (2) exposed rebar after 3-months



Figure 279: Condition of TSZ(2) after patch repairs



Figure 281: Dissection of TSZ (2) after 6-months




Figure 276: Crack-mapping of TSZ(2) after 3-months



Figure 278: Close-up of TSZ(2) exposed rebar after 3-months



Figure 280: Condition of TSZ(2) after 6-months



Figure 282: Close-up of TSZ(2) exposed rebar after 6-months



Figure 283: Condition of EA-A(1) after 3-months



Figure 285: Condition of EA-A(1) exposed rebar after 3-months



Figure 287: Condition of EA-A(1) after patch repairs



Figure 289: Dissection of EA-A(1) after 6-months




Figure 284: Crack-mapping of EA-A(1) after 3-months



Figure 286: Close-up of EA-A(1) exposed rebar after 3-months




Figure 288: Condition of EA-A(1) after 6-months



Figure 290: Close-up of EA-A(1) exposed rebar after 6-months



Figure 291: Condition of EA-A(2) after 3-months



Figure 293: Condition of EA-A(2) exposed rebar after 3-months



Figure 295: Condition of EA-A(2) after patch repairs



Figure 297: Dissection of EA-A(2) after 6-months




Figure 292: Crack-mapping of EA-A(2) after 3-months



Figure 294: Close-up of EA-A(2) exposed rebar after 3-months



Figure 296: Condition of EA-A(2) after 6-months



Figure 298: Close-up of EA-A(2) exposed rebar after 6-months



Figure 299: Condition of EA-A w/A-C(1) after 3-months



Figure 301: Condition of EA-A w/A-C(1) exposed rebar after 3-months



Figure 303: Condition of EA-A w/A-C(1) after patch repairs



Figure 305: Dissection of EA-A w/A-C(1) after 6-months




Figure 300: Crack-mapping of EA-A w/A-C(1) after 3-months



Figure 302: Close-up of EA-A w/A-C(1) exposed rebar after 3-months



Figure 304: Condition of EA-A w/A-C(1) after 6-months



Figure 306: Close-up of EA-A w/A-C(1) exposed rebar after 6-months



Figure 307: Condition of EA-A w/A-C(2) after 3-months



Figure 309: Condition of EA-A w/A-C(2) exposed rebar after 3-months



Figure 311: Condition of EA-A w/A-C(2) after patch repairs



Figure 313: Dissection of EA-A w/A-C(2) after 6-months




Figure 308: Crack-mapping of EA-A w/A-C(2) after 3-months



Figure 310: Close-up of EA-A w/A-C(2) exposed rebar after 3-months



Figure 312: Condition of EA-A w/A-C(2) after 6-months



Figure 314: Close-up of EA-A w/A-C(2) exposed rebar after 6-months



Figure 315: Condition of EA-B(1) after 3-months



Figure 317: Condition of EA-B(1) exposed rebar after 3-months



Figure 319: Condition of EA-B(1) after patch repairs



Figure 321: Dissection of EA-B(1) after 6-months




Figure 316: Crack-mapping of EA-B(1) after 3-months



Figure 318: Close-up of EA-B(1) exposed rebar after 3-months



Figure 320: Condition of EA-B(1) after 6-months



Figure 322: Close-up of EA-B(1) exposed rebar after 6-months

4.3.12 Specimen #28 – EA-B (2)



Figure 323: Condition of EA-B(2) after 3-months



Figure 325: Condition of EA-B(2) exposed rebar after 3-months



Figure 327: Condition of EA-B(2) after patch repairs



Figure 329: Dissection of EA-B(2) after 6-months



Figure 324: Crack-mapping of EA-B(2) after 3-months



Figure 326: Close-up of EA-B(2) exposed rebar after 3-months



Figure 328: Condition of EA-B(2) after 6-months



Figure 330: Close-up of EA-B(2) exposed rebar after 6-months

4.3.13 Specimen #29 – EM (1)



Figure 331: Condition of EM(1) after 3-months



Figure 333: Condition of EM(1) exposed rebar after 3-months



Figure 335: Condition of EM(1) after patch repairs




Figure 337: Dissection of EM(1) after 6-months




Figure 332: Crack-mapping of EM(1) after 3-months



Figure 334: Close-up of EM(1) exposed rebar after 3-months



Figure 336: Condition of EM(1) after 6-months



Figure 338: Close-up of EM(1) exposed rebar after 6-months

4.3.14 Specimen #30 – EM (2)



Figure 339: Condition of EM(2) after 3-months



Figure 341: Condition of EM(2) exposed rebar after 3-months



Figure 343: Condition of EM(2) after patch repairs




Figure 345: Dissection of EM(2) after 6-months




Figure 340: Crack-mapping of EM(2) after 3-months



Figure 342: Close-up of EM(2) exposed rebar after 3-months



Figure 344: Condition of EM(2) after 6-months



Figure 346: Close-up of EM(2) exposed rebar after 6-months

4.3.15 CoC Discussion

It appeared that the conventional patch repair material performed well and aided in reducing chloride ingress.

For reinforcing bars that were not exposed and cleaned at 3-months, extensive buildup of corrosion by-products and loss of section on most bars was evident at dissection. This was evidenced by the rating of "4" for the rebar that was "out" of the patch area. Reinforcing bars within the patches did not appear to exhibit major changes from 3-months to 6-months.

When looking at the patched areas of the TSZ and TSZ w/EP-C specimens, it is interesting to note that the rebar directly connected to the thermal sprayed zinc had the most corrosion. Despite this fact, the TSZ treatment was effective in controlling corrosion in the patches.

Specimens with patches containing the EA-A (without coating) and EA-B did not perform better (in controlling corrosion) compared to the Control specimens. The zinc anodes attracted the chloride ions, resulting in increased corrosion on the rebar it was attached to.

Although the EM material did not display signs of cracking, the existence of the "ring-anode" effect at the perimeter of the patch is cause for concern.

(Page left blank intentionally)

CHAPTER 5

FIELD TESTING OF BRIDGE DECKS

5.1 General

As discussed previously in the report, the project team was informed that numerous bridges in Wisconsin had been constructed with admixtures, sealed with coatings at construction, and sealed with coatings after a few years of exposure. To compare the effectiveness of these treatments, the aforementioned chloride testing procedure was used to determine the surface chloride concentration and diffusion coefficient for each bridge deck in question. By comparing the results to bridge decks that did not receive any treatment, we were able to determine whether or not the treatments were beneficial. The project team would like to thank Mr. Pete Thompson and Mr. Matt Murphy from Dodge County, and Mr. Jerry Hall from Pierce County for providing traffic control for the testing. In addition, Mr. Travis McDaniel from WI DOT was paramount in providing information pertaining to the bridges in question.

5.2 Bridge Decks Tested

The selection of the bridge deck to be tested was based on the year of construction, treatment, average daily traffic (ADT), bridge deck rating (according to the most recent bridge inspection), and the feature under the bridge. The applied sealer, a trisiloxane masonry water repellent, will be referred to as "Sealer." The bridge decks chosen are presented in Table 44. Chloride testing results and plans with the locations of the chloride testing can be found in Appendix G.

179

Bridge	County	Year Built	Treatment	ADT	NBI Deck Rating	Feature Under
B-14-110	Dodge	1994	Sealer at construction (121)	2380	6 (122)	USH 41
B-14-115	Dodge	1994	Sealer at construction (121)	5000	8 (123)	USH 41
B-14-119	Dodge	1995	None	1670	8 (124)	USH 151
B-14-129	Dodge	1994	1/3 Admix A 1/3 None 1/3 Admix B ⁽²⁸⁾	2800	8 ⁽¹²⁵⁾	Rubicon River
B-14-133	Dodge	1995	1/2 None 1/2 Admix C ⁽²⁸⁾	350	8 (126)	C&NWT Railroad
B-47-110	Pierce	1993	Sealer in 1997, yearly after 1999 (127)	200	7 (128)	Rush River
B-47-118	Pierce	1992	None	2390	6 ⁽¹²⁹⁾	Isabelle Creek
B-47-120	Pierce	1992	None	1120	6 ⁽¹³⁰⁾	Pine Creek
B-47-141	Pierce	1994	Sealer in 1998, yearly after 2000 ⁽¹²⁷⁾	900	7 (131)	Rush Coulee Creek

 Table 44: Description of bridge decks tested

5.2.1 Bridge B-14-0110

Bridge B-14-0110 (Figure 347) is located on State Highway 28 and crosses over U.S. Highway 41 in Theresa, WI (Dodge County). The bridge, coated with Sealer after construction only, was constructed in 1994 with coated rebar and



Figure 347: Bridge B-14-0110

is supported by steel plate girders. It is 311.1 ft in length (spans of 140 ft and 165 ft), has a deck width of 71 ft, and a roadway width of 52ft. The most recent inspection gave the bridge deck a NBI rating of 6 and noted that are "Numerous transverse cracks. Several diagonal cracks at the deck ends." ⁽¹²²⁾

5.2.2 Bridge B-14-0115

Bridge B-14-0115 (Figure 348) is located at the junction of State Highway 49/County Highway KK and crosses over U.S. Highway 41 in Lomira, WI (Dodge County). The bridge, coated with Sealer after construction only, was constructed in



Figure 348: Bridge B-14-0115

1994 with coated rebar and is supported by 70" prestressed girders. It is 236.8 ft in length (spans of 115 ft and 115 ft), has a deck width of 71 ft, and a roadway width of 68 ft. The most recent inspection gave the bridge deck a NBI rating of 8 and noted that are "Few light transverse cracks over the pier." ⁽¹²³⁾

5.2.3 Bridge B-14-0119

Bridge B-14-0119 (Figure 349) is located on E. Burnett Street and crosses over U.S. Highway 151 in Beaver Dam, WI (Dodge County). The bridge was constructed in 1995 with coated rebar and is supported by 54" prestressed girders. It



Figure 349: Bridge B-14-0119

is 206.5 ft in length (spans of 104ft and 100ft), has a deck width of 45.2 ft, and a roadway width of 37.7 ft. The most recent inspection gave the bridge deck a NBI rating of 8 and noted that are "Several diagonal cracks and short longits at the deck ends. A few transverse cracks over the pier." ⁽¹²⁴⁾

5.2.4 Bridge B-14-0129

Bridge B-14-0129 (Figure 350) is located on County Highway P and spans over the Rubicon River in Rubicon, WI (Dodge County). The bridge was constructed in 1994 with coated rebar and is supported by 70" prestressed girders. It



Figure 350: Bridge B-14-0129

is 133.7 ft in length (span of 130 ft), has a deck width of 38 ft, and a roadway width of 36 ft. The most recent inspection gave the bridge deck a NBI rating of 8 and noted that there is "some light cracking found on both end of the deck." ⁽¹²⁵⁾

As mentioned before, Admix-A was admixed into the concrete of the northern 1/3 of the deck, regular concrete was used in the center 1/3, and Admix-B was admixed into the concrete of the southern 1/3 of the deck. Since the bridge was a WisDOT test bridge, compressive strength results were provided (Table 45).

Deck	DOT	Breaks	Project	Breaks	(tested at site)			
Section	7-Day (psi)	28-Day (psi)	7-Day (psi)	28-Day (psi)	Slump	Air	Water/ C.Y.	
	3950	5400	4050	5400		3.5" 5.5%		
Admix-A	4100	5420	-	5400	3.5"		22 gal.	
	-	-	-	5630				
	3160	4490	3260*	4330		7.3%	22 gal.	
Control	3360	4440	-	4310	3.25"			
	-	-	-	4600				
Admix-B	3370	4230	3230	4000				
	3220	4400	-	3780	2"	5.1%	22.8 gal.	
	-	-	-	4460				

 Table 45:
 Compressive strength results of Bridge B-14-0129

*Note: Correcting to 5.5% air gives 3800, assuming 300 psi loss in strength for each additional % of air.

5.2.5 Bridge B-14-0133

Bridge B-14-0133 (Figure 351) is located on County Highway G and spans over the Chicago and Northwestern Railroad in Westford, WI (Dodge

County). The bridge was constructed with coated rebar and is supported by 28"



Figure 351: Bridge B-14-0133

prestressed girders. It is 160.6 ft in length (spans of 52.1 ft, 52.7 ft, and 52.1 ft), has a deck width of 32 ft, and a roadway width of 30 ft. The most recent inspection gave the bridge deck a NBI rating of 8 and noted "cracking above pier caps." ⁽¹²⁶⁾

In addition, Admix-C was added to the concrete in the west ½ of the bridge deck, as well as the piers and abutments. Compressive strength results are provided in Table 46.

Deck Section	DOT	Breaks	Ir	ndepender	(tested at site)			
	7-Day (psi)	28-Day (psi)	7-Day (psi)	14-Day (psi)	28-Day (psi)	56-Day (psi)	Slump	Air
Admix-C	_*	-	5200	5532	5402*	-	2.75"	6.5%
	_*	-	5144	5353	6218*	-	2.75	0.3%
Control	_*	-	-	-	-	6180	2.25"	5.8%
Control	_*	-	-	-	-	6149	2.23	3.0%

 Table 46:
 Compressive strength results of Bridge B-14-0133 (132)

*Note: Contained 8% air. No record of any DOT tests.

Because of a color difference between the Admix-C section and control section, a protective surface treatment (TK-26) was placed over the entire bridge deck.⁽¹³²⁾

5.2.6 Bridge B-47-0110

Bridge B-47-0110 (Figure 352) is located on County Highway G and spans over the Rush River in El Paso, WI (Pierce County). The bridge was constructed in 1993 with coated rebar and is supported by 36" prestressed girders. It



Figure 352: Bridge B-47-0110

was first coated with Sealer in 1997 and on a yearly basis since 1999. It is 158 ft in length (spans of 51.1 ft, 51.8 ft, and 51.1 ft), has a deck width of 32 ft, and a roadway width of 30 ft. The most recent inspection gave the bridge deck a NBI rating of 7 and noted "Transverse hair line cracking over piers. Some scaling under guard rail W side." (127), (128)

5.2.7 Bridge B-47-0118

Bridge B-47-0118 (Figure 353) is located on State Highway 35 and spans over the Isabelle Creek in Bay City, WI (Pierce County). The bridge was constructed in 1992 with coated rebar and is supported by haunched slabs. It is



Figure 353: Bridge B-47-0118

133.6 ft in length (spans of 40.0 ft, 53.0 ft, and 40 ft), has a deck width of 46 ft, and a roadway width of 44 ft. The most recent inspection gave the bridge deck a NBI rating of 6 and noted a "Couple hairline longitudinal cracks." On the underside of the deck, it

noted, "Couple hairline longitudinal leaching cracks. All spans have rust staining. North edge, 2 feet wide full length of deck is spalled with exposed rusty rebar." ⁽¹²⁹⁾

5.2.8 Bridge B-47-0120

Bridge B-47-0120 (Figure 354) is located on State Highway 35 and spans over Pine Creek in Maiden Rock, WI (Pierce County). The bridge was constructed in 1992 with coated rebar and is supported by 70" prestressed girders. It



Figure 354: Bridge B-47-0120

is 113.7 ft in length (span of 110 ft), has a deck width of 43 ft, and a roadway width of 40 ft. The most recent inspection gave the bridge deck a NBI rating of 6 and noted "Med. Scaling @ edges" and a "Few hairline diagonal cracks off deck ends." ⁽¹³⁰⁾

5.2.9 Bridge B-47-0141

Bridge B-47-0141 (Figure 355) is located on County Highway S and spans over the Rush Coulee Creek in Plum City, WI (Pierce County). The bridge was constructed in 1994 with coated rebar and is supported by a flat concrete slab. It was



Figure 355: Bridge B-47-0141

first coated with Sealer in 1998 and on a yearly basis since 2000. It is 47.9 ft in length (span of 46.0 ft), has a deck width of 32 ft, and a roadway width of 30 ft. The most

recent inspection gave the bridge deck a NBI rating of 7 and noted that the "concrete deck has minor spalling and small popouts , but there are no cracks at this date." ^{(127), (131)}

5.3 Results

To obtain statistically accurate results, a minimum of three locations were tested for each treatment on each bridge deck. At each location, chloride powders were obtained for each ¼" increment of depth to a total depth of 2" (Figure 356). For instance, since the concrete for the



Figure 356: Obtaining chloride powders from bridge deck

bridge deck of Bridge B-14-0129 was placed in thirds, three locations were tested in the Admix-A section, Control section, and Admix-B section of the bridge deck. For the bridge decks with uniform treatments, four locations were tested. See Appendix G for the chloride powder locations and complete chloride testing results.

After the chloride powders were obtained, they were brought back to the laboratory at UW-Milwaukee and tested in accordance with the aforementioned RCT-1029 test. Following the calculation of the chloride contents, several SSE regression analyses were performed to determine the surface chloride content and diffusion coefficient for each bridge deck.

To show the levels of chlorides present in each bridge deck, Table 47 has been developed to present the average chloride content of each increment of depth. In addition, the chloride content values obtained from this project at a depth of 2" for bridges B-14-0129 and B-14-0133 were compared against the values provided by the

WisDOT (Table 48 and 49).

Donth	B-14-110	B-14-115	B-14-119	B-14-0129			
Depth	B-14-110	В-14-115	Б-14-119	Admix-A	Control	Admix-B	
0" to $\frac{1}{4}$ "	0.643	0.457	0.574	0.477	0.492	0.543	
$\frac{1}{4}$ " to $\frac{1}{2}$ "	0.511	0.458	0.487	0.365	0.403	0.458	
$\frac{1}{2}$ " to $\frac{3}{4}$ "	0.427	0.368	0.327	0.293	0.348	0.377	
³ / ₄ " to 1"	0.379	0.270	0.293	0.257	0.288	0.251	
1" to $1\frac{1}{4}$ "	0.312	0.227	0.205	0.179	0.198	0.202	
$1\frac{1}{4}$ " to $1\frac{1}{2}$ "	0.201	0.202	0.193	0.137	0.136	0.148	
$1\frac{1}{2}$ " to $1\frac{3}{4}$ "	0.188	0.172	0.129	0.083	0.088	0.078	
1 ³ / ₄ " to 2"	0.115	0.132	0.081	0.046	0.046	0.043	
	B-14	.0133	D 47 110			D 47 141	
	D -14	-0133	D 47 110	D 47 110	D 47 130	D 47 141	
Depth	Control	Admix-C	B-47-110	B-47-118	B-47-120	B-47-141	
$\frac{\text{Depth}}{0" \text{ to } \frac{1}{4}"}$	-		B-47-110 0.290	B-47-118 0.406	B-47-120 0.450	B-47-141 0.313	
-	Control	Admix-C					
$0"$ to $\frac{1}{4}"$	Control 0.627	Admix-C 0.513	0.290	0.406	0.450	0.313	
$\frac{0" \text{ to } \frac{1}{4}"}{\frac{1}{4}" \text{ to } \frac{1}{2}"}$	Control 0.627 0.477	Admix-C 0.513 0.380	0.290 0.438	0.406 0.456	0.450 0.615	0.313 0.339	
$\frac{0" \text{ to } \frac{1}{4}"}{\frac{1}{4}" \text{ to } \frac{1}{2}"}$ $\frac{1}{2"} \text{ to } \frac{3}{4}"$	Control 0.627 0.477 0.413	Admix-C 0.513 0.380 0.330	0.290 0.438 0.342	0.406 0.456 0.426	0.450 0.615 0.477	0.313 0.339 0.285	
$\begin{array}{c} 0" \text{ to } \frac{1}{4}" \\ \frac{1}{4}" \text{ to } \frac{1}{2}" \\ \frac{1}{2}" \text{ to } \frac{3}{4}" \\ \frac{3}{4}" \text{ to } 1" \end{array}$	Control 0.627 0.477 0.413 0.342	Admix-C 0.513 0.380 0.330 0.304	0.290 0.438 0.342 0.304	0.406 0.456 0.426 0.321	0.450 0.615 0.477 0.445	0.313 0.339 0.285 0.248	
$\frac{0" \text{ to } \frac{1}{4}"}{\frac{1}{4}" \text{ to } \frac{1}{2}"}$ $\frac{1}{2"} \text{ to } \frac{3}{4}"$ $\frac{3}{4}" \text{ to } 1"$ $1" \text{ to } \frac{1}{4}"$	Control 0.627 0.477 0.413 0.342 0.246	Admix-C 0.513 0.380 0.330 0.304 0.263	0.290 0.438 0.342 0.304 0.234	0.406 0.456 0.426 0.321 0.283	0.450 0.615 0.477 0.445 0.431	0.313 0.339 0.285 0.248 0.208	

 Table 47: Chloride content of Dodge and Pierce County bridge decks

At first glance, it is not completely clear from Table 47 as to what treatment was most effective at reducing the ingress of chlorides. If one were to look only at the chloride content at a depth of 2", it would appear that Bridges B-14-0129 and B-47-0141 had the lowest chloride levels. Although the level of chlorides at 2" (assumed to be at the level of reinforcing steel) may be indicative of the performance of the concrete treatment, it does not provide for a thorough comparison.

Table 48: Chloride content comparison of Bridge B-14-0129 at 2" (lb/yd ³) (30)										
Treatment		Wis DOTWis DOTWHRP 0092-0ResultsAvg.Results)6-06	WHRP Avg.				
Admix-A	1.80	3.24	2.52	1.57	1.88	1.96	1.80			
Control	2.66	2.09	2.38	2.31	1.14	1.96	1.80			
Admix-B	1.91	3.59	2.75	1.45	1.49	2.08	1.67			

Treatment	Wis DOT Results		Wis DOTWHRP 0092-06-06Avg.Results			WHRP Avg.	
Admix-C	3.13	2.55	2.84	3.76	5.29	5.48	4.84
Control	3.53 9.04		6.29	4.50	8.89	6.66	6.68

Table 49: Chloride content comparison of Bridge B-14-0133 at 2" (lb/yd³) ⁽³⁰⁾

When asked about the level chlorides provided by the WisDOT, Peter Kemp replied that, "These structures were cored to look at the chloride ion concentration at the top steel level...Please note that the concrete used does not contain any fly ash or slag. This does not reflect the current state of practice that the department is currently employing." ⁽³⁰⁾ In addition, Kemp stated that the depth was not a measured value, but that 2 inches was typical for a minimum cover. ⁽¹³³⁾ When asked if the chloride content was water or acid-soluble, Kemp looked at the calculations and stated that AgNO3 solution (silver nitrate) was used to calculate the chloride content. Since silver nitrate is very soluble in water, he speculated that the chloride content was water soluble. ⁽¹³⁴⁾

In describing the level of salt used in the winter months, Pete Thompson replied, "They (Bridges B-14-0129 and B-14-0133) are typically treated with a 50/50 sand salt mix in the winter. The application rates are about 300-500 lbs of mix per mile. They are both treated with liquid magnesium chloride through a spray bar from a truck-mounted tank. The magnesium chloride is a 30% solution in 70% water. This is used as an antiicing treatment about every 2-3 days in the frost periods." ⁽¹³⁵⁾

In comparing the WisDOT data and this project's data for Bridge B-14-0129 at a depth of 2", the chloride levels provided by the WisDOT were greater than the levels found for this project. Also, it does not appear that the admixtures were effective in reducing the ingress of chlorides into the concrete of the bridge deck. For Bridge B-14-0133, the chloride levels provided by the WisDOT were less than those found for this project. At a depth of 2", it appears that the bridge section admixed with Admix-C has a

lower chloride content that the control section. As a thorough comparison, further analyses of these bridge decks, as well as the other seven, follow.

To determine the correlation of the results within each bridge deck, analyses were performed utilizing the chloride content at each "individual location" (Figure 357) and the "average of locations" (Figure 358). The regression analyses revealed that the calculated surface chloride contents and diffusion coefficient for the "individual locations" and "average of locations" had excellent agreement (Table 50).




Figure 357: Individual Chloride Content of Locations of Bridge B-14-110




Figure 358: Average Chloride Content of Locations for Bridge B-14-110

		Individual Regression						Average Regression		
Bridge	Treatment		D	ind. (in ² /	/yr)		C _{0-ind}	Davg.	C _{0-avg.}	
		А	В	С	D	Avg.	(%Cl)	(in^2/yr)	(%Cl)	
14-110	Sealer	.03	.06	.11	.09	.08	.69	.07	.67	
14-115	Sealer	.07	.12	.11	.06	.09	.52	.09	.51	
14-119	None	.06	.05	.05	.09	.06	.62	.06	.61	
	Admix-A	.06	.05	.03	-	.05	.56	.05	.56	
14-129	None	.06	.04	.06	-	.06		.06		
	Admix-B	.05	.05	.07	-	.06		.06		
14-133	None	.07	.17	.10	-	.11	.59	.11	57	
14-155	Admix-C	.09	.10	.04	-	.08	.39	.08	.57	
47-110	Sealer	.07	.09	.15	.08	.10	.51	.09	.50	
47-118	None	.05	.07	.35	.09	.14	.56	.11	.55	
47-120	None	.21	.04	.14	.30	.17	.70	.15	.66	
47-141	Sealer	.12	.06	.06	.04	.07	.46	.07	.44	

Table 50: Diffusion coefficients and surface chloride concentrations for each bridge deck

For the bridges in Pierce County, the above analyses did not involve the top ¹/₄" of concrete tested as the chloride content at 0.125" was significantly less than that of the chlorides at 0.375" (Figure 359). A discussion with Jerry Hall, Highway Department Manager for Pierce County, revealed that the bridge decks were flushed with water at the end of April each year, for the last 5 years. ⁽¹³⁶⁾ It was therefore determined that this would account for the reduction of chlorides in the top ¹/₄" of the concrete.




Figure 359: Average chloride content of Pierce County bridge decks

From Table 50 above, it can be seen that the surface chlorides and diffusion coefficients for the "individual locations" and "average of locations" were in close agreement. Therefore, further analyses were performed with the "average of locations."

Since a "virgin chloride content" was not found and the RCT-1029 method of chloride testing is "acid-soluble", a theoretical "base-line" chloride level was calculated for each bridge deck. These calculated values were removed from the "raw data" in subsequent analyses so that, theoretically, only the chlorides that entered the bridge decks during exposure would be compared to each another. For Bridges 14-0129 and 14-0133, the control sections were used for calculating the base-line chlorides.

By utilizing Fick's 2^{nd} Law of diffusion, the data from SHRP S-668 ⁽¹¹⁶⁾, and the data from the control bridges presented above, a determination was made as to what depth chlorides would not be present after 15 years of exposure. This age was used as it was representative of the bridge decks that were tested. Using $C_0 = 10.1$ lb/yd³ (0.258% chlorides by concrete weight) and D = 0.11 in²/yr, as shown in SHRP S-668, chloride levels reached approximately 0% at 5 inches. Using $C_0 = 23.1$ lb/yd³ (0.590% chlorides by concrete weight) and D = 0.097 in²/yr, as found by the control bridge decks in Table 50, chloride levels again reached approximately 0% at 5 inches (Figure 360).




Figure 360: Calculated depth at which chlorides would not be present

Because of these corresponding results, the base-line chlorides were found to be 0% chlorides by mass of concrete at a depth of 5". By removing this calculated "base-line" level of chlorides from the actual chloride contents, a relative regression analysis could then be performed such that the level of chlorides at 5" was approximately 0% chlorides by mass of concrete. The removal of the "theoretical base-line" chloride content would allow for a plausible comparison among the bridge decks (Table 51).

		Average Re	egression	Relative Regression				
Bridge	Treatment	D _{avg.} (in ² /yr)	C _{0-avg.} (% Cl ⁻)	"Base-line" Chlorides	D _{avg.} (in ² /yr)	C₀-avg. (%Cl⁻)	% Cl ⁻ at 5"	
14-110	Sealer	.073	.672	.000	.073	.672	.000	
14-115	Sealer	.092	.511	.010	.087	.502	.001	
14-119	None	.059	.612	.000	.059	.612	.000	
	Admix-A	.047			.047		.000	
14-129	None	.056	.556	.000	.056	.556	.000	
	Admix-B	.058			.058		.000	
14-133	None	.110	.572	.010	.104	.564	.001	
14-155	Admix-C	.082	.372	.010	.077	.304	.000	
47-110	Sealer	.095	.503	.020	.083	.488	.001	
47-118	None	.105	.547	.030	.089	.521	.002	
47-120	None	.155	.664	.050	.126	.619	.009	
47-141	Sealer	.072	.439	.000	.072	.439	.000	

 Table 51:
 Relative regression analysis for bridge decks

In Table 51 above, it is shown that the chlorides at a depth of 5" are now approximately 0.0% chlorides by mass of concrete or less, except for Bridge B-47-120. $D_{avg-rev}$ and $C_{0-avg-rev}$ of the control bridges were calculated at 0.087 in²/yr and 0.574% chlorides by concrete weight, respectively. As a further comparison, the relative regression data was further analyzed to determine the diffusion coefficients for each treatment while also calculating a uniform surface chloride concentration for all of the bridge decks that were tested (Table 52).

		Compa	rative Regression		
Bridge	Treatment	D _{avgcomp} (in ² /yr)	$(\%C1^{-})$ (lb/yd ³		
14-110	Sealer	.106		` `	
14-115	Sealer	.067			
14-119	None	.069			
	Admix-A	.045			
14-129	None	.054			
	Admix-B	.056	.565	22.13	
14-133	None	.103	.305	22.15	
14-155	Admix-C	.077			
47-110	Sealer	.061			
47-118	None	.074			
47-120	None	.164			
47-141	Sealer	.045			

Table 52: Comparative regression analysis for bridge decks

The final regression revealed that the $D_{avg-comp}$ and C_{0-comp} for the control bridge decks were 0.093 in²/yr and 0.565% chlorides by concrete weight, respectively. This compared quite favorably to the values obtained in Table 51 above. Because of the consistent surface chloride content, a direct comparison of the bridge decks can be made using the diffusion coefficients of Table 52.

Furthermore, the diffusion coefficient values obtained compare quite favorable to those calculated for Midwestern states found in SHRP S-668 (see Table 13). However, the surface chloride coefficient for Wisconsin was found to be approximately double that of the SHRP S-668 study.

To show how the analyses involving the "comparative chloride regression" and "relative chloride regression" related to the "raw data", Figures 361 and 362 have been provided as a comparison to Figures 358 and 359 above. The "base-line" chlorides have not been added to the regression plots. The plots show an excellent agreement between the raw data and regression curves.




Figure 361: Bridge B-14-0110 Regression Comparison




Figure 362: Bridge B-47-0110 Regression Comparison

To compare the effectiveness of the admixtures in reducing chloride ingress, Figures 363 and 364 have been developed. In Figure 364, it appears that Admix-A performs slightly better than Control-AB and Admix-B. However, it is shown in Figure 363 that the chloride content for Admix-A, Control-AB, and Admix-B are the same at a depth of 2". Thus, the use of Admix-A and Admix-B do not appear to affect the ingress of chlorides. Furthermore, the lower chloride contents of this bridge deck (B-14-0129) in general appear to be due to the material properties of the concrete, and not the admixtures. This is assumed as the control section displays a lower level of chlorides than the other bridge decks. On the other hand, Figures 363 and 364 both show that Admix-C performs better than its control section, Control-C.




Figure 363: Comparison of chloride contents of tested admixtures




Figure 364: Comparative regression analysis of tested admixtures

5.4 Discussion

From the Dodge County bridge decks, it was discovered that sealers applied at construction only (and without re-application) did not affect the ingress of chlorides. In fact, B-14-0119 performed only slightly worse than B-14-0110 and much better than B-14-0115. Although Admix-A of Bridge B-14-0129 provided a lower diffusion coefficient than Admix-B, it did not perform significantly better than the Control section of that bridge deck. Furthermore, the chloride contents at a depth of 2" were the same for each section of Bridge B-14-0129. In contrast, the diffusion coefficient and level of chlorides at a depth of 2" for Admix-C were less than the Control section of Bridge B-14-0133.

In Pierce County, the bridge decks that have been sealed after a few years of untreated exposure, and with subsequent reapplication, were found to display a lower diffusion coefficient than the bridge decks that had not been sealed at all. This shows that periodic reapplication of sealers, even if not used at construction, aids in reducing chloride ingress. Therefore, it appears that sealers must be periodically re-applied in order to be effective over the long term.

CHAPTER 6

CONCLUSIONS AND RECOMMENDATIONS

6.1 Summary and Conclusions

Based on an extensive literature review, an experimental program was initiated to investigate new or promising techniques to improve the repair and maintenance of reinforced concrete bridges in Wisconsin.

By subjecting 30 laboratory specimens to 6-months of accelerated corrosion testing that consisted of cyclic wet/dry cycles and an applied regulated voltage, the use of galvanic thermal sprayed zinc, galvanic embedded anodes, sealers, coatings, and epoxy repair mortar was evaluated. Sixteen of the specimens received treatment prior to exposure to accelerated corrosion (CoP) while the remaining fourteen specimens were cast with mixed-in chlorides and subjected to patch repair treatments after 3 months of accelerated corrosion testing (CoC). After repairs, these fourteen specimens were subjected to an additional 3 months of testing. Each treatment in question was applied to two specimens. The specimens were evaluated with respect to corrosion currents, chloride ingress, half-cell potential readings, extent of cracking, rust staining, and inspection of the reinforcing steel after the conclusion of testing.

In addition, the use of admixtures and sealers was evaluated on nine different bridge decks across Wisconsin through an extensive analysis of chloride ingress. Two of the bridge decks were cast with admixtures to reduce chloride ingress, four of the bridge decks were treated with surface sealers at various times of exposure, and three of the bridge decks were untreated.

197

6.1.1 Laboratory Specimens

Regarding the corrosion prevention specimens (CoP), the tri-silane sealer (T-SS) and thermal sprayed zinc with epoxy/polyurethane coating (TSZ w/EP-C) were found to be the most effective in preventing the initiation of corrosion. Because of the added cost of the TSZ w/EP-C, the T-SS appears to be the most economical choice in preventing the initiation of corrosion. The EP-C alone offered significant protection as well. Although a connection failed in one of the TSZ specimens, the method appeared to be effective when working properly. The embedded anodes (both EA-A and EA-B) were not found to be effective in the laboratory tests. The anodes attracted more chlorides to their vicinity and created variable chloride concentrations and non-uniform chloride penetrations. The use of coatings in conjunction with the embedded anodes was moderately effective; however, the acrylic coating (A-C) alone was more effective than the embedded anode with acrylic coating (EA-A w/A-C).

In regards to the corrosion control specimens (CoC), embedded anode-A with acrylic coating (EA-A w/A-C), thermal spray zinc (TSZ), and thermal sprayed zinc with epoxy/polyurethane coating (TSZ w/EP-C) were most effective in controlling corrosion. Essentially, these repairs utilized a coating. The performance of the embedded anodes (EA-A without coating and EA-B) were similar to that of the Control specimens. For the epoxy repair material (EM), the initial increase in corrosion current and appearance of the "ring-anode" effect at the perimeter of the patch must be considered. Furthermore, the conventional patch repair material itself did not show any signs of distress.

198

6.1.2 Field Testing of Bridge Decks

Chloride analysis of the bridge decks indicated that sealers applied at construction only (and without subsequent reapplication) did not adequately reduce chloride ingress. It was discovered that sealers should be reapplied on a periodic basis in order to provide long-term protection. In addition, it was discovered that sealing of an untreated bridge, and then providing periodic reapplication, was an effective way to reduce the ingress of chlorides. Furthermore, it was discovered that Admix-A and Admix-B did not perform significantly better than an untreated section of the same bridge deck. In contrast, Admix-C performed better than the untreated section of the same bridge deck.

The surface chloride concentration values calculated in this project were found to be approximately double that of previous findings for Wisconsin while the diffusion coefficient values were found to be similar to earlier reports. This means that measures to prevent the ingress of chlorides are even more important.

6.1.3 Overall Conclusions and Recommendations

For new structures, it is recommended that a surface applied sealer (such as T-SS) be applied prior to exposure to chlorides. A schedule for reapplication of sealers should also be required. Admix-C was found to be the most effective admixture tested when compared to its control section.

For structures with limited exposure and minimal corrosion damage, surface applied sealers should be installed as soon as possible. In addition, a schedule for reapplication of sealers should be required.

For existing structures with significant corrosion damage, the application of thermal sprayed zinc appears to offer benefits. Approved coatings can also be used in

199

conjunction with the thermal sprayed zinc. The embedded anodes did not appear to be beneficial in the laboratory tests. The conventional patch repair material itself performed well.

6.2 Recommendations for Future Research

It is recommended that the testing of sealers and admixtures in the field be expanded. In addition, a long-term study on the use of sealers should be implemented.

REFERENCES

1. United States Department of Transportation Federal Highway Administration Turner-Fairbank Research Center. Corrosion Protection: Concrete Bridges. *Turner-Fairbank Research Center*. [Online] September 1998. [Cited: March 26, 2006.] http://www.tfhrc.gov/structur/corros/corros.htm. FHWA-RD-98-088.

2. Yunovich, Mark, et al. Appendix D: Highway Bridges. [ed.] Gerhardus H. Koch, et al. *Corrosion Cost and Preventive Strategies in the United States*. September 30, 2001.

3. Stein, Jason. Bridge Repairs could cost Wisconsin over \$2 billion. *Wisconsin State Journal*. [Online] August 3, 2007. [Cited: August 6, 2007.] www.madison.com/wsj/topstories/index.php?ntid=204016.

4. United States Department of Transportation Federal Highway Administration Federal Transit Administration. 2004 Status of the Nation's Highways, Bridges, and Transit: Conditions and Performance. 2006.

5. Barker, Richard M. and Puckett, Jay A. *Design of Highway Bridges: Based on AASHTO LRFD Bridge Design Specifications*. New York : John Wiley and Sons, Inc., 1997. 0-471-30434-4.

6. Kay, Ted. Assessment and Renovation of Concrete Structures. New York : John Wiley and Sons, Inc., 1992. 0470-21864-9.

7. Chrest, Anthony P., Smith, Mary S. and Bhuyan, Sam. *Parking Structures: Planning, Design, Construction, Maintenance, and Repair (Second Edition).* New York : Chapman and Hall, 1996. 0-412-99671-5.

8. Newman, Alexander. *Structural Renovation of Buildings: Methods, Details, and Design Examples.* New York : McGraw-Hill, 2001. 0-07-047162-2.

9. American Concrete Institute Committee 222. ACI 222R-01: Protection of Metals in Concrete Against Corrosion. s.l. : American Concrete Institute, 2001.

10. American Concrete Institute Committee 201. *ACI 201.2R-01: Guide to Durable Concrete*. s.l. : American Concrete Institute, 2001.

11. El-Reedy, Mohamed A. *Steel-Reinforced Concrete Structures: Assessment and Repair of Corrosion*. Boca Raton : Taylor & Francis Group, 2008. 978-1-4200-5430-9.

12. Ball, J. Christopher and Whitmore, David W. Corrosion Mitigation Systems for Concrete Structures. *Concrete Repair Bulletin.* July/August, 2003.

13. Bohdanowicz, W. Layer Zinc Anodes in Cathodic Protection of Steel Reinforcement. [book auth.] J. Mietz, R. Polder and B. Elsener. *Corrosion of Reinforcement in Concrete: Corrosion Mechanisms and Corrosion Protection. Papers from EUROCOOR '99.* London : IOM Communications, 2000. 14. Testconstult Ltd. Structures Data Sheet 5: Carbonation of Concrete. [Online] [Cited: April 26, 2008.] http://www.testconsult.co.uk/downloads/st_data05_carb.pdf.

15. Hansson, C. M., Poursaee, A. and Jaffer, S. J. *Corrosion of Reinforcing Bars in Concrete*. Illinois : Portland Cement Association, 2007. R&D Serial No. 3013.

16. Corrosion Doctors. Corrosion in Concrete. *Corrosion Doctors*. [Online] [Cited: March 30, 2006.] http://www.corrosion-doctors.org/Concrete/Introduction.htm.

17. Emmons, Peter H. *Concrete Repair and Maintenance Illustrated*. Kingston, MA : RS Means, 1993. 9-780876-292860.

18. Germann Instruments. Deep Purple and Rainbow Indicator. *Summary of Germann Instruments*. [Online] March 15, 2006. [Cited: November 29, 2008.] www.germann.org/Pages/Products/Indicators/Indicators.htm.

19. Broomfield, J. P., Langford, P. E. and Ewins, A. J. The Use of a Potential Wheel to Survey Reinforced Concrete Structures. [book auth.] Neal S. Berke, Victor Chaker and David Whiting. *Corrosion Rates of Steel in Concrete, ASTM STP 1065*. Philadelphia : American Society for Testing and Materials, 1990.

20. Elcometer Technical Support. March 2008.

21. Moulzolf, Gerard. Concrete Repair Failure: Discovering What Went Wrong. *The American Eagle*. Fall, 2001.

22. Vector Corrosion Technologies. Corrosion Management: Selecting a Corrosion Protection Strategy for Concrete Structures. [Online] [Cited: August 7, 2007.] http://www.vector-corrosion.com/corr_mgmt.html.

23. Helsel, Jayson L. Securing the Deck. *Journal of Architectural Coatings*. March/April, 2007.

24. Tabatabai, Habib, Ghorbanpoor, Al and Turnquist-Nass, Amy. *Rehabilitation Techniques for Concrete Bridges*. s.l. : Wisconsin Department of Transportation Research and Library, June 2005. Project 0092-01-06.

25. Brown, Michael C. Assessment of Commercial Corrosion Inhibiting Admixtures for Reinforced Concrete. Blacksburg : s.n., 1999. ETD-122199-104756.

26. C-Probe Systems Ltd. Systems Bulletin 7: Use of Surface-Applied Corrosion Inhibitors. *Achilles Suite of Structural Asset Management Systems*. [Online] [Cited: August 20, 2007.] http://www.c-probe.com/Systems/bulletin7_2.shtml.

27. Balaguru, P. N. and Nazier, Mohamed. *Evaluation of Corrosion Inhibitors*. Trenton : s.n., 2002. FHWA-NJ-2003-005.

28. Blake, Ed. Personal communication. June 21, 2006.

29. Kemp, Peter. RE: UWM Inquiry for Dodge County Bridge Testing. [Email to M. Pritzl]. May 30, 2008.

30. —. RE: Dodge County Bridges. [Email to M. Pritzl]. August 29, 2007.

31. Hycrete, Inc. Hycrete Admixture. Jersey City : Hycrete, Inc., 2006.

32. Goodwin, Paul D., Frantz, Gregory C. and Stephens, Jack E. *Protection of Reinforcement with Corrosion Inhibitors, Phase II.* s.l. : Connecticut, 2000. JHR 00-279/JHRAC Project 96-2 Phase II.

33. Frantz, Gregory. RE: Protection of Reinforcement with Corrosion Inhibitors, Phase II. [Email to M. Pritzl]. March 31, 2008.

34. Sharp, Stephen R. and Ozyildirim, Celik. *Influence of Hycrete DSS on Virginia Department of Transportation Class A4 Concrete Mix Designs*. Charlottesville, VA : Virginia Transportation Research Council, May 2007. VTRC 07-R30.

35. Vector Corrosion Technologies. *Corrosion Management Strategies: Levels of Active Corrosion Protection*. Minnipeg, MB : Vector Corrosion Technologies, 2003.

36. Cortec Corporation. *MCI: Migrating Corrosion Inhibitors for Concrete Durability*. St. Paul : Cortec Corporation, 2006.

37. Sharp, Stephen R. *Evaluation of Two Corrosion Inhibitors Using Two Surface Application Methods for Reinforced Concrete Structures*. Charlottesville : Virginia Transportation Research Council, 2004. VTRC 05-R16.

38. Cook, Anna Kaye. *Evaluation of The Effectiveness of Surface Applied Corrosion Inhibitors for Concrete Bridges*. Raleigh : North Carolina State University, 2004. ETD-09012004-220324.

39. Jones, Graeme. Case Studies: Corrosion Management of Parking Structures. *Parking*. July, 2007.

40. Cortec Corporation. Competition Puts Up A Fight. MCI Newsletter. 12, 2003.

41. United States Department of Transportation Federal Highway Administration Research and Development. *Long-Term Effectiveness of Cathodic Protection Systems on Highway Structures*. McLean : s.n., 2001. FHWA-RD-01-096.

42. Kepler, Jennifer L., Darwin, David and Locke, Carl E. *Evaluation of Corrosion Protection Methods for Reinforced Concrete Highway Structures*. 2000 : s.n., 2000. K-Tran Project No. KU-99-6.

43. Bennett, Jack and Turk, Thomas. *Technical Alert: Criteria for the Cathodic Protection of Reinforced Concrete Bridges Elements*. Washington, DC : Strategic Highway Research Program, 1994. SHRP-S-359.

44. Corrosion Doctors. Impressed Current Cathodic Protection. [Online] [Cited: August 7, 2007.] http://www.corrosion-doctors.org/CP/Impressed.htm.

45. Francis, P. E. Cathodic Protection.

46. Vector Corrosion Technologies. *Ebonex: Discrete anodes for impressed current cathodic protection*. Canada : Vector Corrosion Technologies, Inc., 2007.

47. Corrosion Restoration Techologies. Metalizing. [Online] [Cited: March 30, 2006.] http://crt-norust.com/metalize/index.html.

48. Supplier A. "EA-A" Data Sheet. 2007.

49. —. "EA-A" Installation Instructions. 2007.

50. Vaysburg, Alexander M. *Appraisal Report: Galvashield Embedded Galvanic Anodes for Repair of Concrete.* Farmington Hills : Concrete Innovations Appraisal Service, 2001. CIAS Report: 01-1.

51. Ashworth, Lindsay and Lathrop, Donald H. *Intallation Report: Galvashield XP Sacrificial Anodes.* s.l. : Vermont Agency of Transportation, June 6, 2003.

52. McMahan, Jerry. *Preliminary Evaluation of Galvashield Installation in BR 48, I-89, Waterbury*. Montpelier, Vermont : Vermont Agency of Transportation, 2005.

53. Michigan Department of Transportation. Qualified Products List. August 21, 2007.

54. Illinois Department of Transportation. *Products Evaluation Circular*. s.l. : State of Illinois Department of Transportation Bureau of Materials and Physical Research, January 25, 2008. Cirfront_2008_01_25.doc.

55. Vespa, Joe. RE: UW-Milwaukee (WI DOT) use of galvashield anodes. [Email to M. Pritzl]. August 15, 2008.

56. Supplier B. "EA-B" Data Sheet. 2008.

57. Supplier A. Invoice for purchase of "EA-A". 2007.

58. Schultz, Todd. RE: "EA-B". [Email to M. Pritzl]. September 5, 2006.

59. Tator, Kenneth B. Innovations for repairing concrete buildings in salt environments. *Journal of Architectural Coatings*. January, 2005.

60. Spriestersbach, J., et al. Lifetime Extension of Thermally Sprayed Zinc Anodes for Corrosion Protection of Reinforced Concrete Structures by Using Organic Top-Coatings. [book auth.] J. Mietz, R. Polder and B. Elsener. *Corrosion of Reinforcement in Concrete: Corrosion Mechanisms and Corrosion Protection Papers from EUROCORR '99.* London : IOM Communications Ltd., 2000. 61. Butler, Joseph T. Metalizing for Corrosion Control: The Coating. [Online] 2000. [Cited: March 26, 2006.] www.metalizing.com/advant.html.

62. Daily, Steven F and Green, Warren K. *Galvanic Cathodic Protection of Reinforced and Prestressed Concrete Structures using CORRYSPRAY - a Thermally Sprayed Aluminum Alloy.* s.l. : Corrpro Companies, Inc. Technical Paper 51.

63. Platt Bros. Phone coversation. November 1, 2006.

64. Steam and Sand Ltd . Hot Metal Arc Spraying. [Online] [Cited: March 26, 2006.] http://www.steamsand.co.nz/thermalarc.htm.

65. Militenberger, Matt. Re: Galvanode ASZ+ Inquiry. [Email to M. Pritzl]. April 19, 2006.

66. Costa, Jorge. RE: Mike MeLampy told me to get a hold of you. [Emails to M. Pritzl]. April 7 and 14, 2006.

67. Matthew, S. A., et al. *Atmospheric Corrosion and Precipitation Runoff From Zinc and Zinc Alloy Surfaces*. Albany, OR : Albany Research Center, U.S. Department of Energy, 2003. DOE/ARC-2003-003.

68. Holcomb, Gordon R., et al. *Humectants to Augment Current from Metallized Zinc Cathodic Protection Systems on Concrete*. Salem, Oregon : Oregon Department of Transportation, 2002. FHWA-OR-RD-03-08.

69. Costa, Jorge. Phone discussion. June 6, 2008.

70. Sandron, Felix. RE: Reapplication of humectant activator. [Email to M. Pritzl]. November 3, 2008.

71. Firlotte, Clem. RE: Corrspray. Email to M. Pritzl. August 15, 2008.

72. Whitney, David, Elcheverry, Leandro and Wheat, Harovel. *Cathodic Protection: Coordinating Corrosion to Save State Structures*. Austin : Center for Transporation Research: The University of Texas at Austin, March 2003.

73. Sagues, Alberto A. and Powers, Rodney G. *Sprayed Zinc Galvanic Anodes for Concrete Marine Bridge Substructures*. Washington, DC : Strategic Highway Research Program National Research Council, 1994. SHRP-S-405.

74. National Research Council Canada. Repair Technologies: A New Look at Repairing Corrosin Damaged Concrete. *Construction Innovation*. Winter, 1996, Vol. 1, 3. http://irc.nrc-cnrc.gc.ca/pubs/ci/v1no3_v1no3_21_e.html.

75. Andrews-Phaedonos, F., Solomon, I. and Payne, D. J. Sprayed Zinc Galvanic Anode System for the Cathodic Protection of Moodys Inlet Bridge, South Gippsland Highway, Victoria. Paper 187, 13th ICC.

76. Transportation Research Board. Observation of Galvanic Production for Bridge Deck - A12112. *Research in Progess*. [Online] August 18, 2005. [Cited: July 17, 2006.] http://rip.trb.org/browse/dproject.asp?n=11069.

77. Gawedzinski, Mark. *Evaluation of Sprayed-On Metalizing for Precast Prestressed Concrete I-Beams*. Springfield, IL : Illinois Department of Transportation, 2002. FHWA/IL/PRR-141.

78. —. FW: evaluation of sprayed-on metalizing for precast prestressed concrete i-beams. [Email to M. Pritzl]. August 15, 2008.

79. Sandron, Felix. *Re: School Structure, Greater Milwaukee Area. Corrosion Mitigation Options and Budgets for CIP exterior columns and beams.* Winnipeg, MB : Vector Corrosion Technologies, April 4, 2008.

80. Pleuss, Chuck. Phone conversation with M. Pritzl. June 26, 2008.

81. Fallaha, Sam and Whitmore, David. *Evaluation of Alternatives for Extending the Service Life of Interstate Route 480 Viaduct Substructure*. s.l. : Transportation Association of Canada, 2004. http://www.tac-atc.ca/english/pdf/conf2004/fallaha.pdf.

82. Whitmore, David. Re: ECE on Prestressed Girders. [Email to M. Pritzl]. June 15, 2006.

83. —. RE: Galvanic Anodes. [Email to M. Pritzl]. June 22, 2006.

84. —. Re: Coatings on thermal sprayed zinc. [Email to M. Pritzl]. August 4, 2006.

85. Firlotte, Clem. RE: detail and general spec for Al-Zn-In Alloy. [Email to M. Pritzl]. July 10, 2008.

86. Ontario Ministry of Transportation. Revolutionizing Bridge Rehabilitation. *Road Talk.* February, 2004, Vol. 10, 1.

87. Vector Corrosion Technologies. *Norcure Chloride Extraction: Electrochemical chloride extraction process for chloride-contaminated concrete*. s.l. : Vector Corrosion Technologies, 2003.

88. —. Norcure Re-alkalization: Electrochemical re-alkalization process for carbonated concrete. 2003.

89. Whitmore, D. W. Electrochemical Treatment of Concrete: A New Approach to Extend the Service Life of Chloride Contaminated, Carbonated, or Alkali Silica Reactive Concrete Structures. *Norcure Chloride Removal Systems*. [Online] [Cited: March 24, 2008.] http://www.norcure.com/tech.htm.

90. United States Department of Transportation Federal Highway Administration. Electrochemical Chloride Extraction: A Win-Win for Maintenance and Traffic. *FOCUS*.

[Online] Turner-Fairbank Highway Research Center, January 2000. [Cited: May 4, 2008.] http://www.tfhrc.gov/focus/focus.htm.

91. Kahl, Steve. *ELECTROCHEMICAL CHLORIDE EXTRACTION*. Lansing : Michigan Department of Transportation, 2001. R-1384/97 TI-1864.

92. Sharp, Stephen R., et al. *Electrochemical Chloride Extraction: Influence of Concrete Surface on*. Springfield, VA : National Technical Information Service , 2002. FHWA-RD-02-107.

93. Purdue University: Division of Construction Engineering and Management. Electrochemical Chloride . *Emerging Construction Technologies*. [Online] April 1, 2001. [Cited: August 14, 2007.] http://rebar.ecn.purdue.edu/ect/Civil/elecchlo.aspx.

94. Chauvin, Mark, et al. *Evaluation of Electrochemical Extraction (ECE) and Fiber Reinforced Polymer (FRP) Wrap Technology.* St. Paul : Minnesota Department of Transportation Office of Research and Strategic Services, 2000. MN/RIC-2000-24.

95. Beaudette, Martin. Re-alkalization: Non-destructive electrochemical treatment to halt ongoing and prevent furture reinforcement corrosion in carbonated concrete. [Online] [Cited: March 24, 2008.] www.norcure.com/tech2.htm.

96. Sandron, Felix. "EA-A" Positioning. [Email to M. Pritzl]. March 2, 2007.

97. Supplier E. Product Data Shet: "A-C". 2006.

98. Supplier B. "EA-B" Successful Application. 2004.

99. Bennett, Jack. Re: "EA-B" Information Request. [Email to M. Pritzl]. March 1, 2007.

100. Supplier A. "TSZ" Specification for Installation. 2006.

101. Sandron, Felix. RE: UW-Milwaukee Use of Thermal Spray. [Email to M. Pritzl]. May 2, 2007.

102. Supplier D Technical Representative. Phone discussion. July 9, 2007.

103. United States Army Corps of Engineers. *Thermal Spraying: New Construction and Maintenance*. Washington, DC : USACE, 1999. EM 1110-2-3401.

104. Sandron, Felix. RE: coatings of thermal spray. Email to M. Pritzl. July 10, 2007.

105. Supplier D. Product Information: "EP-C". 2005.

106. Wisconsin Department of Transportation. *Approved Lists (Pre-qualified Products Lists)*. 2007.

107. Supplier C. Technical Data: "T-SS". 2005.

108. Supplier F. "EM": Technical Data Sheet. 2007.

109. Cheney, Doug. FW: Highway Patch. [Email to M. Pritzl]. March 6, 2008.

110. Five Star Products, Inc. *Five Star Highway Patch: Data Sheet.* s.l. : Five Star Products, Inc., 9/6/2007.

111. BASF Construction Chemicals, LLC. *Set 45 and Set 45 HW: Product Data*. s.l. : BASF, 8/2007.

112. Master Builder's Inc. Engineering Support Laboratory. *Electrical Resistivity Test Method*. 5/9/1998.

113. Sandron, Felix. Concrete Resistivity. [Powerpoint Presentation] March 11, 2008.

114. Wittlinger, Bill. Phone conversation with M. Pritzl. March 12, 2008.

115. Supplier B. "Conventional Patch Material": Product Data Sheet. 2008.

116. Weyers, Richard E., et al. *Concrete Bridge Protection and Rehabilitation: Chemical and Physical Techniques - Service Life Estimates*. Washington, DC : Strategic Highway Research Program - National Research Council, 1994. SHRP-S-668.

117. Supplier B. Bonding Agent and Anti-Corrosion Coating for Reinforcement. 2007.

118. Sandron, Felix. RE: concrete repair for thermal sprayed zinc. [Email to M. Pritzl]. May 12, 2008.

119. *Corrosion Effects on Bond Strength in Reinforced Concrete*. Stanish, Kyle, Hooton, R.D. and Pantazopoulou, S.J. No. 6, November-December 1999, ACI Structural Journal, Vol. V. 96, pp. 915-922.

120. Germann Instruments. RCT & RCTW. *Summary of Germann Instruments*. [Online] March 15, 2006. [Cited: November 29, 2008.] www.germann.org/Pages/Products/RCT%20og%20RCTW/RCT%20og%20RCTW.htm.

121. McDaniel, Travis. FW: 0092-06-06: Evaluation of Methods of Rebar Protection, Spall Prevention, and Repair Techniques on Concrete Girders Research Contract. [Email to H. Tabatabai]. February 27, 2008.

122. Oettinger, Jim E and Shelton, Adam. *Bridge Inspection Report: Wisconsin Department of Transporation: Structure No. B-14-0110.* s.l. : State Highway Department, August 25, 2006.

123. Alsum, Joel. Bridge Inspection Report: Wisconsin Department of Transporation: Structure No. B-14-0115. s.l.: State Highway Department, June 6, 2007.

124. Hall, Jeremy. *Bridge Inspection Report: Wisconsin Department of Transporation: Structure No. B-14-0119.* s.l. : State Highway Department, May 4, 2007.

125. Johnson, Danny R and Kassube, Brian. *Bridge Inspection Report: Wisconsin Department of Transporation: Structure No. B-14-0129.* s.l. : Dodge County Highway, April 4, 2008.

126. Johnson, Dan and Kassure, Brian. Bridge Inspection Report: Wisconsin Department of Transporation: Structure No. B-14-0133. s.l. : Dodge County Highway, March 24, 2006.

127. Hall, Jerry. Personal communication. July 29, 2008.

128. Halls, Jerome D and Redding, Jeff. Bridge Inspection Report: Wisconsin Department of Transporation: Structure No. B-47-0110. s.l. : Pierce County Highway, April 9, 2007.

129. Frueh, Rick J. Bridge Inspection Report: Wisconsin Department of Transporation: Structure No. B-47-0118. s.l. : State Highway Department, April 16, 2008.

130. —. Bridge Inspection Report: Wisconsin Department of Transporation: Structure No. B-47-0120. s.l. : State Highway Department, April 24, 2008.

131. Halls, Jerome D. Bridge Inspection Report: Wisconsin Department of Transporation: Structure No. B-47-0141. s.l. : Pierce County Highway, April 10, 2007.

132. Schuchardt, Lee. Work Plan for Research Project to Evaluate the Performance of Waterproofing Concrete Admixtures Utilized in Dodge County Bridges. s.l. : State of Wisconsin, February 2, 1996.

133. Kemp, Peter. RE: Dodge County Bridge Testing. [Email to M. Pritzl]. December 12, 2007.

134. —. RE: Dodge County Bridges. [Email to M. Pritzl]. August 21, 2008.

135. Thompson, Peter. "Admix C" Info. [Email to M. Pritzl]. February 14, 2007.

136. Hall, Jerry. Personal Communication. August 28, 2008.

(Page left blank intentionally)

APPENDIX A

Reinforcing Steel and Concrete Data

@002/002

Page: 1 Page: 1 Date: 27-Dec-2008 B.L. Number: 334144 Load Number: 5584940 CHEMICAL TEST 016 051 23 40 57 016 049 21 44 57 016 049 21 44 57 009 002 40 57	
ĭ s s s s s s s s s s s s s s s s s s s	
13 12 12 12 12 12 12 12 12 12 12 12 12 12	
MILL TE Kankakee, Kankakee, Kankakee, Nay Nay Ni L 60914 16 16 16	
CERTIFIED MILL TEST REPORT Ship from: Ship from: Ship from: Nucor Steel Kankakee, Inc. One Nucor Way Bourbonnais, IL 60914 B15-937-3131 60914 314% .38 1.02 .34% .38 1.02 .34% .38 1.02 .036 .13 .11 .036 .13 .065	
CX CX BEND S CX	
ANKAKEE, I ANKAKEE, I PHYSICAL TESTS ANPa APPa 13.8% APa 13.8% APa	CTON.
b0-0 Rear enor Rear enor Physical TESTS acting your Inside sales inpresenta Physical TESTS Physical TisNPa 13.8% 0 MPa 707MPa 13.8% 0	THE CORPORT
HJS 60-0 REAR ALCOR STEEL KANKAKE, INC. BAR MILL GROUP AUCOR STEEL KANKAKE, INC. BAR MILL GROUP ACMPa TISMPa BEND 67,324 103,630 13.8% OK 464MPa 715MPa 13.8% OK 464MPa 715MPa 13.8% OK 462MPa 707MPa 13.8% OK 51eel Kankakee cled materials.	ARE CORRECT AS CONTAINED IN THE RECORDS OF THE CORPORATION.
BAR WLCOR S 1 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2	VTAINED IN THE
e, Inc. e, Inc. e, Inc. 1420 1 at Nucor	DRRECT AS CON
#55 b0-0 Hester b0-0 Hester S0LD AMBASSADOR STEEL CORP TO: KOKOMO, IN 46804-2340 MMCCORP SHP AMBASSADOR STEEL CORP WULCOR STEEL CORP TO: KOKOMO, IN 0000- MMCCORP SHP AMBASSADOR STEEL CORP WULCOR STEEL CORP TO: KOKOMO, IN 0000- S1HP AMBASSADOR STEEL CORP TO: KOKOMO, IN 0000- MMCCORP SHP AMBASSADOR STEEL CORP TO: KOKOMO, IN 0000- MMCCORP SHP AMARSADOR STEEL CORP TO: KOKOMO, IN 0000- Material Safey Data Runs MMCCORP AL TO: KOKOMO, IN 0000- MMCCORP AL TO: KOKOMO, IN 0000- Material Safey Data Runs MTCORPAL MTCORPAL STANDAR STEEL CORP TO: KOKOMO, IN 0000- Material Safey Data Runs MTCORPAL MTCORPAL Material Safey Data Runs MTSIA MTCORPAL POM => NUBH Material Runs MTSIA MTSIA MTSIA POM => NUBH Runs MTSIA MTSIA MTSIA MTSIA POM => NUBH Runs MTSIA MTSIA MTSIA MTSIA POM => NUBH Runs MTSIA MTSIA MTSIA MTSIA POM => NUBH RUNCY Steel Kantakae, Inc. MTSIA MTSIA MTSIA POM => NUBH RUNCY Steel Kantakae MTSIA MTSIA MTSIA POM => NUBH RUNCY Steel Kantakae MTSIA MTSIA MTSIA	INEVERY CERTEY THAT THE ABOVE FIGURES ARE CORRECT AS CONTAINED IN THE RECORDS OF THE AIL LIMITED THORAD BADACERES OF THE ADDRESS OF THE CORDS OF THE LIMITED THORAD BADACERES OF THE CORDS OF THE LIMITED THOMAD BADACERES OF THE CORDS OF THE LIMITED THOMAD BADACERES OF THE CORDS OF THE LIMITED THOMAD BADACERES OF THE CORRECT AS CONTAINED IN THE RECORDS OF THE LIMITED THOMAD BADACERES OF THE CORRECT AS CONTAINED IN THE RECORDS OF THE LIMITED THOMAD BADACERES OF THE CORRECT AS CONTAINED IN THE RECORDS OF THE LIMITED THOMAD BADACERES OF THE CORRECT AS CONTAINED IN THE RECORDS OF THE LIMITED THOMAD BADACERES OF THE LIMITED THOMAD BADACERES OF THE LIMITED THOMAD BADACERES OF THE RECORDS OF T
Solub AMBASS, TO: KOKOMOX SHIP AMBASS, TO: KOKOMO Maladral Safety Dat. HEAT NUM. • PO# => KN0610959901 PO# => KN0610959901 PO# => KN0610959901 are ma	IN CERTIFY THAT

	Prairie Group Cor E.O.E. / A.A.	and the second se		(414) 25 (800) 25			F & Res Res F		
DATE	TICKET TIME	DUE AT JOB	CUSTOMER NO.	TAX CODE	PLANT ID	POUR	TYPE		TICKET NO.
3/13/0	7 09:11	09:56	1005054		107	<un< td=""><td>KNOWN></td><td></td><td>758548</td></un<>	KNOWN>		758548
USTOMER N.	AME SHOUNTS PA	YABLE		JOB	ME/ADDRESS	2	~		LOAD NO. 0001
PURCHASE OF	DINED NO.		DRIVERS NAME		MAP PAGE	MIX SLUMP	FOLLOW	VEHICLE	5.50 AIR CONTEN
ONUTAGE OF	NUCH NO.	3	DRIVERS NAME TRK	# 0095 TERRAN	MOLT AUL	5.00	0087		All CONTEN
125 01 03 13	5.	50 H 00 F	000 1 AE NEAT UEL SURCHA NVIRONMENT		ΞĒ		CY CY LD CY		
9:15 a:57 10:15 11:40	Load Arrive Job Start Pour Stop Pour	ing time allow	Min Min Per Min Per Min overnme craves res per yard free unload wed. Additional unload wed. Additional unload wed. Additional unload wed. Additional unload y true	Job Nat Job Bro Job Bro Truck B Adding Solve Pl Slow Pl Other (B G	ke Down roke Down Water Job Early acing Method	: 101	AL MINUTES ALLOWED	SUB-TOTAL SALES TAX SUB-TOTAL AXABLE DELAY TIME GRAND TOTAL	
mixed come TAKE THES 1. Avoid all 2. Wear rub directly w 3. In case o WITH W	ent, mortar, concre SE PRECAUTION contact with eyes, ber boots and glo rith skin or through of contact with skin ATER. n persists, get mee	Contains portla te, or grout ma S: ves, and avoid porous mater or eyes, FLUS	SH THOROUGHLY			WARNING; AG REDUCES ITS 5 FOR STREINGTH MATERIAL IS AI NOT RESPONS COLOR QUALITY WATER A	DDED MAX	CONCRETE MATER R IS NOT RESPONSIG INEN WATER OR OTH EN DA AT HIS REQUE TIVE AGGREGATE KADD WATER GALS.	jal EFE OR OR
G	READY MIS E.C.C. (AA		shall in	– Customer agre demnity seller for	truck within conf objects, undergi delivery point. Si so directed, PU result of SELLEF I have read and above. RECEIVED BY:	inssumes all re ines of the job round utilities, ELLER'S vehic RCHASER as a'S vehicle ins d understand t X able roadway to roperty damage	p site. PURCHAS and overhangii sle is not permitte sumes all respo ide the curb line. he above and a point of delivery between curb an	ER agrees to provi ng wire for SELLE d to travel inside of nsibility for damag gree to assume the SIGN FULL NAME and customers assu	e caused by SELLE de access clear of f RS delivery vehick f, or across curb liner es that may occur a e responsibilities for me responsibility and ur for trucks held at

APPENDIX B

Cylinder Breaks and Baseline Chlorides

Sample #	Break	Compressive Strength (psi)	Average Compressive Strength (psi)
1		5,825	
2		5,994	5,839
3		5,697	

Results of 28-Day Breaks and Compressive Strength

Liquid	Clear	Purple	Green	Pink
%CL	0.005	0.02	0.05	0.5
mV before	99.7	67.8	47.5	-6.2
mV after	99.1	69.8	51.3	-5.3
mV before	103.1	70.7	48.0	-6.0
mV after	100.2	71.0	50.9	-4.6

 Baseline Chlorides
 MDP

 Date:
 NDP

 5 Minute Test
 10/18/2007


 24 Hour Test
 10/19/2007

Assumed weight of concrete = 145.0 lb/yd3

	5 N	/inute Test		24 Hour Test			
Sample No.	mV	%Cl by mass of concret e	lb. Cl/yd ³ concret e	mV	%Cl by mass of concret e	lb. Cl/yd ³ concret e	
11B 1/2"	60.8	0.029	1.135	55.5	0.037	1.449	
11B 1"	60.9	0.029	1.135	57.8	0.034	1.331	
11C 1/2"	57.8	0.032	1.253	51.0	0.046	1.801	
11C 1"	57.3	0.034	1.331	54.2	0.040	1.566	
13B 1/2"	59.9	0.030	1.175	56.9	0.035	1.370	
13B 1"	64.7	0.024	0.940	59.2	0.033	1.292	
13C 1/2"	58.8	0.031	1.214	49.7	0.048	1.879	
13C 1"	54.2	0.039	1.527	50.4	0.046	1.801	
15B 1/2"	54.6	0.037	1.449	49.3	0.050	1.958	
15B 1"	57.6	0.032	1.253	49.8	0.048	1.879	
15C 1/2"	54.9	0.037	1.449	49.5	0.049	1.918	
15C 1"	58.9	0.031	1.214	54.3	0.039	1.527	
	Averages:	0.032	1.256		0.042	1.648	

Theoretical Chloride Content

	5 Minute	e Test	24 Hour Test		
Depth	%Cl by mass of concrete	Total %Cl	%Cl by mass of concret e	Total %Cl	
0" to 1/4"	0.113	0.145	0.113	0.155	
1/4" to 1/2"	0.113	0.145	0.113	0.155	
1/2" to 3/4"	0.113	0.145	0.113	0.155	
3/4" to 1"	0.113	0.145	0.113	0.155	
1" to 1-1/4"	0.049	0.081	0.048	0.090	
1-1/4" to 1- 1/2"	0.049	0.081	0.048	0.090	
1-1/2" to 2"	0.049	0.081	0.048	0.090	
2" to 2-1/2"	0.015	0.047	0.014	0.056	
2-1/2" to 3"	0.015	0.047	0.014	0.056	



APPENDIX C

CoP Chlorides

Specimen #1 - 6 Month Exposure

Liquid	Clear	Purple	Green	Pink			
%CL	0.005	0.02	0.05	0.5			Date:
mV before	106.7	73.4	50.3	-4.7	5 Mini	ite Test	6/8/2008
mV after	100.5	67.8	44.5	-11.3	J wint	ite rest	0/0/2008
mV after	93.0	62.8	41.8	-13.9	1/4 - 3/4	24 Hour	6/23/2008
mV after	98.9	68.5	45.2	-11.5	1 - 2	Test	6/22/2008
	Assum			ed weight o	f concrete =	145.0	lb/cubic yard
Sample No.	4	5 Minute Tes	st	4	24 Hour Tes	t	
	mV	%Cl by mass of concrete	lb. Cl/yd ³ concrete	mV	%Cl by mass of concrete	lb. Cl/yd ³ concrete	
1D						I	
0" to 1/4"	20.3	0.137	5.356	15.6	0.146	5.719	-
1/4" to 1/2"	54.1	0.034	1.336	40.0	0.051	2.007	
1/2" to 3/4"	58.0	0.029	1.138	45.8	0.040	1.565	
3/4" to 1"	55.7	0.032	1.251	49.5	0.041	1.608	
1" to 1-1/4"	64.9	0.022	0.857	61.9	0.025	0.962	
1-1/4" to 1-1/2"	59.3	0.028	1.079	52.0	0.037	1.450	
1-1/2" to 1-3/4"	68.8	0.019	0.730	67.6	0.019	0.760	
1-3/4" to 2"	79.6	0.012	0.469	69.7	0.018	0.696	
							-
1E							
0" to 1/4"	4.9	0.258	10.084	2.5	0.256	10.033	
1/4" to 1/2"	30.6	0.090	3.508	19.4	0.124	4.859	
1/2" to 3/4"	41.7	0.057	2.224	32.2	0.072	2.805	
3/4" to 1"	72.2	0.016	0.635	65.8	0.021	0.818	
1" to 1-1/4"	84.8	0.010	0.379	72.7	0.016	0.615	
1-1/4" to 1-1/2"	76.9	0.013	0.524	65.2	0.021	0.839	
1-1/2" to 1-3/4"	78.7	0.012	0.486	69.4	0.018	0.705	
1-3/4" to 2"	75.3	0.014	0.559	60.3	0.026	1.028	
							-
1F							
0" to 1/4"	6.6	0.240	9.404	9.6	0.189	7.398	
1/4" to 1/2"	24.3	0.116	4.545	15.6	0.146	5.719	
1/2" to 3/4"	48.5	0.043	1.682	31.5	0.074	2.891	
3/4" to 1"	71.7	0.017	0.648	48.2	0.043	1.697]
1" to 1-1/4"	84.8	0.010	0.379	69.4	0.018	0.705]
1-1/4" to 1-1/2"	62.0	0.025	0.966	61.6	0.025	0.974	
1-1/2" to 1-3/4"	48.3	0.043	1.696	43.6	0.052	2.053	
1-3/4" to 2"	49.4	0.041	1.621	46.8	0.046	1.798	
-	-	-	-	-		•	-

Specimen #2 - 6 Month Exposure

Liquid	Clear	Purple	Green	Pink			
%CL	0.005	0.02	0.05	0.5			Date:
mV before	106.7	73.4	50.3	-4.7	5 M.	·	C 18 12000
mV after	100.5	67.8	44.5	-11.3	5 Mint	ite Test	6/8/2008
mV after	93.0	62.8	41.8	-13.9	1/4 - 3/4	24 Hour	6/23/2008
mV after	98.9	68.5	45.2	-11.5	1 - 2	Test	6/22/2008
			Assur	ned weight o	of concrete =	145.0	lb/cubic yard
Sample No.		5 Minute Tes	st		24 Hour Tes	t	
		%Cl by	lb. Cl/yd ³		%Cl by	lb. Cl/yd ³	
	mV	mass of	concrete	mV	mass of	concrete	
		concrete			concrete		
2D		T			[[_
0" to 1/4"	-14.3	0.567	22.190	-4.1	0.340	13.318	_
1/4" to 1/2"	0.8	0.305	11.934	15.6	0.146	5.719	_
1/2" to 3/4"	26.4	0.106	4.169	29.9	0.079	3.096	_
3/4" to 1"	42.9	0.054	2.117	42.1	0.056	2.185	
1" to 1-1/4"	56.3	0.031	1.221	51.9	0.037	1.456	
1-1/4" to 1-1/2"	55.1	0.033	1.282	50.6	0.039	1.536	
1-1/2" to 1-3/4"	66.2	0.021	0.813	58.1	0.029	1.126	
1-3/4" to 2"	68.4	0.019	0.743	60.7	0.026	1.011	
							7
2E		T			r	r	_
0" to 1/4"	-15.4	0.593	23.216	-6.6	0.379	14.826	_
1/4" to 1/2"	9.8	0.211	8.245	10.0	0.186	7.272	_
1/2" to 3/4"	36.5	0.070	2.753	39.8	0.052	2.025	_
3/4" to 1"	49.6	0.041	1.607	53.4	0.035	1.368	_
1" to 1-1/4"	48.9	0.042	1.654	51.7	0.037	1.468	_
1-1/4" to 1-1/2"	66.5	0.021	0.803	62.8	0.024	0.927	_
1-1/2" to 1-3/4"	82.8	0.010	0.411	78.7	0.012	0.480	_
1-3/4" to 2"	86.5	0.009	0.353	77.7	0.013	0.500	
							7
2F							
0" to 1/4"	-10.3	0.481	18.828	1.0	0.273	10.700	
1/4" to 1/2"	7.3	0.233	9.137	11.5	0.174	6.819	
1/2" to 3/4"	42.7	0.055	2.134	49.6	0.034	1.330]
3/4" to 1"	60.4	0.026	1.031	57.6	0.029	1.149]
1" to 1-1/4"	63.9	0.023	0.893	64.9	0.022	0.849	
1-1/4" to 1-1/2"	65.1	0.022	0.850	67.2	0.020	0.772]
1-1/2" to 1-3/4"	64.8	0.022	0.861	62.4	0.024	0.942]
1-3/4" to 2"	85.2	0.010	0.372	79.2	0.012	0.470]
	-	•	•	-			-

Specimen #3 - 6 Month Exposure


Liquid	Clear	Purple	Green	Pink						
%CL	0.005	0.02	0.05	0.5	-		Date:			
mV before	106.7	73.4	50.3	-4.7		_				
mV after	100.5	67.8	44.5	-11.3	5 Minu	ite Test	6/8/2008			
mV before	93.0	62.8	41.8	-13.9	1/4 - 3/4	24 Hour	6/23/2008			
mV after	98.9	68.5	45.2	-11.5	1 - 2	Test	6/22/2008			
· · · · ·	Assum				of concrete =	145.0	lb/cubic yard			
Sample No.	4	5 Minute Tes	st		24 Hour Tes	t				
	mV	%Cl by mass of concrete	lb. Cl/yd ³ concrete	mV	%Cl by mass of concrete	lb. Cl/yd ³ concrete				
3D	ND									
0" to 1/4"	15.9	0.164	6.418	13.4	0.161	6.285	4			
1/4" to 1/2"	54.8	0.033	1.298	43.0	0.045	1.765	4			
1/2" to 3/4"	42.3	0.055	2.170	32.7	0.070	2.746	4			
3/4" to 1"	39.5	0.062	2.434	33.5	0.080	3.120	_			
1" to 1-1/4"	65.9	0.021	0.823	52.8	0.036	1.402	_			
1-1/4" to 1-1/2"	66.3	0.021	0.809	55.8	0.032	1.238	_			
1-1/2" to 1-3/4"	76.8	0.013	0.526	63.4	0.023	0.904	_			
1-3/4" to 2"	60.0	0.027	1.049	47.5	0.045	1.747				
3E]			
0" to 1/4"	33.3	0.080	3.140	27.3	0.088	3.462				
1/4" to 1/2"	54.2	0.034	1.331	43.2	0.045	1.750				
1/2" to 3/4"	61.1	0.026	1.002	47.1	0.038	1.480				
3/4" to 1"	76.3	0.014	0.537	62.0	0.024	0.958				
1" to 1-1/4"	46.7	0.046	1.811	39.9	0.061	2.393				
1-1/4" to 1-1/2"	52.2	0.037	1.445	45.1	0.049	1.929				
1-1/2" to 1-3/4"	78.7	0.012	0.486	63.7	0.023	0.893				
1-3/4" to 2"	86.6	0.009	0.352	74.6	0.015	0.568				
3F]			
0" to 1/4"	49.9	0.041	1.588	46.0	0.040	1.552	1			
1/4" to 1/2"	57.0	0.030	1.186	51.6	0.040	1.220	1			
1/2" to 3/4"	67.1	0.020	0.783	60.3	0.021	0.840	-			
3/4" to 1"	70.2	0.020	0.690	57.0	0.021	1.178	1			
1" to 1-1/4"	63.9	0.023	0.893	54.9	0.033	1.285	-			
1-1/4" to 1-1/2"	67.1	0.020	0.783	57.6	0.033	1.149	1			
1-1/2" to 1-3/4"	76.8	0.013	0.526	62.8	0.025	0.927	1			
1-3/4" to 2"	70.0	0.015	0.625	50.6	0.039	1.536	1			


Specimen #4 - 6 Month Exposure


$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	Liquid	Clear	Purple	Green	Pink			
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	%CL	0.005	0.02	0.05	0.5			Date:
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	mV before	106.7	73.4	50.3	-4.7			
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	mV after	100.5	67.8	44.5	-11.3	5 Minu	ite Test	6/8/2008
Assumed weight of concrete = 145.0 lb/cubic yar Sample No. 5 Minute Test 24 Hour Test mV ${}^{9}Cl$ by concrete lb. Cl/yd ³ concrete mV ${}^{9}Cl$ by mass of concrete lb. Cl/yd ³ concrete 4D	mV before	93.0	62.8	41.8	-13.9	1/4 - 3/4	24 Hour	6/23/2008
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	mV after	98.9	68.5	45.2	-11.5	1 - 2	Test	6/22/2008
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$				Assum	ed weight o	f concrete =	145.0	lb/cubic yard
$ \frac{mV}{12^{m} \text{ b}^{2} \text{ concrete}} = \frac{mV}{mV} = \frac{m}{2000} \frac{mV}{2000000000000000000000000000000000000$	Sample No.	5	5 Minute Tes	st		24 Hour Tes	t	
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$		mV	mass of	•	mV	mass of	-	
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$	4D							
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$	0" to 1/4"	3.5	0.273	10.681	9.3	0.191	7.494	
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$		46.8	0.046	1.803	30.9	0.076	2.966	
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$			0.024	0.923		0.054		_
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	3/4" to 1"	72.7	0.016	0.622	56.4	0.031	1.208	_
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$		71.7	0.017	0.648	59.9	0.027		_
1-3/4" to $2"$ 71.8 0.016 0.646 62.4 0.024 0.942 4E 0" to $1/4"$ 19.9 0.139 5.445 20.5 0.118 4.635 $1/4"$ to $1/2"$ 69.4 0.018 0.713 61.7 0.020 0.791 $1/2"$ to $3/4"$ 54.7 0.033 1.304 41.0 0.049 1.923 $3/4"$ to $1"$ 61.0 0.026 1.006 49.9 0.040 1.581 $1"$ to $1-1/4"$ 63.9 0.023 0.893 56.5 0.031 1.203 $1-1/4"$ to $1-1/2"$ 61.4 0.025 0.990 55.8 0.032 1.238 $1-1/4"$ to $1-1/2"$ 61.4 0.025 0.990 55.8 0.033 1.285 $1-3/4"$ to $2"$ 77.4 0.013 0.513 63.5 0.023 0.900	1-1/4" to 1-1/2"	53.6	0.035	1.364	38.0	0.066	2.589	1
4E 0" to $1/4$ " 19.9 0.139 5.445 20.5 0.118 4.635 $1/4$ " to $1/2$ " 69.4 0.018 0.713 61.7 0.020 0.791 $1/2$ " to $3/4$ " 54.7 0.033 1.304 41.0 0.049 1.923 $3/4$ " to 1" 61.0 0.026 1.006 49.9 0.040 1.581 1" to $1-1/4$ " 63.9 0.023 0.893 56.5 0.031 1.203 $1-1/4$ " to $1-1/2$ " 61.4 0.025 0.990 55.8 0.032 1.238 $1-1/2$ " to $1-3/4$ " 59.7 0.027 1.062 54.9 0.033 1.285 $1-3/4$ " to 2" 77.4 0.013 0.513 63.5 0.023 0.900 4F 0" to $1/4$ " 2.5 0.284 11.129 0.4 0.280 10.979 $1/4$ " to $1/2$ " 35.7 0.073 2.845 31.5 0.074 2.891 $1/2$ " to $3/4$ " 52.3 0.037 1.439 38.2 0.055 2.168		78.4	0.013	0.492	62.1	0.024	0.954	1
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	1-3/4" to 2"	71.8	0.016	0.646	62.4	0.024	0.942	
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	4F							7
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$		19.9	0.139	5.445	20.5	0.118	4.635	-
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$							0.791	1
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$								1
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$		61.0				0.040		1
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	1" to 1-1/4"	63.9	0.023	0.893	56.5	0.031	1.203	1
1-3/4" to 2" 77.4 0.013 0.513 63.5 0.023 0.900 4F 0" to 1/4" 2.5 0.284 11.129 0.4 0.280 10.979 1/4" to 1/2" 35.7 0.073 2.845 31.5 0.074 2.891 1/2" to 3/4" 52.3 0.037 1.439 38.2 0.055 2.168	1-1/4" to 1-1/2"	61.4	0.025	0.990	55.8	0.032	1.238	1
4F 0" to 1/4" 2.5 0.284 11.129 0.4 0.280 10.979 1/4" to 1/2" 35.7 0.073 2.845 31.5 0.074 2.891 1/2" to 3/4" 52.3 0.037 1.439 38.2 0.055 2.168	1-1/2" to 1-3/4"	59.7	0.027	1.062	54.9	0.033	1.285	1
0" to 1/4" 2.5 0.284 11.129 0.4 0.280 10.979 1/4" to 1/2" 35.7 0.073 2.845 31.5 0.074 2.891 1/2" to 3/4" 52.3 0.037 1.439 38.2 0.055 2.168	1-3/4" to 2"	77.4	0.013	0.513	63.5	0.023	0.900	
0" to 1/4" 2.5 0.284 11.129 0.4 0.280 10.979 1/4" to 1/2" 35.7 0.073 2.845 31.5 0.074 2.891 1/2" to 3/4" 52.3 0.037 1.439 38.2 0.055 2.168								-
1/4" to 1/2" 35.7 0.073 2.845 31.5 0.074 2.891 1/2" to 3/4" 52.3 0.037 1.439 38.2 0.055 2.168	4F		-					
1/2" to 3/4" 52.3 0.037 1.439 38.2 0.055 2.168	0" to 1/4"	2.5	0.284	11.129	0.4	0.280	10.979	
	1/4" to 1/2"	35.7	0.073	2.845	31.5	0.074	2.891	
3/4" to 1" 64.7 0.022 0.864 54.6 0.033 1.302	1/2" to 3/4"	52.3	0.037	1.439	38.2	0.055	2.168	
	3/4" to 1"	64.7	0.022	0.864	54.6	0.033	1.302	
1" to 1-1/4" 55.4 0.032 1.267 49.2 0.042 1.628	1" to 1-1/4"	55.4	0.032	1.267	49.2	0.042	1.628	
1-1/4" to 1-1/2" 56.8 0.031 1.196 51.5 0.038 1.480	1-1/4" to 1-1/2"	56.8	0.031	1.196	51.5	0.038	1.480	
1-1/2" to 1-3/4" 67.8 0.019 0.761 56.3 0.031 1.213	1-1/2" to 1-3/4"	67.8	0.019	0.761	56.3	0.031	1.213	
1-3/4" to 2" 47.8 0.044 1.731 40.0 0.061 2.383	1-3/4" to 2"	47.8	0.044	1.731	40.0	0.061	2.383	


1,2,3,&4 Five-Minutes Chlorides


6/8/2008	%Cl	0.005	0.020	0.050	0.500	
	mV before	106.7	73.4	50.3	-4.7	
	mV after	100.5	67.8	44.5	-11.3	














0.500

-4.9

-11.5

Specimen #5 - 6 Month Exposure

Liquid	Clear	Purple	Green	Pink			
%CL	0.005	0.02	0.05	0.5			Date:
mV before	93.6	68.2	45.8	-11.4	5 M		7/02/2009
mV after	96.8	69.5	46.1	-10.6	5 Mint	ite Test	7/23/2008
mV before	99.4	71.0	47.5	-9.1	24 Цо	ur Test	7/24/2008
mV after	97.4	69.8	46.7	-10.3			7/24/2008
			Assun	ned weight o	of concrete =	145.0	lb/cubic yard
Sample No.		5 Minute Tes	st		24 Hour Tes	t	
	mV	%Cl by mass of	lb. Cl/yd ³	mV	%Cl by mass of	lb. Cl/yd ³	
	III V	concrete	concrete	111 V	concrete	concrete	
5D		controtte			controlo		_
0" to 1/4"	-2.3	0.367	14.376	-4.7	0.425	16.628	-
1/4" to 1/2"	1.1	0.318	12.433	-4.7	0.423	14.350	_
1/4" to 1/2" 1/2" to 3/4"	14.7	0.178	6.955	12.1	0.209	8.196	_
3/4" to 1"	47.4	0.044	1.721	41.8	0.207	2.347	_
1" to 1-1/4"	53.6	0.034	1.321	51.2	0.040	1.580	_
1-1/4" to 1-1/2"	50.3	0.039	1.520	48.5	0.045	1.770	_
1-1/2" to 1-3/4"	63.1	0.022	0.880	59.4	0.029	1.118	_
1-3/4" to 2"	70.0	0.017	0.655	66.2	0.021	0.840	-
10/1002	, 010	01017	01000	00.2	01021	01010	_
5E]
0" to 1/4"	-6.2	0.434	16.981	-7.5	0.478	18.709	
1/4" to 1/2"	-1.3	0.352	13.775	-3.4	0.402	15.743	
1/2" to 3/4"	13.0	0.191	7.479	12.0	0.210	8.231	
3/4" to 1"	42.9	0.053	2.086	40.7	0.063	2.458	
1" to 1-1/4"	58.6	0.027	1.067	54.5	0.035	1.375	
1-1/4" to 1-1/2"	72.0	0.015	0.602	67.7	0.020	0.788	
1-1/2" to 1-3/4"	59.7	0.026	1.018	56.5	0.032	1.264	
1-3/4" to 2"	42.3	0.055	2.140	40.1	0.064	2.521	
							-
5F							
0" to 1/4"	-8.1	0.470	18.417	-10.8	0.549	21.499	
0" to 1/4" 1/4" to 1/2"	-8.1 4.9	0.470 0.270	18.417 10.570	-10.8 2.5	0.549 0.314	21.499 12.279	
							-
1/4" to 1/2"	4.9	0.270	10.570	2.5	0.314	12.279	
1/4" to 1/2" 1/2" to 3/4"	4.9 39.7	0.270 0.061	10.570 2.391	2.5 38.6	0.314 0.069	12.279 2.685	
1/4" to 1/2" 1/2" to 3/4" 3/4" to 1"	4.9 39.7 50.2	0.270 0.061 0.039	10.570 2.391 1.527	2.5 38.6 47.6	0.314 0.069 0.047	12.279 2.685 1.838	
1/4" to 1/2" 1/2" to 3/4" 3/4" to 1" 1" to 1-1/4"	4.9 39.7 50.2 35.6	0.270 0.061 0.039 0.073	10.570 2.391 1.527 2.849	2.5 38.6 47.6 35.0	0.314 0.069 0.047 0.080	12.279 2.685 1.838 3.125	


Specimen #7 - 6 Month Exposure

$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	Liquid	Clear	Purple	Green	Pink]		
mV after 96.8 69.5 46.1 -10.6 mV before 99.4 71.0 47.5 -9.1 24 Hour Test 7/23/2008 mV after 97.4 69.8 46.7 -10.3 24 Hour Test 7/24/2008 Sample No. 5 Minute Test 24 Hour Test 1b/cubic yard mV mV concrete ib. Cl/yd³ mV %Cl by ib. Cl/yd³ ib. Cl/yd³ mV mV samed weight of concrete 145.0 ib/cubic yard 0" to 1/4 -6.0 0.430 16.837 -5.7 0.443 17.344 1/4" to 1/2" 4.1 0.397 15.524 -3.5 0.404 15.809 1/2" to 3/4" 13.2 0.189 7.415 11.7 0.213 8.335 3/4" to 1" 18.4 0.152 5.938 17.5 0.167 6.529 1-1/4" to 1-1/2" 52.4 0.036 1.390 50.1 0.042 1.654 1-1/2" to 1/4" to 1/2 0.558 <td< td=""><td>%CL</td><td>0.005</td><td>0.02</td><td>0.05</td><td>0.5</td><td></td><td></td><td>Date:</td></td<>	%CL	0.005	0.02	0.05	0.5			Date:
mV after 96.8 69.5 446.1 -10.6 mV before 99.4 71.0 47.5 -9.1 24 Hour Test 7/24/2008 mV after 97.4 69.8 46.7 -10.3 24 Hour Test 7/24/2008 Sample No. 5 Minute Test 24 Hour Test 145.0 1b/cubic yard mV mg Sci b 1b. Cl/yd mV %Cl by mov for concrete 10/2 16.837 -5.7 0.443 17.344 1/4" to 1/2" -4.1 0.397 15.524 -3.5 0.404 15.809 1/2" to 3/4" 13.2 0.189 7.415 11.7 0.213 8.335 3/4" to 1" 18.4 0.152 5.938 17.5 0.167 6.529 1" to 1.1/4" 13.2 0.036 1.390 50.1 0.042 1.654 1-1.2" to 1.34" 66.5 0.019 0.761 63.2 0.024 0.951 1-1/4" to 1.12" 0.545 21.336 0.584 22.868 1.16	mV before	93.6	68.2	45.8	-11.4	5 Minu	to Tost	7/22/2008
$\begin{tabular}{ c c c c c c c c c c c c c c c c c c c$	mV after	96.8	69.5	46.1	-10.6	5 Iviiiit	ile Test	1/23/2008
mV after 97.4 69.8 46.7 -10.3 Assumed weight of concrete 145.0 Ib/cubic yard Sample No. 5 5 Minute Test 24 24 Ib/cubic yard mV %Cl by mass of concrete b. Cl/yd ³ mV %Cl by mass of concrete b. Cl/yd ³ mV %Cl by mass of concrete b. Cl/yd ³ concrete ib. Cl/yd ³ concrete ib. Cl/yd ³ concrete 7D - - 0.144" -6.0 0.430 16.837 -5.7 0.443 17.344 1/4" to 1/2" -4.1 0.397 15.524 -3.5 0.404 15.809 1/2" to 3/4" 13.2 0.189 7.415 11.7 0.213 8.335 3/4" to 1/2" 5.2.4 0.036 1.390 50.1 0.042 1.654 1-1/2" to 1.3/4" 66.5 0.019 0.761 63.2 0.024 0.953 1-3/4" to 1/2" 0.545 21.336 0.584 22.864 1.75 1.414 1/2" to 3/4" 0.558 21.850 0.618		99.4	71.0	47.5	-9.1	24 Ho	ur Test	7/24/2008
Sample No. 5 Minute Test 24 Hour Test mV %Cl by mass of concrete mV %Cl by mass of concrete mV %Cl by mass of concrete b. Cl/yd³ concrete 0" to 1/4" -6.0 0.430 16.837 -5.7 0.443 17.344 1/4" to 1/2" -4.1 0.397 15.524 -3.5 0.404 15.809 1/2" to 3/4" 13.2 0.189 7.415 11.7 0.213 8.335 3/4" to 1" 18.4 0.152 5.938 17.5 0.167 6.529 1" to 1-1/4" 34.3 0.077 3.011 32.8 0.088 3.428 1-1/2" to 1-3/4" 66.5 0.019 0.761 63.2 0.024 0.953 1-3/4" to 1/2" 0.545 21.336 0.558 21.864 1117 1/4" to 1/2" 0.558 21.850 0.618 24.191 1.421 3/4" to 1" 0.505 19.782 0.558 21.864 1173 1-3/4" to 1-3/4" 0.027 1.073	mV after	97.4	69.8					7/24/2008
mV %Cl by mass of concrete lb. Cl/yd³ concrete mV %Cl by mass of concrete lb. Cl/yd³ concrete 7D mV %Cl by mass of concrete lb. Cl/yd³ concrete 1/4" to 1/2" -4.1 0.397 15.524 -3.5 0.404 15.809 1/2" to 3/4" to 1" 18.4 0.152 5.938 17.5 0.167 6.529 1" to 1-1/4" 34.3 0.077 3.011 32.8 0.088 3.428 1-1/4" to 1-1/2" 52.4 0.036 1.390 50.1 0.042 1.654 1-1/2" to 1-3/4" to 2" 8.38 0.009 0.364 77.8 0.013 0.515 7E Average				Assum	ed weight o	of concrete =	145.0	lb/cubic yard
mV mass of concrete ib. Cryat concrete mV mass of concrete ib. Cryat concrete ib. Cryat concrete ib. Cryat concrete 7D	Sample No.	4	5 Minute Tes	st		24 Hour Tes	t	
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$		mV	mass of	-	mV	mass of	-	
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	7D		1	1		1		
$\begin{array}{c c c c c c c c c c c c c c c c c c c $		-6.0	0.430	16.837		0.443	17.344	
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	1/4" to 1/2"		0.397	15.524	-3.5	0.404	15.809	_
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$		13.2	0.189	7.415		0.213	8.335	
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$			0.152			0.167	6.529	_
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	1" to 1-1/4"	34.3				0.088		_
I-3/4" to 2" 83.8 0.009 0.364 77.8 0.013 0.515 7E Average 0" to 1/4" 0.481 18.837 0.509 19.912 1/4" to 1/2" 0.545 21.336 0.584 22.868 1/2" to 3/4" 0.558 21.850 0.618 24.191 3/4" to 1" 0.505 19.782 0.558 21.864 1" to 1-1/4" 0.266 10.424 0.292 11.421 1-1/2" to 1-3/4" 0.027 1.073 0.030 1.173 1-3/4" to 2" 0.017 0.653 0.020 0.774 F 0" to 1/4" 6.1 0.257 10.042 3.8 0.297 11.625 1/4" to 1/2" 13.1 0.190 7.447 10.1 0.228 8.916 1/2" to 3/4" 21.5 0.133 5.202 18.7 0.159 6.207 3/4" to 1" 38.2 0.065 2.549 35.4 0.078 3.073 1" to 1-1/4" 57.9 0.028 1.099 55.3 0.034 1.329 <tr< td=""><td></td><td>52.4</td><td>0.036</td><td></td><td></td><td>0.042</td><td>1.654</td><td>_</td></tr<>		52.4	0.036			0.042	1.654	_
TE Average 0" to 1/4" 0.481 18.837 0.509 19.912 1/4" to 1/2" 0.545 21.336 0.584 22.868 1/2" to 3/4" 0.558 21.850 0.618 24.191 3/4" to 1" 0.505 19.782 0.558 21.864 1" to 1-1/4" 0.266 10.424 0.292 11.421 1-1/4" to 1-1/2" 0.064 2.508 0.070 2.757 1-1/2" to 1-3/4" 0.027 1.073 0.030 1.173 1-3/4" to 2" 0.017 0.653 0.020 0.774	1-1/2" to 1-3/4"	66.5	0.019	0.761	63.2	0.024	0.953	_
$\begin{array}{c c c c c c c c c c c c c c c c c c c $	1-3/4" to 2"	83.8	0.009	0.364	77.8	0.013	0.515	
$\begin{array}{c c c c c c c c c c c c c c c c c c c $	TE Avenage							٦
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	0		0.491	10.027		0.500	10.012	-
1-3/4" to $2"$ 0.017 0.653 0.020 0.774 7F 0" to $1/4"$ 6.1 0.257 10.042 3.8 0.297 11.625 $1/4"$ to $1/2"$ 13.1 0.190 7.447 10.1 0.228 8.916 $1/2"$ to $3/4"$ 21.5 0.133 5.202 18.7 0.159 6.207 $3/4"$ to $1"$ 38.2 0.065 2.549 35.4 0.078 3.073 $1"$ to $1-1/4"$ 57.9 0.028 1.099 55.3 0.034 1.329 $1-1/4"$ to $1-1/2"$ 71.6 0.016 0.612 69.1 0.019 0.743 $1-1/2"$ to $1-3/4"$ 76.9 0.012 0.488 74.3 0.015 0.597								Sp
1-3/4" to $2"$ 0.017 0.653 0.020 0.774 7F 0" to $1/4"$ 6.1 0.257 10.042 3.8 0.297 11.625 $1/4"$ to $1/2"$ 13.1 0.190 7.447 10.1 0.228 8.916 $1/2"$ to $3/4"$ 21.5 0.133 5.202 18.7 0.159 6.207 $3/4"$ to $1"$ 38.2 0.065 2.549 35.4 0.078 3.073 $1"$ to $1-1/4"$ 57.9 0.028 1.099 55.3 0.034 1.329 $1-1/4"$ to $1-1/2"$ 71.6 0.016 0.612 69.1 0.019 0.743 $1-1/2"$ to $1-3/4"$ 76.9 0.012 0.488 74.3 0.015 0.597								ecij
1-3/4" to $2"$ 0.017 0.653 0.020 0.774 7F 0" to $1/4"$ 6.1 0.257 10.042 3.8 0.297 11.625 $1/4"$ to $1/2"$ 13.1 0.190 7.447 10.1 0.228 8.916 $1/2"$ to $3/4"$ 21.5 0.133 5.202 18.7 0.159 6.207 $3/4"$ to $1"$ 38.2 0.065 2.549 35.4 0.078 3.073 $1"$ to $1-1/4"$ 57.9 0.028 1.099 55.3 0.034 1.329 $1-1/4"$ to $1-1/2"$ 71.6 0.016 0.612 69.1 0.019 0.743 $1-1/2"$ to $1-3/4"$ 76.9 0.012 0.488 74.3 0.015 0.597								vera
1-3/4" to $2"$ 0.017 0.653 0.020 0.774 7F 0" to $1/4"$ 6.1 0.257 10.042 3.8 0.297 11.625 $1/4"$ to $1/2"$ 13.1 0.190 7.447 10.1 0.228 8.916 $1/2"$ to $3/4"$ 21.5 0.133 5.202 18.7 0.159 6.207 $3/4"$ to $1"$ 38.2 0.065 2.549 35.4 0.078 3.073 $1"$ to $1-1/4"$ 57.9 0.028 1.099 55.3 0.034 1.329 $1-1/4"$ to $1-1/2"$ 71.6 0.016 0.612 69.1 0.019 0.743 $1-1/2"$ to $1-3/4"$ 76.9 0.012 0.488 74.3 0.015 0.597								us #
1-3/4" to $2"$ 0.017 0.653 0.020 0.774 7F 0" to $1/4"$ 6.1 0.257 10.042 3.8 0.297 11.625 $1/4"$ to $1/2"$ 13.1 0.190 7.447 10.1 0.228 8.916 $1/2"$ to $3/4"$ 21.5 0.133 5.202 18.7 0.159 6.207 $3/4"$ to $1"$ 38.2 0.065 2.549 35.4 0.078 3.073 $1"$ to $1-1/4"$ 57.9 0.028 1.099 55.3 0.034 1.329 $1-1/4"$ to $1-1/2"$ 71.6 0.016 0.612 69.1 0.019 0.743 $1-1/2"$ to $1-3/4"$ 76.9 0.012 0.488 74.3 0.015 0.597								9 Da
1-3/4" to $2"$ 0.017 0.653 0.020 0.774 7F 0" to $1/4"$ 6.1 0.257 10.042 3.8 0.297 11.625 $1/4"$ to $1/2"$ 13.1 0.190 7.447 10.1 0.228 8.916 $1/2"$ to $3/4"$ 21.5 0.133 5.202 18.7 0.159 6.207 $3/4"$ to $1"$ 38.2 0.065 2.549 35.4 0.078 3.073 $1"$ to $1-1/4"$ 57.9 0.028 1.099 55.3 0.034 1.329 $1-1/4"$ to $1-1/2"$ 71.6 0.016 0.612 69.1 0.019 0.743 $1-1/2"$ to $1-3/4"$ 76.9 0.012 0.488 74.3 0.015 0.597			1			1		nd #
7F 0" to 1/4" 6.1 0.257 10.042 3.8 0.297 11.625 1/4" to 1/2" 13.1 0.190 7.447 10.1 0.228 8.916 1/2" to 3/4" 21.5 0.133 5.202 18.7 0.159 6.207 3/4" to 1" 38.2 0.065 2.549 35.4 0.078 3.073 1" to 1-1/4" 57.9 0.028 1.099 55.3 0.034 1.329 1-1/4" to 1-1/2" 71.6 0.016 0.612 69.1 0.019 0.743 1-1/2" to 1-3/4" 76.9 0.012 0.488 74.3 0.015 0.597								fter #10
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$	1-3/4" to 2"		0.017	0.653		0.020	0.774]
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$	7 F]
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$	0" to 1/4"	6.1	0.257	10.042	3.8	0.297	11.625	1
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$								1
3/4" to 1" 38.2 0.065 2.549 35.4 0.078 3.073 1" to 1-1/4" 57.9 0.028 1.099 55.3 0.034 1.329 1-1/4" to 1-1/2" 71.6 0.016 0.612 69.1 0.019 0.743 1-1/2" to 1-3/4" 76.9 0.012 0.488 74.3 0.015 0.597								1
1" to 1-1/4" 57.9 0.028 1.099 55.3 0.034 1.329 1-1/4" to 1-1/2" 71.6 0.016 0.612 69.1 0.019 0.743 1-1/2" to 1-3/4" 76.9 0.012 0.488 74.3 0.015 0.597								1
1-1/4" to 1-1/2" 71.6 0.016 0.612 69.1 0.019 0.743 1-1/2" to 1-3/4" 76.9 0.012 0.488 74.3 0.015 0.597								1
1-1/2" to 1-3/4" 76.9 0.012 0.488 74.3 0.015 0.597								1
								1
	1-3/4" to 2"	81.8	0.012	0.396	77.8	0.013	0.515	1

5-Minute Test for #5 and #7


7/23/2008

%Cl	0.005	0.020	0.050	0.500
mV before	93.6	68.2	45.8	-11.4
mV after	96.8	69.5	46.1	-10.6
mV average	95.2	68.9	46.0	-11.0



24-Hour Test for #5 and #7

7/24/2008	%Cl	0.005	0.020	0.050	0.500
	mV before	99.4	71.0	47.5	-9.1
	mV after	97.4	69.8	46.7	-10.3
	mV average	98.4	70.4	47.1	-9.7



Specimen #6 - 6 Month Exposure

Liquid	Clear	Purple	Green	Pink			
%CL	0.005	0.02	0.05	0.5			Date:
mV before	100.5	73.5	49.4	-7.0	5 M		0/4/2000
mV after	99.9	72.3	48.3	-7.6	5 Minute Test		8/4/2008
mV before	95.7	70.1	47.5	-7.4	24 Hour Test		8/6/2008
mV after	94.2	68.4	46.3	-8.7	24 П0	ui iest	0/0/2000
			Assun	ned weight o	of concrete =	145.0	lb/cubic yard
Sample No.	1	5 Minute Tes	st	,	24 Hour Tes	t	
	mV	%Cl by mass of concrete	lb. Cl/yd ³ concrete	mV	%Cl by mass of concrete	lb. Cl/yd ³ concrete	
6D							
0" to 1/4"	-5.4	0.482	18.881	-6.5	0.495	19.398	
1/4" to 1/2"	16.6	0.190	7.453	14.3	0.198	7.760	
1/2" to 3/4"	43.8	0.060	2.362	39.6	0.065	2.546	
3/4" to 1"	56.4	0.035	1.387	53.9	0.035	1.356	
1" to 1-1/4"	60.6	0.030	1.161	52.5	0.037	1.442	
1-1/4" to 1-1/2"	74.9	0.016	0.635	60.8	0.026	1.001	
1-1/2" to 1-3/4"	82.1	0.012	0.468	66.3	0.020	0.785	
1-3/4" to 2"	86.6	0.010	0.387	76.7	0.013	0.497	
							-
6E		1	1		1	1	_
0" to 1/4"		0.520	20.373	-8.4	0.539	21.092	
1/4" to 1/2"	2.1	0.351	13.753	0.3	0.367	14.377	
1/2" to 3/4"	9.3	0.259	10.146	8.1	0.260	10.197	
3/4" to 1"	29.1	0.112	4.395	24.9	0.124	4.865	_
1" to 1-1/4"	53.4	0.040	1.574	48.7	0.044	1.705	_
1-1/4" to 1-1/2"	70.1	0.020	0.777	62.9	0.023	0.912	_
1-1/2" to 1-3/4"	71.5	0.019	0.733	62.3	0.024	0.937	_
1-3/4" to 2"	56.0	0.036	1.411	48.2	0.045	1.743	
6F]
0" to 1/4"	1.5	0.360	14.106	-1.8	0.403	15.771	1
1/4" to 1/2"	8.0	0.274	10.719	4.5	0.305	11.949	1
1/2" to 3/4"	27.5	0.120	4.703	26.3	0.117	4.574	1
3/4" to 1"	57.6	0.034	1.318	50.0	0.041	1.610	1
1" to 1-1/4"	73.3	0.017	0.679	65.8	0.021	0.803	1
1-1/4" to 1-1/2"	77.1	0.015	0.578	67.9	0.019	0.732	1
1-1/2" to 1-3/4"	86.7	0.010	0.386	74.3	0.014	0.552	1
1 1/2 (0 1 5/1							


Specimen #8 - 6 Month Exposure

Liquid	Clear	Purple	Green	Pink]		
%CL	0.005	0.02	0.05	0.5			Date:
mV before	100.5	73.5	49.4	-7.0	5 M		8/4/2008
mV after	99.9	72.3	48.3	-7.6	5 Mint	5 Minute Test	
mV before	95.7	70.1	47.5	-7.4	24 Цо	24 Hour Test	
mV after	94.2	68.4	46.3	-8.7	24 ПО	ur Test	8/6/2008
			Assun	ned weight	of concrete =	145.0	lb/cubic yard
Sample No.		5 Minute Tes	st		24 Hour Tes	t	
		%Cl by	lb. Cl/yd ³		%Cl by	lb. Cl/yd ³	
	mV	mass of	concrete	mV	mass of	concrete	
		concrete	concrete		concrete	concrete	
3D							
0" to 1/4"	3.8	0.327	12.800	2.0	0.341	13.340	
1/4" to 1/2"	22.7	0.147	5.760	19.1	0.160	6.281	
1/2" to 3/4"	33.2	0.094	3.696	29.2	0.103	4.025	
3/4" to 1"	39.1	0.074	2.881	35.6	0.078	3.036	
1" to 1-1/4"	48.3	0.050	1.953	44.7	0.052	2.034	
1-1/4" to 1-1/2"	54.6	0.038	1.497	50.5	0.040	1.575	
1-1/2" to 1-3/4"	67.4	0.022	0.871	62.1	0.024	0.945	
1-3/4" to 2"	87.8	0.009	0.368	72.9	0.015	0.587	
							-
BE							
0" to 1/4"	-3.8	0.451	17.647	-4.9	0.462	18.078	
1/4" to 1/2"	-6.0	0.495	19.366	-7.8	0.525	20.542	
1/2" to 3/4"	5.9	0.299	11.713	3.7	0.316	12.377	
3/4" to 1"	21.8	0.153	5.983	18.0	0.168	6.593	
1" to 1-1/4"	42.0	0.065	2.548	35.7	0.077	3.023	
1-1/4" to 1-1/2"	63.6	0.026	1.023	55.9	0.032	1.242	
1-1/2" to 1-3/4"	84.3	0.011	0.427	75.1	0.014	0.533	
1-3/4" to 2"	81.2	0.012	0.486	68.7	0.018	0.707	
							-
BF							
0" to 1/4"	3.0	0.338	13.240	0.7	0.361	14.126	
	21.8	0.153	5.983	19.0	0.161	6.309	
1/4 to $1/2$				36.3	0.075	2.944	_
1/4" to 1/2" 1/2" to 3/4"		0.070	2.750				-
1/2" to 3/4"	40.2	0.070	2.750 0.989		0.029	1.152	
		0.025	0.989	57.6	0.029	1.152 0.873	
1/2" to 3/4" 3/4" to 1" 1" to 1-1/4"	40.2 64.4					1.152 0.873 0.768	
1/2" to 3/4" 3/4" to 1"	40.2 64.4 72.9	0.025 0.018	0.989 0.691	57.6 63.9	0.022	0.873	-

5-Minute Test for #6 and #8


8/4/2008

%Cl	0.005	0.020	0.050	0.500
mV before	100.5	73.5	49.4	-7.0
mV after	99.9	72.3	48.3	-7.6
mV average	100.2	72.9	48.9	-7.3



24-Hour Test for #6 and #8

8/6/2008	%Cl	0.005	0.020	0.050	0.500
	mV before	95.7	70.1	47.5	-7.4
	mV after	94.2	68.4	46.3	-8.7
	mV average	95.0	69.3	46.9	-8.1



Specimen #9 - 6 Month Exposure

Liquid	Clear	Purple	Green	Pink]		
%CL	0.005	0.02	0.05	0.5			Date:
mV before	91.4	68.4	46.2	-9.7	5 14	· T ·	5/18/2008
mV after	94.8	67.8	45.7	-10.3	5 Minute Test		7/21/2008
mV before	100.8	72.5	49.0	-7.7	24 11-	Т 4	7/22/2008
mV after	93.6	68.2	45.8	-11.4	24 H0	ur Test	7/23/2008
			Assun	ned weight o	of concrete =	145.0	lb/cubic yard
Sample No.		5 Minute Tes	st		24 Hour Tes	t	
		%Cl by	lb. Cl/yd ³		%Cl by	lb. Cl/yd ³	
	mV	mass of	concrete	mV	mass of	concrete	
		concrete	concrete		concrete	concrete	
) Average							
0" to 1/4"		0.461	18.048		0.454	17.789	
1/4" to 1/2"		0.493	19.312		0.407	15.943	Se
1/2" to 3/4"		0.451	17.647		0.348	13.633	See Average Data
3/4" to 1"		0.436	17.051		0.428	16.748	ver
1" to 1-1/4"		0.521	20.387		0.675	26.420	age
1-1/4" to 1-1/2"		0.663	25.959		0.633	24.792	Da
1-1/2" to 1-3/4"		0.461	18.032		0.623	24.398	ta
1-3/4" to 2"		0.268	10.486		0.314	12.304	
							-
E Average		T			T		_
0" to 1/4"		0.504	19.726		0.575	22.502	_
1/4" to 1/2"		0.690	27.014		0.551	21.560	Seg
1/2" to 3/4"		0.497	19.467		0.490	19.199	See Average Data
3/4" to 1"		0.601	23.548		0.661	25.889	vera
1" to 1-1/4"		0.716	28.013		0.592	23.192	lige
1-1/4" to 1-1/2"		0.662	25.912		0.489	19.140	Dat
1-1/2" to 1-3/4"		0.393	15.390		0.214	8.389	a
1-3/4" to 2"		0.286	11.203		0.101	3.941	
							7
ر					•		_
0" to 1/4"	3.3	0.305	11.943	1.7	0.306	11.984	
1/4" to 1/2"	7.0	0.259	10.130	2.4	0.297	11.628	5-N
1/2" to 3/4"	23.0	0.127	4.969	21.8	0.129	5.039	finu 5/
3/4" to 1"	41.4	0.056	2.191	37.6	0.065	2.550	5-Minute Data from 5/18/2008.
1" to 1-1/4"	40.3	0.059	2.301	34.3	0.075	2.940	Data
1-1/4" to 1-1/2"	28.5	0.099	3.890	28.2	0.098	3.824	3. fr
1-1/2" to 1-3/4"	34.9	0.075	2.926	34.1	0.076	2.966	mc
1-1/2 10 1-3/4	51.7	0.072	= 0				

Specimen #10 - 6 Month Exposure

Liquid	Clear	Purple	Green	Pink]		
%CL	0.005	0.02	0.05	0.5			Date:
mV before	91.4	68.4	46.2	-9.7	5 Minu	ta Tast	5/18/2008
mV after	94.8	67.8	45.7	-10.3	5 Minute Test		7/21/2008
mV before	100.8	72.5	49.0	-7.7	24 110	ur Test	7/23/2008
mV after	93.6	68.2	45.8	-11.4	24 110	ui iest	7/23/2008
			Assun	ned weight o	of concrete =	145.0	lb/cubic yard
Sample No.		5 Minute Tes	t		24 Hour Tes	t	
		%Cl by	lb. Cl/yd ³		%Cl by	lb. Cl/yd ³	
	mV	mass of	concrete	mV	mass of	concrete	
		concrete			concrete		
10D Average		1					_
0" to 1/4"		0.697	27.272		0.665	26.040	_
1/4" to 1/2"		0.755	29.573		0.695	27.207	Se
1/2" to 3/4"		0.648	25.378		0.579	22.675	See Average Data
3/4" to 1"		0.621	24.295		0.533	20.871	ven
1" to 1-1/4"		0.571	22.350		0.551	21.583	age
1-1/4" to 1-1/2"		0.694	27.155		0.586	22.948	Da
1-1/2" to 1-3/4"		0.492	19.279		0.408	15.983	ta
1-3/4" to 2"		0.291	11.383		0.256	10.008	
							-
10E(2)		1		1	I		
0" to 1/4"	-15.4	0.660	25.846	-16.2	0.662	25.921	
1/4" to 1/2"	-5.1	0.423	16.548	-7.0	0.445	17.436	5-Minute Data from 7/21/2008.
1/2" to 3/4"	-3.0	0.386	15.110	-3.8	0.388	15.190	Tinu 7/2
3/4" to 1"	1.3	0.320	12.544	0.4	0.324	12.674	1te I 21/2
1" to 1-1/4"	8.9	0.231	9.027	4.2	0.275	10.760	finute Data 1 7/21/2008.
1-1/4" to 1-1/2"	11.7	0.204	7.997	10.1	0.213	8.344	3.
1-1/2" to 1-3/4"	36.4	0.070	2.745	34.9	0.073	2.865	Ĕ
1-3/4" to 2"	54.0	0.033	1.281	50.8	0.037	1.444	
							-
10F							
0" to 1/4"	0.4	0.347	13.589	-0.6	0.338	13.233	
1/4" to 1/2"	3.4	0.304	11.890	1.9	0.303	11.881	5-N
1/2" to 3/4"	4.3	0.292	11.423	2.4	0.297	11.628	۰ 5/
3/4" to 1"	6.5	0.265	10.358	3.5	0.283	11.089	5-Minute Data from 5/18/2008.
1" to 1-1/4"	12.0	0.207	8.109	9.2	0.222	8.674	Dat 200
1-1/4" to 1-1/2"	30.1	0.093	3.623	23.8	0.118	4.623	
1-1/2" to 1-3/4"	59.7	0.025	0.970	54.9	0.031	1.210	Om
1-3/4" to 2"	68.6	0.017	0.653	57.9	0.027	1.063]
1-3/ T 10 2	00.0	0.017	0.055	51.7	0.027	1.005	_

Specimen #11 - 6 Month Exposure


	-	I	~		7		
Liquid	Clear	Purple	Green	Pink	_		
%CL	0.005	0.02	0.05	0.5			Date:
mV before	101.7	76.6	54.8	-2.1	5 Minu	ite Test	5/18/2008
mV after	91.4	68.4	46.2	-9.7	-		0,10,2000
mV before	101.6	75.9	53.6	-2.8	24 Ho	ur Test	5/21/2008
mV after	98.1	72.1	51.2	-5.2	_		0/21/2000
·			Assum	ed weight o	of concrete =	145.0	lb/cubic yard
Sample No.	4	5 Minute Tes	st		24 Hour Tes	t	_
	mV	%Cl by mass of concrete	lb. Cl/yd ³ concrete	mV	%Cl by mass of concrete	lb. Cl/yd ³ concrete	
11D							
0" to 1/4"	47.7	0.042	1.655	43.9	0.066	2.591	
1/4" to 1/2"	71.4	0.015	0.576	63.5	0.028	1.100	
1/2" to 3/4"	68.8	0.017	0.647	63.9	0.028	1.081	
3/4" to 1"	68.2	0.017	0.665	62.2	0.030	1.165	
1" to 1-1/4"	73.7	0.013	0.520	65.7	0.026	0.999	
1-1/4" to 1-1/2"	62.7	0.022	0.849	58.6	0.035	1.363	
1-1/2" to 1-3/4"	57.6	0.027	1.065	55.2	0.040	1.581	
1-3/4" to 2"	79.8	0.010	0.397	70.9	0.020	0.796	
115							7
11E		0.040	4 470	44.0	0.070		-
0" to 1/4"	47.5	0.043	1.670	41.8	0.073	2.840	_
1/4" to 1/2"	57.4	0.027	1.075	51.9	0.047	1.827	-
1/2" to 3/4"	66.3	0.018	0.723	59.5	0.033	1.310	_
3/4" to 1"	69.5	0.016	0.627	61.6	0.031	1.195	-
1" to 1-1/4"	82.6	0.009	0.350	73.1	0.018	0.723	4
1-1/4" to 1-1/2"	89.9	0.006	0.253	80.7	0.013	0.519	4
1-1/2" to 1-3/4"	78.8	0.011	0.415	71.0	0.020	0.793	-
1-3/4" to 2"	79.7	0.010	0.398	71.8	0.020	0.766	
11F(2)] _
0" to 1/4"	41.0	0.075	2.941	34.5	0.088	3.442	≓iv€ 24
1/4" to 1/2"	70.7	0.021	0.803	59.9	0.028	1.091	- ho
1/2" to 3/4"	78.1	0.015	0.581	67.7	0.020	0.767	ive minute tests: <i>S</i> /21/(24-hour tests: <i>S</i> /22/08
3/4" to 1"	78.9	0.013	0.561	69.5	0.018	0.707	e te :esta
1" to 1-1/4"	80.3	0.013	0.528	73.8	0.015	0.582	sts: 3: 5/
1-1/4" to 1-1/2"	89.1	0.009	0.359	77.8	0.012	0.486	5/2
1-1/2" to 1-3/4"	87.5	0.010	0.385	75.3	0.012	0.544	Five minute tests: 5/21/08 24-hour tests: 5/22/08
1-3/4" to 2"	89.7	0.009	0.350	78.9	0.011	0.462	~ ~
1 5/1 10 2	07.1	0.007	0.000		0.012	0.102	

Specimen #12 - 6 Month Exposure

Liquid	Clear	Purple	Green	Pink			
%CL	0.005	0.02	0.05	0.5			Date:
mV before	101.7	76.6	54.8	-2.1	5 M	4- T4	5/19/2009
mV after	91.4	68.4	46.2	-9.7	5 Mint	ite Test	5/18/2008
mV before	101.6	75.9	53.6	-2.8	24 Цо	24 Hour Test	
mV after	98.1	72.1	51.2	-5.2	24 П0	ui iest	5/21/2008
			Assun	ned weight o	of concrete =	145.0	lb/cubic yard
Sample No.	4	5 Minute Tes	st		24 Hour Tes	t	
		%Cl by	lb. Cl/yd ³		%Cl by	lb. Cl/yd ³	
	mV	mass of	concrete	mV	mass of	concrete	
		concrete	tontrete		concrete	contrott	
12D		1	1				
0" to 1/4"	47.1	0.043	1.700	44.1	0.066	2.568	_
1/4" to 1/2"	79.3	0.010	0.406	70.4	0.021	0.814	
1/2" to 3/4"	72.4	0.014	0.551	65.5	0.026	1.008	
3/4" to 1"	83.9	0.008	0.330	73.8	0.018	0.701	
1" to 1-1/4"	75.0	0.013	0.491	66.8	0.024	0.952	
1-1/4" to 1-1/2"	57.8	0.027	1.056	53.6	0.043	1.696	
1-1/2" to 1-3/4"	49.2	0.040	1.548	48.3	0.055	2.138	
1-3/4" to 2"	61.7	0.023	0.888	58.7	0.035	1.357	
							7
12E					1	r	_
0" to 1/4"	36.8	0.069	2.689	38.4	0.084	3.295	_
1/4" to 1/2"	68.7	0.017	0.650	62.4	0.029	1.154	_
1/2" to 3/4"	81.9	0.009	0.361	71.9	0.019	0.762	_
3/4" to 1"	87.8	0.007	0.278	76.8	0.016	0.615	
1" to 1-1/4"	80.4	0.010	0.386	72.3	0.019	0.749	_
1-1/4" to 1-1/2"	69.2	0.016	0.636	62.4	0.029	1.154	_
1-1/2" to 1-3/4"	68.8	0.017	0.647	61.8	0.030	1.185	_
1-3/4" to 2"	65.9	0.019	0.736	61.4	0.031	1.206	
							7
12F							
0" to 1/4"	18.4	0.156	6.099	19.1	0.196	7.658	
1/4" to 1/2"	59.6	0.025	0.975	50.1	0.050	1.976	
1/2" to 3/4"	79.5	0.010	0.402	71.7	0.020	0.769	
3/4" to 1"	73.2	0.014	0.532	68.0	0.023	0.904	
1" to 1-1/4"	86.9	0.007	0.289	77.1	0.016	0.607	
1-1/4" to 1-1/2"	79.0	0.010	0.411	72.4	0.019	0.746	
1-1/2" to 1-3/4"	84.3	0.008	0.325	76.1	0.016	0.634	
1-3/4" to 2"	78.2	0.011	0.426	71.7	0.020	0.769	
							_


5-Minute Test for 9F and 10F


5/18/2008	%Cl	0.005	0.020	0.050	0.500
	mV before	101.7	76.6	54.8	-2.1
	mV after	91.4	68.4	46.2	-9.7




5-Minute Test for 10E(2)


7/21/2008	%Cl	0.005	0.020	0.050	0.500
	mV before	103.3	75.6	53.0	<u>-2.9</u>
	mV after	94.8	67.8	45.7	-10.3






3/2008	%Cl	0.005	0.020	0.050	0.500
	mV				
	before	100.8	72.5	49.0	-7.7
	mV after	93.6	68.2	45.8	-11.4







		5-Minu	ute Test	24-Hour	Test	By: MDP
		mV	%Cl	mV	%Cl	
7E(1)	1/4"	2.2	0.303	-1.0	0.363	
q	1/2"	-10.8	0.528	-13.4	0.613	
an	3/4"	-13.5	0.592	-16.8	0.707	
3/08	1"	-9.0	0.489	-11.7	0.570	
d 7/23/08 7/24/08	1-1/4"	2.1	0.304	-0.4	0.354	
eq ,	1-1/2"	48.4	0.042	45.5	0.051	
Tested 7/23/08 and 7/24/08	1-3/4"	68.6	0.018	66.8	0.021	
E	2"	75.9	0.013	71.9	0.017	
7E(2)	1/4"	-12.2	0.643	-13.4	0.671	
-	1/2"	-7.5	0.527	-9.3	0.561	
Tested 8/4/08 and 8/6/08	3/4"	-3.0	0.436	-3.9	0.442	
08 08	1"	-2.3	0.423	-4.4	0.452	
d 8/4/08 8/6/08	1-1/4"	25.4	0.131	23.0	0.135	
õ &	1-1/2"	71.5	0.019	63.7	0.022	
Tesi	1-3/4"	74.8	0.016	67.2	0.019	
L L	2"	78.0	0.014	69.6	0.017	
7E(3)	1/4"	-11.6	0.498	-11.2	0.491	
put	1/2"	-15.0	0.580	-14.9	0.579	
Tested 8/25/08/08 and 8/28/08/08	3/4"	-17.4	0.646	-19.3	0.705	
1 8/25/08/0 8/28/08/08	1"	-15.9	0.604	-17.6	0.653	
8/08	1-1/4"	-4.6	0.363	-5.8	0.386	
18/2	1-1/2"	18.0	0.131	17.3	0.137	
stee	1-3/4"	40.3	0.048	40.1	0.050	
Te	2"	56.9	0.023	55.4	0.025	
7E Average of 5-Minute Tests	1/4"	0.481	ur	1/4"	0.509	
lin	1/2"	0.545	·Ho	1/2"	0.584	
5-1	3/4"	0.558	24	3/4"	0.618	
ge of : Tests	1"	0.505	tge of Tests	1"	0.558	
age	1-1/4"	0.266	Tć Tć	1-1/4"	0.292	
ven	1-1/2"	0.064	ver	1-1/2"	0.070	
Ā	1-3/4"	0.027	7E Average of 24-Hour Tests	1-3/4"	0.030	
11	2"	0.017	F	2"	0.020	


		5-Minu	ute Test	24-Ho	ur Test	By: MDP
		mV	%Cl	mV	%Cl	2
9D (1)	1/4"	0.3	0.349	-8.1	0.370	
	1/2"	-13.8	0.653	-6.6	0.346	
ano	3/4"	-16.3	0.730	-7.8	0.365	
⁰⁸	1"	-5.4	0.449	-18.1	0.583	
d 5/18/0 8/13/08	1-1/4"	-17.2	0.760	-41.0	1.650	
8/7 8/7	1-1/2"	-34.4	1.634	-40.8	1.635	
Tested 5/18/08 and 8/13/08	1-3/4"	-13.3	0.639	-41.1	1.657	
E	2"	14.1	0.189	-17.9	0.578	
9D(2)	1/4"	3.7	0.289	1.2	0.288	
	1/2"	-7.3	0.465	-9.0	0.447	
ano	3/4"	-0.6	0.348	0.0	0.303	
80 / 08	1"	-9.0	0.500	-9.6	0.459	
Tested 7/21/08 and 8/13/08	1-1/4"	-19.1	0.775	-19.4	0.701	
2 pc /8	1-1/2"	-16.4	0.689	-15.3	0.587	
este	1-3/4"	-22.3	0.890	-20.9	0.748	
E	2"	-18.2	0.745	-16.2	0.610	
9D(3)	1/4"	-5.8	0.415	-6.4	0.396	
q	1/2"	7.4	0.240	8.1	0.207	
Tested 8/14/08 and 8/28/08	3/4"	25.1	0.115	21.9	0.112	
80/1	1"	35.2	0.075	32.7	0.069	
d 8/14/0 8/28/08	1-1/4"	33.6	0.080	30.8	0.075	
8 pe	1-1/2"	30.0	0.093	26.2	0.092	
esto	1-3/4"	27.9	0.102	24.6	0.099	
E	2"	35.1	0.076	32.6	0.069	
						9D 5-Min Average
9D(4)	1/4"	-14.5	0.567	-13.6	0.546	1/4" 0.461
р	1/2"	-11.8	0.502	-9.7	0.459	1/2" 0.493
Tested 8/25/08 and 8/28/08	3/4"	-6.1	0.389	-3.6	0.350	3/4" 0.451
2/08	1"	18.2	0.130	19.9	0.122	1" 0.436
d 8/25/0 8/28/08	1-1/4"	36.0	0.058	37.8	0.055	1-1/4" 0.521
% eq	1-1/2"	48.5	0.033	50.4	0.031	1-1/2" 0.663
lest	1-3/4"	49.4	0.032	51.5	0.030	1-3/4" 0.461
	2"	53.6	0.026	54.4	0.026	2" 0.268
						9D 24-Hr Average
9D(5)	1/4"	-18.7	0.685	-18.2	0.671	1/4" 0.454
q	1/2"	-16.0	0.607	-14.8	0.577	1/2" 0.407
8 an	3/4"	-18.3	0.673	-16.1	0.611	3/4" 0.348
5/0{ 08	1"	-27.6	1.022	-24.9	0.905	1" 0.428
d 8/25/09 8/28/08	1-1/4"	-25.5	0.930	-24.6	0.893	1-1/4" 0.675
ed { 8/	1-1/2"	-23.9	0.866	-22.7	0.820	1-1/2" 0.633
Tested 8/25/08 and 8/28/08	1-3/4"	-17.2	0.640	-15.0	0.582	1-3/4" 0.623
L	2"	-0.6	0.303	0.8	0.287	2" 0.314

		5-Minu	ite Test	24-Ho	ur Test	B	y: MDP
		mV	%Cl	mV	%Cl		
9E(1)	1/4"	-10.1	0.554	-13.6	0.476		
q	1/2"	-28.7	1.268	-18.7	0.599		
an	3/4"	-22.1	0.945	-17.6	0.570		
8/28	1"	-13.1	0.633	-23.9	0.759		
1 5/18/0 8/13/08	1-1/4"	2.1	0.322	-8.5	0.377		
5 pe 8/ 8	1-1/2"	6.6	0.263	6.2	0.194		
Tested 5/18/08 and 8/13/08	1-3/4"	38.2	0.065	21.4	0.097		
E	2"	22.7	0.129	26.7	0.076		
9E(2)	1/4"	3.7	0.289	-4.3	0.365		
	1/4 1/2"	-7.3	0.289	-4.3 -6.5	0.303		
pun							
Tested 7/21/08 and 8/13/08	3/4" 1"	-0.6	0.348	-15.7	0.597		
1 7/21/0 8/13/08		-9.0	0.500	-12.7	0.525		
17/2	1-1/4"	-19.1	0.775	5.9	0.235		
sted 8	1-1/2"	-16.4	0.689	24.0	0.107		
Tes	1-3/4"	-22.3	0.890	31.4	0.078		
	2"	-18.2	0.745	34.6	0.068		
9E(3)	1/4"	-16.3	0.577	-19.3	0.705		
q	1/2"	-15.8	0.564	-19.0	0.695		
an	3/4"	2.9	0.250	-0.4	0.303		
80/-08	1"	-19.1	0.652	-20.2	0.734		
d 8/14/0 8/28/08	1-1/4"	-34.0	1.250	-32.5	1.271		
Tested 8/14/08 and 8/28/08	1-1/2"	-32.1	1.150	-30.0	1.137		
este	1-3/4"	-2.2	0.312	-6.1	0.391		
F	2"	13.0	0.161	15.0	0.152		
						9E 5-Min Avera	ige
9E(4)	1/4"	-15.6	0.596	-20.8	0.754	1/4"	0.504
q	1/2"	-10.0	0.463	-11.9	0.506	1/2"	0.690
an	3/4"	-9.2	0.447	-11.2	0.491	3/4"	0.497
80/3	1"	-16.5	0.620	-16.7	0.628	1"	0.601
d 8/25/0 8/28/08	1-1/4"	-12.4	0.516	-11.0	0.487	1-1/4"	0.716
Tested 8/25/08 and 8/28/08	1-1/2"	-13.6	0.545	-12.4	0.518	1-1/2"	0.662
este	1-3/4"	-0.8	0.306	0.5	0.291	1-3/4"	0.393
F	2"	21.9	0.110	23.1	0.106	2"	0.286
						9E 24-Hr Avera	ge


23.1	0.106	2"	0.286
		9E 24-Hr Avera	ige
		1/4"	0.575
		1/2"	0.551
		3/4"	0.490
		1"	0.661
		1-1/4"	0.592
		1-1/2"	0.489
		1-3/4"	0.214
		2"	0.101

		5-Minu	ıte Test	24-Ho	ur Test		By: MDP
		mV	%Cl	mV	%Cl		
10D(1)	1/4"	-12.1	0.605	-16.9	0.552		
q	1/2"	-15.7	0.711	-18.5	0.594		
Tested 5/18/08 and 8/13/08	3/4"	-26.6	1.154	-29.0	0.957		
80/8	1"	-23.2	0.992	-28.2	0.923		
d 5/18/0 8/13/08	1-1/4"	-18.8	0.816	-27.6	0.898		
5 pe /8	1-1/2"	-7.0	0.482	-9.8	0.400		
este	1-3/4"	-12.7	0.622	-14.4	0.493		
H	2"	6.1	0.269	-0.5	0.262		
10D(2)	1/4"	-19.8	0.799	-18.6	0.677		
q	1/2"	-15.5	0.663	-14.0	0.555		
an	3/4"	-10.5	0.534	-7.5	0.419		
80/ 80	1"	-24.7	0.987	-18.8	0.683		
8/13/08	1-1/4"	-20.7	0.830	-19.6	0.707		
2 pe	1-1/2"	-31.5	1.325	-26.3	0.944		
Tested 7/21/08 and 8/13/08	1-3/4"	-13.0	0.595	-9.4	0.455		
L	2"	1.2	0.322	15.6	0.154		
10D(3)	1/4"	5.3	0.225	4.7	0.241		
q	1/2"	12.5	0.164	9.5	0.195		
s an	3/4"	23.2	0.103	21.1	0.116		
08 08	1"	24.9	0.095	21.0	0.117		
d 8/14/0 8/28/08	1-1/4"	18.8	0.125	16.1	0.145		
eq 3	1-1/2"	18.9	0.124	14.9	0.153		
Tested 8/14/08 and 8/28/08	1-3/4"	12.9	0.161	8.4	0.205		
F	2"	3.1	0.247	1.5	0.278		
						10D 5-Min Aver	rage
10D(4)	1/4"	-6.1	0.389	-5.2	0.376	1/4"	0.697
р	1/2"	-7.4	0.412	-5.8	0.386	1/2"	0.755
8 ar	3/4"	-1.5	0.316	0.4	0.292	3/4"	0.648
08	1"	-8.3	0.429	-6.3	0.394	1"	0.621
Tested 8/25/08 and 8/28/08	1-1/4"	-25.1	0.914	-23.4	0.846	1-1/4"	0.571
% eq	1-1/2"	-34.3	1.382	-32.8	1.288	1-1/2"	0.694
lest	1-3/4"	-28.0	1.041	-23.5	0.850	1-3/4"	0.492
	2"	-15.5	0.593	-14.2	0.561	2"	0.291
						10D 24-Hr Avei	-
10D(5)	1/4"	-35.6	1.466	-35.9	1.479	1/4"	0.665
р	1/2"	-40.5	1.827	-39.6	1.745	1/2"	0.695
8 ar	3/4"	-29.9	1.134	-29.5	1.112	3/4"	0.579
5/0:	1"	-15.7	0.599	-13.7	0.549	1"	0.533
1 8/25/0 8/28/08	1-1/4"	12.3	0.170	13.9	0.160	1-1/4"	0.551
% %	1-1/2"	14.5	0.154	16.1	0.145	1-1/2"	0.586
Tested 8/25/08 and 8/28/08	1-3/4"	42.8	0.043	45.9	0.038	1-3/4"	0.408
	2"	57.6	0.022	58.7	0.022	2"	0.256


8/13/08 24-Hour Tests for 9D, 9E, 10D					
0.005	0.020	0.050	0.500		
-	68.9	4 9.1	-5.1		
-	54.1	38.7	-15.3		



8/13/08 24-Hour Tests for 9D(2),9E(2),10D(2)						
0.005	0.020	0.050	0.500			
-	68.9	49.1	-5.1			
-	62.3	42.5	-11.8			




8/14/08 Five Minute Test for 9D(3)						
0.005	0.020	0.050	0.500			
-	69.6	4 6.8	-7.8			
-	67.3	44.5	-10.1			




By: MDP


8/14/08 Five Minute Tests for 9E(3)&10D(3)					
0.005	0.020	0.050	0.500		
-	67.3	44 .5	-10.1		
-	60.5	40.0	-13.1		



8/25/08 Five-Minute Tests					
0.005	0.020	0.050	0.500		
95.4	71.2	51.0	-5.5		
-	59.3	40.2	-11.9		



8/28/08 24-Hour Tests								
0.005	0.020	0.050	0.500					
99.0	72.7	4 9.8	-5.8					
-	58.9	42.0	-12.1					



8/13/2008	%Cl Calibration Numbers						
8/13/2008	0.005	0.020	0.050	0.500			
Start	-	68.9	49.1	-5.1			
After 9D 1-1/4" and 1-3/4"	-	54.1	38.7	-15.3			
After remainder of 9D	-	-	38.9	-			
After 9E and 10D	-	-	38.4	-			
After 9D(2) 1/4" and 1/2"	-	62.3	42.5	-11.8			
After remainder of 9D(2)	-	-	42.1	-			
After 9E(2) and 10D(2)	-	-	42.9	-			

8/14/2008	%Cl Calibration Numbers					
8/14/2008	0.005	0.020	0.050	0.500		
Start	-	69.6	46.8	-7.8		
After 9D(3) 1/4" and 1/2"	-	-	44.6	-		
After remainder of 9D(3)	-	-	44.4	-		
After 9E(3)	-	-	39.8	-		
After 10D(3) 1/4" and 1/2"	-	-	43.1	-		
After remainder of 10D(3)	-	60.5	40.0	-13.1		

8/25/2008	%Cl Calibration Numbers					
8/25/2008	0.005	0.020	0.050	0.500		
Start	95.4	71.2	51.0	-5.5		
After 9E(4) 1/4" to 1"	-	65.4	45.7	-		
After 9E(4) and 9E(3) at 1-1/4"	-	-	38.1	-		
After 7E(3)	-	-	43.3	-		
After 9D(4)	-	-	40.9	-		
After 9D(5)	-	-	39.7	-		
After 10D(4)	-	-	39.3	-		
After 10D(5)	-	56.6	36.3	-14.3		
After remainder of 9E(3) and (4)	-	57.4	38.3	-13.8		

8/28/2008	%Cl Calibration Numbers						
8/28/2008	0.005	0.020	0.050	0.500			
Start	99.0	72.7	49.8	-5.8			
After 9D(3)	-	-	42.2	-			
After 9E(3)	-	-	39.0	-			
After 10D(3)	-	-	40.5	-			
After 10D(4)	-	-	39.8	-			
After 10D(5)	-	59.0	39.5	-12.6			
After 9D(5)	-	-	38.8	-			
After 9E(4)	-	58.9	42.0	-12.1			

Specimen #13 - 6 Month Exposure

Liquid	Clear	Purple	Green	Pink			
%CL	0.005	0.02	0.05	0.5			Date:
mV before	102.1	75.5	54.0	-2.2	5 M.	· T ·	5/16/2000
mV after	98.7	72.3	53.3	-3.0	5 Mint	ite Test	5/16/2008
mV before	98.0	75.3	53.8	-2.6	24 11.0	ur Test	5/17/2008
mV after	94.5	73.3	52.4	-2.8	24 П0	ui iest	3/17/2008
			Assun	ned weight o	of concrete =	145.0	lb/cubic yard
Sample No.	4	5 Minute Tes	st	,	24 Hour Tes	t	
		%Cl by	lb. Cl/yd ³		%Cl by	lb. Cl/yd ³	
	mV	mass of	concrete	mV	mass of	concrete	
		concrete	controtte		concrete	controlo	_
13D		1	r		r	r	
0" to 1/4"	15.7	0.240	9.379	12.1	0.282	11.021	_
1/4" to 1/2"	50.4	0.052	2.024	43.8	0.067	2.616	
1/2" to 3/4"	77.3	0.016	0.617	74.9	0.016	0.638	
3/4" to 1"	75.8	0.017	0.659	75.0	0.016	0.635	
1" to 1-1/4"	74.2	0.018	0.707	69.4	0.021	0.819	
1-1/4" to 1-1/2"	82.6	0.012	0.488	75.8	0.016	0.612	
1-1/2" to 1-3/4"	76.6	0.016	0.636	69.9	0.020	0.800	
1-3/4" to 2"	65.6	0.026	1.034	54.9	0.040	1.581	
							7
13E		1		[r	r	_
0" to 1/4"		0.365	14.272	2.6	0.433	16.959	_
1/4" to 1/2"	15.4	0.243	9.504	12.0	0.283	11.071	_
1/2" to 3/4"	29.7	0.129	5.052	27.4	0.141	5.505	_
3/4" to 1"	39.1	0.085	3.335	34.6	0.101	3.971	_
1" to 1-1/4"	60.3	0.033	1.307	53.3	0.043	1.700	_
1-1/4" to 1-1/2"	62.4	0.030	1.191	56.1	0.038	1.497	_
1-1/2" to 1-3/4"	57.8	0.037	1.460	50.0	0.050	1.974	_
1-3/4" to 2"	60.7	0.033	1.284	54.9	0.040	1.581	
							7
13F							
0" to 1/4"	0.4	0.471	18.442	-1.9	0.531	20.800	
1/4" to 1/2"	7.7	0.341	13.357	4.4	0.399	15.629	
1/2" to 3/4"	21.8	0.183	7.163	17.7	0.218	8.548	
3/4" to 1"	49.6	0.054	2.097	43.2	0.069	2.688	
1" to 1-1/4"	65.0	0.027	1.062	60.7	0.031	1.215	
1-1/4" to 1-1/2"	69.7	0.022	0.863	64.2	0.026	1.037	
1-1/2" to 1-3/4"	62.8	0.030	1.170	52.7	0.045	1.747	
1-3/4" to 2"	60.7	0.033	1.284	52.8	0.044	1.739	

Specimen #14 - 6 Month Exposure

Liquid	Clear	Purple	Green	Pink			
%CL	0.005	0.02	0.05	0.5			Date:
mV before	102.1	75.5	54.0	-2.2	5 Minu	ite Test	5/16/2008
mV after	98.7	72.3	53.3	-3.0	5 Milliu	ite Test	5/16/2008
mV before	98.0	75.3	53.8	-2.6	24 Цо	ur Tost	5/17/2008
mV after	94.5	73.3	52.4	-2.8	24 Hour Test		3/17/2008
			Assun	ned weight o	of concrete =	145.0	lb/cubic yard
Sample No.	4	5 Minute Tes	st		24 Hour Tes	t	
		%Cl by	lb. Cl/yd ³		%Cl by	lb. Cl/yd ³	
	mV	mass of	concrete	mV	mass of	concrete	
		concrete			concrete		_
14D						r	_
0" to 1/4"	64.4	0.028	1.090	60.8	0.031	1.210	_
1/4" to 1/2"	69.8	0.022	0.859	64.0	0.027	1.046	4
1/2" to 3/4"	76.9	0.016	0.628	68.6	0.022	0.849	4
3/4" to 1"	72.8	0.019	0.752	67.7	0.023	0.884	_
1" to 1-1/4"	72.2	0.020	0.772	64.1	0.027	1.041	_
1-1/4" to 1-1/2"	71.2	0.021	0.807	64.3	0.026	1.032	_
1-1/2" to 1-3/4"	81.0	0.013	0.524	73.8	0.017	0.671	_
1-3/4" to 2"	80.6	0.014	0.533	76.3	0.015	0.599	
							7
14E							_
0" to 1/4"	65.6	0.026	1.034	60.4	0.031	1.232	_
1/4" to 1/2"	66.8	0.025	0.981	62.0	0.029	1.145	_
1/2" to 3/4"	65.7	0.026	1.029	63.3	0.028	1.080	_
3/4" to 1"	67.8	0.024	0.938	65.4	0.025	0.982	_
1" to 1-1/4"	80.4	0.014	0.538	69.9	0.020	0.800	_
1-1/4" to 1-1/2"	83.8	0.012	0.463	72.7	0.018	0.705	_
1-1/2" to 1-3/4"	83.6	0.012	0.467	71.9	0.019	0.731	_
1-3/4" to 2"	85.9	0.011	0.422	72.2	0.018	0.721]
							1
14F						[_
0" to 1/4"	48.6	0.056	2.192	47.3	0.057	2.232	
1/4" to 1/2"	58.2	0.037	1.434	52.6	0.045	1.755	
	62.8	0.030	1.170	57.7	0.036	1.392	1
1/2" to 3/4"		0.005	0.981	62.2	0.029	1.135	
3/4" to 1"	66.8	0.025	0.901	02.2			
	75.2	0.025	0.981	71.7	0.019	0.738	
3/4" to 1"					0.019 0.026		
3/4" to 1" 1" to 1-1/4"	75.2	0.017	0.677	71.7		0.738	-


Specimen #15 - 6 Month Exposure

Liquid	Clear	Purple	Green	Pink			
%CL	0.005	0.02	0.05	0.5			Date:
mV before	102.1	75.5	54.0	-2.2	5 M	4- T4	5/16/2008
mV after	98.7	72.3	53.3	-3.0	5 Mint	ite Test	5/16/2008
mV before	98.0	75.3	53.8	-2.6	24 11-0	un Teat	5/17/2008
mV after	94.5	73.3	52.4	-2.8	24 ПО	ur Test	5/17/2008
			Assun	ned weight o	of concrete =	145.0	lb/cubic yard
Sample No.	4	5 Minute Tes	st		24 Hour Tes	t	
		%Cl by	lb. Cl/yd ³		%Cl by	lb. Cl/yd ³	
	mV	mass of	concrete	mV	mass of	concrete	
		concrete	concrete		concrete	concrete	
15D		1	1		1	r	_
0" to 1/4"	13.0	0.270	10.568	11.6	0.288	11.274	
1/4" to 1/2"	14.3	0.255	9.978	11.7	0.287	11.223	
1/2" to 3/4"	32.7	0.113	4.425	29.3	0.129	5.050	
3/4" to 1"	41.3	0.077	3.026	39.7	0.080	3.151	_
1" to 1-1/4"	36.5	0.096	3.741	33.7	0.106	4.136	_
1-1/4" to 1-1/2"	35.4	0.100	3.927	34.8	0.101	3.935	_
1-1/2" to 1-3/4"	42.5	0.073	2.870	40.7	0.077	3.011	_
1-3/4" to 2"	62.7	0.030	1.175	57.8	0.035	1.386	
							7
15E(2)		1	1		1		_
0" to 1/4"	4.0	0.379	14.838	0.5	0.417	16.320	Te
1/4" to 1/2"	8.0	0.320	12.536	2.8	0.376	14.738	stee
1/2" to 3/4"	14.4	0.245	9.573	10.6	0.266	10.429	Tested 7/7/08 and 7/8/08
3/4" to 1"	22.1	0.177	6.920	19.7	0.178	6.966	7/08
1" to 1-1/4"	33.3	0.110	4.317	31.3	0.106	4.165	an
1-1/4" to 1-1/2"	34.7	0.104	4.069	30.4	0.111	4.335	.d 7,
1-1/2" to 1-3/4"	42.5	0.075	2.929	36.5	0.084	3.307	0/8/
1-3/4" to 2"	51.9	0.050	1.971	44.7	0.059	2.299	õ
							-
15F							
0" to 1/4"	10.3	0.304	11.907	8.8	0.327	12.801	
1/4" to 1/2"	20.5	0.194	7.587	18.4	0.212	8.281	
1/2" to 3/4"	36.8	0.094	3.692	34.6	0.101	3.971]
3/4" to 1"	69.4	0.022	0.874	67.0	0.023	0.913]
1" to 1-1/4"	75.9	0.017	0.656	69.1	0.021	0.830]
1-1/4" to 1-1/2"	77.8	0.015	0.603	74.2	0.017	0.659]
1-1/2" to 1-3/4"	54.7	0.043	1.674	52.4	0.045	1.771]
1-3/4" to 2"	55.8	0.041	1.594	53.9	0.042	1.654	
·		•	•		•	•	

Specimen #16 - 6 Month Exposure


Liquid	Clear	Purple	Green	Pink]		
%CL	0.005	0.02	0.05	0.5			Date:
mV before	102.1	75.5	54.0	-2.2	~ \ f	· T	5/16/2000
mV after	98.7	72.3	53.3	-3.0	5 Mini	ite Test	5/16/2008
mV before	98.0	75.3	53.8	-2.6	24 11-	Т	5/17/2008
mV after	94.5	73.3	52.4	-2.8	24 Hour Test		5/17/2008
			Assum	ed weight o	f concrete =	145.0	lb/cubic yard
Sample No.	4	5 Minute Tes	t		24 Hour Tes	t	
		%Cl by	lb. Cl/yd ³		%Cl by	lb. Cl/yd ³	
	mV	mass of	concrete	mV	mass of	concrete	
		concrete			concrete		
16D					1		
0" to 1/4"	7.5	0.344	13.475	6.0	0.371	14.535	4
1/4" to 1/2"	14.6	0.252	9.846	13.2	0.268	10.484	_
1/2" to 3/4"	32.6	0.114	4.445	30.8	0.121	4.718	_
3/4" to 1"	57.8	0.037	1.460	53.7	0.043	1.669	_
1" to 1-1/4"	50.6	0.051	2.006	46.5	0.059	2.314	_
1-1/4" to 1-1/2"	55.8	0.041	1.594	51.4	0.047	1.853	_
1-1/2" to 1-3/4"	69.0	0.023	0.890	65.7	0.025	0.968	_
1-3/4" to 2"	62.2	0.031	1.202	58.5	0.034	1.343	
16E							7
0" to 1/4"	77	0.241	12 257	((0.261	14 145	-
1/4" to 1/2"	7.7	0.341 0.277	13.357 10.852	6.6 11.2	0.361 0.293	14.145 11.480	-
1/4 to 1/2 1/2" to 3/4"							-
	24.7	0.161	6.302 3.627	22.6 35.6	0.175	6.844	-
3/4" to 1" 1" to 1-1/4"	37.2 53.1	0.093			0.097	3.795	-
1-1/4" to 1-1/2"	68.0	0.046	1.796 0.930	51.9 66.9	0.046	1.811 0.917	-
1-1/4 to $1-1/21-1/2$ " to $1-3/4$ "	72.8	0.024	0.930	68.5	0.023	0.917	-
1-1/2 to 1-3/4 1-3/4" to 2"	61.7	0.019	1.228	58.4	0.022	1.349	-
1-3/4 10 2	01.7	0.031	1.220	50.4	0.034	1.349	
16F]
0" to 1/4"	7.8	0.340	13.298	5.3	0.383	15.004	
1/4" to 1/2"	13.0	0.270	10.568	11.3	0.292	11.428	
1/2" to 3/4"	23.2	0.172	6.733	20.9	0.189	7.393	
3/4" to 1"	36.8	0.094	3.692	35.5	0.097	3.812	
1" to 1-1/4"	49.3	0.054	2.125	46.7	0.059	2.293	
1-1/4" to 1-1/2"	66.0	0.026	1.016	60.7	0.031	1.215	1
1-1/2" to 1-3/4"	78.4	0.015	0.587	72.9	0.018	0.699	1
1-3/4" to 2"	66.3	0.026	1.002	61.5	0.030	1.172]


5-Minute Tests for #13 to #16 5/16/2008 0.005 0.050 0.500 %Cl 0.020 mV before 102.1 75.5 54.0 -2.2 mv after 98.7 72.3 53.3 -3.0 100.4 mV average 73.9 53.7 -2.6





24-Hour Tests for #13 to #16

5/17/2008	%Cl	0.005	0.020	0.050	0.500
	mV before	98.0	75.3	53.8	-2.6
	mv after	94.5	73.3	52.4	-2.8
	mV average	96.3	74.3	53.1	-2.7









APPENDIX D


CoC Chlorides at 0-Months

Liquid	Clear	Purple	Green	Pink	0" to 1/4"
%CL	0.005	0.02	0.05	0.5	
mV before	96.9	71.7	49.8	-4.5	5 Minute Test
mV after	97.5	72.7	50.7	-4.9	5 Willitle Test
mV before	97.2	71.6	49.7	-4.6	24 Hour Test
mV after	96.9	70.9	49.1	-4.8	24 Hour Test


By: MDP Date: 1/2/2008

1/3/2008 Test

Sample No								
	•		te Test	r			ur Test	
		%Cl by	lb. Cl/yd ³	Average lb. Cl/vd ³		%Cl by	lb. Cl/yd ³	Average lb.
	mV	mass of	concrete	Cl/yd ³ concrete	mV	mass of concrete	concrete	Cl/yd ³ concrete
174	20.5	concrete 0.172	6 724	concrete	10.1		7.047	concrete
17A			6.734	6 605	19.1	0.180		6.042
17B	27.4	0.129	5.050	6.695	26.5	0.132	5.168	6.943
17C	15.5	0.212	8.300		14.6	0.220	8.613	
18A	20.4	0.173	6.773	7.439	18.0	0.190	7.439	7 000
18B	16.9	0.200	7.830	7.439	15.1	0.214	8.378	7.882
18C	17.3	0.197	7.713		16.9	0.200	7.830	
19A	20.1	0.175	6.851	6 692	19.0	0.180	7.047	7 1 5 1
19B	18.1	0.190	7.439	6.682	15.5	0.210	8.222	7.151
19C	24.2	0.147	5.755		22.3	0.158	6.186	
20A	18.2	0.190	7.439	6 60 7	16.8	0.200	7.830	- 1 - 0
20B	23.9	0.150	5.873	6.695	22.0	0.160	6.264	7.178
20C	20.4	0.173	6.773		18.1	0.190	7.439	
21A	21.0	0.170	6.656		17.5	0.193	7.556	
21B	20.4	0.173	6.773	6.695	18.4	0.187	7.321	7.439
21C	21.0	0.170	6.656		18.0	0.190	7.439	
22A	21.4	0.167	6.538		20.0	0.173	6.773	
22B	18.6	0.188	7.360	6.760	17.2	0.193	7.556	
22C	21.8	0.163	6.381		19.8	0.176	6.890	
23A	20.2	0.174	6.812		17.7	0.190	7.439	
23B	17.1	0.200	7.830	7.191	15.4	0.210	8.222	7.582
23C	19.8	0.177	6.930		18.9	0.181	7.086	
24A	22.2	0.160	6.264		21.0	0.168	6.577	
24B	21.1	0.168	6.577	6.577	19.4	0.178	6.969	6.930
24C	20.0	0.176	6.890		18.4	0.185	7.243	
25A	24.1	0.148	5.794		22.2	0.158	6.186	
25B	21.8	0.163	6.381	6.512	20.6	0.170	6.656	6.890
25C	18.4	0.188	7.360		16.9	0.200	7.830	
26A	19.3	0.180	7.047		17.8	0.190	7.439	
26B	17.8	0.192	7.517	7.204	17.1	0.195	7.634	7.399
26C	19.4	0.180	7.047		18.7	0.182	7.125	
27A	23.8	0.150	5.873		21.7	0.160	6.264	
27B	20.1	0.175	6.851	6.003	18.0	0.189	7.399	6.355
27C	26.2	0.135	5.285		25.5	0.138	5.403	
28A	18.2	0.190	7.439		16.0	0.205	8.026	
28B	25.2	0.140	5.481	6.656	23.3	0.150	5.873	7.478
28C	19.6	0.180	7.047		14.8	0.218 8.535		
29A	21.2	0.168	6.577		19.7	0.177	6.930	
29B	24.0	0.148	5.794	6.381	22.0	0.160	6.264	6.812
29C	20.3	0.173	6.773	1	18.5	0.185	7.243	
30A	23.1	0.153	5.990		20.0	0.175	6.851	
30B	21.9	0.162	6.342	6.290	18.6	0.185	7.243	7.008
30D	21.2	0.162	6.538		19.7	0.177	6.930	




Measurement of the acid soluble chloride content of hardened concrete by the RCT method




Liquid	Clear	Purple	Green	Pink	1/4" to 1/2"			By: MDP
%CL	0.005	0.02	0.05	0.5			Date:	
mV before	96.2	72.4	50.9	-4.1	5 Minute Test		12/14/200	7
mV after	96.8	74.2	52.8	-3.7			12/14/200	1
mV before	93.9	72.2	51.4	-3.2	24 Hour Test		12/15/2007	
mV after	96.6	73.2	52.0	-4.0			12/13/200	1
	1			ned weight of	concrete =	145.0	lb/yd3	
Sample No.		5 Mir	ute Test			24 Ho	our Test	
		%Cl by	lb.	Average		%Cl by	lb.	Average
	mV	mass of	Cl/yd ³	lb. Cl/yd ³	mV	mass of	Cl/yd ³	lb. Cl/yd ³
		concrete	concrete	concrete		concrete	concrete	concrete
17A	22.0	0.170	6.656		18.7	0.200	7.830	
17B	25.4	0.148	5.794	6.825	22.2	0.170	6.656	7.830
17C	18.0	0.205	8.026		15.3	0.230	9.005	
18A	20.7	0.180	7.047	4	17.4	0.210	8.222	
18B	21.0	0.178	6.969	6.825	16.8	0.215	8.417	8.091
18C	23.0	0.165	6.460		19.2	0.195	7.634	
19A	23.0	0.165	6.460	5.677	19.1	0.197	7.713	
19B	29.2	0.128	5.011		25.7	0.150	5.873	6.616
19C	26.3	0.142	5.559		24.0	0.160	6.264	1
20A	22.2	0.170	6.656	6.081	19.4	0.194	7.595	6.747
20B	25.4	0.148	5.794		24.4	0.158	6.186	
20C	25.3	0.148	5.794		23.2	0.165	6.460	
21A	30.3	0.120	4.698	4.868	27.5	0.138	5.403	5.455
21B	25.4	0.148	5.794		23.8	0.162	6.342	
21C	33.2	0.105	4.111		31.6	0.118	4.620	
22A	24.4	0.155	6.068		21.6	0.178	6.969	
22B	24.2	0.155	6.068	5.964	22.1	0.172	6.734	6.760
22C	25.6	0.147	5.755		23.0	0.168	6.577	
23A	25.3	0.148	5.794		23.8	0.162	6.342	7.530
23B	21.5	0.175	6.851	6.825	20.1	0.190	7.439	
23C	18.2	0.200	7.830		15.7	0.225	8.809	
24A	25.7	0.147	5.755		23.8	0.162	6.342	
24B	-	-	-	6.264	-	-	-	6.793
24C	21.7	0.173	6.773		20.4	0.185	7.243	
25A	28.2	0.130	5.090		27.0	0.142	5.559	
25B	28.8	0.128	5.011	5.155	25.7	0.150	5.873	5.859
25C	27.4	0.137	5.364		24.6	0.157	6.147	
26A	21.9	0.172	6.734		19.3	0.195	7.634	
26B	24.1	0.155	6.068	6.107	22.0	0.173	6.773	6.825
26C	26.6	0.141	5.520		24.8	0.155	6.068]
27A	26.1	0.145	5.677		22.5	0.170	6.656	
27B	26.8	0.140	5.481	5.390	22.9	0.167	6.538	6.290
27C	28.9	0.128	5.011		26.5	0.145	5.677	
28A	22.2	0.170	6.656		20.2	0.188	7.360	
28B	38.3	0.086	3.367	4.920	36.6	0.096	3.758	5.598
28C	30.1	0.121	4.737		26.8	0.145	5.677	
29A	28.2	0.131	5.129		24.5	0.155	6.068	
29B	23.4	0.160	6.264	5.598	21.6	0.178	6.969	6.303
29C	27.0	0.138	5.403		25.7	0.150	5.873]
30A	21.6	0.175	6.851		16.2	0.222	8.691	
30B	26.7	0.140	5.481	6.042	25.8	0.148	5.794	6.969
30C	25.4	0.148	5.794	1	23.5	0.164	6.421	1

Liquid	Clear	Purple	Green	Pink	1/2" to 3/4"			By: MDP	
%CL	0.005	0.02	0.05	0.5			Date:		
mV before	96.2	72.4	50.9	-4.1	5 Minute Test		12/14/2007		
mV after	96.8	74.2	52.8	-3.7			12/14/200	/	
mV before	93.9	72.2	51.4	-3.2	24 Hour Test		12/15/2007		
mV after	96.6	73.2	52.0	-4.0		ur Test	12/13/200	/	
	-		Assum	ed weight of	concrete =	145.0	lb/yd3		
Sample No.		5 Min	ute Test			24 Ho	our Test		
		%Cl by	lb.	Average		%Cl by	lb.	Average	
	mV	mass of	Cl/yd ³	lb. Cl/yd ³	mV	mass of	Cl/yd ³	lb. Cl/yd ³	
		concrete	concrete	concrete		concrete	concrete	concrete	
17A	25.3	0.150	5.873	5.233	24.0	0.160	6.264		
17B	28.3	0.130	5.090		27.5	0.138	5.403	5.585	
17C	30.2	0.121	4.737		28.6	0.130	5.090		
18A	24.8	0.150	5.873		24.4	0.158	6.186		
18B	29.4	0.125	4.894	5.546	27.3	0.140	5.481	6.238	
18C	25.1	0.150	5.873	1 5.540	21.5	0.180	7.047		
19A	29.3	0.130	4.894		27.1	0.100	5.559		
19R	34.8	0.125	3.915	4.502	33.9	0.142	4.189	4.959	
19D	30.7	0.100	4.698	4.302	28.7	0.131	5.129	4.757	
20A	27.7	0.120	5.285		25.1	0.151	5.951		
20A 20B	27.0	0.133	5.403	5.090	25.8	0.152	5.873	5.638	
20B 20C	31.0	0.138	4.581		23.8	0.130	5.090		
20C 21A	29.5	0.117	4.381		28.9	0.130	5.285		
21A 21B		0.123	4.894 5.090	4.698	27.3	0.133	5.481	5 050	
	28.6			4.096				5.050	
21C	33.8	0.105	4.111		32.5	0.112	4.385		
22A	29.2	0.127	4.972	5.050	27.6	0.138	5.403	5.481	
22B	27.1	0.138	5.403	5.050	25.6	0.150	5.873		
22C	29.9	0.122	4.776		28.7	0.132	5.168		
23A	24.4	0.155	6.068	6.255	20.4	0.185	7.243	7164	
23B	26.4	0.142	5.559	6.355	23.3	0.164	6.421	7.164	
23C	19.6	0.190	7.439		18.5	0.200	7.830		
24A	24.0	0.155	6.068	5.5.0	22.5	0.170	6.656		
24B	28.1	0.132	5.168	5.768	26.8	0.144	5.638	6.381	
24C	24.0	0.155	6.068		22.0	0.175	6.851		
25A	29.5	0.125	4.894	5.000	28.4	0.134	5.246	7 000	
25B	25.0	0.150	5.873	5.220	22.6	0.170	6.656	5.899	
25C	29.4	0.125	4.894		26.0	0.148	5.794		
26A	25.6	0.147	5.755		24.8	0.155	6.068		
26B	27.1	0.138	5.403	5.285	26.0	0.148	5.794	5.651	
26C	30.3	0.120	4.698		29.0	0.130	5.090		
27A	31.0	0.118	4.620		30.2	0.123	4.815		
27B	34.0	0.103	4.032	4.594	31.2	0.119	4.659	5.142	
27C	28.3	0.131	5.129		25.3	0.152	5.951		
28A	24.2	0.155	6.068	-	23.0	0.165	6.460		
28B	36.6	0.093	3.641	4.463	36.2	0.096	3.758	4.711	
28C	36.3	0.094	3.680		35.3	0.100	3.915		
29A	29.2	0.127	4.972		28.1	0.135	5.285		
29B	30.0	0.121	4.737	4.150	29.7	0.128	5.011	4.398	
29C	43.3	0.070	2.741		42.8	0.074	2.897		
30A	18.4	0.200	7.830		16.0	0.222	8.691		
30B	49.0	0.054	2.114	4.972	49.3	0.056	2.192	5.520	
30C	29.0	0.127	4.972		26.8	0.145	5.677		



Measurement of the acid soluble chloride content of hardened concrete by the RCT method




Measurement of the acid soluble chloride content of hardened concrete by


Liquid	Clear	Purple	Green	Pink		3/4" to 1"		By: MDP
%CL	0.005	0.02	0.05	0.5			Date:	
mV before	97.2	72.8	50.5	-4.2	5 Minute Test		11/24/2007	
mV after	99.9	73.4	51.5	-3.8				
mV before	98.4	72.9	51.4	-4.5	24 He	our Test	11/25/2007	
mV after	97.4	72.6	50.3	-3.9		Jui Test	11/23/200	/
				d weight of	concrete =	145.0	lb/yd3	
Sample No.		5 Minu	ite Test	1		24 Ho	ur Test	
		%Cl by	lb.	Average		%Cl by	lb.	Average
	mV	mass of	Cl/yd ³	lb.	mV	mass of	Cl/yd ³	lb. Cl/yd ³
		concrete	concrete	Cl/yd ³		concrete	concrete	concrete
17A	23.7	0.155	6.068		23.1	0.159	6.225	
17B	28.0	0.130	5.090	5.311	27.8	0.130	5.090	5.442
17C	29.3	0.122	4.776		28.0	0.128	5.011	
18A	31.2	0.112	4.385		30.5	0.115	4.502	
18B	26.2	0.141	5.520	4.920	24.6	0.148	5.794	5.129
18C	29.0	0.124	4.855		27.8	0.130	5.090	
19A	28.8	0.125	4.894		27.7	0.130	5.090	
19B	27.3	0.132	5.168	4.450	24.4	0.145	5.677	4.711
19C	38.3	0.084	3.289		37.1	0.086	3.367	
20A	33.0	0.105	4.111		31.7	0.110	4.307	
20B	31.2	0.112	4.385	3.758	28.4	0.125	4.894	4.032
20C	42.5	0.071	2.780		40.9	0.074	2.897	
21A	27.1	0.135	5.285		26.1	0.138	5.403	
21B	29.2	0.122	4.776	5.220	27.5	0.130	5.090	5.559
21C	25.7	0.143	5.598		23.0	0.158	6.186	
22A	26.2	0.141	5.520		24.6	0.145	5.677	
22B	28.3	0.127	4.972	5.298	27.1	0.132	5.168	5.455
22C	26.5	0.138	5.403		25.8	0.141	5.520	
23A	27.0	0.135	5.285		22.5	0.160	6.264	
23B	32.3	0.108	4.228	5.063	29.9	0.118	4.620	5.612
23C	25.2	0.145	5.677		23.9	0.152	5.951	
24A	28.3	0.128	5.011		27.0	0.132	5.168	
24B	27.9	0.130	5.090	5.207	27.3	0.132	5.168	5.337
24C	26.2	0.141	5.520		25.3	0.145	5.677	
25A	31.7	0.111	4.346		29.5	0.120	4.698	
25B	26.2	0.141	5.520	4.881	22.3	0.160	6.264	5.351
25C	29.2	0.122	4.776		27.2	0.130	5.090	
26A	28.3	0.127	4.972		27.1	0.130	5.090	- 101
26B	26.9	0.135	5.285	5.011	26.5	0.138	5.403	5.194
26C	29.1	0.122	4.776		27.5	0.130	5.090	
27A	36.0	0.093	3.641		34.9	0.094	3.680	
27B	30.1	0.120	4.698	5.063	28.3	0.125	4.894	5.181
27C	21.1	0.175	6.851		20.3	0.178	6.969	
28A	30.3	0.118	4.620		28.8	0.124	4.855	4.0
28B	28.0	0.130	5.090	4.594	26.3	0.135	5.285	4.855
28C	33.1	0.104	4.072		30.8	0.113	4.424	
29A	27.3	0.133	5.207		24.2	0.150	5.873	
29B	38.5	0.084	3.289	4.137	36.9	0.087	3.406	4.463
29C	33.9	0.100	3.915		33.1	0.105	4.111	
30A	21.9	0.168	6.577		20.7	0.175	6.851	
30B	58.6	0.036	1.409	3.889	54.6	0.046	1.801	4.137
30C	35.7	0.094	3.680		35.0	0.096	3.758	


Liquid	Clear	Purple	Green	Pink	1" to 1-1/4"			By: MDP	
%CL	0.005	0.02	0.05	0.5			Date:	-	
mV before	97.2	72.8	50.5	-4.2	5 Minute Test		11/24/200		
mV after	99.9	73.4	51.5	-3.8			11/24/200	1	
mV before	98.4	72.9	51.4	-4.5	24 Hour Test		11/25/207		
mV after	97.4	72.6	50.3	-3.9		ui iest	11/25/207		
			Assume	d weight of	concrete =	145.0	lb/yd3		
Sample No.		5 Minu	ite Test			24 Ho	our Test		
		%Cl by	lb.	Average		%Cl by	lb.	Average	
	mV	mass of	Cl/yd ³	lb.	mV	mass of	Cl/yd ³	lb. Cl/yd ³	
		concrete	concrete	Cl/yd ³		concrete	concrete	concrete	
17A	28.7	0.125	4.894		26.0	0.140	5.481		
17B	27.2	0.133	5.207	4.972	25.2	0.142	5.559	5.377	
17C	28.9	0.123	4.815		27.5	0.130	5.090		
18A	25.4	0.145	5.677		24.1	0.150	5.873		
18B	31.8	0.111	4.346	4.789	29.8	0.119	4.659	4.998	
18C	31.7	0.111	4.346		30.4	0.114	4.463		
19A	29.2	0.122	4.776	4.954	26.0	0.140	5.481	4.511	
19B	34.1	0.100	3.915	4.254	31.6	0.110	4.307	4.711	
19C	33.2	0.104	4.072		31.2	0.111	4.346		
20A	26.0	0.140	5.481	4 40 4	24.2	0.150	5.873	4.842	
20B	39.1	0.082	3.210	4.424	38.5	0.086	3.367		
20C	30.7	0.117	4.581		26.8	0.135	5.285		
21A	30.8	0.117	4.581	4 100	28.9 0.122	4.776	4 2 2 2		
21B	33.1	0.104	4.072	4.189	32.8	0.105	4.111	4.333	
21C	34.2	0.100	3.915		32.6	0.105	4.111		
22A	26.3	0.140	5.481	1.500	24.6	0.145	5.677	4 7 1 1	
22B	35.4	0.095	3.719	4.568	34.8	0.098	3.837	4.711	
22C	30.9	0.115	4.502		30.1	0.118	4.620		
23A	28.1	0.128	5.011	4 424	25.8	0.140	5.481	4.750	
23B	36.0	0.093	3.641	4.424	35.2 27.2	0.094	3.680	4.750	
23C	30.4	0.118	4.620			0.130	5.090		
24A	32.0	0.110	4.307	4 1 1 1	29.2	0.120	4.698	1 (1(
24B	33.2	0.103	4.032	4.111	27.7 32.8	0.130	5.090	4.646	
24C	33.7	0.102	3.993 4.111			0.106 0.110	4.150 4.307		
25A	33.1 33.7	0.105 0.102	3.993	3.876	31.6 27.7	0.110	4.307 5.090	4.385	
25B	36.8	0.102	3.524	5.870	34.8	0.130	3.758	4.383	
25C						0.090	3.132		
26A	41.4 30.0	0.074 0.120	2.897 4.698	4.098	39.1 25.2	0.080	5.559	4.855	
26B 26C	30.0	0.120	4.698	4.096	23.2	0.142	5.873	4.835	
	-								
27A	36.2	0.092	3.602	2 002	34.9 29.5	0.096	3.758	4.581	
27B	35.0	0.096	3.758	3.993		0.120	4.698	4.581	
27C	30.4 33.1	0.118	4.620		26.5	0.135	5.285		
28A 28B	36.8	0.104 0.090	4.072 3.524	3.563	31.1 35.1	0.112 0.095	4.385 3.719	3.824	
28B 28C	40.0	0.090	3.093	5.505	37.2	0.095	3.367	5.024	
	35.1	0.079	3.758		37.2	0.088	3.993		
29A	41.4	0.096		1.046	<u> </u>			1 222	
29B	-	0.074	2.897	4.046	24.1	0.080	3.132	4.333	
29C	26.2		5.481			0.150	5.873		
30A	34.4	0.100	3.915	1 127	33.8	0.100	3.915	1 960	
30B	30.2	0.120	4.698	4.437	25.1	0.140	5.481	4.868	
30C	30.1	0.120	4.698		27.0	0.133	5.207		

Liquid	Clear	Purple	Green	Pink	1-1/4" to 1-1/2"			By: MDP
%CL	0.005	0.02	0.05	0.5			Date:	
mV before	97.2	72.8	50.5	-4.2	5 Minute Test		11/04/005	
mV after	99.9	73.4	51.5	-3.8			11/24/207	
mV before	99.6	73.1	50.7	-3.9	24 Hour Test		11/25/2007	7
mV after	96.4	69.4	47.2	-5.5			11/23/200	
				d weight of	concrete =	145.0	lb/yd3	
Sample No.			ite Test				our Test	
		%Cl by	lb.	Average		%Cl by	lb.	Average
	mV	mass of	Cl/yd ³	lb. Cl/yd ³	mV	mass of	Cl/yd ³	lb. Cl/yd ³
		concrete	concrete	Ci/yu	22.4	concrete	concrete	concrete
17A	36.7	0.091	3.563	4.05.4	32.6	0.100	3.915	4.022
17B	28.8	0.127	4.972	4.254	23.6	0.150	5.873	4.933
17C	32.8	0.108	4.228		27.0	0.128	5.011	
18A	32.1	0.110	4.307		27.7	0.125	4.894	1.000
18B	34.2	0.100	3.915	3.876	30.8	0.110	4.307	4.293
18C	37.5	0.087	3.406		34.4	0.094	3.680	
19A	32.0	0.110	4.307	3.967	28.2	0.120	4.698	
19B	35.2	0.096	3.758		39.7	0.115	4.502	4.502
19C	34.4	0.098	3.837		30.3	0.110	4.307	
20A	34.9	0.099	3.876	3.941	31.3	0.107	4.189	4.346
20B	32.8	0.108	4.228		29.0	0.118	4.620	
20C	35.4	0.095	3.719		31.0	0.108	4.228	
21A	39.3	0.081	3.171		35.4	0.090	3.524	I
21B	32.6	0.108	4.228	3.458	28.2	0.120	4.698	3.889
21C	41.0	0.076	2.975		35.9	0.088	3.445	
22A	31.8	0.111	4.346		28.0	0.122	4.776	
22B	34.5	0.099	3.876	4.176	27.4	0.126	4.933	4.737
22C	32.0	0.110	4.307		29.4	0.115	4.502	
23A	29.1	0.125	4.894		24.0	0.144	5.638	
23B	40.0	0.079	3.093	3.863	37.6	0.082	3.210	4.333
23C	36.1	0.092	3.602		31.1	0.106	4.150	
24A	42.5	0.071	2.780		38.3	0.078	3.054	
24B	36.7	0.091	3.563	3.210	31.2	0.105	4.111	3.667
24C	38.4	0.084	3.289		33.1	0.098	3.837	
25A	33.4	0.103	4.032		28.4	0.120	4.698	
25B	34.4	0.100	3.915	3.132	29.1	0.117	4.581	3.641
25C	58.5	0.037	1.449		53.8	0.042	1.644	
26A	34.6	0.098	3.837		29.3	0.115	4.502	
26B	38.1	0.085	3.328	3.758	32.4	0.100	3.915	4.437
26C	33.0	0.105	4.111		27.8	0.125	4.894	
27A	40.2	0.079	3.093		35.7	0.090	3.524	
27B	38.9	0.082	3.210	3.380	34.4	0.094	3.680	3.863
27C	34.8	0.098	3.837		30.0	0.112	4.385	
28A	33.3	0.104	4.072		28.9	0.119	4.659	
28B	34.7	0.099	3.876	3.537	30.9	0.109	4.267	3.967
28C	43.8	0.068	2.662		39.2	0.076	2.975	
29A	31.8	0.112	4.385		29.0	0.118	4.620	
29B	40.5	0.077	3.015	3.837	34.5	0.093	3.641	4.385
29B 29C	33.2	0.105	4.111	2.007	27.8	0.125	4.894	
30A	34.9	0.097	3.798		30.6	0.125	4.307	
30B	34.2	0.100	3.915	3.980	31.7	0.110	4.111	4.502
	5 1.4	0.100	5.715	5.700	21.1	0.105		


Liquid	Clear	Purple	Green	Pink		1-1/2" to	2''	By: MDP
%CL	0.005	0.02	0.05	0.5			Date:	
mV before	97.2	72.8	50.5	-4.2	5 Minute Test		11/24/2007	
mV after	99.9	73.4	51.5	-3.8			11/24/200	/
mV before	99.6	73.1	50.7	-3.9	24 Hour Test		11/25/2007	
mV after	96.4	69.4	47.2	-5.5			11/25/200	1
	1			ed weight of	concrete =	145.0	lb/yd3	
Sample No.		5 Minu	ite Test				our Test	1
		%Cl by	lb.	Average		%Cl by	lb.	Average
	mV	mass of	Cl/yd ³	lb. Cl/yd ³	mV	mass of	Cl/yd ³	lb. Cl/yd ³
	10.0	concrete	concrete	CI/yu	24.0	concrete	concrete	concrete
17A	40.2	0.079	3.093	2 1 1 5	34.0	0.095	3.719	2 705
17B	34.5	0.099	3.876	3.445	31.8	0.105	4.111	3.785
17C	37.9	0.086	3.367		35.4	0.090	3.524	
18A	42.7	0.071	2.780	0.575	36.1	0.086	3.367	2.1.50
18B	40.6	0.077	3.015	2.767	35.2	0.090	3.524	3.158
18C	45.0	0.064	2.506		42.9	0.066	2.584	
19A	35.1	0.096	3.758		31.2	0.106	4.150	
19B	48.1	0.056	2.192	3.002	42.3	0.067	2.623	3.484
19C	40.4	0.078	3.054		34.1	0.094	3.680	
20A	46.1	0.061	2.388		42.0	0.068	2.662	3.132
20B	38.3	0.084	3.289	2.819	35.2	0.090	3.524	
20C	42.8	0.071	2.780		37.1	0.082	3.210	
21A	41.4	0.074	2.897		35.7	0.089	3.484	3.615
21B	35.5	0.095	3.719	3.028	29.3	0.115	4.502	
21C	45.6	0.063	2.466		40.3	0.073	2.858	
22A	36.1	0.092	3.602		31.1	0.108	4.228	
22B	40.8	0.077	3.015	3.615	36.5	0.086	3.367	3.967
22C	32.2	0.108	4.228		30.6	0.110	4.307	
23A	35.5	0.095	3.719		29.4	0.115	4.502	3.680
23B	49.4	0.053	2.075	3.028	44.4	0.061	2.388	
23C	38.3	0.084	3.289		32.4	0.106	4.150	
24A	44.3	0.066	2.584		39.0	0.076	2.975	
24B	42.2	0.071	2.780	2.545	35.5	0.090	3.524	3.054
24C	47.2	0.058	2.271		42.0	0.068	2.662	
25A	36.0	0.093	3.641		30.3	0.110	4.307	
25B	39.2	0.081	3.171	3.028	35.2	0.090	3.524	3.458
25C	47.6	0.058	2.271		43.1	0.065	2.545	
26A	40.8	0.076	2.975		34.9	0.092	3.602	
26B	48.3	0.056	2.192	2.727	43.0	0.066	2.584	3.184
26C	40.5	0.077	3.015		36.6	0.086	3.367	5.104
27A	46.4	0.060	2.349		39.7	0.074	2.897	
27B	47.4	0.058	2.271	2.701	41.7	0.068	2.662	3.067
27D 27C	36.8	0.089	3.484	2.701	34.6	0.093	3.641	5.007
27C	37.6	0.089	3.445		31.1	0.108	4.228	
28R	38.4	0.084	3.289	3.080	34.0	0.095	3.719	3.563
28B 28C	45.1	0.064	2.506	2.000	41.5	0.070	2.741	5.505
28C 29A	39.8	0.080	3.132		34.0	0.095	3.719	
29A 29B	41.3	0.080	2.936	3.119	34.0	0.093	3.524	3.654
	-	0.075		5.119	35.0	0.090		5.054
29C	38.4		3.289				3.719	
30A	35.3	0.096	3.758	2 704	30.9	0.110	4.307	4.1.62
30B	38.8	0.084	3.289	3.706	34.4	0.094	3.680	4.163
30C	33.4	0.104	4.072		29.4	0.115	4.502	










Liquid	Clear	Purple	Green	Pink		2" to 2-1/2	2''	By: MDP
%CL	0.005	0.02	0.05	0.5			Date:	
mV before	99.4	71.3	47.3	-5.3	5 M (11/2/2007	
mV after	98.6	71.4	49.0	-4.7	5 Minu	ite Test	11/3/2007	
mV before	100.5	71.1	47.2	-5.2	24 Ho	ur Test	11/4/207	
mV after	99.3	71.4	48.4	-5.3		ui iest		
				ed weight of	concrete =	145.0	lb/yd3	
Sample No.			ite Test				our Test	
		%Cl by	lb.	Average		%Cl by	lb.	Average
	mV	mass of	Cl/yd ³	lb. Cl/yd ³	mV	mass of	Cl/yd ³	lb. Cl/yd ³
15.	11.2	concrete	concrete	CI/yu	20.0	concrete	concrete	concrete
17A	44.3	0.058	2.271	2.240	38.3	0.076	2.975	0.714
17B	40.2	0.070	2.741	2.349	37.3	0.078	3.054	2.714
17C	47.2	0.052	2.036		46.3	0.054	2.114	
18A	40.3	0.070	2.741	2.226	35.9	0.084	3.289	2 ((2
18B	43.2	0.061	2.388	2.336	42.0	0.064	2.506	2.662
18C	48.9	0.048	1.879		45.3	0.056	2.192	
19A	45.1	0.056	2.192	0.000	43.8	0.058	2.271	0.000
19B	42.2	0.064	2.506	2.323	40.2	0.070	2.741	2.636
19C	44.3	0.058	2.271		38.6	0.074	2.897	
20A	42.4	0.064	2.506	2 702	36.0	0.084	3.289	0.015
20B	34.9	0.086	3.367	2.793	33.2	0.094	3.680	3.315
20C	42.2	0.064	2.506		37.7	0.076	2.975	
21A	43.9	0.058	2.271		38.2	0.076	2.975	
21B	41.8	0.064	2.506	2.453	38.1	0.076	2.975	2.975
21C	41.2	0.066	2.584		38.0	0.076	2.975	
22A	38.8	0.072	2.819		35.9	0.084	3.289	
22B	47.5	0.050	1.958	2.506	44.0	0.058	2.271	2.975
22C	39.4	0.070	2.741		35.1	0.086	3.367	
23A	47.5	0.050	1.958		43.9	0.058	2.271	
23B	48.4	0.049	1.918	2.284	43.7	0.058	2.271	2.741
23C	38.4	0.076	2.975		33.4	0.094	3.680	
24A	38.4	0.076	2.975		34.3	0.090	3.524	
24B	41.9	0.064	2.506	2.427	36.6	0.080	3.132	2.949
24C	49.9	0.046	1.801		45.3	0.056	2.192	
25A	46.6	0.052	2.036		42.2	0.064	2.506	
25B	42.0	0.064	2.506	2.414	37.1	0.080	3.132	2.845
25C	40.1	0.069	2.701		38.9	0.074	2.897	
26A	42.7	0.060	2.349		39.0	0.072	2.819	
26B	45.2	0.056	2.192	2.375	39.9	0.070	2.741	2.975
26C	41.1	0.066	2.584		35.4	0.086	3.367	
27A	46.5	0.051	1.997		40.7	0.068	2.662	
27B	53.9	0.039	1.527	2.036	49.9	0.045	1.762	2.597
27C	41.4	0.066	2.584		35.1	0.086	3.367	
28A	44.1	0.058	2.271		37.1	0.078	3.054	
28B	53.0	0.041	1.605	1.958	47.9	0.049	1.918	2.414
28C	46.6	0.051	1.997		43.8	0.058	2.271	
29A	44.0	0.058	2.271		39.1	0.074	2.897	
29B	43.8	0.058	2.271	2.453	37.9	0.076	2.975	3.080
29C	38.8	0.072	2.819		35.1	0.086	3.367	
30A	35.6	0.082	3.210		31.3	0.104	4.072	
30B	39.7	0.070	2.741	2.767	36.0	0.084	3.289	3.393
30C	43.4	0.060	2.349	1	39.4	0.072	2.819	





Liquid	Clear	Purple	Green	Pink		2-1/2" to 2	3''	By: MDP
%CL	0.005	0.02	0.05	0.5			Date:	
mV before	100.8	71.5	49.4	-4.8	5 Minu	to Tost	11/2/2007	
mV after	100.2	72.5	49.8	-4.2	5 Mint	ite Test	11/3/2007	
mV before	100.5	71.1	47.2	-5.2	24 Ho	ur Test	11/4/207	
mV after	99.3	71.4	48.4	-5.3			11/4/207	
				ed weight of	concrete =	145.0	lb/yd3	
Sample No.			ite Test	1			our Test	
		%Cl by	lb.	Average		%Cl by	lb.	Average
	mV	mass of	Cl/yd ³	lb. Cl/yd ³	mV	mass of	Cl/yd ³	lb. Cl/yd^3
		concrete	concrete	CI/yu		concrete	concrete	concrete
17A	57.4	0.037	1.449	1.500	52.9	0.040	1.566	1.607
17B	50.5	0.047	1.840	1.592	47.8	0.048	1.879	1.697
17C	56.8	0.038	1.488		51.9	0.042	1.644	
18A	40.0	0.082	3.210		34.0	0.090	3.524	
18B	50.1	0.048	1.879	2.558	47.2	0.050	1.958	2.832
18C	44.3	0.066	2.584		37.5	0.077	3.015	
19A	51.1	0.047	1.840		45.5	0.054	2.114	
19B	43.3	0.069	2.701	2.297	37.0	0.079	3.093	2.597
19C	45.6	0.060	2.349		40.9	0.066	2.584	
20A	42.1	0.073	2.858		36.1	0.082	3.210	
20B	55.8	0.038	1.488	2.153	52.6	0.040	1.566	2.427
20C	48.4	0.054	2.114		41.8	0.064	2.506	
21A	37.6	0.088	3.445		34.5	0.088	3.445	
21B	46.1	0.060	2.349	2.558	39.8	0.070	2.741	2.845
21C	49.8	0.048	1.879		42.9	0.060	2.349	
22A	41.1	0.076	2.975		35.8	0.082	3.210	
22B	50.4	0.048	1.879	2.179	44.1	0.058	2.271	2.414
22C	53.1	0.043	1.683		50.0	0.045	1.762	
23A	52.8	0.043	1.683		49.7	0.045	1.762	
23B	59.4	0.034	1.331	1.592	55.1	0.037	1.449	1.749
23C	52.1	0.045	1.762		45.9	0.052	2.036	
24A	48.1	0.053	2.075		45.1	0.056	2.192	
24B	49.2	0.050	1.958	1.801	44.4	0.058	2.271	1.971
24C	58.1	0.035	1.370		55.2	0.037	1.449	
25A	46.6	0.056	2.192		41.1	0.064	2.506	
25B	54.2	0.041	1.605	1.788	50.4	0.045	1.762	1.984
25C	55.1	0.040	1.566		50.9	0.043	1.683	
26A	50.3	0.048	1.879		45.9	0.052	2.036	
26B	53.9	0.041	1.605	1.853	49.2	0.046	1.801	2.036
26C	47.9	0.053	2.075		44.2	0.058	2.271	
27A	46.8	0.056	2.192		40.6	0.066	2.584	
27B	60.1	0.033	1.292	1.971	54.4	0.038	1.488	2.297
27C	44.8	0.062	2.427		38.8	0.072	2.819	
28A	52.9	0.043	1.683		49.2	0.046	1.801	
28B	50.7	0.048	1.879	1.670	48.3	0.049	1.918	1.801
28C	57.2	0.037	1.449		50.8	0.043	1.683	
29A	50.5	0.047	1.840		43.3	0.060	2.349	
29B	42.7	0.070	2.741	2.101	39.3	0.072	2.819	2.375
29C	51.9	0.044	1.723	1	47.0	0.050	1.958	
30A	45.7	0.060	2.349		41.0	0.066	2.584	
30B	57.3	0.037	1.449	1.801	50.7	0.043	1.683	2.036
30C	54.0	0.041	1.605		49.1	0.047	1.840	





(Page left blank intentionally)

APPENDIX E

CoC Chlorides at 3-Months

Specimen #17 - 3 Month Exposure

					-		
Liquid	Clear	Purple	Green	Pink			
%CL	0.005	0.02	0.05	0.5			Date:
mV before	103.4	74.2	53.2	-2.9	5 Minu	ite Test	3/16/2008
mV after	100.2	75.4	53.6	-3.3	Jiviinu	lie Test	5/10/2008
mV before	97.8	74.0	53.0	-3.0	24 Ho	ur Test	3/17/2008
mV after	93.4	72.4	50.6	-4.4		ui iest	5/17/2008
			Assume	d weight of	concrete =	145.0	lb/yd3
Sample No.	5	5 Minute Tes	st	,	24 Hour Tes	t	
		%Cl by	lb.		%Cl by	lb.	
	mV	mass of	Cl/yd ³	mV	mass of	Cl/yd ³	
		concrete	concrete		concrete	concrete	
17D		1	n	r	1		
0" to 1/4"	5.7	0.349	13.663	1.6	0.405	15.856	
1/4" to 1/2"	4.5	0.365	14.290	0.2	0.425	16.639	
1/2" to 3/4"	17.4	0.215	8.417	12.3	0.258	10.101	
3/4" to 1"	36.8	0.100	3.915	33.1	0.108	4.228	
1" to 1-1/4"	38.0	0.094	3.680	34.8	0.102	3.993	
1-1/4" to 1-1/2"	39.2	0.089	3.484	35.0	0.101	3.954	
1-1/2" to 1-3/4"	39.0	0.090	3.524	33.8	0.106	4.150	
1-3/4" to 2"	26.2	0.151	5.912	21.4	0.177	6.930	
·							1
17E		1	1	1	1		
0" to 1/4"	2.2	0.402	15.738	-1.8	0.460	18.009	
1/4" to 1/2"	6.2	0.340	13.311	2.0	0.400	15.660	
1/2" to 3/4"	20.8	0.189	7.399	17.0	0.212	8.300	
3/4" to 1"	22.6	0.177	6.930	17.8	0.208	8.143	
1" to 1-1/4"	25.2	0.158	6.186	20.5	0.182	7.125	
1-1/4" to 1-1/2"	26.0	0.153	5.990	20.7	0.181	7.086	
1-1/2" to 1-3/4"	38.9	0.091	3.563	32.6	0.112	4.385	
1-3/4" to 2"	46.8	0.066	2.584	39.5	0.084	3.289	
							1
17F		1			1		
0" to 1/4"	-4.0	0.510	19.967	-8.8	0.610	23.882	
1/4" to 1/2"	7.8	0.320	12.528	1.6	0.405	15.856	
1/2" to 3/4"	18.3	0.208	8.143	13.6	0.245	9.592	
3/4" to 1"	29.2	0.133	5.207	24.4	0.158	6.186	
			5 402	22.8	0.169	6.616	
1" to 1-1/4"	28.8	0.138	5.403			0.020	
1" to 1-1/4" 1-1/4" to 1-1/2"	37.3	0.138 0.097	3.798	31.6	0.117	4.581	

Specimen #18 - 3 Month Exposure


Liquid	Clear	Purple	Green	Pink]		
%CL	0.005	0.02	0.05	0.5			Date:
mV before	103.4	74.2	53.2	-2.9			0.11.6/00000
mV after	100.2	75.4	53.6	-3.3	5 Minu	ite Test	3/16/2008
mV before	97.8	74.0	53.0	-3.0	04.11	T (2/17/2000
mV after	93.4	72.4	50.6	-4.4	24 Ho	ur Test	3/17/2008
		•	Assume	d weight of	concrete =	145.0	lb/yd3
Sample No.	4	5 Minute Tes	st		24 Hour Tes	t	
		%Cl by	lb.		%Cl by	lb.	
	mV	mass of	Cl/yd ³	mV	mass of	Cl/yd ³	
		concrete	concrete		concrete	concrete	
18D							
0" to 1/4"	2.8	0.392	15.347	-1.6	0.460	18.009	
1/4" to 1/2"	12.4	0.261	10.218	4.8	0.355	13.898	
1/2" to 3/4"	17.3	0.213	8.339	12.0	0.261	10.218	
3/4" to 1"	6.1	0.342	13.389	3.0	0.380	14.877	
1" to 1-1/4"	22.0	0.180	7.047	17.4	0.210	8.222	
1-1/4" to 1-1/2"	36.2	0.101	3.954	30.1	0.122	4.776	
1-1/2" to 1-3/4"	41.4	0.081	3.171	32.2	0.113	4.424	
1-3/4" to 2"	52.6	0.052	2.036	46.5	0.063	2.466	
							1
18G	r	1	1	r	1	r	. 1
0" to 1/4"	9.8	0.295	11.549	8.4	0.320	12.528	Fest
1/4" to 1/2"	5.3	0.355	13.898	3.2	0.395	15.464	led
1/2" to 3/4"	15.2	0.234	9.161	14.7	0.243	9.513	5/10
3/4" to 1"	17.3	0.217	8.496	15.6	0.233	9.122	Tested 5/16/08 and 5/17/08
1" to 1-1/4"	26.1	0.159	6.225	23.8	0.170	6.656	an
1-1/4" to 1-1/2"	19.0	0.204	7.987	16.4	0.227	8.887	d 5,
1-1/2" to 1-3/4"	25.5	0.158	6.186	24.0	0.170	6.656	/17/
1-3/4" to 2"	29.6	0.132	5.168	27.8	0.146	5.716	80
							1
18F		1	1		1		
0" to 1/4"	0.7	0.430	16.835	-3.9	0.500	19.575	
1/4" to 1/2"	11.2	0.277	10.845	5.5	0.345	13.507	
1/2" to 3/4"	17.8	0.212	8.300	12.0	0.261	10.218	
3/4" to 1"	25.1	0.158	6.186	17.0	0.212	8.300	
1" to 1-1/4"	30.6	0.127	4.972	22.5	0.170	6.656	
1-1/4" to 1-1/2"	36.3	0.100	3.915	30.1	0.122	4.776	
1-1/2" to 1-3/4"	39.2	0.089	3.484	34.0	0.105	4.111	
1-3/4" to 2"	43.6	0.075	2.936	38.2	0.088	3.445]


Specimen #19 - 3 Month Exposure

Liquid	Clear	Purple	Green	Pink			
%CL	0.005	0.02	0.05	0.5			Date:
mV before	103.4	74.2	53.2	-2.9	5 M		2/16/2009
mV after	100.2	75.4	53.6	-3.3	5 Mint	ite Test	3/16/2008
mV before	97.8	74.0	53.0	-3.0	24 11.0	ur Test	3/17/2008
mV after	93.4	72.4	50.6	-4.4	24 П0	ui iest	3/1//2008
			Assume	d weight of	concrete =	145.0	lb/yd3
Sample No.		5 Minute Tes	st	,	24 Hour Tes	t	
		%Cl by	lb.		%Cl by	lb.	
	mV	mass of	Cl/yd ³	mV	mass of	Cl/yd ³	
		concrete	concrete		concrete	concrete	
19D	r	1	T	r	T	T	
0" to 1/4"	1.1	0.420	16.443	-2.5	0.480	18.792	
1/4" to 1/2"	3.5	0.380	14.877	-1.3	0.452	17.696	
1/2" to 3/4"	8.9	0.308	12.058	4.6	0.358	14.016	
3/4" to 1"	23.8	0.168	6.577	19.2	0.192	7.517	
1" to 1-1/4"	33.7	0.112	4.385	27.8	0.138	5.403	
1-1/4" to 1-1/2"	38.5	0.092	3.602	32.0	0.115	4.502	
1-1/2" to 1-3/4"	44.0	0.074	2.897	36.7	0.094	3.680	
1-3/4" to 2"	43.8	0.074	2.897	37.2	0.092	3.602	
							1
19E							
0" to 1/4"	3.3	0.380	14.877	-0.2	0.435	17.030	
1/4" to 1/2"	4.7	0.362	14.172	-1.2	0.450	17.618	
1/2" to 3/4"	16.9	0.221	8.652	12.0	0.262	10.257	
3/4" to 1"	29.0	0.136	5.324	24.3	0.158	6.186	
1" to 1-1/4"	41.6	0.081	3.171	36.5	0.095	3.719	
1-1/4" to 1-1/2"	39.3	0.088	3.445	34.0	0.105	4.111	
1-1/2" to 1-3/4"	33.4	0.102	3.993	28.9	0.131	5.129	
1-3/4" to 2"	41.2	0.082	3.210	35.8	0.098	3.837	
407							1
19F				2.0			
0" to 1/4"	1.3	0.412	16.130	-2.8	0.480	18.792	
1/4" to 1/2"	12.1	0.262	10.257	9.1	0.293	11.471	
1/2" to 3/4"	15.0	0.238	9.318	11.0	0.273	10.688	
3/4" to 1"	21.0	0.188	7.360	18.3	0.201	7.869	
1" to 1-1/4"	29.8	0.132	5.168	24.4	0.158	6.186	
1-1/4" to 1-1/2"	35.3	0.105	4.111	29.0	0.130	5.090	
1-1/2" to 1-3/4"	38.5	0.092	3.602	29.8	0.127	4.972	
1-3/4" to 2"	42.3	0.079	3.093	38.3	0.088	3.445	l

Specimen #20 - 3 Month Exposure

Liquid	Clear	Purple	Green	Pink			
%CL	0.005	0.02	0.05	0.5			Date:
mV before	103.4	74.2	53.2	-2.9	5 M		2/1//2000
mV after	100.2	75.4	53.6	-3.3	5 Mint	ite Test	3/16/2008
mV before	97.8	74.0	53.0	-3.0	24 Цо	ur Tost	2/17/2000
mV after	93.4	72.4	50.6	-4.4	24 ПО	ur Test	3/17/2008
			Assume	d weight of	concrete =	145.0	lb/yd3
Sample No.	-	5 Minute Tes	st		24 Hour Tes	t	
		%Cl by	lb.		%Cl by	lb.	
	mV	mass of	Cl/yd ³	mV	mass of	Cl/yd ³	
		concrete	concrete		concrete	concrete	
20D		1	1	1	1	1	-
0" to 1/4"	-2.2	0.485	18.988	-5.1	0.538	21.063	-
1/4" to 1/2"	1.4	0.415	16.247	-2.7	0.480	18.792	
1/2" to 3/4"	6.2	0.340	13.311	3.0	0.380	14.877	-
3/4" to 1"	11.7	0.270	10.571	6.8	0.327	12.802	-
1" to 1-1/4"	33.5	0.112	4.385	29.7	0.126	4.933	
1-1/4" to 1-1/2"	31.5	0.122	4.776	27.5	0.138	5.403	
1-1/2" to 1-3/4"	33.3	0.112	4.385	29.4	0.127	4.972	-
1-3/4" to 2"	40.6	0.085	3.328	35.3	0.100	3.915	
							٦
20E		1					-
0" to 1/4"	1.0	0.420	16.443	-1.3	0.455	17.813	-
1/4" to 1/2"	2.8	0.395	15.464	-0.3	0.435	17.030	-
1/2" to 3/4"	16.7	0.222	8.691	12.6	0.255	9.983	-
3/4" to 1"	25.4	0.158	6.186	21.8	0.175	6.851	-
1" to 1-1/4"	32.6	0.117	4.581	28.3	0.132	5.168	-
1-1/4" to 1-1/2"	33.8	0.112	4.385	29.7	0.127	4.972	-
1-1/2" to 1-3/4"	38.8	0.092	3.602	34.3	0.104	4.072	
1-3/4" to 2"	42.8	0.077	3.015	38.6	0.087	3.406	
							7
20F		1	I	I	1	1	
0" to 1/4"	2.8	0.395	15.464	1.2	0.410	16.052	
1/4" to 1/2"	6.1	0.341	13.350	4.0	0.365	14.290	-
1/2" to 3/4"	15.5	0.231	9.044	11.9	0.262	10.257	
3/4" to 1"	29.7	0.132	5.168	24.4	0.158	6.186	
1" to 1-1/4"	32.0	0.120	4.698	26.3	0.143	5.598	
1-1/4" to 1-1/2"	30.0	0.130	5.090	26.4	0.142	5.559	
1-1/2" to 1-3/4"	33.9	0.111	4.346	29.7	0.127	4.972	
1-3/4" to 2"	31.2	0.123	4.815	25.8	0.149	5.833	





Specimen #21 - 3 Month Exposure

Liquid	Clear	Purple	Green	Pink			
%CL	0.005	0.02	0.05	0.5			Date:
mV before	95.1	74.7	52.8	-2.1	5 M		2/0/2009
mV after	102.8	76.9	55.0	-1.9	5 Mint	ite Test	2/9/2008
mV before	100.3	75.9	53.8	-2.6	24 Цо	ur Tost	2/10/2008
mV after	96.9	73.5	52.0	-4.6	24 ПО	ur Test	2/10/2008
			Assume	d weight of	concrete =	145.0	lb/yd3
Sample No.	4	5 Minute Tes	st	,	24 Hour Tes	t	
		%Cl by	lb.		%Cl by	lb.	
	mV	mass of	Cl/yd ³	mV	mass of	Cl/yd ³	
		concrete	concrete		concrete	concrete	
21D	1	1	1	1	I	1	
0" to 1/4"	-2.4	0.505	19.771	-4.2	0.515	20.162	
1/4" to 1/2"	-1.1	0.475	18.596	-2.9	0.500	19.575	ļ
1/2" to 3/4"	0.3	0.445	17.422	-1.2	0.455	17.813	ļ
3/4" to 1"	0.8	0.430	16.835	-0.3	0.440	17.226	
1" to 1-1/4"	7.1	0.328	12.841	5.2	0.350	13.703	
1-1/4" to 1-1/2"	20.9	0.190	7.439	17.5	0.210	8.222	
1-1/2" to 1-3/4"	37.7	0.095	3.719	32.9	0.110	4.307	
1-3/4" to 2"	45.8	0.068	2.662	37.4	0.092	3.602	
r							1
21E		1			1		
0" to 1/4"	-4.6	0.545	21.337	-7.4	0.595	23.294	
1/4" to 1/2"	8.3	0.315	12.332	4.9	0.355	13.898	
1/2" to 3/4"	17.1	0.220	8.613	11.3	0.270	10.571	
3/4" to 1"	28.7	0.138	5.403	23.1	0.165	6.460	
1" to 1-1/4"	33.5	0.112	4.385	28.0	0.135	5.285	
1-1/4" to 1-1/2"	34.0	0.110	4.307	29.0	0.130	5.090	
1-1/2" to 1-3/4"	34.2	0.109	4.267	30.7	0.122	4.776	
1-3/4" to 2"	41.4	0.082	3.210	35.2	0.102	3.993	
							1
21F	1	1	1	1	1	1	
0" to 1/4"	-10.6	0.700	27.405	-12.9	0.740	28.971	
1/4" to 1/2"	-1.1	0.460	18.009	-4.9	0.540	21.141	
1/2" to 3/4"	8.6	0.310	12.137	3.8	0.370	14.486	
3/4" to 1"	21.0	0.190	7.439	15.0	0.232	9.083	
	29.4	0.134	5.246	24.0	0.160	6.264	
1" to 1-1/4"				.	0.100		1
1-1/4" to 1-1/2"	34.9	0.106	4.150	29.6	0.128	5.011	
		0.106 0.070	4.150 2.741	29.6 41.1 52.0	0.128	5.011 3.093	

Specimen #22 - 3 Month Exposure

			1				
Liquid	Clear	Purple	Green	Pink			
%CL	0.005	0.02	0.05	0.5]		Date:
mV before	95.1	74.7	52.8	-2.1	5 M:	to Tost	2/0/2
mV after	102.8	76.9	55.0	-1.9	5 Mint	ite Test	2/9/2
mV before	100.3	75.9	53.8	-2.6	24 110	ur Test	2/10/2
mV after	96.9	73.5	52.0	-4.6	24 ПО	ur Test	2/10/.
			Assume	d weight of	concrete =	145.0	lb/yd.
Sample No.	4	5 Minute Tes	st		24 Hour Tes	t	
		%Cl by	lb.		%Cl by	lb.	
	mV	mass of	Cl/yd ³	mV	mass of	Cl/yd ³	
		concrete	concrete		concrete	concrete	
22D		1			T	n	
0" to 1/4"	-5.8	0.570	22.316	-8.9	0.630	24.665	
1/4" to 1/2"	2.4	0.400	15.660	-0.9	0.445	17.422	
1/2" to 3/4"	17.9	0.213	8.339	14.0	0.240	9.396	
3/4" to 1"	26.3	0.152	5.951	21.2	0.180	7.047	
1" to 1-1/4"	37.0	0.098	3.837	32.5	0.112	4.385	
	a a i	0.089	3.484	34.3	0.104	4.072	
1-1/4" to 1-1/2"	39.4	0.007					
1-1/4" to 1-1/2" 1-1/2" to 1-3/4"	39.4 44.3	0.072	2.819	37.0	0.093	3.641	
			2.819 2.153	37.0 43.7	0.093 0.071	3.641 2.780	
1-1/2" to 1-3/4" 1-3/4" to 2"	44.3	0.072					
1-1/2" to 1-3/4" 1-3/4" to 2" 22E	44.3	0.072	2.153		0.071	2.780]
1-1/2" to 1-3/4" 1-3/4" to 2" 22E 0" to 1/4"	44.3	0.072 0.055 0.550	2.153 21.533				
1-1/2" to 1-3/4" 1-3/4" to 2" 22E 0" to 1/4" 1/4" to 1/2"	44.3 51.0 -4.8 6.3	0.072 0.055 0.550 0.340	2.153 21.533 13.311	43.7 -7.7 2.8	0.071 0.600 0.385	2.780 23.490 15.073	
1-1/2" to 1-3/4" 1-3/4" to 2" 22E 0" to 1/4" 1/4" to 1/2" 1/2" to 3/4"	44.3 51.0 -4.8	0.072 0.055 0.550	2.153 21.533	43.7 -7.7	0.071	2.780 23.490	
1-1/2" to 1-3/4" 1-3/4" to 2" 22E 0" to 1/4" 1/4" to 1/2"	44.3 51.0 -4.8 6.3 16.4 35.1	0.072 0.055 0.550 0.340	2.153 21.533 13.311	43.7 -7.7 2.8	0.071 0.600 0.385	2.780 23.490 15.073	
1-1/2" to 1-3/4" 1-3/4" to 2" 22E 0" to 1/4" 1/4" to 1/2" 1/2" to 3/4"	44.3 51.0 -4.8 6.3 16.4	0.072 0.055 0.550 0.340 0.228	2.153 21.533 13.311 8.926	43.7 -7.7 2.8 12.2	0.071 0.600 0.385 0.260	2.780 23.490 15.073 10.179	
1-1/2" to 1-3/4" 1-3/4" to 2" 22E 0" to 1/4" 1/4" to 1/2" 1/2" to 3/4" 3/4" to 1" 1" to 1-1/4" 1-1/4" to 1-1/2"	44.3 51.0 -4.8 6.3 16.4 35.1	0.072 0.055 0.550 0.340 0.228 0.105	2.153 21.533 13.311 8.926 4.111	43.7 -7.7 2.8 12.2 29.8	0.071 0.600 0.385 0.260 0.126	2.780 23.490 15.073 10.179 4.933	
1-1/2" to 1-3/4" 1-3/4" to 2" 22E 0" to 1/4" 1/4" to 1/2" 1/2" to 3/4" 3/4" to 1" 1" to 1-1/4" 1-1/4" to 1-1/2" 1-1/2" to 1-3/4"	44.3 51.0 -4.8 6.3 16.4 35.1 43.5	0.072 0.055 0.550 0.340 0.228 0.105 0.074	2.153 21.533 13.311 8.926 4.111 2.897	43.7 -7.7 2.8 12.2 29.8 39.3	0.071 0.600 0.385 0.260 0.126 0.085	2.780 23.490 15.073 10.179 4.933 3.328	
1-1/2" to 1-3/4" 1-3/4" to 2" 22E 0" to 1/4" 1/4" to 1/2" 1/2" to 3/4" 3/4" to 1" 1" to 1-1/4" 1-1/4" to 1-1/2"	44.3 51.0 -4.8 6.3 16.4 35.1 43.5 42.6	0.072 0.055 0.550 0.340 0.228 0.105 0.074 0.078	2.153 21.533 13.311 8.926 4.111 2.897 3.054	43.7 -7.7 2.8 12.2 29.8 39.3 37.0	0.071 0.600 0.385 0.260 0.126 0.085 0.093	2.780 23.490 15.073 10.179 4.933 3.328 3.641	
1-1/2" to 1-3/4" 1-3/4" to 2" 22E 0" to 1/4" 1/4" to 1/2" 1/2" to 3/4" 3/4" to 1" 1" to 1-1/4" 1-1/4" to 1-1/2" 1-1/2" to 1-3/4" 1-3/4" to 2"	44.3 51.0 -4.8 6.3 16.4 35.1 43.5 42.6 36.3	0.072 0.055 0.550 0.340 0.228 0.105 0.074 0.078 0.100	2.153 21.533 13.311 8.926 4.111 2.897 3.054 3.915	43.7 -7.7 2.8 12.2 29.8 39.3 37.0 29.8	0.071 0.600 0.385 0.260 0.126 0.085 0.093 0.126	2.780 23.490 15.073 10.179 4.933 3.328 3.641 4.933	
1-1/2" to 1-3/4" 1-3/4" to 2" 22E 0" to 1/4" 1/4" to 1/2" 1/2" to 3/4" 3/4" to 1" 1" to 1-1/4" 1-1/4" to 1-1/2" 1-1/2" to 1-3/4" 1-3/4" to 2" 22F	44.3 51.0 -4.8 6.3 16.4 35.1 43.5 42.6 36.3	0.072 0.055 0.550 0.340 0.228 0.105 0.074 0.078 0.100	2.153 21.533 13.311 8.926 4.111 2.897 3.054 3.915	43.7 -7.7 2.8 12.2 29.8 39.3 37.0 29.8	0.071 0.600 0.385 0.260 0.126 0.085 0.093 0.126	2.780 23.490 15.073 10.179 4.933 3.328 3.641 4.933	
1-1/2" to 1-3/4" 1-3/4" to 2" 22E 0" to 1/4" 1/4" to 1/2" 1/2" to 3/4" 3/4" to 1" 1" to 1-1/4" 1-1/4" to 1-1/2" 1-1/2" to 1-3/4" 1-3/4" to 2" 22F 0" to 1/4"	44.3 51.0 -4.8 6.3 16.4 35.1 43.5 42.6 36.3 41.8 -4.1	0.072 0.055 0.550 0.340 0.228 0.105 0.074 0.078 0.100 0.080	2.153 21.533 13.311 8.926 4.111 2.897 3.054 3.915 3.132 21.141	43.7 -7.7 2.8 12.2 29.8 39.3 37.0 29.8 36.5 -8.3	0.071 0.600 0.385 0.260 0.126 0.085 0.093 0.126	2.780 23.490 15.073 10.179 4.933 3.328 3.641 4.933	
1-1/2" to 1-3/4" 1-3/4" to 2" 22E 0" to 1/4" 1/4" to 1/2" 1/2" to 3/4" 3/4" to 1" 1" to 1-1/4" 1-1/4" to 1-1/2" 1-1/2" to 1-3/4" 1-3/4" to 2" 22F 0" to 1/4" 1/4" to 1/2"	44.3 51.0 -4.8 6.3 16.4 35.1 43.5 42.6 36.3 41.8	0.072 0.055 0.550 0.340 0.228 0.105 0.074 0.078 0.100 0.080	2.153 21.533 13.311 8.926 4.111 2.897 3.054 3.915 3.132	43.7 -7.7 2.8 12.2 29.8 39.3 37.0 29.8 36.5	0.071 0.600 0.385 0.260 0.126 0.085 0.093 0.126 0.095	2.780 23.490 15.073 10.179 4.933 3.328 3.641 4.933 3.719	
1-1/2" to 1-3/4" 1-3/4" to 2" 22E 0" to 1/4" 1/4" to 1/2" 1/2" to 3/4" 3/4" to 1" 1" to 1-1/4" 1-1/4" to 1-1/2" 1-1/2" to 1-3/4" 1-3/4" to 2" 22F 0" to 1/4"	44.3 51.0 -4.8 6.3 16.4 35.1 43.5 42.6 36.3 41.8 -4.1	0.072 0.055 0.550 0.340 0.228 0.105 0.074 0.078 0.100 0.080	2.153 21.533 13.311 8.926 4.111 2.897 3.054 3.915 3.132 21.141	43.7 -7.7 2.8 12.2 29.8 39.3 37.0 29.8 36.5 -8.3	0.071 0.600 0.385 0.260 0.126 0.085 0.093 0.126 0.095 0.095	2.780 23.490 15.073 10.179 4.933 3.328 3.641 4.933 3.719 24.273	
1-1/2" to 1-3/4" 1-3/4" to 2" 22E 0" to 1/4" 1/4" to 1/2" 1/2" to 3/4" 3/4" to 1" 1" to 1-1/4" 1-1/4" to 1-1/2" 1-1/2" to 1-3/4" 1-3/4" to 2" 22F 0" to 1/4" 1/4" to 1/2"	44.3 51.0 -4.8 6.3 16.4 35.1 43.5 42.6 36.3 41.8 -4.1 3.1	0.072 0.055 0.550 0.340 0.228 0.105 0.074 0.078 0.100 0.080 0.540 0.390	2.153 21.533 13.311 8.926 4.111 2.897 3.054 3.915 3.132 21.141 15.269	43.7 -7.7 2.8 12.2 29.8 39.3 37.0 29.8 36.5 -8.3 -0.3	0.071 0.600 0.385 0.260 0.126 0.085 0.093 0.126 0.095 0.620 0.435	2.780 23.490 15.073 10.179 4.933 3.328 3.641 4.933 3.719 24.273 17.030	
1-1/2" to 1-3/4" 1-3/4" to 2" 22E 0" to 1/4" 1/4" to 1/2" 1/2" to 3/4" 3/4" to 1" 1" to 1-1/4" 1-1/4" to 1-1/2" 1-1/2" to 1-3/4" 1-3/4" to 2" 22F 0" to 1/4" 1/4" to 1/2" 1/4" to 1/2" 1/4" to 1/2"	44.3 51.0 -4.8 6.3 16.4 35.1 43.5 42.6 36.3 41.8 -4.1 3.1 19.0	0.072 0.055 0.550 0.340 0.228 0.105 0.074 0.078 0.100 0.080 0.540 0.390 0.205	2.153 21.533 13.311 8.926 4.111 2.897 3.054 3.915 3.132 21.141 15.269 8.026	43.7 -7.7 2.8 12.2 29.8 39.3 37.0 29.8 36.5 -8.3 -0.3 15.6	0.071 0.600 0.385 0.260 0.126 0.085 0.093 0.126 0.095 0.620 0.435 0.227	2.780 23.490 15.073 10.179 4.933 3.328 3.641 4.933 3.719 24.273 17.030 8.887	
1-1/2" to 1-3/4" 1-3/4" to 2" 22E 0" to 1/4" 1/4" to 1/2" 1/2" to 3/4" 3/4" to 1" 1" to 1-1/4" 1-1/4" to 1-1/2" 1-1/2" to 1-3/4" 1-3/4" to 2" 22F 0" to 1/4" 1/4" to 1/2" 1/2" to 3/4" 3/4" to 1"	44.3 51.0 -4.8 6.3 16.4 35.1 43.5 42.6 36.3 41.8 -4.1 3.1 19.0 28.9	0.072 0.055 0.340 0.228 0.105 0.074 0.078 0.100 0.080 0.540 0.390 0.205 0.136	2.153 21.533 13.311 8.926 4.111 2.897 3.054 3.915 3.132 21.141 15.269 8.026 5.324	43.7 -7.7 2.8 12.2 29.8 39.3 37.0 29.8 36.5 -8.3 -0.3 15.6 23.2	0.071 0.600 0.385 0.260 0.126 0.085 0.093 0.126 0.095 0.095 0.620 0.435 0.227 0.164	2.780 23.490 15.073 10.179 4.933 3.328 3.641 4.933 3.719 24.273 17.030 8.887 6.421	
1-1/2" to 1-3/4" 1-3/4" to 2" 22E 0" to 1/4" 1/4" to 1/2" 1/2" to 3/4" 3/4" to 1" 1-1/4" to 1-1/2" 1-1/2" to 1-3/4" 1-3/4" to 2" 22F 0" to 1/4" 1/4" to 1/2" 1/2" to 3/4" 3/4" to 1" 1/2" to 3/4" 3/4" to 1" 1" to 1-1/4"	44.3 51.0 -4.8 6.3 16.4 35.1 43.5 42.6 36.3 41.8 -4.1 3.1 19.0 28.9 33.7	0.072 0.055 0.550 0.340 0.228 0.105 0.074 0.078 0.100 0.080 0.540 0.390 0.205 0.136 0.112	2.153 21.533 13.311 8.926 4.111 2.897 3.054 3.915 3.132 21.141 15.269 8.026 5.324 4.385	43.7 -7.7 2.8 12.2 29.8 39.3 37.0 29.8 36.5 -8.3 -0.3 15.6 23.2 27.6	0.071 0.600 0.385 0.260 0.126 0.085 0.093 0.126 0.095 0.620 0.435 0.227 0.164 0.138	2.780 23.490 15.073 10.179 4.933 3.328 3.641 4.933 3.719 24.273 17.030 8.887 6.421 5.403	

Specimen #23 - 3 Month Exposure


$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	Licuid	Class	Dug-1-	Castra	D:1-	1		
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	Liquid % CI	Clear	Purple	Green	Pink			Data
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$								Date:
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$						5 Minu	ite Test	2/9/2008
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$								
Assumed weight of concrete = 145.0 Ib/yd3 Sample No. 5 Minute Test 24 Hour Test Ib. mV %Cl by Ib. mV %Cl by Ib. 0" to 1/4" -3.1 0.520 20.358 -5.6 0.550 21.533 1/4" to 1/2" -0.2 0.445 17.422 -3.3 0.500 19.575 1/2" to 3/4" 17.3 0.220 8.613 13.6 0.247 9.670 3/4" to 1" 23.8 0.170 6.656 19.0 0.195 7.668 1-1/4" to 1-1/4" 32.9 0.115 4.502 28.5 0.132 5.168 1-1/4" to 1-1/4" 32.9 0.053 2.075 42.2 0.075 2.936 23G						24 Ho	ur Test	2/10/2008
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	inv atter	90.9	/ 5.5			concrete –	145.0	1h/v.42
$\begin{tabular}{ c c c c c c c c c c c c c c c c c c c$	Sample No	4	Minuto Tor					10/yas
$\begin{tabular}{ c c c c c c c c c c c c c c c c c c c$	Sample No.	•			^			
$\begin{tabular}{ c c c c c c c c c c c c c c c c c c c$		mV		$\frac{10}{C1/vd^3}$	mV	-	$C1/vd^3$	
$\begin{array}{c c c c c c c c c c c c c c c c c c c $		111 V		•	111 V		•	
$\begin{array}{c c c c c c c c c c c c c c c c c c c $	23D							
$\begin{array}{c c c c c c c c c c c c c c c c c c c $		-3.1	0.520	20.358	-5.6	0.550	21.533	
$\begin{array}{c c c c c c c c c c c c c c c c c c c $								
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$								
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$								1
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$								1
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$	1-1/4" to 1-1/2"	40.6	0.084	3.289	34.9	0.103	4.032	
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$	1-1/2" to 1-3/4"	41.4	0.081	3.171	33.0	0.110	4.307	
$\begin{array}{c c c c c c c c c c c c c c c c c c c $	1-3/4" to 2"	51.0	0.053	2.075	42.2	0.075	2.936	
$\begin{array}{c c c c c c c c c c c c c c c c c c c $								
23F 0" to 1/4" 1.8 0.410 16.052 -1.9 0.465 18.205 1/4" to 1/2" 8.3 0.315 12.332 3.4 0.375 14.681 1/2" to 3/4" 27.4 0.145 5.677 21.0 0.180 7.047 3/4" to 1" 30.7 0.127 4.972 24.0 0.160 6.264 1" to 1-1/4" 38.3 0.092 3.602 32.7 0.112 4.385 1-1/4" to 1-1/2" 45.0 0.070 2.741 39.0 0.086 3.367 1-1/2" to 1-3/4" 46.4 0.066 2.584 40.5 0.081 3.171	23G							
23F 0" to 1/4" 1.8 0.410 16.052 -1.9 0.465 18.205 1/4" to 1/2" 8.3 0.315 12.332 3.4 0.375 14.681 1/2" to 3/4" 27.4 0.145 5.677 21.0 0.180 7.047 3/4" to 1" 30.7 0.127 4.972 24.0 0.160 6.264 1" to 1-1/4" 38.3 0.092 3.602 32.7 0.112 4.385 1-1/4" to 1-1/2" 45.0 0.070 2.741 39.0 0.086 3.367 1-1/2" to 1-3/4" 46.4 0.066 2.584 40.5 0.081 3.171	0" to 1/4"	4.2	0.370	14.486	3.6	0.385	15.073	Tes
23F 0" to 1/4" 1.8 0.410 16.052 -1.9 0.465 18.205 1/4" to 1/2" 8.3 0.315 12.332 3.4 0.375 14.681 1/2" to 3/4" 27.4 0.145 5.677 21.0 0.180 7.047 3/4" to 1" 30.7 0.127 4.972 24.0 0.160 6.264 1" to 1-1/4" 38.3 0.092 3.602 32.7 0.112 4.385 1-1/4" to 1-1/2" 45.0 0.070 2.741 39.0 0.086 3.367 1-1/2" to 1-3/4" 46.4 0.066 2.584 40.5 0.081 3.171	1/4" to 1/2"	6.8	0.338	13.233	4.9	0.368	14.407	ted
23F 0" to 1/4" 1.8 0.410 16.052 -1.9 0.465 18.205 1/4" to 1/2" 8.3 0.315 12.332 3.4 0.375 14.681 1/2" to 3/4" 27.4 0.145 5.677 21.0 0.180 7.047 3/4" to 1" 30.7 0.127 4.972 24.0 0.160 6.264 1" to 1-1/4" 38.3 0.092 3.602 32.7 0.112 4.385 1-1/4" to 1-1/2" 45.0 0.070 2.741 39.0 0.086 3.367 1-1/2" to 1-3/4" 46.4 0.066 2.584 40.5 0.081 3.171	1/2" to 3/4"	14.1	0.245	9.592	11.8	0.278	10.884	5/1
23F 0" to 1/4" 1.8 0.410 16.052 -1.9 0.465 18.205 1/4" to 1/2" 8.3 0.315 12.332 3.4 0.375 14.681 1/2" to 3/4" 27.4 0.145 5.677 21.0 0.180 7.047 3/4" to 1" 30.7 0.127 4.972 24.0 0.160 6.264 1" to 1-1/4" 38.3 0.092 3.602 32.7 0.112 4.385 1-1/4" to 1-1/2" 45.0 0.070 2.741 39.0 0.086 3.367 1-1/2" to 1-3/4" 46.4 0.066 2.584 40.5 0.081 3.171	3/4" to 1"	27.9	0.213	8.339	25.8	0.158	6.186	6/0
23F 0" to 1/4" 1.8 0.410 16.052 -1.9 0.465 18.205 1/4" to 1/2" 8.3 0.315 12.332 3.4 0.375 14.681 1/2" to 3/4" 27.4 0.145 5.677 21.0 0.180 7.047 3/4" to 1" 30.7 0.127 4.972 24.0 0.160 6.264 1" to 1-1/4" 38.3 0.092 3.602 32.7 0.112 4.385 1-1/4" to 1-1/2" 45.0 0.070 2.741 39.0 0.086 3.367 1-1/2" to 1-3/4" 46.4 0.066 2.584 40.5 0.081 3.171	1" to 1-1/4"	43.4	0.075	2.936	41.1	0.084	3.289	8 an
23F 0" to 1/4" 1.8 0.410 16.052 -1.9 0.465 18.205 1/4" to 1/2" 8.3 0.315 12.332 3.4 0.375 14.681 1/2" to 3/4" 27.4 0.145 5.677 21.0 0.180 7.047 3/4" to 1" 30.7 0.127 4.972 24.0 0.160 6.264 1" to 1-1/4" 38.3 0.092 3.602 32.7 0.112 4.385 1-1/4" to 1-1/2" 45.0 0.070 2.741 39.0 0.086 3.367 1-1/2" to 1-3/4" 46.4 0.066 2.584 40.5 0.081 3.171	1-1/4" to 1-1/2"	43.4	0.075	2.936	41.5	0.082	3.210	1d 5
23F 0" to 1/4" 1.8 0.410 16.052 -1.9 0.465 18.205 1/4" to 1/2" 8.3 0.315 12.332 3.4 0.375 14.681 1/2" to 3/4" 27.4 0.145 5.677 21.0 0.180 7.047 3/4" to 1" 30.7 0.127 4.972 24.0 0.160 6.264 1" to 1-1/4" 38.3 0.092 3.602 32.7 0.112 4.385 1-1/4" to 1-1/2" 45.0 0.070 2.741 39.0 0.086 3.367 1-1/2" to 1-3/4" 46.4 0.066 2.584 40.5 0.081 3.171	1-1/2" to 1-3/4"	42.0	0.080	3.132	39.3	0.090	3.524	/17,
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$	1-3/4" to 2"	32.8	0.117	4.581	29.4	0.135	5.285	80/
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$								
$\begin{array}{c c c c c c c c c c c c c c c c c c c $	23F							
1/2" to 3/4" 27.4 0.145 5.677 21.0 0.180 7.047 3/4" to 1" 30.7 0.127 4.972 24.0 0.160 6.264 1" to 1-1/4" 38.3 0.092 3.602 32.7 0.112 4.385 1-1/4" to 1-1/2" 45.0 0.070 2.741 39.0 0.086 3.367 1-1/2" to 1-3/4" 46.4 0.066 2.584 40.5 0.081 3.171	0" to 1/4"	1.8	0.410	16.052	-1.9	0.465	18.205	
3/4" to 1" 30.7 0.127 4.972 24.0 0.160 6.264 1" to 1-1/4" 38.3 0.092 3.602 32.7 0.112 4.385 1-1/4" to 1-1/2" 45.0 0.070 2.741 39.0 0.086 3.367 1-1/2" to 1-3/4" 46.4 0.066 2.584 40.5 0.081 3.171			0.315	12.332	3.4	0.375	14.681	
1" to 1-1/4" 38.3 0.092 3.602 32.7 0.112 4.385 1-1/4" to 1-1/2" 45.0 0.070 2.741 39.0 0.086 3.367 1-1/2" to 1-3/4" 46.4 0.066 2.584 40.5 0.081 3.171	1/2" to 3/4"	27.4	0.145	5.677	21.0	0.180	7.047	
1-1/4" to 1-1/2" 45.0 0.070 2.741 39.0 0.086 3.367 1-1/2" to 1-3/4" 46.4 0.066 2.584 40.5 0.081 3.171		30.7	0.127	4.972	24.0	0.160	6.264	
1-1/2" to 1-3/4" 46.4 0.066 2.584 40.5 0.081 3.171	1" to 1-1/4"	38.3	0.092	3.602	32.7	0.112	4.385	
	1-1/4" to 1-1/2"	45.0	0.070	2.741		0.086	3.367	
1-3/4" to 2" 51.2 0.054 2.114 47.3 0.061 2.388	1-1/2" to 1-3/4"	46.4	0.066	2.584	40.5	0.081	3.171	
	1-3/4" to 2"	51.2	0.054	2.114	47.3	0.061	2.388	


Specimen #24 - 3 Month Exposure

Liquid	Clear	Purple	Green	Pink			
%CL	0.005	0.02	0.05	0.5			Date:
mV before	95.1	74.7	52.8	-2.1	5 M.	· T ·	2/0/2008
mV after	102.8	76.9	55.0	-1.9	5 Mint	ite Test	2/9/2008
mV before	100.3	75.9	53.8	-2.6	24 Цо	ur Test	2/10/2008
mV after	96.9	73.5	52.0	-4.6	24 П0	ui iest	2/10/2008
			Assume	d weight of	concrete =	145.0	lb/yd3
Sample No.	4	5 Minute Tes	st	,	24 Hour Tes	t	
		%Cl by	lb.		%Cl by	lb.	
	mV	mass of	Cl/yd ³	mV	mass of	Cl/yd ³	
		concrete	concrete		concrete	concrete	
24D		1	1		1		
0" to 1/4"	4.8	0.365	14.290	2.4	0.390	15.269	
1/4" to 1/2"	11.4	0.280	10.962	7.2	0.320	12.528	
1/2" to 3/4"	18.1	0.210	8.222	15.8	0.227	8.887	
3/4" to 1"	25.3	0.158	6.186	22.7	0.170	6.656	
1" to 1-1/4"	36.2	0.100	3.915	32.6	0.112	4.385	
1-1/4" to 1-1/2"	42.1	0.079	3.093	37.2	0.092	3.602	
1-1/2" to 1-3/4"	45.0	0.070	2.741	40.0	0.082	3.210	
1-3/4" to 2"	47.3	0.064	2.506	44.5	0.069	2.701	
							1
24E		1	1				
0" to 1/4"	4.6	0.365	14.290	2.0	0.400	15.660	
1/4" to 1/2"	15.5	0.235	9.200	12.3	0.260	10.179	
1/2" to 3/4"	24.0	0.165	6.460	20.7	0.183	7.164	
3/4" to 1"	31.6	0.120	4.698	27.0	0.140	5.481	
1" to 1-1/4"	38.4	0.092	3.602	34.2	0.105	4.111	
1-1/4" to 1-1/2"	44.5	0.072	2.819	39.2	0.085	3.328	
1-1/2" to 1-3/4"	44.8	0.071	2.780	41.1	0.080	3.132	
1-3/4" to 2"	37.6	0.096	3.758	35.8	0.100	3.915	J
							1
24F			1	r	1	r	
0" to 1/4"	-2.1	0.500	19.575	-6.4	0.570	22.316	
1/4" to 1/2"	13.6	0.255	9.983	8.3	0.305	11.941	
1/2" to 3/4"	29.8	0.131	5.129	25.8	0.150	5.873	
3/4" to 1"	36.6	0.099	3.876	31.5	0.118	4.620	
1" to 1-1/4"	48.6	0.061	2.388	43.2	0.072	2.819	
1-1/4" to 1-1/2"	45.0	0.070	2.741	42.6	0.074	2.897	
1-1/2" to 1-3/4"	39.1	0.089	3.484	35.8	0.099	3.876	
1-3/4" to 2"	37.0	0.097	3.798	32.7	0.112	4.385	

Specimen #25 - 3 Month Exposure

Liquid	Clear	Purple	Green	Pink			
%CL	0.005	0.02	0.05	0.5			Date:
mV before	95.1	74.7	52.8	-2.1	5 M:		2/0/2009
mV after	102.8	76.9	55.0	-1.9	5 Minu	ite Test	2/9/2008
mV before	100.3	75.9	53.8	-2.6	24 110	ur Test	2/10/2008
mV after	96.9	73.5	52.0	-4.6	24 П0	ur Test	2/10/2008
			Assume	d weight of	concrete =	145.0	lb/yd3
Sample No.	4	5 Minute Tes	st	,	24 Hour Tes	t	
		%Cl by	lb.		%Cl by	lb.	
	mV	mass of	Cl/yd ³	mV	mass of	Cl/yd ³	
		concrete	concrete		concrete	concrete	
25D		1			1		
0" to 1/4"	-0.1	0.440	17.226	-2.2	0.470	18.401	
1/4" to 1/2"	12.5	0.265	10.375	9.6	0.290	11.354	
1/2" to 3/4"	20.4	0.192	7.517	17.0	0.213	8.339	
3/4" to 1"	30.8	0.125	4.894	25.8	0.150	5.873	
1" to 1-1/4"	34.9	0.107	4.189	31.9	0.118	4.620	
1-1/4" to 1-1/2"	35.0	0.105	4.111	31.7	0.118	4.620	
1-1/2" to 1-3/4"	36.2	0.100	3.915	30.6	0.122	4.776	
1-3/4" to 2"	44.0	0.073	2.858	38.5	0.088	3.445	
							1
25E	L	1		L		L	
0" to 1/4"	0.4	0.435	17.030	-1.8	0.460	18.009	
1/4" to 1/2"	14.3	0.248	9.709	9.8	0.290	11.354	
1/2" to 3/4"	22.9	0.173	6.773	18.0	0.205	8.026	
3/4" to 1"	36.2	0.100	3.915	31.7	0.118	4.620	
1" to 1-1/4"	43.7	0.074	2.897	41.0	0.080	3.132	
1-1/4" to 1-1/2"	45.8	0.068	2.662	42.4	0.075	2.936	
1-1/2" to 1-3/4"	41.3	0.081	3.171	37.5	0.092	3.602	
1-3/4" to 2"	47.5	0.064	2.506	44.0	0.070	2.741	
							1
25F							
0" to 1/4"	-0.9	0.455	17.813	-3.6	0.500	19.575	
1/4" to 1/2"	4.0	0.375	14.681	1.5	0.410	16.052	
1/2" to 3/4"	13.2	0.258	10.101	10.7	0.280	10.962	
3/4" to 1"	29.8	0.131	5.129	26.1	0.145	5.677	
1" to 1-1/4"	34.4	0.108	4.228	32.2	0.113	4.424	
1-1/4" to 1-1/2"	41.2	0.082	3.210	37.1	0.093	3.641	
	16 -	0.0	a a = :		0 6		
1-1/2" to 1-3/4" 1-3/4" to 2"	49.7 52.1	0.058	2.271 2.036	45.5 49.0	0.066 0.057	2.584 2.232	





Specimen #26 - 3 Month Exposure

Liquid	Clear	Purple	Green	Pink]		
%CL	0.005	0.02	0.05	0.5			Date:
mV before	99.2	73.6	51.5	-3.0	5 Minu	ite Test	2/2/2008
mV after	101.2	74.6	52.5	-3.2	5 IVIIII	ne rest	2/2/2008
mV before	99.4	73.1	51.2	-3.1	24 110	ur Test	2/3/2008
mV after	97.8	72.7	51.0	-4.1	24 П0	ui iest	2/3/2008
			Assume	d weight of	concrete =	145.0	lb/yd3
Sample No.		5 Minute Tes	st		24 Hour Tes	t	
		%Cl by	lb.		%Cl by	lb.	
	mV	mass of	Cl/yd ³	mV	mass of	Cl/yd ³	
		concrete	concrete		concrete	concrete	
26D		1	T	r	1	T	
0" to 1/4"	0.4	0.425	16.639	-2.9	0.470	18.401	
1/4" to 1/2"	16.6	0.218	8.535	13.7	0.235	9.200	
1/2" to 3/4"	19.3	0.190	7.439	15.2	0.222	8.691	
3/4" to 1"	28.4	0.132	5.168	24.6	0.150	5.873	
1" to 1-1/4"	36.3	0.094	3.680	32.2	0.109	4.267	
1-1/4" to 1-1/2"	38.7	0.086	3.367	32.3	0.108	4.228	
1-1/2" to 1-3/4"	42.1	0.074	2.897	37.9	0.086	3.367	
1-3/4" to 2"	46.7	0.062	2.427	40.0	0.079	3.093	
							1
26E		T	1	r	r	1	
0" to 1/4"	-0.4	0.440	17.226	-3.1	0.475	18.596	
1/4" to 1/2"	7.2	0.320	12.528	4.3	0.350	13.703	
1/2" to 3/4"	22.2	0.170	6.656	18.9	0.192	7.517	
3/4" to 1"	23.6	0.160	6.264	19.2	0.188	7.360	
1" to 1-1/4"	28.2	0.132	5.168	23.6	0.157	6.147	
1-1/4" to 1-1/2"	36.4	0.094	3.680	29.3	0.123	4.815	
1-1/2" to 1-3/4"	46.2	0.062	2.427	41.4	0.074	2.897	
1-3/4" to 2"	52.8	0.048	1.879	47.7	0.057	2.232	
							1
26F		1	1	1	1	1	
0" to 1/4"	2.4	0.390	15.269	0.8	0.410	16.052	
1/4" to 1/2"	10.2	0.280	10.962	7.7	0.307	12.019	
1/2" to 3/4"	19.3	0.190	7.439	15.5	0.220	8.613	
3/4" to 1"	28.0	0.133	5.207	24.1	0.153	5.990	
1" to 1-1/4"	38.8	0.086	3.367	33.1	0.104	4.072	
1-1/4" to 1-1/2"	43.8	0.069	2.701	40.6	0.077	3.015	
1-1/2" to 1-3/4"	42.6	0.073	2.858	36.8	0.090	3.524	
1-3/4" to 2"	41.4	0.076	2.975	35.2	0.096	3.758	

Specimen #27 - 3 Month Exposure

Liquid	Clear	Purple	Green	Pink]		
%CL	0.005	0.02	0.05	0.5			Date:
mV before	99.2	73.6	51.5	-3.0			
mV after	101.2	74.6	52.5	-3.2	5 Minu	ite Test	2/2/2008
mV before	99.4	73.1	51.2	-3.1	24.11	m (2/2/2000
mV after	97.8	72.7	51.0	-4.1	24 Hour Test		2/3/2008
	•	•	Assume	d weight of	concrete =	145.0	lb/yd3
Sample No.	4	5 Minute Tes	st	,	24 Hour Tes	t	
		%Cl by	lb.		%Cl by	lb.	
	mV	mass of	Cl/yd ³	mV	mass of	Cl/yd ³	
		concrete	concrete		concrete	concrete	
27D	1		r	1			
0" to 1/4"	-9.0	0.630	24.665	-14.2	0.750	29.363	
1/4" to 1/2"	5.2	0.342	13.389	0.5	0.410	16.052	
1/2" to 3/4"	18.2	0.200	7.830	14.0	0.235	9.200	
3/4" to 1"	26.4	0.142	5.559	21.2	0.171	6.695	
1" to 1-1/4"	28.2	0.132	5.168	24.0	0.154	6.029	
1-1/4" to 1-1/2"	36.1	0.095	3.719	32.4	0.108	4.228	
1-1/2" to 1-3/4"	35.8	0.096	3.758	32.3	0.109	4.267	
1-3/4" to 2"	44.6	0.067	2.623	40.3	0.078	3.054	
							1
27E							-
0" to 1/4"	-1.9	0.470	18.401	-5.4	0.530	20.750	
1/4" to 1/2"	10.4	0.280	10.962	6.5	0.320	12.528	
1/2" to 3/4"	18.0	0.200	7.830	12.8	0.248	9.709	
3/4" to 1"	29.2	0.128	5.011	25.8	0.143	5.598	
1" to 1-1/4"	40.8	0.079	3.093	37.9	0.086	3.367	
1-1/4" to 1-1/2"	43.9	0.070	2.741	39.3	0.081	3.171	
1-1/2" to 1-3/4"	47.3	0.060	2.349	42.7	0.071	2.780	
1-3/4" to 2"	54.9	0.044	1.723	52.1	0.048	1.879	J
							1
27F							
0" to 1/4"	-1.5	0.460	18.009	-5.4	0.530	20.750	
1/4" to 1/2"	12.7	0.255	9.983	8.6	0.292	11.432	
1/2" to 3/4"	16.9	0.212	8.300	12.5	0.250	9.788	
3/4" to 1"	33.0	0.105	4.111	28.2	0.129	5.050	
1" to 1-1/4"	40.9	0.078	3.054	36.2	0.092	3.602	
1-1/4" to 1-1/2"	42.6	0.073	2.858	38.5	0.084	3.289	
1-1/2" to 1-3/4"	49.2	0.055	2.153	46.4	0.060	2.349	
1-3/4" to 2"	50.6	0.051	1.997	46.9	0.059	2.310	

Specimen #28 - 3 Month Exposure


Liquid	Clear	Purple	Green	Pink]		
%CL	0.005	0.02	0.05	0.5			Date:
mV before	99.2	73.6	51.5	-3.0	5 M	4- T4	2/2/2009
mV after	101.2	74.6	52.5	-3.2	5 Mint	ite Test	2/2/2008
mV before	99.4	73.1	51.2	-3.1	24 Цо	ur Test	2/3/2008
mV after	97.8	72.7	51.0	-4.1	24 П0	ui iest	2/3/2008
			Assume	d weight of	concrete =	145.0	lb/yd3
Sample No.		5 Minute Tes	st		24 Hour Tes	t	
		%Cl by	lb.		%Cl by	lb.	
	mV	mass of	Cl/yd ³	mV	mass of	Cl/yd ³	
		concrete	concrete		concrete	concrete	
28D		1	1	1	1		
0" to 1/4"	-2.6	0.480	18.792	-4.9	0.508	19.888	
1/4" to 1/2"	8.0	0.310	12.137	3.1	0.367	14.368	
1/2" to 3/4"	24.6	0.154	6.029	21.9	0.168	6.577	
3/4" to 1"	38.7	0.086	3.367	35.7	0.094	3.680	
1" to 1-1/4"	41.5	0.076	2.975	37.5	0.087	3.406	
1-1/4" to 1-1/2"	41.2	0.077	3.015	35.0	0.097	3.798	
1-1/2" to 1-3/4"	43.1	0.072	2.819	38.8	0.084	3.289	
1-3/4" to 2"	44.9	0.066	2.584	42.0	0.072	2.819	
							1
28E	[1	1			[
0" to 1/4"	-1.3	0.046	1.801	-4.2	0.500	19.575	-
1/4" to 1/2"	12.0	0.026	1.018	8.5	0.295	11.549	-
1/2" to 3/4"	20.8	0.181	7.086	16.2	0.212	8.300	-
3/4" to 1"	31.2	0.118	4.620	25.6	0.142	5.559	-
1" to 1-1/4"	35.4	0.099	3.876	30.2	0.119	4.659	-
1-1/4" to 1-1/2"	39.7	0.082	3.210	35.1	0.097	3.798	
1-1/2" to 1-3/4"	38.7	0.086	3.367	34.8	0.099	3.876	-
1-3/4" to 2"	43.2	0.071	2.780	37.7	0.087	3.406	
							1
28F	[1	1			[
0" to 1/4"	-1.7	0.460	18.009	-4.3	0.500	19.575	
1/4" to 1/2"	11.2	0.270	10.571	8.0	0.300	11.745	
1/2" to 3/4"	19.9	0.189	7.399	16.7	0.210	8.222	
3/4" to 1"	26.8	0.142	5.559	22.6	0.163	6.381	
1" to 1-1/4"	25.0	0.152	5.951	20.6	0.178	6.969	
1-1/4" to 1-1/2"	26.8	0.142	5.559	21.1	0.171	6.695	
1-1/2" to 1-3/4"	41.7	0.076	2.975	38.6	0.084	3.289	
1-3/4" to 2"	45.3	0.065	2.545	39.2	0.081	3.171	J


Specimen #29 - 3 Month Exposure

					-		
Liquid	Clear	Purple	Green	Pink			
%CL	0.005	0.02	0.05	0.5			Date:
mV before	99.2	73.6	51.5	-3.0	5 Minu	ite Test	2/2/2008
mV after	101.2	74.6	52.5	-3.2	5 Millio	ile Test	2/2/2008
mV before	99.4	73.1	51.2	-3.1	24 Ho	ur Test	2/3/2008
mV after	97.8	72.7	51.0	-4.1	24 110	ui iest	2/3/2008
			Assume	d weight of	concrete =	145.0	lb/yd3
Sample No.	4	5 Minute Tes	st		24 Hour Tes	t	
		%Cl by	lb.		%Cl by	lb.	
	mV	mass of	Cl/yd ³	mV	mass of	Cl/yd ³	
		concrete	concrete		concrete	concrete	
29D	r	1			r		
0" to 1/4"	-1.2	0.455	17.813	-4.3	0.500	19.575	
1/4" to 1/2"	13.0	0.250	9.788	8.2	0.298	11.667	
1/2" to 3/4"	22.0	0.172	6.734	19.0	0.190	7.439	
3/4" to 1"	32.0	0.113	4.424	28.4	0.128	5.011	
1" to 1-1/4"	44.1	0.068	2.662	40.4	0.077	3.015	
1-1/4" to 1-1/2"	47.2	0.060	2.349	42.0	0.073	2.858	
1-1/2" to 1-3/4"	52.2	0.050	1.958	44.2	0.066	2.584	
1-3/4" to 2"	46.3	0.062	2.427	38.4	0.084	3.289	
							1
29E	1	1	1		1		
0" to 1/4"	-4.8	0.522	20.436	-7.9	0.580	22.707	
1/4" to 1/2"	7.3	0.320	12.528	2.0	0.385	15.073	
1/2" to 3/4"	18.2	0.200	7.830	14.2	0.231	9.044	
3/4" to 1"	32.8	0.110	4.307	29.3	0.124	4.855	
1" to 1-1/4"	37.0	0.092	3.602	30.6	0.117	4.581	
1-1/4" to 1-1/2"	39.6	0.083	3.249	33.7	0.104	4.072	
1-1/2" to 1-3/4"	43.4	0.070	2.741	35.9	0.094	3.680	
1-3/4" to 2"	47.7	0.059	2.310	41.7	0.073	2.858	
							1
29F	1	1			1	-	
0" to 1/4"	-1.0	0.450	17.618	-4.1	0.500	19.575	
1/4" to 1/2"	7.1	0.320	12.528	3.8	0.360	14.094	
1/2" to 3/4"	23.7	0.160	6.264	19.0	0.190	7.439	
3/4" to 1"	28.8	0.130	5.090	23.5	0.158	6.186	
4.0. 4.4.4.0	32.0	0.112	4.385	27.3	0.134	5.246	
1" to 1-1/4"							1
1-1/4" to 1-1/2"	41.7	0.076	2.975	39.0	0.082	3.210	
		0.076 0.061	2.975 2.388	39.0 46.2	0.082	3.210 2.349	

Specimen #30 - 3 Month Exposure

Liquid	Clear	Purple	Green	Pink]		
%CL	0.005	0.02	0.05	0.5			Date:
mV before	99.2	73.6	51.5	-3.0	5 Minu	ite Test	2/2/2008
mV after	101.2	74.6	52.5	-3.2	5 Mint	ite Test	2/2/2008
mV before	99.4	73.1	51.2	-3.1	24 Цо	ur Tost	2/3/2008
mV after	97.8	72.7	51.0	-4.1	24 Hour Test		2/3/2008
			Assume	d weight of	concrete =	145.0	lb/yd3
Sample No.	4	5 Minute Tes	st		24 Hour Tes	t	
		%Cl by	lb.		%Cl by	lb.	
	mV	mass of	Cl/yd ³	mV	mass of	Cl/yd ³	
		concrete	concrete		concrete	concrete	
30D		1	T	r	T	r	
0" to 1/4"	-3.3	0.500	19.575	-5.4	0.520	20.358	
1/4" to 1/2"	5.6	0.340	13.311	2.0	0.385	15.073	
1/2" to 3/4"	16.4	0.218	8.535	11.8	0.258	10.101	
3/4" to 1"	23.3	0.161	6.303	22.1	0.165	6.460	
1" to 1-1/4"	26.2	0.145	5.677	23.4	0.157	6.147	
1-1/4" to 1-1/2"	28.3	0.131	5.129	24.0	0.154	6.029	
1-1/2" to 1-3/4"	40.5	0.080	3.132	35.6	0.095	3.719	
1-3/4" to 2"	40.1	0.081	3.171	34.7	0.099	3.876	
							1
30E		1	1	1	1	1	
0" to 1/4"	3.8	0.370	14.486	1.4	0.395	15.464	
1/4" to 1/2"	13.4	0.248	9.709	9.9	0.275	10.766	
1/2" to 3/4"	24.1	0.156	6.107	21.4	0.170	6.656	
3/4" to 1"	36.8	0.093	3.641	32.0	0.108	4.228	
1" to 1-1/4"	38.8	0.086	3.367	32.5	0.107	4.189	
1-1/4" to 1-1/2"	34.4	0.102	3.993	30.0	0.120	4.698	
1-1/2" to 1-3/4"	26.0	0.147	5.755	22.6	0.165	6.460	
1-3/4" to 2"	29.4	0.127	4.972	27.1	0.134	5.246	
30F							
0" to 1/4"	0.1	0.430	16.835	-2.4	0.465	18.205	
1/4" to 1/2"	16.9	0.213	8.339	12.1	0.252	9.866	
1/2" to 3/4"	24.2	0.155	6.068	21.5	0.170	6.656	
3/4" to 1"	30.2	0.122	4.776	27.2	0.135	5.285	
1" to 1-1/4"	35.3	0.099	3.876	29.9	0.120	4.698	
1-1/4" to 1-1/2"	47.8	0.059	2.310	46.2	0.061	2.388	
1-1/2" to 1-3/4"	58.4	0.038	1.488	54.8	0.043	1.683	
1-3/4" to 2"	46.8	0.062	2.427	43.2	0.069	2.701	





(Page left blank intentionally)


APPENDIX F


CoC Chlorides at 6-Months

Liquid	Clear	Purple	Green	Pink]	By:
%CL	0.005	0.020	0.050	0.500	Patch Material	Date:
mV before	95.4	71.2	51.0	-5.5	5 Minute Test	8/25/2008
mV after	-	-	-	-	5 Williute Test	8/23/2008
mV before	99.0	72.7	49.8	-5.8	24 Hour Test	8/28/2008
mV after	-	-	-	-	24 Hour rest	8/28/2008
	lb/yd ³					
Sample No.	5	Minute Tree		24 Hann Tart	7	

MDP

	Averages:	0.006	0.252		0.008	0.331	
B 1"	101.6	0.005	0.176	99.8	0.005	0.214	
B 1/2"	85.7	0.009	0.360	81.6	0.012	0.470	
A 1"	101.0	0.005	0.181	94.9	0.007	0.264	
A 1/2"	90.5	0.007	0.290	86.6	0.010	0.378	
	mV	%Cl by mass of concrete	lb. Cl/yd ³ concrete	mV	%Cl by mass of concrete	lb. Cl/yd ³ concrete	
Sample No.	5 Minute Test			24 Hour Test			





	~		~		1		
Liquid	Clear	Purple	Green	Pink			By: MDP
%CL	0.005	0.020	0.050	0.500			Date:
mV before	101.6	73.9	51.2	-4.3	5 Minu	ite Test	10/28/2008
mV after	97.2	68.3	47.4	-8.1			
mV after	101.1	73.6	50.4	-4.7	24-Но	ur Test	11/4/2008
mV after	99.1	70.7	49.1	-6.4			
r				d weight of	concrete =	145.0	lb/cubic yard
Sample No.		5 Minute Tes	st	2	24 Hour Tes	t	
		%Cl by	lb.		%Cl by	lb.	
	mV	mass of	Cl/yd ³	mV	mass of	Cl/yd ³	
1.50		concrete	concrete		concrete	concrete	
17B							
0" to 1/4"	23.7	0.144	5.623	18.8	0.183	7.148	
1/4" to 1/2"	98.8	0.006	0.219	89.3	0.009	0.341	
1/2" to 3/4"	101.8	0.005	0.192	89.9	0.008	0.332	
3/4" to 1"	95.9	0.006	0.248	90.1	0.008	0.329	
1" to 1-1/4"	100.7	0.005	0.201	89.9	0.008	0.332	
1-1/4" to 1-1/2"	101.6	0.005	0.194	91.5	0.008	0.310	
1-1/2" to 1-3/4"	97.1	0.006	0.235	89.1	0.009	0.344	
1-3/4" to 2"	93.5	0.007	0.275	85.7	0.010	0.398	
17H							
0" to 1/4"	-2.7	0.450	17.609	-6.4	0.542	21.209	
1/4" to 1/2"	0.1	0.398	15.601	-1.5	0.438	17.166	
1/2" to 3/4"	6.8	0.298	11.677	4.5	0.338	13.250	
3/4" to 1"	13.3	0.225	8.816	12.2	0.243	9.503	
1" to 1-1/4"	24.2	0.141	5.503	20.7	0.168	6.585	
1-1/4" to 1-1/2"	27.4	0.122	4.792	26.6	0.130	5.105	
1-1/2" to 1-3/4"	29.0	0.114	4.471	25.0	0.140	5.470	
1-3/4" to 2"	30.4	0.108	4.209	27.0	0.128	5.017	
18B	12.2	0.060	0.400	26.4	0.005	2.244	
0" to 1/4"	43.2	0.062	2.420	36.4	0.085	3.344	
1/4" to 1/2"	99.4	0.005	0.213	88.2	0.009	0.358	
1/2" to 3/4"	104.8	0.004	0.169	91.9	0.008	0.305	
3/4" to 1"	105.5	0.004	0.164	94.7 94.9	0.007	0.270	
1" to 1-1/4"	106.8	0.004	0.155	94.9	0.007	0.268	•
1-1/4" to 1-1/2"	104.3	0.004	0.172	80.6	0.008	0.311	•
1-1/2" to 1-3/4" 1-3/4" to 2"	90.8	0.008		91.8	0.013	0.496	•
1-3/4" to 2"	103.7	0.005	0.177	71.0	0.008	0.306	•
	65	0.520	20 754	-8.1	0.592	22 022	
0" to 1/4" 1/4" to 1/2"	-6.5	0.530	20.754 14.941	0.1	0.583	22.823 16.021	•
1/4 to 1/2 1/2" to 3/4"	1.1 2.9	0.382	13.822	1.2	0.409	15.278	
3/4" to 1"	2.9 9.8	0.353	13.822	9.8	0.390	10.540	
1" to 1-1/4"	9.8	0.282	8.740	13.8	0.289	8.869	4
1-1/4" to 1-1/2"			7.041	17.4	0.227	7.593	•
	18.5 22.4	0.180		21.7		6.307	•
1-1/2" to $1-3/4$ "		0.152	5.948	29.0	0.161		
1-3/4" to 2"	30.8	0.106	4.137	29.0	0.118	4.602	J

Liquid	Clear	Dumla	Crean	Dinle	1		
Liquid %CL	Clear 0.005	Purple	Green	Pink 0.500			By: MDP
mV before	95.8	0.020 67.1	0.050 45.7	-9.4			Date:
mV after	93.8	67.7	43.7	-9.4	5 Minu	ite Test	10/29/2008
mV after	101.1	73.6	50.4	-4.7			
mV after	99.1	73.0	49.1	-4.7	24-Но	ur Test	11/4/2008
III v altei	<i>77</i> .1	/0./		-0.4 d weight of	concrete -	145.0	11- /1-:
Sample No.		Minuto To		-			lb/cubic yard
Sample No.		5 Minute Tes			24 Hour Tes		
	mV	%Cl by mass of	lb. Cl/yd ³	mV	%Cl by mass of	lb. Cl/yd ³	
	111 V	concrete	concrete	111 V	concrete	concrete	
23B							-
0" to 1/4"	53.7	0.035	1.354	51.8	0.044	1.720	•
1/4" to 1/2"	92.4	0.006	0.250	87.1	0.010	0.375	
1/2" to 3/4"	102.7	0.004	0.160	93.9	0.007	0.280	
3/4" to 1"	103.2	0.004	0.156	90.2	0.008	0.328	1
1" to 1-1/4"	93.5	0.006	0.239	89.8	0.009	0.334	
1-1/4" to 1-1/2"	99.9	0.005	0.180	93.0	0.007	0.291	
1-1/2" to 1-3/4"	102.9	0.004	0.158	94.8	0.007	0.269	
1-3/4" to 2"	97.8	0.005	0.198	91.5	0.008	0.310	
23Н							
0" to 1/4"	-1.1	0.378	14.781	-2.0	0.448	17.540	
1/4" to 1/2"	0.2	0.357	13.966	0.1	0.409	16.021	
1/2" to 3/4"	7.0	0.265	10.381	6.5	0.310	12.154	
3/4" to 1"	14.8	0.189	7.387	15.4	0.211	8.277	
1" to 1-1/4"	31.1	0.093	3.628	31.6	0.105	4.114	
1-1/4" to 1-1/2"	27.5	0.108	4.245	28.2	0.122	4.764	
1-1/2" to 1-3/4"	31.4	0.091	3.581	31.7	0.105	4.096	
1-3/4" to 2"	27.3	0.109	4.282	26.4	0.132	5.149	
24B		1				1	
0" to 1/4"	57.2	0.030	1.162	53.6	0.041	1.592	
1/4" to 1/2"	84.6	0.009	0.352	76.4	0.015	0.595	
1/2" to 3/4"	99.8	0.005	0.181	89.8	0.009	0.334	
3/4" to 1"	104.9	0.004	0.145	94.1	0.007	0.277	
1" to 1-1/4"	100.7	0.004	0.174	93.4	0.007	0.286	
1-1/4" to 1-1/2"	96.4	0.005	0.210	92.0	0.008	0.303	
1-1/2" to 1-3/4"	101.5	0.004	0.168	91.7	0.008	0.307	
1-3/4" to 2"	81.3	0.010	0.406	78.8	0.014	0.536	
24H				10.0			
0" to 1/4"	-12.6	0.623	24.409	-12.2	0.696	27.242	4
1/4" to 1/2"	-4.9	0.446	17.446	-4.4	0.497	19.455	4
1/2" to 3/4"	-0.5	0.368	14.399	-0.2	0.415	16.229	4
3/4" to 1"	-1.9	0.391	15.306	-1.7	0.442	17.315	4
1" to 1-1/4"	-12.8	0.629	24.623	-12.5	0.705	27.597	4
1-1/4" to 1-1/2"	-1.7	0.388	15.173	-0.8	0.425	16.655	4
1-1/2" to 1-3/4"	14.3	0.193	7.550	14.0	0.225	8.793	4
1-3/4" to 2"	26.6	0.113	4.415	25.3	0.138	5.399	J

	~1		~		7		
Liquid	Clear	Purple	Green	Pink	_		By
%CL	0.005	0.020	0.050	0.500	_		Date:
mV before	95.8	67.1	45.7	-9.4	5 Minu	ite Test	10/29/2008
mV after	97.2	67.7	47.5	-7.6	_		
mV after	95.0	65.0	45.5	-9.4	24-Ho	ur Test	11/5/2008
mV after	94.4	64.1	44.3	-9.2			
				d weight of		145.0	lb/cubic yard
Sample No.	-	5 Minute Tes			24 Hour Tes		
	* 7	%Cl by	lb.	X 7	%Cl by	lb.	
	mV	mass of concrete	Cl/yd ³ concrete	mV	mass of concrete	Cl/yd ³ concrete	
25B		concrete	concrete		concrete	concrete	
	82.2	0.010	0.201	74.6	0.012	0.406	
0" to 1/4"		0.010	0.391		0.013	0.496	
1/4" to 1/2" 1/2" to 3/4"	102.4 99.7	0.004 0.005	0.162 0.182	94.9 88.5	0.005	0.202 0.268	
3/4" to 1"				88.3 89.7		0.208	
1" to 1-1/4"	98.9 103.8	0.005	0.188	89.7 91.8	0.006	0.234	1
1-1/4" to 1-1/2"	103.8	0.004	0.132	93.2	0.006	0.232	
1-1/4 to 1-1/2 1-1/2" to 1-3/4"	98.8	0.004	0.149	93.2	0.000	0.218	
1-1/2 to 1-3/4 1-3/4" to 2"	104.5	0.003	0.139	90.1 95.9	0.005	0.230	
25H	104.5	0.004	0.140	93.9	0.005	0.195	
0" to 1/4"	-7.8	0.506	19.798	-9.5	0.521	20.403	
1/4" to 1/2"	-6.5	0.300	18.707	-7.3	0.473	18.512	
1/2" to 3/4"	2.7	0.320	12.523	2.1	0.312	12.218	
3/4" to 1"	17.0	0.320	6.711	15.5	0.173	6.758	
1" to 1-1/4"	27.6	0.108	4.227	24.0	0.119	4.641	
1-1/4" to 1-1/2"	29.2	0.101	3.942	25.7	0.110	4.305	
1-1/2" to 1-3/4"	34.0	0.082	3.197	28.3	0.098	3.838	
1-3/4" to 2"	39.4	0.065	2.526	31.4	0.085	3.346	
26B		•			•		
0" to 1/4"	84.9	0.009	0.347	74.9	0.012	0.489	
1/4" to 1/2"	95.4	0.006	0.220	88.7	0.007	0.266	
1/2" to 3/4"	101.7	0.004	0.167	91.2	0.006	0.238	
3/4" to 1"	103.8	0.004	0.152	91.9	0.006	0.231	
1" to 1-1/4"	106.3	0.003	0.136	93.5	0.005	0.215	
1-1/4" to 1-1/2"	103.5	0.004	0.154	90.8	0.006	0.242	
1-1/2" to 1-3/4"	100.6	0.004	0.175	89.6	0.007	0.255	
1-3/4" to 2"	102.7	0.004	0.160	90.5	0.006	0.246	
26H		1					
0" to 1/4"	-5.1	0.450	17.599	-8.1	0.490	19.179	
1/4" to 1/2"	-2.4	0.400	15.643	-4.3	0.414	16.213	
1/2" to 3/4"	4.8	0.292	11.427	2.7	0.304	11.899	
3/4" to 1"	15.7	0.181	7.103	13.5	0.189	7.382	
1" to 1-1/4"	31.4	0.091	3.581	28.6	0.097	3.787	
1-1/4" to 1-1/2"	43.9	0.053	2.076	38.4	0.063	2.456	
1-1/2" to 1-3/4"	36.4	0.074	2.879	30.9	0.087	3.421	4
1-3/4" to 2"	44.1	0.053	2.058	39.7	0.059	2.319	J

T · · 1	Cl	D 1	C	D' 1	1		
Liquid	Clear	Purple	Green	Pink			By: MDP
%CL mV before	0.005	0.020	0.050	0.500	-		Date:
mv before mV after	97.2	68.3	51.2 47.4	-4.3 -8.1	5 Minu	ite Test	10/28/2008
mV after					-		
mv after mV after	101.1	73.6	50.4	-4.7	24-Ho	ur Test	11/4/2008
mv alter	99.1	70.7	49.1	-6.4		145.0	
C I N				d weight of		145.0	lb/cubic yard
Sample No.	3	Minute Tes		2	24 Hour Tes		
	mV	%Cl by mass of	lb. Cl/yd ³	mV	%Cl by mass of	lb. Cl/yd ³	
	111 v	concrete	concrete	111 V	concrete	concrete	
27B		Contracto	Controlo		controlo	Controlo	
0" to 1/4"	27.4	0.122	4.792	25.6	0.136	5.330	-
1/4" to 1/2"	58.9	0.031	1.227	57.1	0.035	1.369	•
1/4 to 1/2 1/2" to 3/4"	78.7	0.013	0.521	75.0	0.035	0.632	1
3/4" to 1"	92.3	0.013	0.321	87.2	0.010	0.032	1
1" to 1-1/4"	92.3	0.007	0.290	93.5	0.010	0.373	1
1-1/4" to 1-1/2"	99.1	0.005	0.201	93.5	0.007	0.284	-
1-1/2" to 1-3/4"	99.1 96.6	0.006	0.210	90.4	0.008	0.307	-
1-1/2 to 1-3/4 1-3/4" to 2"	100.5	0.000	0.240	90.4	0.008	0.323	-
27H	100.5	0.005	0.203	92.0	0.007	0.293	-
0" to 1/4"	-3.7	0.470	18.387	-5.8	0.528	20.667	-
1/4" to 1/2"	-2.8	0.470	17.685	-2.5	0.328	17.923	-
1/4 to 1/2 1/2" to 3/4"		0.432					-
3/4" to 1"	0.0	0.400	15.669	0.5	0.402	15.746	
1" to 1-1/4"	14.9 15.6	0.210	8.227 7.981	15.2 16.0	0.213	8.349 8.066	-
1-1/4" to 1-1/2"	23.3	0.204	5.721	22.8	0.208	6.014	
1-1/2" to 1-3/4" 1-3/4" to 2"	28.9 30.5	0.115 0.107	4.491 4.191	28.1 29.3	0.122 0.116	4.785 4.543	
28B	30.5	0.107	4.191	29.5	0.110	4.343	-
0" to 1/4"	45.5	0.056	2.191	42.1	0.067	2.615	-
1/4" to 1/2"	43.5 99.9	0.005	0.208	92.8	0.007	0.293	-
1/4 to 1/2 1/2" to 3/4"		0.003		99.3			-
3/4" to 1"	104.5 105.7	0.004	0.171 0.162	99.3 97.5	0.006	0.221 0.239	4
1" to 1-1/4"	103.7	0.004	0.162	99.0	0.006	0.239	4
1-1/4" to 1-1/2"	107.0	0.004	0.149	96.8	0.000	0.224	1
1-1/2" to 1-3/4"	102.1	0.005	0.190	96.4	0.006	0.247	1
1-1/2 to 1-3/4 1-3/4" to 2"	100.8	0.005	0.201	94.3	0.000	0.231	1
28H	100.5	0.005	0.203	77.3	0.007	0.213	1
0" to 1/4"	-1.4	0.425	16.646	-4.2	0.493	19.288	1
1/4" to 1/2"	3.7	0.423	13.352	0.0	0.493	16.090	1
1/4" to 1/2 1/2" to 3/4"	4.8	0.325	12.732	4.0	0.346	13.539	1
3/4" to 1"	12.5	0.233	9.126	11.5	0.250	9.795	1
1" to 1-1/4"	12.5	0.233	8.051	14.3	0.220	8.680	1
1-1/4" to 1-1/2"	27.0	0.125	4.875	25.7	0.136	5.307	1
1-1/2" to 1-3/4"	33.2	0.095	3.729	28.9	0.130	4.622	1
1-3/4" to 2"	42.9	0.063	2.451	41.4	0.069	2.695	1
1-3/4 10 2	74.7	0.005	2.431	11.7	0.009	2.095	J

Liquid	Clear	Purple	Green	Pink
%CL	0.005	0.020	0.050	0.500
mV before	96.0	66.8	46.0	-8.9
mV after	97.0	66.4	47.4	-6.7
mV after	101.1	73.6	50.4	-4.7
mV after	99.1	70.7	49.1	-6.4

Date: 5 Minute Test 10/2/2008 24-Hour Test 11/4/2008

50.0 lb/yd^3

mV after	99.1	70.7	49.1	-6.4		
	Concrete weight =	145.0	lb/cubic ya	ard		Epoxy mortar weight =
Sample No.	5	Minute Tes	st	,	24 Hour Tes	
	mV	%Cl by mass of concrete	lb. Cl/yd ³ concrete	mV	%Cl by mass of concrete	lb. Cl/yd ³ concrete
29B/C					•	•
0" to 1/4"	129.7	0.001	0.048	130.8	0.001	0.020
1/4" to 1/2"	143.3	0.001	0.026	140.7	0.001	0.013
1/2" to 3/4"	149.4	0.001	0.020	146.2	0.001	0.010
3/4" to 1"	137.3	0.001	0.034	138.4	0.001	0.014
1" to 1-1/4"	141.8	0.001	0.028	138.0	0.001	0.014
1-1/4" to 1-1/2"	142.1	0.001	0.028	138.9	0.001	0.014
1-1/2" to 1-3/4"	134.9	0.001	0.038	139.3	0.001	0.014
1-3/4" to 2"	120.7	0.002	0.071	123.8	0.002	0.027
29H						
0" to 1/4"	-7.4	0.509	19.933	-7.1	0.558	21.859
1/4" to 1/2"	-6.2	0.483	18.907	-5.7	0.526	20.578
1/2" to 3/4"	-3.9	0.436	17.086	-4.3	0.495	19.371
3/4" to 1"	17.1	0.173	6.776	19.0	0.181	7.086
1" to 1-1/4"	28.3	0.106	4.138	29.8	0.114	4.446
1-1/4" to 1-1/2"	25.1	0.122	4.764	24.0	0.146	5.711
1-1/2" to 1-3/4"	30.0	0.098	3.839	28.5	0.120	4.703
1-3/4" to 2"	29.7	0.099	3.890	30.2	0.112	4.370
30B/C						-
0" to 1/4"	109.6	0.003	0.115	112.4	0.003	0.043
1/4" to 1/2"	134.5	0.001	0.039	139.7	0.001	0.013
1/2" to 3/4"	108.8	0.003	0.119	108.9	0.004	0.050
3/4" to 1"	68.8	0.018	0.695	72.8	0.018	0.240
1" to 1-1/4"	45.0	0.051	1.983	46.3	0.056	0.752
1-1/4" to 1-1/2"	50.9	0.039	1.529	50.7	0.046	0.622
1-1/2" to 1-3/4"	62.7	0.023	0.910	62.9	0.027	0.367
1-3/4" to 2"	59.6	0.027	1.043	61.4	0.029	0.392
30H					r	
0" to 1/4"	-4.1	0.440	17.237	-3.4	0.476	18.633
1/4" to 1/2"	6.8	0.272	10.665	7.7	0.295	11.540
1/2" to 3/4"	4.0	0.308	12.065	4.6	0.337	13.193
3/4" to 1"	-0.8	0.381	14.905	-1.2	0.433	16.945
1" to 1-1/4"	3.3	0.318	12.443	3.2	0.358	14.014
1-1/4" to 1-1/2"	8.2	0.256	10.028	8.5	0.285	11.149
1-1/2" to 1-3/4"	2.6	0.328	12.832	2.9	0.363	14.197
1-3/4" to 2"	2.5	0.329	12.889	3.2	0.358	14.014

By: MDP

301

Liquid	Clear	Purple	Green	Pink]		By: MDP
%CL	0.005	0.020	0.050	0.500			Date:
mV before	96.0	66.8	46.0	-8.9	5 M		11/2/2009
mV after	97.0	66.4	47.4	-6.7	5 Mint	ite Test	11/2/2008
mV after	101.1	73.6	50.4	-4.7	24 Цо	ur Test	11/4/2008
mV after	99.1	70.7	49.1	-6.4	24-110	ui iest	11/4/2008
			Assume	d weight of	concrete =	145.0	lb/cubic yard
Sample No.	4	5 Minute Tes	st	,	24 Hour Tes	t	
		%Cl by	lb.		%Cl by	lb.	
	mV	mass of	Cl/yd ³	mV	mass of	Cl/yd ³	
		concrete	concrete		concrete	concrete	
18i			r		1	r	
0" to 1/4"	-7.1	0.502	19.671	-7.5	0.568	22.240	
1/4" to 1/2"	3.3	0.318	12.443	2.8	0.364	14.258	
1/2" to 3/4"	5.4	0.290	11.344	4.7	0.336	13.136	
3/4" to 1"	14.6	0.193	7.565	13.9	0.226	8.831	
1" to 1-1/4"	29.7	0.099	3.890	28.3	0.121	4.743	
1-1/4" to 1-1/2"	33.8	0.083	3.248	31.5	0.106	4.132	
1-1/2" to 1-3/4"	41.6	0.059	2.303	40.9	0.070	2.754	
1-3/4" to 2"	44.5	0.052	2.027	45.1	0.059	2.297	
24i		1	r		1	n	
0" to 1/4"	-8.8	0.542	21.201	-8.8	0.601	23.523	
1/4" to 1/2"	-8.9	0.544	21.294	-9.3	0.614	24.037	
1/2" to 3/4"	-0.7	0.379	14.840	-1.5	0.438	17.166	
3/4" to 1"	8.1	0.257	10.072	7.1	0.303	11.843	
1" to 1-1/4"	9.6	0.241	9.428	9.4	0.274	10.724	
1-1/4" to 1-1/2"	4.3	0.304	11.907	3.6	0.352	13.774	
1-1/2" to 1-3/4"	13.0	0.207	8.117	12.5	0.240	9.381	
1-3/4" to 2"	31.4	0.092	3.610	30.7	0.109	4.277	
24G		1			1	1	
0" to 1/4"	-5.9	0.477	18.659	-5.7	0.526	20.578	
1/4" to 1/2"	-5.3	0.464	18.172	-5.1	0.512	20.052	
1/2" to 3/4"	8.6	0.252	9.853	8.0	0.291	11.392	
3/4" to 1"	15.0	0.190	7.433	14.6	0.219	8.568	
1" to 1-1/4"	14.3	0.196	7.665	13.8	0.227	8.869	
1-1/4" to 1-1/2"	17.1	0.173	6.776	15.2	0.213	8.349	
1-1/2" to 1-3/4"	15.4	0.187	7.303	14.7	0.218	8.531	
1-3/4" to 2"	27.3	0.110	4.324	26.5	0.131	5.127	J

Liquid	Clear	Purple	Green	Pink
1				
%CL	0.005	0.020	0.050	0.500
mV before	96.0	66.8	46.0	-8.9
mV after	97.0	66.4	47.4	-6.7
mV after	101.1	73.6	50.4	-4.7
mV after	99.1	70.7	49.1	-6.4

Date: 5 Minute Test 10/2/2008


11/4/2008 24-Hour Test

 lb/yd^3 50.0

mV after	99.1	70.7	49.1	-6.4		
	Concrete weight =	145.0	lb/cubic ya	ard		Epoxy mortar weight =
Sample No.	5	Minute Tes	st	/	24 Hour Tes	t
	mV	%Cl by mass of concrete	lb. Cl/yd ³ concrete	mV	%Cl by mass of concrete	lb. Cl/yd ³ concrete
30D						
0" to 1/4"	115.0	0.002	0.091	109.6	0.004	0.049
1/4" to 1/2"	139.0	0.001	0.032	138.7	0.001	0.014
1/2" to 3/4"	62.5	0.023	0.918	61.9	0.028	0.384
3/4" to 1"	27.8	0.108	4.230	30.6	0.110	1.481
1" to 1-1/4"	29.1	0.102	3.994	31.0	0.108	1.456
1-1/4" to 1-1/2"	44.2	0.052	2.054	43.0	0.064	0.867
1-1/2" to 1-3/4"	54.7	0.033	1.294	53.2	0.041	0.558
1-3/4" to 2"	90.9	0.007	0.263	87.5	0.009	0.127
30E						
0" to 1/4"	123.8	0.002	0.062	122.3	0.002	0.028
1/4" to 1/2"	142.5	0.001	0.027	140.7	0.001	0.013
1/2" to 3/4"	150.3	0.000	0.019	141.6	0.001	0.012
3/4" to 1"	140.7	0.001	0.029	137.3	0.001	0.015
1" to 1-1/4"	139.4	0.001	0.031	139.5	0.001	0.013
1-1/4" to 1-1/2"	153.9	0.000	0.016	142.9	0.001	0.012
1-1/2" to 1-3/4"	149.6	0.001	0.020	145.8	0.001	0.010
1-3/4" to 2"	153.3	0.000	0.017	148.2	0.001	0.009
30i						
0" to 1/4"	2.4	0.331	12.946	3.1	0.360	14.075
1/4" to 1/2"	4.3	0.304	11.907	4.5	0.338	13.250
1/2" to 3/4"	1.0	0.352	13.769	0.8	0.397	15.544
3/4" to 1"	10.1	0.236	9.223	9.7	0.270	10.586
1" to 1-1/4"	7.3	0.266	10.433	7.0	0.304	11.894
1-1/4" to 1-1/2"	0.6	0.358	14.014	0.1	0.409	16.021
1-1/2" to 1-3/4"	-6.8	0.496	19.413	-6.4	0.542	21.209
1-3/4" to 2"	-2.5	0.410	16.064	-2.2	0.452	17.693
30G						
0" to 1/4"	-4.6	0.450	17.620	-3.4	0.476	18.633
1/4" to 1/2"	2.0	0.337	13.176	0.5	0.402	15.746
1/2" to 3/4"	7.6	0.263	10.296	6.8	0.306	11.998
3/4" to 1"	13.5	0.203	7.940	12.7	0.238	9.300
1" to 1-1/4"	17.2	0.172	6.746	14.9	0.216	8.458
1-1/4" to 1-1/2"	23.1	0.133	5.203	21.1	0.165	6.472
1-1/2" to 1-3/4"	11.0	0.226	8.864	10.0	0.267	10.450
1-3/4" to 2"	10.5	0.231	9.062	9.3	0.275	10.770


5 Minute Test for #17, #18, #27, and #30

10/25/2008	0.005	0.020	0.050	0.500
mV before	101.6	73.9	51.2	-4.3
mV after	97.2	68.3	47.4	-8.1
mV average	99.4	71.1	49.3	-6.2




5 Minute Test for #23, #24, #25, and #26

10/29/2008	0.005	0.020	0.050	0.500
mV before	95.8	67.1	45.7	-9.4
mV after	97.2	67.7	47.5	-7.6
mV average	96.5	67.4	46.6	-8.5




5 Minute Test for #29, #30, #18i, #24(I,G), and #30(D,E,G,i)

11/2/2008	0.005	0.020	0.050	0.500
mV before	96.0	66.8	46.0	-8.9
mV after	97.0	66.4	47.4	-6.7
mV average	96.5	66.6	46.7	-7.8




24-Hour Test for #17, #18, #23, #24, #27, #28, #29, and #30								
11/4/2008	0.005	0.020	0.050	0.500				
mV before	101.1	73.6	50.4	-4.7				
mV after	99.1	70.7	49.1	-6.4				
mV average	100.1	72.2	49.8	-5.6				



24-Hour Test for #25 and #26


11/5/2008	0.005	0.020	0.050	0.500
mV before	95.0	65.0	45.5	-9.4
mV after	94.4	64.1	44.3	-9.2
mV average	94.7	64.6	44.9	-9.3




Liquid	Clear	Dumla	Green	Pink	1		
Liquid %CL	0.005	Purple 0.020	0.050	0.500	-		By: MDP
mV before	102.3	73.6	53.1	-3.8			Date:
mV after	102.5		e attached	-5.0	5 Minu	ite Test	10/31/2008
mV befre	94.4	64.1	44.3	-9.2	-		
mV after	74.4		e attached	-7.2	24-Но	ur Test	11/5/2008
in v uter		vanes s		d weight of	concrete =	145.0	lb/cubic yard
Sample No.	4	5 Minute Tes		-	24 Hour Tes		
Sumple 100.		%Cl by	lb.		%Cl by	lb.	
	mV	mass of	Cl/yd^3	mV	mass of	Cl/yd ³	
		concrete	concrete		concrete	concrete	
19B							
0" to 1/4"	40.2	0.031	1.222	20.4	0.065	2.526	
1/4" to 1/2"	88.1	0.004	0.165	78.3	0.007	0.286	
1/2" to 3/4"	97.4	0.004	0.144	90.7	0.006	0.238]
3/4" to 1"	90.9	0.005	0.192	85.8	0.008	0.296	
1" to 1-1/4"	95.0	0.004	0.160	91.3	0.006	0.232	
1-1/4" to 1-1/2"	95.3	0.004	0.158	92.9	0.006	0.216	ļ
1-1/2" to 1-3/4"	92.8	0.005	0.176	87.6	0.007	0.273	
1-3/4" to 2"	97.1	0.004	0.146	92.5	0.006	0.220	
19H		T	r	1	1	1	
0" to 1/4"	-17.1	0.305	11.944	-23.0	0.496	19.424	
1/4" to 1/2"	-6.8	0.274	10.724	-15.5	0.518	20.272	
1/2" to 3/4"	8.0	0.215	8.421	8.3	0.236	9.234	-
3/4" to 1"	16.7	0.147	5.745	17.6	0.156	6.110	-
1" to 1-1/4"	18.1	0.138	5.402	18.8	0.148	5.793	-
1-1/4" to 1-1/2"	29.3	0.084	3.302	27.7	0.100	3.902	-
1-1/2" to 1-3/4"	36.6	0.061	2.395	34.3	0.074	2.911	
1-3/4" to 2"	41.4	0.050	1.940	39.8	0.058	2.280	
20B				10 7			-
0" to 1/4"	58.8	0.014	0.540	40.7	0.025	0.973	4
1/4" to 1/2"	98.7	0.003	0.104	85.9	0.005	0.202	4
1/2" to 3/4"	92.3	0.005	0.180	86.8	0.007	0.283	4
3/4" to 1"	89.4	0.005	0.205	86.5	0.007	0.287	4
1" to 1-1/4"	89.1	0.005	0.208	92.1	0.006	0.224	4
1-1/4" to 1-1/2"	91.9	0.005	0.183	89.4 80.7	0.006	0.252	4
1-1/2" to $1-3/4$ "	88.7	0.005	0.211	89.7 88.9	0.006	0.249	4
1-3/4" to 2" 20H	88.6	0.005	0.212	00.9	0.007	0.258	1
0" to 1/4"	-40.4	0.850	32 761	-39.5	1.077	42.183	4
1/4" to 1/2"	-40.4	0.850	33.264 13.479	-39.3	0.515	42.185 20.181	4
1/4 to 1/2 1/2" to 3/4"	-12.0	0.344	17.984	-13.4	0.313	18.178	1
3/4" to 1"	-12.4 -9.8	0.439	16.042	-11.6	0.464	16.981	1
1" to 1-1/4"	6.1	0.204	7.974	5.0	0.204	7.988	1
1-1/4" to 1-1/2"	10.7	0.166	6.514	8.3	0.176	6.876	1
1-1/4 to $1-1/21-1/2$ " to $1-3/4$ "	19.6	0.100	4.405	18.1	0.113	4.405	1
1-3/4" to 2"	28.4	0.076	8.421	24.8	0.083	3.249	1
	- 21 .			1	0.000		1

Liquid	Clear	Dumla	Groop	Dink	1		
%CL	0.005	Purple 0.020	Green 0.050	Pink 0.500			By: MDP Date:
mV before	102.3	73.6	53.1	-3.8			Date:
mV after	102.5		ee attached	-5.0	5 Minu	ite Test	10/31/2008
mV before	94.4	64.1	44.3	-9.2	-		
mV after	2		ee attached		- 24-Ho	ur Test	11/5/2008
				d weight of	concrete =	145.0	lb/cubic yard
Sample No.		5 Minute Te		-	24 Hour Tes		
		%Cl by	lb.		%Cl by	lb.	
	mV	mass of	Cl/yd ³	mV	mass of	Cl/yd ³	
		concrete	concrete		concrete	concrete	
21B		-	-	-		-	
0" to 1/4"	68.3	0.009	0.355	64.5	0.008	0.318	
1/4" to 1/2"	95.4	0.003	0.120	84.6	0.005	0.215	
1/2" to 3/4"	92.8	0.005	0.202	84.9	0.006	0.251	
3/4" to 1"	100.9	0.004	0.142	90.5	0.005	0.195	
1" to 1-1/4"	102.7	0.003	0.131	91.8	0.005	0.183	
1-1/4" to 1-1/2"	74.0	0.012	0.463	66.3	0.015	0.580	-
1-1/2" to 1-3/4"	85.2	0.007	0.283	76.7	0.009	0.363	
1-3/4" to 2"	98.3	0.004	0.159	88.3	0.005	0.215	
21H	27.4	0.000		10.0	1.0-0	10	
0" to 1/4"	-35.6	0.688	26.936	-43.0	1.270	49.725	
1/4" to 1/2"	6.1	0.155	6.083	-5.6	0.330	12.929	
1/2" to 3/4" 3/4" to 1"	8.8 15.7	0.181	7.082 5.229	7.8	0.208	8.134	
1" to 1-1/4"	24.0	0.134 0.093	3.630	15.8 25.1	0.143	5.669 3.725	-
1-1/4" to 1-1/2"	31.4	0.067	2.622	29.0	0.095	3.124	-
1-1/2" to 1-3/4"	41.9	0.042	1.653	36.2	0.058	2.257	
1-3/4" to 2"	41.4	0.043	1.690	40.7	0.047	1.842	•
22B							
0" to 1/4"	41.2	0.030	1.170	37.0	0.030	1.158	
1/4" to 1/2"	85.3	0.005	0.187	77.5	0.008	0.296	
1/2" to 3/4"	95.9	0.005	0.177	88.5	0.005	0.213	
3/4" to 1"	94.5	0.005	0.188	87.3	0.006	0.225	
1" to 1-1/4"	94.6	0.005	0.187	89.3	0.005	0.205	
1-1/4" to 1-1/2"	96.4	0.004	0.173	88.9	0.005	0.209	
1-1/2" to 1-3/4"	93.9	0.005	0.193	86.2	0.006	0.236	
1-3/4" to 2"	99.7	0.004	0.150	92.6	0.005	0.177	-
22H		1					
0" to 1/4"	-37.7	0.755	29.541	-43.7	1.313	51.388	4
1/4" to 1/2"	-11.3	0.334	13.070	-13.1	0.464	18.178	4
1/2" to 3/4"	-10.4	0.421	16.470	-9.7	0.458	17.922	4
3/4" to 1"	3.2	0.231	9.059	3.0 9.6	0.258	10.102	1
1" to 1-1/4"	9.4	0.176	6.897 3.964	21.8	0.192	7.499	1
1-1/4" to 1-1/2" 1-1/2" to 1-3/4"	22.0 30.5	0.101 0.070	3.964 2.728	33.0	0.110 0.067	4.324 2.608	1
1-1/2 to 1-3/4 1-3/4" to 2"	30.3	0.070	2.728	32.2	0.067	2.008	1
1-3/4 to 2	50.5	0.070	2.132	32.2	0.009	2.704	J

After 22H (all tests):



Calibration values based on difference of 0.050% Cl checks. 21H, 22H, 20B, 20H, 19B avg. = 39.0 Avg. change = 3.1 0.005 0.020 0.050 0.500 89.3 59.9 39.0 -15.0





.050% =30.1 Significant change, calibrations redone: .005% = 92.4 .020% = 63.0 .050% = 42.1 -11.9 .500% =All 1/4" & 1/2" samples to be tested at end. After 22B Tests: .005% = 41.8 After 21B Tests: .005% = 42.5 After 21H Tests: .005% = 38.9 After 22H Tests: .005% =39.1 After 20B Tests: .005% = 37.0 After 20H Tests: .005% = 39.6 After 19B Tests: .005% = 40.2 After 19H Tests: .005% = 41.5 After 1/2" Tests:


.005% = 32.8 After 1/4" Tests (B): .005% = 30.4 After 1/4" Tests (H): .020% = 46.5 .050% = 24.3


5 Minute Test: Tests at depth of 1/2"

10/31/2008	Change a	t .050% Cl =	9.3	
	0.005	0.020	0.050	0.500
	83.1	53.7	32.8	-21.2














Change a	t .020% Cl =	16.5		Change at .050% Cl =	17.8
0.005	0.020	0.050	0.500	Avg. Change =	17.2
75.3	45.9	25.0	-29.1		





0.005	0.020	0.050	0.500	
90.4	58.8	40.4	-11.9	



By: MDP 1/4" and 1/2" tests performed at end.

After 19H Tests: .05 =43.5 After 19B Tests: .05 = 43.0 After 20B Tests: .05 = 43.3 After 21H Tests: .05 = 39.7 After 21B Tests: 0.005 =90.4 .02 = 58.8 .05 = 40.4 .50 = -11.9 After 22B Tests: .05 =40.4 After 22H Tests: .05 = 39.3 After 20H Tests: .005= 87.0 .02 = 55.8 .05 = 35.7 .50 = -14.5 After 1/2"(B) Tests: .05 = 35.4 After 1/2"(H) Tests: 35.0 .05 = After 1/4"(B) Tests: .05 = 24.1 After 1/4"(H) Tests: .005= 76.7

.02 =


.05 =


.50 =

43.9

23.8

-21.6







(Page left blank intentionally)

APPENDIX G


Bridge Deck Chlorides



1	Liquid	Clear	Purple	Green	Pink]		Bridge B-	14-0110
	%CL	0.005	0.020	0.050	0.500			Date:	
	mV before	95.8	69.2	46.9	-8.7		-		
	mV after	95.5	71.0	48.5	-7.1	5 Minute	l'est	8/5/2008	
	mV before	94.6	69.4	48.0	-5.9			0/0/2000	
	mV after	95.7	70.2	49.1	-6.4	24 Hour T	est	8/8/2008	
	Assume	d weight of	concrete =	145.0	lb/cubic y	ard			By: M
	Sample No.	4	5 Minute Te	st		24 Hour Tes	t		
	А	mV	%CL	lb. Cl	mV	%CL	lb. Cl		
	0" to 1/4"	-9.1	0.562	21.992	-9.8	0.630	24.655		
	1/4" to 1/2"	2.7	0.335	13.119	3.0	0.355	13.891		
	1/2" to 3/4"	3.4	0.325	12.723	4.5	0.332	12.988		
	3/4" to 1"	6.6	0.283	11.060	7.2	0.294	11.508		
	1" to 1-1/4"	15.3	0.193	7.557	16.4	0.195	7.619		
	1-1/4" to 1-1/2"	27.6	0.113	4.410	27.9	0.116	4.551		
	1-1/2" to 1-3/4"	35.9	0.078	3.067	35.0	0.085	3.310		
Į	1-3/4" to 2"	47.4	0.047	1.854	45.8	0.052	2.040		
1								1	
	Sample No.		5 Minute Te			24 Hour Tes			
	В	mV	%CL	lb. Cl	mV	%CL	lb. Cl		
	0" to 1/4"	-10.8	0.605	23.691	-11.5	0.680	26.607		
	1/4" to 1/2"	-6.5	0.501	19.626	-5.8	0.526	20.608		
	1/2" to 3/4"	4.9	0.304	11.915	5.6	0.316	12.363		
	3/4" to 1"	8.6	0.259	10.133	8.1	0.282	11.053		
	1" to 1-1/4"	5.1	0.302	11.811	5.3	0.320	12.531		
	1-1/4" to 1-1/2"	9.4	0.250	9.784	10.0	0.259	10.151		
	1-1/2" to 1-3/4"	19.5	0.161	6.288	19.8	0.167	6.542		
ļ	1-3/4" to 2"	25.0	0.126	4.942	24.2	0.137	5.371	J	
1	Comple No		- M ² / T			04.II T		1	
	Sample No. C		5 Minute Te			24 Hour Tes			
	-	mV	%CL	lb. Cl	mV	%CL	lb. Cl	-	
	0" to $1/4"$	-12.1 -6.2	0.641 0.495	25.079	-11.4	0.677	26.488		
	1/4" to 1/2" 1/2" to 3/4"	-0.2	0.493	19.370 21.235	-5.9 -7.1	0.529	20.701 21.845		
	3/4" to 1"	-8.5	0.524	20.504	-7.1	0.589	23.052		
	1" to 1-1/4"	-1.7	0.324	15.906	-0.6	0.339	16.324		
	1-1/4" to 1-1/2"	14.1	0.203	7.964	15.0	0.207	8.113		
	1-1/2" to 1-3/4"	10.8	0.235	9.202	11.5	0.242	9.491		
	1-3/4" to 2"	28.3	0.109	4.277	29.1	0.110	4.312		
ļ	1 5/4 10 2	20.5	0.109	4.277	29.1	0.110	4.512	1	
1	Sample No.		5 Minute Te	st		24 Hour Tes	t	1	
	D	mV	%CL	lb. Cl	mV	%CL	lb. Cl	1	
ļ	0" to 1/4"	-7.9	0.533	20.867	-8.2	0.586	22.948	1	
ļ	1/4" to 1/2"	-9.8	0.579	22.677	-9.9	0.633	24.765	1	
ļ	1/2" to 3/4"	-4.5	0.459	17.981	-4.7	0.501	19.617	1	
	3/4" to 1"	2.0	0.346	13.528	3.2	0.352	13.767	1	
	1" to 1-1/4"	5.0	0.303	11.863	5.5	0.317	12.419	1	
ļ	1-1/4" to 1-1/2"	13.1	0.213	8.321	13.6	0.221	8.638	1	
ļ	1-1/2" to 1-3/4"	11.2	0.231	9.043	10.0	0.259	10.151	1	
ļ	1-3/4" to 2"	20.0	0.157	6.151	20.6	0.161	6.312]	
1				-					




Liquid	Clear	Purple	Green	Pink	1		Bridge B	-14-0115
%CL	0.005	0.020	0.050	0.500	-		Date:	-14-0115
mV before	95.8	69.2	46.9	-8.7	-			
mV after	95.5	71.0	48.5	-7.1	5 Minute	Fest	8/5/2008	
mV before	94.6	69.4	48.0	-5.9	-			
mV after	95.7	70.2	49.1	-6.4	24 Hour T	est	8/8/2008	
	ed weight of		145.0	lb/cubic y	ard			By: MDI
Sample No.	-	5 Minute Tes			24 Hour Tes	t]	5
A	mV	%CL	lb. Cl	mV	%CL	lb. Cl		
0" to 1/4"	2.5	0.338	13.235	1.9	0.373	14.593		
1/4" to 1/2"	5.2	0.300	11.759	6.1	0.309	12.089		
1/2" to 3/4"	3.3	0.326	12.779	2.5	0.363	14.206		
3/4" to 1"	13.4	0.210	8.212	15.4	0.204	7.969		
1" to 1-1/4"	12.8	0.215	8.431	12.5	0.232	9.075		
1-1/4" to 1-1/2"	24.1	0.131	5.141	24.3	0.137	5.347		
1-1/2" to 1-3/4"	19.6	0.160	6.260	19.8	0.167	6.542		
1-3/4" to 2"	17.9	0.172	6.744	17.0	0.189	7.417		
							-	
Sample No.		5 Minute Tes	st		24 Hour Tes	t		
В	mV	%CL	lb. Cl	mV	%CL	lb. Cl		
0" to 1/4"	-1.3	0.399	15.630	-1.9	0.442	17.303		
1/4" to 1/2"	-4.2	0.453	17.746	-3.7	0.479	18.757		
1/2" to 3/4"	-5.5	0.480	18.785	-5.9	0.529	20.701		
3/4" to 1"	0.0	0.377	14.765	-0.8	0.421	16.471		
1" to 1-1/4"	12.5	0.218	8.542	11.4	0.244	9.533		
1-1/4" to 1-1/2"	19.3	0.162	6.343	18.0	0.181	7.092		
1-1/2" to 1-3/4"	20.1	0.156	6.125	19.7	0.168	6.572		
1-3/4" to 2"	27.4	0.114	4.449	26.2	0.125	4.911		
							1	
Sample No.		5 Minute Tes			24 Hour Tes		-	
С	mV	%CL	lb. Cl	mV	%CL	lb. Cl		
0" to 1/4"	1.4	0.355	13.888	0.7	0.393	15.400		
1/4" to 1/2"	-6.1	0.493	19.285	-6.6	0.546	21.360	-	
1/2" to 3/4"	5.8	0.293	11.454	6.1	0.309	12.089	-	
3/4" to 1"	7.1	0.276	10.821	7.5	0.290	11.354	-	
1" to 1-1/4"	8.2	0.263	10.312	9.0	0.271	10.616	-	
1-1/4" to 1-1/2"	10.4	0.239	9.365	10.3	0.256	10.015	-	
1-1/2" to 1-3/4"	14.9	0.196	7.690	15.5	0.203	7.933		
1-3/4" to 2"	24.7	0.128	5.007	25.1	0.132	5.159		
Courselo No		5 M ² / T		1	0411 T		1	
Sample No.		5 Minute Tes			24 Hour Tes		-	
0" to 1/4"	mV	%CL	lb. Cl	mV	%CL	lb. Cl	-	
1/4" to 1/2"	-7.7	0.528	20.685	-9.4	0.619	24.217 19.442		
-	-2.9		16.764	-4.5	0.497			
1/2" to 3/4"	8.7	0.258	10.089	9.0	0.271	10.616	-	
3/4" to 1"	20.5	0.154	6.018	19.8	0.167	6.542	-	
1" to 1-1/4" 1-1/4" to 1-1/2"	20.1 13.5	0.156 0.209	6.125 8.176	20.6 12.2	0.161	6.312	-	
1-1/4 to 1-1/2 1-1/2" to 1-3/4"	23.2	0.209	8.176 5.347			9.197 5.928	4	
1-1/2 to 1-3/4 1-3/4" to 2"	36.0	0.137	5.347	22.0	0.151 0.082	3.208	-	
1-3/4 l0 2	30.0	0.078	3.053	35.7	0.082	3.208]	




Liquid	Clear	Purple	Green	Pink	1		Bridge B-14-0119
%CL	0.005	0.020	0.050	0.500	-		Date:
mV before	95.8	69.2	46.9	-8.7	-		Date.
mV after	95.5	71.0	48.5	-7.1	5 Minute Te	est	8/5/2008
mV before	94.6	69.4	48.0	-5.9	-		
mV after	95.7	70.2	49.1	-6.4	24 Hour Tes	st	8/8/2008
		of concrete =		lb/cubic yai	_ rd		By: 1
Sample No.		5 Minute Te			24 Hour Tes	t]
A	mV	%CL	lb. Cl	mV	%CL	lb. Cl	_
0" to 1/4"	-10.5	0.597	23.382	-11.9	0.692	27.088	_
1/4" to 1/2"	1.8	0.349	13.647	2.0	0.371	14.528	
1/2" to 3/4"	12.7	0.216	8.468	13.3	0.224	8.755	
3/4" to 1"	8.1	0.265	10.357	8.8	0.274	10.711	
1" to 1-1/4"	14.6	0.199	7.792	13.9	0.218	8.523	
1-1/4" to 1-1/2"	11.0	0.233	9.122	9.3	0.268	10.474	
1-1/2" to 1-3/4"	25.6	0.123	4.814	24.2	0.137	5.371	
1-3/4" to 2"	34.8	0.082	3.218	34.4	0.087	3.400	
Sample No.		5 Minute Te	st		24 Hour Tes	t	
В	mV	%CL	lb. Cl	mV	%CL	lb. Cl	
0" to 1/4"	-1.6	0.405	15.837	-1.5	0.434	16.996	
1/4" to 1/2"	-3.5	0.440	17.210	-4.1	0.488	19.096	
1/2" to 3/4"	8.9	0.255	10.001	9.0	0.271	10.616	
3/4" to 1"	11.3	0.230	9.003	11.2	0.246	9.619	
1" to 1-1/4"	17.7	0.174	6.803	16.6	0.193	7.551	
1-1/4" to 1-1/2"	18.5	0.168	6.569	17.2	0.188	7.351	
1-1/2" to 1-3/4"	29.4	0.104	4.076	27.6	0.118	4.612	
1-3/4" to 2"	44.1	0.055	2.142	41.5	0.063	2.474	
							_
Sample No.	-	5 Minute Te	st		24 Hour Tes	t	
C	mV	%CL	lb. Cl	mV	%CL	lb. Cl	
0" to 1/4"	3.8	0.319	12.502	3.5	0.347	13.584	
1/4" to 1/2"	-9.4	0.569	22.283	-10.6	0.653	25.555	_
1/2" to 3/4"	6.7	0.281	11.012	6.1	0.309	12.089	_
3/4" to 1"	11.0	0.233	9.122	9.9	0.260	10.196	4
1" to 1-1/4"	17.4	0.176	6.893	15.0	0.207	8.113	_
1-1/4" to 1-1/2"	29.3	0.105	4.094	27.5	0.118	4.633	_
1-1/2" to 1-3/4"	39.5	0.067	2.619	36.6	0.079	3.081	_
1-3/4" to 2"	52.1	0.039	1.509	48.0	0.047	1.848	
Sample No.		5 Minute Te	-+	T	24 Hour Tes	+	7
D	mV	%CL	lb. Cl	mV	%CL	lb. Cl	_
0" to 1/4"	-15.4	0.740	28.977	-15.8	0.824	32.262	_
1/4" to 1/2"	-1.7	0.406	15.906	-1.6	0.436	17.072	_
1/4 to 1/2 1/2" to 3/4"	-4.5	0.400	17.981	-4.9	0.430	19.793	-
3/4" to 1"	1.3	0.356	13.949	0.7	0.393	15.400	-
1" to 1-1/4"	16.1	0.330	7.297	15.5	0.203	7.933	-1
1-1/4" to 1-1/2"	16.9	0.180	7.046	16.1	0.197	7.722	1
1-1/2" to 1-3/4"	18.8	0.166	6.483	17.9	0.197	7.122	1
1-3/4" to 2"	27.6	0.113	4.410	26.0	0.102	4.955	1
10,102	-7.0	0.110		_0.0	0.127		


:	5-Minute T	est for B-14-	0110, B-14-(0115, & B-14-01	19
%Cl	0.005	0.020	0.050	0.500	
mV before	95.8	69.2	46.9	-8.7	
mV after	95.5	71.0	48.5	-7.1	
mV average	95.7	70.1	47.7	-7.9	



24-Hour Test for B-14-0110, B-14-0115, & B-14-0119


%	Cl 0.005	0.020	0.050	0.500	
mV	before 94.6	69.4	48.0	-5.9	
m	V after 95.7	70.2	49.1	-6.4	
mV a	verage 95.2	69.8	48.6	-6.2	







Liquid	Clear	Purple	Green	Pink	7		Bridge B-14-	0120
%CL	0.0	0.02	0.05	0.5	_		Date:	0129
mV before	98.8	74.4	51.8	-3.9	_		Date.	
mV after	99.8	73.2	51.7	-4.0	-5 Minute Te	st	11/17/2007	
mV before	100.3	74.6	52.2	-4.0	_			
mV after	98.1	71.6	49.6	-3.8	-24 Hour Tes	t	11/18/2007	
		71.0		lb/cubic ya	rd.			By: MDP
Sample No.		5 Minute Tes			24 Hour Tes	t	٦	by. MDI
A A	mV	%CL	lb. Cl	mV	%CL	lb. Cl	_	
0" to 1/4"	-4.7	0.520	20.358	-6.8	0.560	21.924	^a 0.10g short	
1/4" to 1/2"	-3.9	0.520	19.575	-4.8	0.520	20.358	0.10g short	
1/2" to 3/4"	5.3	0.340	13.311	2.8	0.365	14.290		
3/4" to 1"	11.1	0.270	10.571	8.9	0.285	11.158	_	
1" to 1-1/4"	19.9	0.185	7.243	17.3	0.200	7.830	-	
1-1/4" to 1-1/2"	30.8	0.118	4.620	27.2	0.135	5.285	_	
1-1/4" to 1-1/2 1-1/2" to 1-3/4"	50.5	0.053	2.075	46.7	0.060	2.349	_	
1-3/4" to 2"	60.7	0.033	1.331	56.2	0.040	1.566	_	
1-3/4 10 2	00.7	0.034	1.551	50.2	0.040	1.500		
Sample No.	4	5 Minute Tes	at		24 Hour Tes	t	٦	
B	mV	%CL	lb. Cl	mV	%CL	lb. Cl		
0" to 1/4"	6.5	0.325	12.724	4.4	0.340	13.311	-	
1/4" to 1/2"	-0.6	0.435	17.030	-1.5	0.340	17.226	-	
1/2" to 3/4"	4.0	0.360	14.094	0.8	0.395	15.464		
3/4" to 1"	7.4	0.310	12.137	5.6	0.325	12.724		
1" to 1-1/4"	15.3	0.225	8.809	14.0	0.230	9.005		
1-1/4" to 1-1/2"	28.0	0.133	5.207	26.5	0.137	5.364	_	
1-1/2" to 1-3/4"	37.4	0.090	3.524	33.9	0.100	3.915	_	
1-3/4" to 2"	51.4	0.052	2.036	47.0	0.059	2.310	_	
Sample No.	4	5 Minute Tes	st		24 Hour Tes	t		
C	mV	%CL	lb. Cl	mV	%CL	lb. Cl		
0" to 1/4"	-5.6	0.550	21.533	-7.9	0.580	22.707		
1/4" to 1/2"	0.2	0.420	16.443	-1.7	0.440	17.226		
1/2" to 3/4"	7.1	0.320	12.528	5.4	0.330	12.920		
3/4" to 1"	16.1	0.220	8.613	12.3	0.247	9.670		
1" to 1-1/4"	19.9	0.185	7.243	17.1	0.200	7.830		
1-1/4" to 1-1/2"	26.1	0.145	5.677	22.2	0.162	6.342		
1-1/2" to 1-3/4"	44.0	0.069	2.701	40.6	0.078	3.054		
1-3/4" to 2"	61.3	0.034	1.331	58.2	0.037	1.449		
Sample No.		5 Minute Tes	st		24 Hour Tes	t		
D	mV	%CL	lb. Cl	mV	%CL	lb. Cl		
0" to 1/4"	-0.2	0.420	16.443	-3.7	0.480	18.792		
1/4" to 1/2"	1.9	0.390	15.269	-1.4	0.435	17.030		
1/2" to 3/4"	8.6	0.300	11.745	3.9	0.350	13.703		
3/4" to 1"	14.8	0.230	9.005	13.3	0.235	9.200		
1" to 1-1/4"	22.3	0.170	6.656	19.2	0.185	7.243		
1-1/4" to 1-1/2"	27.0	0.140	5.481	23.7	0.155	6.068		
1-1/2" to 1-3/4"	44.3	0.069	2.701	42.7	0.071	2.780		
1-3/4" to 2"	59.8	0.035	1.370	57.8	0.038	1.488		

Sample No.	-	Minute Tes	st		24 Hour Tes	ŀ	Bridge B-14-0129
E	mV	%CL	lb. Cl	mV	%CL	lb. Cl	
0" to 1/4"	-5.8	0.540	21.141	-7.7	0.570	22.316	By: MDP
1/4" to 1/2"	-3.0	0.480	18.792	-4.2	0.500	19.575	
1/2" to 3/4"	0.2	0.420	16.443	-1.9	0.450	17.618	
3/4" to 1"	11.0	0.265	10.375	9.9	0.270	10.571	
1" to 1-1/4"	18.4	0.200	7.830	15.1	0.221	8.652	
1-1/4" to 1-1/2"	33.9	0.105	4.111	28.5	0.126	4.933	
1-1/2" to 1-3/4"	39.4	0.084	3.289	37.9	0.086	3.367	
1-3/4" to 2"	54.6	0.044	1.723	49.4	0.053	2.075	
Sample No.	5	Minute Tes	st		24 Hour Tes	t	
F	mV	%CL	lb. Cl	mV	%CL	lb. Cl	
0" to 1/4"	4.6	0.345	13.507	3.8	0.355	13.898	
1/4" to 1/2"	2.8	0.370	14.486	2.0	0.380	14.877	
1/2" to 3/4"	12.2	0.255	9.983	11.1	0.260	10.179	
3/4" to 1"	15.0	0.230	9.005	12.4	0.250	9.788	
1" to 1-1/4"	17.8	0.205	8.026	16.1	0.210	8.222	
1-1/4" to 1-1/2"	31.3	0.118	4.620	29.2	0.122	4.776	
1-1/2" to 1-3/4"	43.6	0.070	2.741	41.1	0.075	2.936	
1-3/4" to 2"	67.1	0.026	1.018	63.9	0.029	1.135	
							1
Sample No.		Minute Tes			24 Hour Tes		
G	mV	%CL	lb. Cl	mV	%CL	lb. Cl	
0" to 1/4"	-12.9	0.720	28.188	-14.9	0.780	30.537	
1/4" to 1/2"	2.3	0.385	15.073	1.1	0.390	15.269	
1/2" to 3/4"	2.4	0.380	14.877	1.0	0.390	15.269	
3/4" to 1"	11.1	0.265	10.375	8.4	0.290	11.354	
1" to 1-1/4"	26.0	0.145	5.677	23.6	0.155	6.068	
1-1/4" to 1-1/2"	27.6	0.135	5.285	24.3	0.150	5.873	
1-1/2" to $1-3/4$ "	40.5	0.080	3.132	36.7 50.9	0.090	3.524	
1-3/4" to 2"	54.1	0.040	1.801	50.9	0.050	1.958	J
Sample No.	5	Minute Tes	st		24 Hour Tes	t	
Н	mV	%CL	lb. Cl	mV	%CL	lb. Cl	
0" to 1/4"	-5.8	0.540	21.141	-7.6	0.570	22.316	
1/4" to 1/2"	7.3	0.315	12.332	5.6	0.325	12.724	
1/2" to 3/4"	8.8	0.295	11.549	6.4	0.315	12.332	
3/4" to 1"	13.2	0.245	9.592	11.0	0.260	10.179	
1" to 1-1/4"	26.2	0.145	5.677	22.0	0.167	6.538	
1-1/4" to 1-1/2"	28.0	0.135	5.285	23.2	0.158	6.186	
1-1/2" to 1-3/4"	38.0	0.088	3.445	34.0	0.100	3.915	
1-3/4" to 2"	55.7	0.042	1.644	51.8	0.048	1.879]
Comple Me		Minute T	*	[24 Horr T		1
Sample No.		Minute Tes			24 Hour Tes		
	mV	%CL	lb. Cl	mV	%CL	lb. Cl	0.00 h
0" to 1/4" 1/4" to 1/2"	9.1	0.290	11.354	7.2	0.300	11.745	^b 0.22g short
1/4" to 1/2" 1/2" to 3/4"	- 18.1	0.200	- 7.830	- 17.7	0.200	- 7.830	•
3/4" to 1"				17.7	0.200	8.809	4
1" to 1-1/4"	15.9 22.1	0.220 0.170	8.613 6.656	21.6	0.223	6.656	•
1 + 10 + 1/4 1-1/4" to 1-1/2"	31.5	0.115	4.502	30.1	0.170	4.620	4
1-1/2" to 1-3/4"	39.9	0.080	3.132	37.0	0.090	3.524	1
1-1/2 to 1-3/4 1-3/4" to 2"	54.1	0.080	1.801	50.7	0.090	1.958	4
1-5/4 WZ	JH.1	0.040	1.001	50.7	0.050	1.750	J





Measurement of the acid soluble chloride content of hardened concrete by the RCT method





Liquid	Clear	Purple	Green	Pink]		Bridge B-14-0133
%CL	0.005	0.02	0.05	0.5			Date:
mV before	95.6	70.9	49.0	-4.3	5 Minuta Tag	+	11/6/2007
mV after	105.5	75.8	53.4	-3.7	-5 Minute Test		11/0/2007
mV before	101.9	72.9	51.1	-4.3	24 Hour Test		11/7/2007
mV after	102.0	74.1	51.4	-4.1	24 110ui 1est		11/7/2007
Assu	Ŭ	of concrete =		lb/cubic yard			By: MDP
Sample No.		5 Minute Tes	t		24 Hour Test		
Α	mV	%CL	lb. Cl	mV	%CL	lb. Cl	
0" to 1/4"	-14.5	0.780	30.537	-15.7	0.800	31.320	
1/4" to 1/2"	2.3	0.390	15.269	0.6	0.415	16.247	
1/2" to 3/4"	5.2	0.340	13.311	3.8	0.360	14.094	
3/4" to 1"	11.2	0.265	10.375	10.4	0.277	10.845	
1" to 1-1/4"	17.5	0.205	8.026	16.8	0.210	8.222	
1-1/4" to 1-1/2"	22.1	0.170	6.656	21.5	0.172	6.734	^a 0.10g short
1-1/2" to 1-3/4"	30.5	0.120	4.698	29.0	0.125	4.894	
1-3/4" to 2"	31.8	0.110	4.307	31.1	0.115	4.502	
				1			-
Sample No.		5 Minute Tes			24 Hour Test		
В	mV	%CL	lb. Cl	mV	%CL	lb. Cl	
0" to 1/4"	-5.1	0.520	20.358	-6.0	0.540	21.141	
1/4" to 1/2"	-6.9	0.560	21.924	-8.2	0.595	23.294	
1/2" to 3/4"	0.4	0.420	16.443	-1.2	0.440	17.226	
3/4" to 1"	4.1	0.360	14.094	1.1	0.400	15.660	
1" to 1-1/4"	10.9	0.270	10.571	9.5	0.282	11.040	
1-1/4" to 1-1/2"	9.1	0.290	11.354	8.1	0.295	11.549	
1-1/2" to 1-3/4"	17.3	0.210	8.222	14.5	0.232	9.083	
1-3/4" to 2"	16.9	0.210	8.222	15.0	0.227	8.887	
				T			-
Sample No.		5 Minute Tes			24 Hour Test		_
C	mV	%CL	lb. Cl	mV	%CL	lb. Cl	_
0" to 1/4"	-10.9	0.660	25.839	-12.4	0.700	27.405	_
1/4" to 1/2"	4.1	0.360	14.094	1.2	0.390	15.269	_
1/2" to 3/4"	7.5	0.310	12.137	6.0	0.330	12.920	_
3/4" to 1"	5.9	0.330	12.920	4.5	0.350	13.703	4
1" to 1-1/4"	10.0	0.280	10.962	6.6	0.320	12.528	_
1-1/4" to 1-1/2"	19.9	0.190	7.439	18.4	0.195	7.634	_
1-1/2" to 1-3/4"	25.7	0.145	5.677	21.4	0.175	6.851	_
1-3/4" to 2"	35.9	0.094	3.680	35.5	0.096	3.758	
		-) <i>(</i> '		1	<u></u>		7
Sample No.		5 Minute Tes		T 7	24 Hour Test	11 (71	-
D	mV	%CL	lb. Cl	mV	%CL	lb. Cl	-
0" to 1/4"	-3.8	0.500	19.575	-5.2	0.510	19.967	-
1/4" to 1/2"	2.4	0.390	15.269	1.8	0.450	17.618	-
1/2" to 3/4"	1.5	0.400	15.660	0.5	0.420	16.443	-
3/4" to 1"	6.0	0.330	12.920	3.8	0.360	14.094	-
1" to 1-1/4"	11.8	0.260	10.179	10.6	0.270	10.571	-
1-1/4" to 1-1/2"	17.5	0.205	8.026	16.9	0.210	8.222	4
1-1/2" to 1-3/4"	22.8	0.165	6.460	22.4	0.170	6.656	4
1-3/4" to 2"	28.3	0.130	5.090	27.1	0.135	5.285	


ridge	B-14-	0133
-------	-------	------

Sample No.	5 Minute Test			24 Hour Test		
Е	mV	%CL	lb. Cl	mV	%CL	lb. Cl
0" to 1/4"	7.6	0.300	11.745	5.8	0.330	12.920
1/4" to 1/2"	9.5	0.285	11.158	8.1	0.300	11.745
1/2" to 3/4"	14.4	0.235	9.200	13.3	0.240	9.396
3/4" to 1"	19.1	0.190	7.439	17.9	0.203	7.947
1" to 1-1/4"	19.3	0.190	7.439	18.0	0.200	7.830
1-1/4" to 1-1/2"	25.2	0.150	5.873	24.4	0.155	6.068
1-1/2" to 1-3/4"	25.6	0.140	5.481	23.2	0.160	6.264
1-3/4" to 2"	27.5	0.135	5.285	26.3	0.140	5.481


Sample No.	-	5 Minute Tes	t	24 Hour Test		
F	mV	%CL	lb. Cl	mV	%CL	lb. Cl
0" to 1/4"	-5.4	0.530	20.750	-6.0	0.540	21.141
1/4" to 1/2"	1.5	0.400	15.660	-0.1	0.420	16.443
1/2" to 3/4"	-0.2	0.430	16.835	-0.9	0.440	17.226
3/4" to 1"	5.4	0.340	13.311	4.4	0.350	13.703
1" to 1-1/4"	14.8	0.230	9.005	12.9	0.245	9.592
1-1/4" to 1-1/2"	24.8	0.150	5.873	25.2	0.150	5.873
1-1/2" to 1-3/4"	21.5	0.170	6.656	21.3	0.175	6.851
1-3/4" to 2"	22.2	0.170	6.656	21.9	0.170	6.656









$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$						1		
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	-							Bridge B-47-0110
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$								Date:
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$						5 Minute Te	est	8/4/2008
mV after 94.6 71.6 50.8 -4.2 44 Hour Test 87//2008 Assumed weight of concrete 145.0 hb/cubic yard 24 Hour Test 24 Hour Test By: Sample No. 5 Minute Test 24 Hour Test 24 Hour Test By: 0" to 1/4" 7.4 0.278 10.902 9.1 0.288 11.288 1/2" to 3/4" 8.5 0.266 10.399 9.2 0.287 11.237 34" to 1" 6.0 0.296 11.577 6.7 0.322 12.590 1"4" to 1/1" 1.3 5.12 2.2.6 0.134 5.259 1-1/2" to 1-3/4" 23.3 0.141 5.512 2.2.6 0.156 6.111 1-3/4" to 1" 8.1 0.270 10.579 8.6 0.295 11.548 1" to 1-1/4" 15.7 0.151 5.904 2.2.5 0.157 6.139 1/4" to 1/2" 1.6.0 0.193 7.539 15.8 0.213 8.324 1						-		
Inv atter 94.6 71.6 50.8 -4.2 Assumed weight of concrete = 145.0 Ib/cubic yard By: Sample No. 5 Minute Test 24 Hour Test 24 Hour Test A mV %CL lb. Cl mV %CL lb. Cl 0" to 1/4" 7.4 0.278 10.902 9.1 0.288 11.288 1/4" to 1/2" 2.3 0.347 13.567 3.8 0.367 14.364 1/2" to 3/4" 8.5 0.266 11.577 6.7 0.322 12.590 1"10" to 1/4" 17.9 0.177 6.949 18.3 0.190 7.430 1-1/4" to 1-1/2" 24.5 0.134 5.512 22.6 0.156 6.111 1-3/4" to 2" 23.0 0.143 5.584 22.1 0.160 6.251 Sample No. S Minute Test 24 Hour Test B mV %CL lb. Cl 0.44" to 1" 8.1 0.270 10.579 8.6						24 Hour Tes	st	8/7/2008
Sample No. 5 Minute Test 24 Hour Test A mV %CL lb. Cl mV %CL lb. Cl 0" to 1/4" 7.4 0.278 l0.902 9.1 0.288 l1.288 14" to 12" 2.3 0.347 l3.567 3.8 0.367 l4.364 1/2" to 3/4" 8.5 0.266 l0.399 9.2 0.287 l1.237 3/4" to 1" 6.0 0.296 l1.577 6.7 0.322 l2.590 1" to 1-1/4" 17.9 0.177 6.549 l8.3 0.190 7.430 1-1/4" to 1-1/2" 24.5 0.134 5.526 25.9 0.134 5.259 1-1/2" to 1.3/4" 23.0 0.143 5.584 22.1 0.160 6.251 Sample No. 5 Minute Test 24 Hour Test 8 0.47 0.57 6.139 1/4" to 1/2" 1.4 0.360 14.101 2.3 0.393 15.377 1/2" to 3/4" 3.5 0.					1			
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$		Ų			· · · ·			By:
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$						1		_
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$								-
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$								-
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$								-
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$								-
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$								-
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$								-
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$								-
Sample No. 5 Minute Test 24 Hour Test B mV %CL lb.Cl mV %CL lb.Cl 0" to 1/4" 21.7 0.151 5.904 22.5 0.157 6.139 1/4" to 1/2" 1.4 0.360 14.101 2.3 0.393 15.377 1/2" to 3/4" 3.5 0.329 12.887 4.1 0.362 14.169 3/4" to 1" 8.1 0.270 10.579 8.6 0.295 11.548 1" to 1-1/4" 15.7 0.195 7.637 16.2 0.209 8.174 1-1/2" to 1-3/4" 20.8 0.157 6.136 20.9 0.169 6.602 1-3/4" to 2" 23.2 0.141 5.536 23.8 0.148 5.786 Sample No. 5 Minute Test 24 Hour Test 2 1/2" to 1/4" 2.6 0.342 13.394 1.8 0.402 15.731 1/4" to 1/2" -6.1 0.497 19.452 -5.4 0.557 <td< td=""><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td>-</td></td<>								-
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	1-3/4" to 2"	23.0	0.143	5.584	22.1	0.160	6.251	
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	Sample No	5	Minuto To	+	,	1 Uour Too	+	7
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$								-
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$								
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$								
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$								
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$								
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$								
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$								-
$\begin{array}{ c c c c c c c c c c c c c c c c c c c$								-
Sample No.5 Minute Test24 Hour TestCmV%CLlb. ClmV%CLlb. Cl0" to 1/4"2.60.34213.3941.80.40215.7311/4" to 1/2"-6.10.49719.452-5.40.55721.8221/2" to 3/4"-3.80.45017.625-2.60.49119.2143/4" to 1"2.50.34413.4523.00.38014.8961" to 1-1/4"9.10.25910.1359.40.28411.1351-1/4" to 1-1/2"16.40.1897.41116.80.2037.9541-1/2" to 1-3/4"23.50.1405.46523.10.1535.9731-3/4" to 2"16.00.1937.53915.40.2178.477Sample No.5 Minute Test24 Hour TestDmV%CLlb. ClmV%CLlb. Cl0" to 1/4"5.50.30211.8277.20.31412.3071/4" to 1/2"-1.20.40315.7650.10.43416.9951/2" to 3/4"12.10.2288.91214.10.2308.9933/4" to 1"14.50.2058.04015.10.2208.5931" to 1-1/4"12.00.2298.95011.90.2549.939								-
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	1-3/4 10 2	23.2	0.141	5.550	25.0	0.140	5.780	
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$	Sample No	5	Minute Tes	t	,	74 Hour Tes	t	7
$ \begin{array}{ c c c c c c c c c c c c c c c c c c c$								
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$								
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$								
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$								-
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$								
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$								1
$\begin{array}{c c c c c c c c c c c c c c c c c c c $								1
$\begin{array}{c c c c c c c c c c c c c c c c c c c $				5.465				
D mV %CL lb. Cl mV %CL lb. Cl 0" to 1/4" 5.5 0.302 11.827 7.2 0.314 12.307 1/4" to 1/2" -1.2 0.403 15.765 0.1 0.434 16.995 1/2" to 3/4" 12.1 0.228 8.912 14.1 0.230 8.993 3/4" to 1" 14.5 0.205 8.040 15.1 0.220 8.593 1" to 1-1/4" 12.0 0.229 8.950 11.9 0.254 9.939		16.0	0.193	7.539	15.4	0.217	8.477	
D mV %CL lb. Cl mV %CL lb. Cl 0" to 1/4" 5.5 0.302 11.827 7.2 0.314 12.307 1/4" to 1/2" -1.2 0.403 15.765 0.1 0.434 16.995 1/2" to 3/4" 12.1 0.228 8.912 14.1 0.230 8.993 3/4" to 1" 14.5 0.205 8.040 15.1 0.220 8.593 1" to 1-1/4" 12.0 0.229 8.950 11.9 0.254 9.939								
0" to 1/4" 5.5 0.302 11.827 7.2 0.314 12.307 1/4" to 1/2" -1.2 0.403 15.765 0.1 0.434 16.995 1/2" to 3/4" 12.1 0.228 8.912 14.1 0.230 8.993 3/4" to 1" 14.5 0.205 8.040 15.1 0.220 8.593 1" to 1-1/4" 12.0 0.229 8.950 11.9 0.254 9.939	Sample No.	5	Minute Tes	st		24 Hour Tes	t	7
1/4" to 1/2"-1.20.40315.7650.10.43416.9951/2" to 3/4"12.10.2288.91214.10.2308.9933/4" to 1"14.50.2058.04015.10.2208.5931" to 1-1/4"12.00.2298.95011.90.2549.939	D	mV	%CL	lb. Cl	mV	%CL	lb. Cl	
1/2" to 3/4"12.10.2288.91214.10.2308.9933/4" to 1"14.50.2058.04015.10.2208.5931" to 1-1/4"12.00.2298.95011.90.2549.939	0" to 1/4"	5.5	0.302	11.827	7.2	0.314	12.307	
3/4" to 1" 14.5 0.205 8.040 15.1 0.220 8.593 1" to 1-1/4" 12.0 0.229 8.950 11.9 0.254 9.939	1/4" to 1/2"	-1.2	0.403	15.765	0.1	0.434	16.995	1
1" to 1-1/4" 12.0 0.229 8.950 11.9 0.254 9.939	1/2" to 3/4"	12.1	0.228	8.912	14.1	0.230	8.993	1
1" to 1-1/4" 12.0 0.229 8.950 11.9 0.254 9.939	3/4" to 1"	14.5	0.205	8.040	15.1	0.220	8.593	1
								1
$1^{-1/4}$ 10 $1^{-1/2}$ 14.7 0.204 7.971 13.2 0.219 0.334	1-1/4" to 1-1/2"	14.7	0.204	7.971	15.2	0.219	8.554	1
1-1/2" to 1-3/4" 20.3 0.160 6.269 19.7 0.178 6.972	1-1/2" to 1-3/4"	20.3	0.160	6.269	19.7	0.178	6.972	7
1-3/4" to 2" 21.5 0.152 5.955 20.8 0.169 6.632	1-3/4" to 2"	21.5	0.152	5.955	20.8	0.169	6.632	7



Liquid	Clear	Purple	Green	Pink]		Bridge B-47	-0118
%CL	0.005	0.020	0.050	0.500			Date:	
mV before	99.9	72.3	48.3	-7.6	5 Minute Te	t	8/1/2008	
mV after	96.7	71.3	48.7	-7.4	5 Minute 16	est	8/4/2008	
mV before	93.4	71.8	49.0	-5.6	24 Hour Tes	.	8/7/2008	
mV after	94.6	71.6	50.8	-4.2	24 HOUI 16	si	8/7/2008	
Assun	ned weight of	of concrete =	145.0	lb/cubic yar	d		_	By: N
Sample No.		5 Minute Te	st		24 Hour Tes	t		
А	mV	%CL	lb. Cl	mV	%CL	lb. Cl		
0" to 1/4"	5.3	0.305	11.929	6.2	0.329	12.879		
1/4" to 1/2"	8.0	0.271	10.625	9.6	0.282	11.035		
1/2" to 3/4"	2.2	0.348	13.626	2.7	0.386	15.100		
3/4" to 1"	7.5	0.277	10.855	7.6	0.309	12.085		
1" to 1-1/4"	13.7	0.213	8.321	13.0	0.241	9.454		
1-1/4" to 1-1/2"	21.2	0.154	6.032	21.4	0.165	6.453		
1-1/2" to 1-3/4"	37.6	0.076	2.985	38.8	0.075	2.926		
1-3/4" to 2"	26.0	0.125	4.910	24.9	0.141	5.504		
	I			1			_	
Sample No.		5 Minute Te			24 Hour Tes			
В	mV	%CL	lb. Cl	mV	%CL	lb. Cl		
0" to 1/4"	8.5	0.266	10.399	9.4	0.284	11.135		
1/4" to 1/2"	-2.0	0.417	16.315	-1.7	0.471	18.444		
1/2" to 3/4"	2.0	0.351	13.743	2.9	0.382	14.964		
3/4" to 1"	11.6	0.233	9.105	12.8	0.244	9.541		
1" to 1-1/4"	9.7	0.252	9.878	10.2	0.274	10.738		
1-1/4" to 1-1/2"	16.3	0.190	7.443	16.0	0.211	8.249		
1-1/2" to 1-3/4"	20.9	0.156	6.110	21.3	0.166	6.483		
1-3/4" to 2"	36.5	0.080	3.129	36.1	0.084	3.308		
				T			-	
Sample No.		5 Minute Te	1		24 Hour Tes		_	
С	mV	%CL	lb. Cl	mV	%CL	lb. Cl	_	
0" to 1/4"	-4.4	0.462	18.084	-4.2	0.528	20.664	_	
1/4" to 1/2"	-6.9	0.514	20.131	-6.3	0.581	22.734	_	
1/2" to 3/4"	-5.1	0.476	18.635	-3.8	0.518	20.291	_	
3/4" to 1"	-2.9	0.433	16.957	-1.6	0.469	18.360	4	
1" to 1-1/4"	3.9	0.324	12.668	4.1	0.362	14.169	4	
1-1/4" to 1-1/2"	4.7	0.313	12.240	5.0	0.347	13.601	4	
1-1/2" to 1-3/4"	0.0	0.382	14.974	0.7	0.422	16.537	4	
1-3/4" to 2"	10.2	0.247	9.668	10.4	0.272	10.640		
Comple M-		5 Minute Th	_4	-	04 II. T		٦	
Sample No.		5 Minute Te			24 Hour Tes		-	
D 0" to 1/4"	mV	%CL	lb. Cl	mV	%CL	lb. Cl	-	
	-3.5	0.444	17.399	-2.2	0.482	18.868	-	
1/4" to 1/2"	-3.4	0.443	17.325	-2.6	0.491	19.214	-	
1/2" to 3/4"	0.2	0.379	14.846	0.9	0.419	16.388	-	
3/4" to 1"	10.1	0.248	9.710	11.1	0.263	10.307	-	
1" to 1-1/4"	11.4	0.235	9.183	11.8	0.255	9.984	-	
$\frac{1-1/4"}{1-1/2"}$ to $1-1/2"$	12.5	0.224	8.760	13.0	0.241	9.454	-	
1-1/2" to 1-3/4"	13.1	0.218	8.537	13.7	0.234	9.158	-	
1-3/4" to 2"	21.0	0.155	6.084	20.3	0.173	6.784		




Liquid	Clear	Purple	Green	Pink	1		Bridge B-47-0120
%CL	0.005	0.020	0.050	0.500			Date:
mV before	99.9	72.3	48.3	-7.6			
mV after	96.7	71.3	48.7	-7.4	5 Minute Te	st	8/4/2008
mV before	93.4	71.8	49.0	-5.6			
mV after	94.6	71.6	50.8	-4.2	24 Hour Tes	t	8/7/2008
		of concrete =		lb/cubic yar	d		By: 1
Sample No.	-	5 Minute Tes			24 Hour Test	t]
A	mV	%CL	lb. Cl	mV	%CL	lb. Cl	
0" to 1/4"	3.7	0.326	12.777	5.2	0.344	13.478	
1/4" to 1/2"	-5.4	0.482	18.877	-4.9	0.545	21.332	
1/2" to 3/4"	-3.5	0.444	17.399	-1.7	0.471	18.444	
3/4" to 1"	0.1	0.381	14.910	1.8	0.402	15.731	
1" to 1-1/4"	-7.9	0.537	21.013	-7.4	0.610	23.899	
1-1/4" to 1-1/2"	3.4	0.331	12.942	5.1	0.346	13.539	
1-1/2" to 1-3/4"	2.8	0.339	13.280	2.5	0.389	15.238	
1-3/4" to 2"	2.4	0.345	13.509	3.1	0.379	14.828	
	-			-			_
Sample No.		5 Minute Tes	st		24 Hour Tes	t	
В	mV	%CL	lb. Cl	mV	%CL	lb. Cl	
0" to 1/4"	-0.7	0.394	15.430	-0.4	0.444	17.385	
1/4" to 1/2"	1.0	0.366	14.345	2.1	0.396	15.518	
1/2" to 3/4"	10.1	0.248	9.710	10.8	0.267	10.449	
3/4" to 1"	7.5	0.277	10.855	8.0	0.303	11.867	
1" to 1-1/4"	11.9	0.230	8.988	14.3	0.228	8.912	_
1-1/4" to 1-1/2"	19.9	0.163	6.378	20.6	0.171	6.692	_
1-1/2" to 1-3/4"	21.1	0.155	6.058	21.5	0.164	6.424	
1-3/4" to 2"	20.7	0.157	6.163	20.8	0.169	6.632	
				1	• • • • • • • •		7
Sample No.		5 Minute Tes			24 Hour Test		_
С	mV	%CL	lb. Cl	mV	%CL	lb. Cl	_
0" to 1/4"	0.9	0.368	14.407	2.3	0.393	15.377	_
1/4" to 1/2"	-11.1	0.616	24.105	-10.7	0.709	27.768	_
1/2" to 3/4"	-5.7	0.488	19.121	-5.4	0.557	21.822	_
3/4" to 1"	-3.4	0.443	17.325	-3.5	0.511	20.017	_
1" to 1-1/4"	1.5	0.359	14.041	2.0	0.398	15.588	_
1-1/4" to 1-1/2"	2.7	0.341	13.337	3.3	0.375	14.694	_
1-1/2" to 1-3/4"	11.0	0.239	9.342	11.8	0.255	9.984	-
1-3/4" to 2"	10.3	0.246	9.627	11.1	0.263	10.307	
Sample No.	4	5 Minute Tes	at		24 Hour Test	ŀ	7
D	mV	%CL	lb. Cl	mV	%CL	lb. Cl	
0" to 1/4"	-9.1	0.565	22.123	-7.7	0.619	24.228	
1/4" to 1/2"	-14.2	0.703	27.532	-13.6	0.809	31.681	-
1/4" to 1/2 1/2" to 3/4"	-8.2	0.544	21.285	-13.0	0.613	24.008	1
3/4" to 1"	-6.6	0.508	19.874	-7.3	0.565	24.008	-
1" to 1-1/4"	-2.7	0.429	16.813	-2.4	0.303	19.040	-
1-1/4" to 1-1/2"	2.4	0.345	13.509	3.5	0.430	19.040	-
1-1/2" to 1-3/4"	-1.7	0.345	16.107	-1.2	0.372	18.029	-
1-1/2 to 1-5/4 1-3/4" to 2"	4.1	0.321	12.559	4.9	0.401	13.663	-
1-J/7 10 2	7.1	0.521	12.337	т. <i>)</i>	0.347	15.005	_




Liquid	Clear	Purple	Green	Pink]		Bridge B-	47-0141
%CL	0.005	0.020	0.050	0.500	_		Date:	
mV before	99.9	72.3	48.3	-7.6	5 Minute Te	st	8/4/2008	
mV after	96.7	71.3	48.7	-7.4			0/ 1/2000	
mV before	93.4	71.8	49.0	-5.6	24 Hour Tes	ŀ	8/7/2008	
mV after	94.6	71.6	50.8	-4.2			0,1,2000	
Assu	med weight	of concrete =	145.0	lb/cubic yar			_	By: MDP
Sample No.		5 Minute Tes	t		24 Hour Test			
A	mV	%CL	lb. Cl	mV	%CL	lb. Cl		
0" to 1/4"	-3.8	0.450	17.625	-3.5	0.511	20.017		
1/4" to 1/2"	0.2	0.379	14.846	0.7	0.422	16.537		
1/2" to 3/4"	-0.9	0.398	15.563	-1.2	0.461	18.029		
3/4" to 1"	2.6	0.342	13.394	2.8	0.384	15.032		
1" to 1-1/4"	8.3	0.268	10.489	7.7	0.307	12.030		
1-1/4" to 1-1/2"	18.0	0.177	6.919	18.3	0.190	7.430		
1-1/2" to 1-3/4"	35.8	0.082	3.225	36.6	0.083	3.234		
1-3/4" to 2"	39.6	0.070	2.740	40.0	0.071	2.771		
							_	
Sample No.		5 Minute Tes	t		24 Hour Test			
В	mV	%CL	lb. Cl	mV	%CL	lb. Cl		
0" to 1/4"	19.7	0.164	6.433	20.5	0.172	6.723		
1/4" to 1/2"	4.1	0.321	12.559	4.2	0.360	14.105		
1/2" to 3/4"	18.0	0.177	6.919	18.7	0.186	7.296		
3/4" to 1"	17.3	0.182	7.130	18.2	0.191	7.464		
1" to 1-1/4"	17.3	0.182	7.130	17.6	0.196	7.670		
1-1/4" to 1-1/2"	22.7	0.144	5.656	23.3	0.151	5.919		
1-1/2" to 1-3/4"	29.9	0.106	4.153	29.2	0.116	4.527		
1-3/4" to 2"	33.5	0.091	3.559	32.5	0.100	3.896		
				T			_	
Sample No.		5 Minute Tes	t		24 Hour Test			
С	mV	%CL	lb. Cl	mV	%CL	lb. Cl		
0" to 1/4"	2.9	0.338	13.223	3.4	0.374	14.627		
1/4" to 1/2"	5.0	0.309	12.084	5.7	0.337	13.175		
1/2" to 3/4"	10.3	0.246	9.627	10.8	0.267	10.449		
3/4" to 1"	16.9	0.185	7.253	17.6	0.196	7.670		
1" to 1-1/4"	16.5	0.188	7.379	16.1	0.210	8.212		
1-1/4" to 1-1/2"	22.7	0.144	5.656	22.3	0.158	6.195		
1-1/2" to 1-3/4"	32.5	0.095	3.715	33.2	0.096	3.774		
1-3/4" to 2"	38.8	0.072	2.835	37.0	0.081	3.175		
							_	
Sample No.		5 Minute Tes			24 Hour Test			
D	mV	%CL	lb. Cl	mV	%CL	lb. Cl		
0" to 1/4"	17.5	0.181	7.069	17.7	0.195	7.635		
1/4" to 1/2"	13.4	0.215	8.428	13.6	0.235	9.200		
1/2" to 3/4"	14.1	0.209	8.179	14.3	0.228	8.912	_	
3/4" to 1"	15.0	0.201	7.869	14.8	0.223	8.711	_	
1" to 1-1/4"	27.9	0.116	4.525	28.2	0.121	4.737		
1-1/4" to 1-1/2"	33.8	0.090	3.514	34.6	0.090	3.541	_	
1-1/2" to 1-3/4"	39.1	0.071	2.799	37.4	0.080	3.118	_	
1-3/4" to 2"	55.2	0.036	1.403	54.1	0.037	1.459		

5-N	Ainute Test	for B-47-01	10, B-47-011	8, B-47-0120,	& B-47-0141
%Cl	0.005	0.020	0.050	0.500	
mV before	99.9	72.3	48.3	-7.6	
mV after	96.7	71.3	48.7	-7.4	
mV average	98.3	71.8	48.5	-7.5	



24-Hour Test for B-47-0110, B-47-0118, B-47-0120, & B-47-0141

%Cl	0.005	0.020	0.050	0.500
mV before	93.4	71.8	49.0	-5.6
mV after	94.6	71.6	50.8	-4.2
mV average	94.0	71.7	49.9	-4.9



(Page left blank intentionally)

IMPLEMENTATION PLAN

WisDOT Research	Wisconsin Department of Transportation	Nina McLawhorn, Research Administrator
	4802 Sheboygan Ave., Rm. 451	Ann Pahnke, Program Analyst
	P.O. Box 7965	Linda Keegan, Program Analyst
	Madison, WI 53707-7965	Louis Bearden, Program Analyst
	www.dot.state.wi.us/dtid/research	Pat Casey, Communications Consultant

Implementation of Research Results

Project Information							
Project Title:	Project ID: Today's Date:						
Technical Oversight Committee (WHRP or	TOC Chair and Phone number:						
COR):							
Project Start Date:	Approved Contract Amount:						
Project End Date:	Final Project Expenditures:						
Reference Final Report Draft Dated:							
Principal Investigator:	Phone:						
Organization:	E-Mail:						

Technical Oversight Committee Recommendations

1. Check one of the two choices below:

□ Yes. We recommend changes to current practice based on <u>some or all</u> of the results of this report. The research was sound, and the report's conclusions appear to offer an advance over current practice.

□ No. We do not recommend changes to current practice at this time. This approach does not appear fruitful OR future study is needed OR our objectives have changed, etc.

2. If implementation is not recommended, we suggest the following actions instead:

3. If implementation <u>is recommended</u>, we suggest the following <u>specific</u> changes to current practice, detailed on the <u>attached work plan and timeline</u> (check applicable items):

□ Standard Specifications

Quality Management Program (QMP) Specifications

□ Facilities Development Manual (FDM)

□ Highway Maintenance Manual

□ Training, outreach

□ Other (describe):

4. Approval of this implementation plan	Signature:
by the Technical Oversight Committee	
(chair on behalf of entire committee):	Date:
5. Approval of this implementation plan by the	Signature(s):
Council on Research (for COR approved	
projects):	Date:

6. Referral for development of detailed work plan and timeline to (check one):	□ WisDOT/Industry Technical Committee on: □ □ Other WisDOT policy body:
7. Approval of work plan and timeline by the WisDOT Bureau Director(s) responsible for the policies described in item #3 above:	Signature(s): Date
8. Acceptance by a project manager of the responsibility for completing these implementation efforts according to the attached work plan and timeline:	Signature: Date:

Rev. 4/8/01

Implementation Work Plan				
1. Project Title:	2. Prepared by:			
1. Scope and objectives of implement	ition, including specific changes to	WisDOT procedures.		
2. Estimated cost (if any) to impleme	t			
4. Expected benefits and how they wi	l be measured (dollar savings, time	savings, other).		
7 D				
5. Possible pitfalls and how they will	be avoided.			

Implementation Timeline (Gantt Chart)											
Tasks/Person Responsible											

Rev. 5/8/01

Wisconsin Highway Research Program University of Wisconsin-Madison 1415 Engineering Drive Madison, WI 53706 608/262-2013 www.whrp.org