

WisDOT Pit and Quarry Listing for Use in 2019.

Acceptable "**Pit**" sources are those tested in 2015 to 2019.

Acceptable "**Quarry**" sources are those tested in 2017 to 2019.

All source test data (both satisfactory and non-satisfactory) is shown, please check source data to ensure source meets specification requirements for the intended usage.

Certified sources expire at end of allocated calendar years.

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric			
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS	LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine
A TO Z AGGREGATE SOLUTIONS 55-51-001-PIT Created On: 02/14/17 Updated On:	P		SW 3	3N	19E	Racine	0-223-13-2017		0.0	0.0			2.681	1.204
AGGRECON 55-36-002-PIT Created On: 06/05/15 Updated On:	P		SE 33	17N	21E	Manitowoc	0-162-26-2015		0.0	0.0	1		2.751	0.817
AMERICAN MATERIALS #31 55-18-003-PIT Created On: 04/18/12 Updated On:	P	N	NE 2	26N	10W	Eau Claire	0-162-22-2012		0.0	0.0	2		2.627	0.432
AMERICAN MATERIALS #31 55-18-003-PIT Created On: 02/13/17 Updated On:	P	N	NE 2	26N	10W	Eau Claire	0-223-5-2017		0.0	0.0	1		2.627	0.695
BADGERLAND 55-36-031-PIT Created On: 05/15/14 Updated On:	P		33	21N	23E	Manitowoc	0-162-21-2014		0.0	0.0	1		2.686	1.194
BADGERLAND 55-36-031-PIT Created On: 01/29/19 Updated On:	P		33	21N	23E	Manitowoc	0-223-14-2019		0.0	0.0	1		2.689	1.112
BADGERLAND X PIT 55-36-039-PIT Created On: 08/30/18 Updated On:	P		SW 9	17N	22E	Manitowoc	0-223-55-2018		0.0	0.0	1		2.734	0.806

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric					
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS	LA Wear (%)	Sp. Gravity	Absorp. %		
											100	500	Crse	Fine	Crse	Fine
BAUMEISTER	P		NW	19	2N	19E	Racine	0-162-33-2016		0.0	0.0	1			2.638	1.317
55-51-005-PIT Created On: 03/30/16 Updated On:																
BEAN CITY	P	SW	SW	24	22N	14E	Waupaca	0-223-24-2018		0.0	0.0	1			2.632	0.604
55-68-035-PIT Created On: 03/23/18 Updated On:																
BECK	P	SE	NE	34	4N	19E	Racine	0-223-53-2018		0.0	0.0	1			2.634	1.256
55-51-32-PIT Created On: 08/08/18 Updated On:																
BERESS	P	SW	SE	32	14N	19E	Fond Du Lac	0-162-24-2015		0.0	0.0	1			2.715	1.174
55-20-004-PIT Created On: 05/15/15 Updated On:																
BIBBY	P	NE	NW	8	22N	9E	Portage	0-223-32-2019		0.0	0.0	1			2.633	0.543
55-49-028-PIT Created On: 04/17/19 Updated On:																
BIEHL	P	S	NW	18	30N	21E	Marinette	0-223-45-2018		0.0	0.0	1			2.680	0.503
55-38-007-PIT Created On: 06/18/18 Updated On:																
BLAU (LYCON)	P	NE	NW	2	11N	8E	Columbia	0-162-3-2012		0.0	0.0	1			2.676	0.654
55-11-006-PIT Created On: 01/13/12 Updated On:																

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric			
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
BLAU (LYCON)	P	NE	NW	2	11N	8E	Columbia	0-223-11-2017		0.0	0.0	1		2.671	0.553
55-11-006-PIT															
Created On: 02/14/17		Updated On:													
BLOOMFIELD	P	E	SW	1	1N	19E	Walworth	0-162-8-2014		0.0	0.0	1		2.649	0.664
55-64-008-PIT															
Created On: 01/15/14		Updated On:													
BLOOMFIELD	P	E	SW	1	1N	19E	Walworth	0-223-13-2019		0.0	0.0	1		2.634	0.888
55-64-008-PIT															
Created On: 01/29/19		Updated On:													
BLUE RIVER	P	SW	SW	35	9N	2W	Richland	0-162-2-2014		0.0	0.0	1		2.644	0.170
55-52-005-PIT															
Created On: 01/02/14		Updated On:													
BLUE RIVER	P	SW	SW	35	9N	2W	Richland	0-223-39-2019		0.0	0.0	1		2.636	0.371
55-52-005-PIT															
Created On: 05/06/19		Updated On:													
BLUFF CITY SOUTH BELOIT	P						Illinois	0-223-46-2019		0.0	0.0	1		2.622	0.867
17-99-002-PIT															
Created On: 06/26/19		Updated On:													
BOHL #720	P	NW	SE	10	32N	11W	Barron	0-162-16-2012		0.0	0.0	1		2.652	0.432
55-03-006-PIT															
Created On: 04/04/12		Updated On:													

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine		
BOHL #720	P	NW	SE	10	32N	11W	Barron		0-223-14-2017		0.0	0.0	1		2.611	0.857
55-03-006-PIT																
Created On: 02/23/17		Updated On:														
BONDE	P		NE	5	17N	22E	Manitowoc		0-162-37-2012		0.0	0.0	1		2.755	0.563
55-36-008-PIT																
Created On: 07/09/12		Updated On:														
BONDE	P		NE	5	17N	22E	Manitowoc		0-223-2-2017		0.0	0.0	1		2.735	0.969
55-36-008-PIT																
Created On: 02/13/17		Updated On:														
BREUNIG	P	NE	NW	7	9N	7E	Dane		0-162-6-2012		0.0	0.0	1		2.672	0.715
55-13-006-PIT																
Created On: 01/19/12		Updated On:														
BREUNIG	P	NE	NW	7	9N	7E	Dane		0-223-10-2017		0.0	0.0	1		2.663	0.857
55-13-006-PIT																
Created On: 02/13/17		Updated On:														
BROCK	P		NE	29	31N	7E	Lincoln		0-162-11-2015		0.0	0.0	1		2.633	0.725
55-35-003-PIT																
Created On: 03/20/15		Updated On:														
BROWN	P	NW	SW	18	12N	10E	Columbia		0-162-21-2012		0.0	0.0	1		2.644	0.492
55-11-010-PIT																
Created On: 04/18/12		Updated On:														

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric			
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
BROWN	P	NW	SW	18	12N	10E	Columbia		0-223-3-2018	0.0	0.0	2		2.641	0.503
55-11-010-PIT															
Created On: 01/03/18		Updated On:													
BRUHA	P	SW	NE	13	36N	12W	Barron		0-162-20-2012	0.0	0.0	1		2.654	0.644
55-03-008-PIT															
Created On: 04/18/12		Updated On:													
BRUHA	P	SW	NE	13	36N	12W	Barron		0-162-30-2015	0.0	0.0	1		2.642	1.092
55-03-008-PIT															
Created On: 07/01/15		Updated On:													
BUCKLEY	Q	NW	NW	32	48N	12W	Douglas		0-223-35-2017	0.0	0.0	1		2.805	1.616
55-16-002-QRY															
Created On: 08/16/17		Updated On:													
BURLINGTON SPRING VALLEY	P			6	2N	19E	Racine		0-162-32-2016	0.0	0.0	1		2.622	1.502
55-51-006-PIT															
Created On: 03/28/16		Updated On:													
CAPITOL SAND & GRAVEL	P			11	7N	7E	Dane		0-162-10-2012	0.0	0.0	1		2.643	0.533
55-13-010-PIT															
Created On: 03/22/12		Updated On:													
CAPITOL SAND & GRAVEL	P			11	7N	7E	Dane		0-223-57-2018	0.0	0.0	1		2.630	0.949
55-13-010-PIT															
Created On: 09/27/18		Updated On:													

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	Crse	Fine	Crse	Fine
CAREW - EDEN	P	W	SE	23	14N	18E	Fond Du Lac	0-162-11-2011		0.0	0.0	1			2.714		1.226
55-20-006-PIT Created On: 01/28/11 Updated On:																	
CAREW - EDEN	P	W	SE	23	14N	18E	Fond Du Lac	0-162-20-2016		0.0	0.0	1			2.716		1.000
55-20-006-PIT Created On: 01/25/16 Updated On:																	
CAREW-MARIBEL	P	NE	NW	19	21N	22E	Manitowoc	0-223-54-2018		0.0	0.0	1			2.711		1.174
55-36-013-PIT Created On: 08/15/18 Updated On:																	
CASEY	P		SE	16	30N	18W	St. Croix	0-162-7-2015		0.0	0.0	1			2.652		0.695
55-55-016-PIT Created On: 01/16/15 Updated On:																	
CEDAR LAKE	P	N	SW	35	11N	18E	Washington	0-162-35-2015		0.0	0.0	1			2.685		0.857
55-66-004-PIT Created On: 08/13/15 Updated On:																	
CEDAR LAKE S&G-DIVISION ROAD	P	SW	NE	19	15N	20E	Sheboygan	0-162-20-2011		0.0	0.0	1			2.715		0.372
55-59-003-PIT Created On: 04/22/11 Updated On:																	
CEDAR LAKE S&G-DIVISION ROAD	P	SW	NE	19	15N	20E	Sheboygan	0-162-6-2016		0.0	0.0	1			2.693		1.061
55-59-003-PIT Created On: 01/04/16 Updated On:																	

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS	LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
CEMETERY	P			18	7N	7W	Crawford	0-162-44-2011		0.0	0.0	1		2.660	0.231
55-12-006-PIT		Created On: 09/30/11		Updated On:											
CEMETERY	P			18	7N	7W	Crawford	0-162-4-2016		0.0	0.0	1		2.623	0.756
55-12-006-PIT		Created On: 01/04/16		Updated On:											
CLARK	P	NW	SW	26	41N	17W	Pine	0-162-34-2011		0.0	0.0	1		2.703	0.796
27-00-013-PIT		Created On: 06/16/11		Updated On:											
CLARK	P	NW	SW	26	41N	17W	Pine	0-162-48-2016		0.0	0.0	1		2.681	0.990
27-00-013-PIT		Created On: 05/11/16		Updated On:											
COLRUE	P	SW	NE	31	23N	12E	Waupaca	0-223-19-2018		0.0	0.0	1		2.646	0.492
55-68-033-PIT		Created On: 03/07/18		Updated On:											
CRETEX-MAIN	P		NW	6	2N	19E	Racine	0-162-5-2013		0.0	0.0	1		2.671	0.644
55-51-015-PIT		Created On: 01/25/13		Updated On:											
CRETEX-MAIN	P		NW	6	2N	19E	Racine	0-223-41-2018		0.0	0.0	1		2.651	1.245
55-51-015-PIT		Created On: 05/23/18		Updated On:											

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS				LA Wear (%)	Sp. Gravity		Absorp. %	
											100	500	Crse	Fine	Crse	Fine
CROFT	Q	NW	SE	24	6N	3W	Grant	0-223-40-2018		0.0	0.0	1			2.664	0.583
55-22-010-QRY Created On: 05/23/18 Updated On:																
CRONIN	P	S	SE	5	2N	13E	Rock	0-162-2-2013		0.0	0.0	1			2.640	1.215
55-53-006-PIT Created On: 01/10/13 Updated On:																
CRONIN	P	S	SE	5	2N	13E	Rock	0-223-39-2018		0.0	0.0	1			2.630	1.092
55-53-006-PIT Created On: 05/21/18 Updated On:																
CROOKED LAKE	P	SW	NW	36	47N	8W	Bayfield	0-162-27-2014		0.0	0.0	1			2.672	0.604
55-04-003-PIT Created On: 06/19/14 Updated On:																
CROOKED LAKE	P	SW	NW	36	47N	8W	Bayfield	0-223-8-2019		0.0	0.0	1			2.660	0.766
55-04-003-PIT Created On: 01/02/19 Updated On:																
CRYSTAL LAKE	P	E	SE	32	16N	21E	Sheboygan	0-162-41-2011		0.0	0.0	1			2.727	0.675
55-59-004-PIT Created On: 08/24/11 Updated On:																
CRYSTAL LAKE	P	E	SE	32	16N	21E	Sheboygan	0-162-35-2012		0.0	0.0	1			2.741	0.432
55-59-004-PIT Created On: 06/28/12 Updated On:																

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS	LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
CUSTER	P		E	4	23N	9E	Portage	0-162-8-2011		0.0	0.0	1		2.642	0.442
55-49-004-PIT															
Created On: 01/20/11		Updated On:													
CUSTER	P		E	4	23N	9E	Portage	0-162-11-2016		0.0	0.0	1		2.641	0.452
55-49-004-PIT															
Created On: 01/04/16		Updated On:													
DELPHOSE	P	W	SE	2	22N	18E	Outagamie	0-162-13-2012		0.0	0.0	1		2.730	0.604
55-44-010-PIT															
Created On: 03/30/12		Updated On:													
DIPPEL	P	NE	SE	32	15N	20E	Sheboygan	0-162-18-2013		0.0	0.0	1		2.694	0.523
55-59-005-PIT															
Created On: 05/06/13		Updated On:													
DUESSING	P	N	SW	33	32N	1E	Taylor	0-162-32-2012		0.0	0.0	1		2.683	0.735
55-60-007-PIT															
Created On: 06/06/12		Updated On:													
DUESSING	P	N	SW	33	32N	1E	Taylor	0-223-32-2017		0.0	0.0	1		2.646	1.082
55-60-007-PIT															
Created On: 06/29/17		Updated On:													
DW	P		SW	7	3N	13E	Rock	0-223-45-2019		0.0	0.0	1		2.656	0.806
55-53-043-PIT															
Created On: 06/20/19		Updated On:													

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric					
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS	LA Wear (%)	Sp. Gravity	Absorp. %		
											100	500	Crse	Fine	Crse	Fine
EASTON	P		SW	23	29N	9E	Marathon	0-162-7-2012		0.0	0.0	1			2.647	0.412
55-37-026-PIT Created On: 03/21/12 Updated On:																
EASTON	P		SW	23	29N	9E	Marathon	0-223-9-2017		0.0	0.0	1			2.634	0.523
55-37-026-PIT Created On: 02/13/17 Updated On:																
ELMWOOD	Q	SE	SE	36	27N	15W	Pierce	0-162-19-2015		0.0	0.0	1			2.624	2.312
55-47-008-QRY Created On: 04/27/15 Updated On:																
EVERS	P	NE	SW	5	21N	18E	Outagamie	0-223-51-2018		0.0	0.0	1			2.729	0.837
55-44-030-PIT Created On: 07/05/18 Updated On:																
FAULKES Q-PIT	P	SW	SE	17	22N	11E	Waupaca	0-162-17-2012		0.0	0.0	1			2.655	0.311
55-68-010-PIT Created On: 04/10/12 Updated On:																
* FEHR	P	NE	NE	36	27N	10W	Eau Claire	0-162-14-2014		0.0	0.0	1			2.870	0.664
55-18-006-PIT Created On: 03/27/14 Updated On:																
FILMORE	P		SW	36	87N	1W	Dubuque	0-162-34-2015		0.0	0.0	1			2.596	0.847
19-00-004-PIT Created On: 08/05/15 Updated On:																

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric			
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
FOLEY ROAD	P	SE	SW	7	22N	11E	Waupaca	0-162-21-2013		0.0	0.0	1		2.641	0.220
55-68-011-PIT															
Created On: 05/08/13		Updated On:													
FOLEY ROAD	P	SE	SW	7	22N	11E	Waupaca	0-223-27-2018		0.0	0.0	1		2.641	0.482
55-68-011-PIT															
Created On: 03/23/18		Updated On:													
FOX RIDGE	P		NE	22	12N	6E	Sauk	0-162-38-2016		0.0	0.0	1		2.644	0.492
55-56-008-PIT															
Created On: 04/13/16		Updated On:													
FRANK BROS MH	P	SW	NE	2	3N	13E	Rock	0-223-46-2018		0.0	0.0	1		2.652	0.918
55-53-012-PIT															
Created On: 06/19/18		Updated On:													
FRANK BROS. MH	Q	SW	NE	2	3N	13E	Rock	0-162-25-2012		0.0	0.0	1		2.641	0.837
55-53-014-QRY															
Created On: 04/26/12		Updated On:													
FRITZ	P	NE	SW	23	19N	10E	Waushara	0-223-7-2017		0.0	0.0	1		2.642	0.715
55-69-004-PIT															
Created On: 02/13/17		Updated On:													
* FRONTANAC	P		SW	14	112N	13W	Goodhue	0-162-32-2014		0.0	0.0	2		2.675	0.857
27-00-006-PIT															
Created On: 08/07/14		Updated On:													

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric					
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS	LA Wear (%)	Sp. Gravity		Absorp. %	
											100	500	Crse	Fine	Crse	Fine
FROSTMAN	P		NW	26	47N	8W	Bayfield	0-162-26-2014		0.0	0.0	1			2.655	0.654
55-04-004-PIT		Created On: 06/19/14		Updated On:												
FROSTMAN	P		NW	26	47N	8W	Bayfield	0-223-9-2019		0.0	0.0	1			2.668	0.827
55-04-004-PIT		Created On: 01/02/19		Updated On:												
GANDER MOUNTAIN	P			5	46N	9E	Mchenry	0-162-14-2013		0.0	0.0	1			2.648	0.980
17-00-006-PIT		Created On: 04/19/13		Updated On:												
GANDER MOUNTAIN	P			5	46N	9E	Mchenry	0-223-11-2018		0.0	0.0	1			2.612	1.523
17-00-006-PIT		Created On: 01/05/18		Updated On:												
GENESEE / HILLVIEW	P		SE	8	8N	19E	Waukesha	0-162-8-2016		0.0	0.0	1			2.633	1.184
55-67-005-PIT		Created On: 01/04/16		Updated On:												
GENESSE/OTTAWA	P		SW	1	6N	17E	Waukesha	0-162-1-2011		0.0	0.0	1			2.654	0.807
55-67-006-PIT		Created On: 01/05/11		Updated On:												
GENESSE/OTTAWA	P		SW	1	6N	17E	Waukesha	0-162-9-2016		0.0	0.0	1			2.642	0.929
55-67-006-PIT		Created On: 01/04/16		Updated On:												

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric			
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
GENESSEE	P	NE	SE	29	6N	18E	Waukesha	0-162-2-2011		0.0	0.0	1		2.631	0.969
55-67-007-PIT Created On: 01/05/11 Updated On:															
GENESSEE	P	NE	SE	29	6N	18E	Waukesha	0-162-10-2016		0.0	0.0	1		2.636	1.235
55-67-007-PIT Created On: 01/04/16 Updated On:															
GIBB	P		SE	25	18N	9W	Trempealeau	0-162-18-2014		0.0	0.0	1		2.609	1.031
55-61-006-PIT Created On: 05/15/14 Updated On:															
GIBB	P		SE	25	18N	9W	Trempealeau	0-223-49-2019		0.0	0.0	1		2.638	0.685
55-61-006-PIT Created On: 08/19/19 Updated On:															
GRAHL-EMPIRE	P	S	SE	36	15N	18E	Fond Du Lac	0-162-50-2016		0.0	0.0	1		2.699	1.143
55-20-014-PIT Created On: 05/18/16 Updated On:															
GRANT RIVER	P	SW	NE	10	3N	2N	Grant	0-162-15-2015		0.0	0.0	1		2.635	0.766
55-22-018-PIT Created On: 04/10/15 Updated On:															
GREY CLOUD NELSON	P	S	NW	31	27N	21W	Lakeland	0-162-39-2016		0.0	0.0	1		2.634	1.802
27-00-010-PIT Created On: 04/13/16 Updated On:															

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric			
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
GUELIG	P	NW	SE	9	16N	19E	Fond Du Lac	0-162-6-2011		0.0	0.0	1		2.761	0.929
55-20-015-PIT															
Created On: 01/05/11		Updated On:													
HAAS 124	P	SE	SE	6	30N	8W	Chippewa	0-223-44-2019		0.0	0.0	1		2.653	0.715
55-09-025-PIT															
Created On: 06/10/19		Updated On:													
* HACKBARTH	Q	NW	NE	8	105N	6W	Wabasha	0-162-44-2016		0.0	0.0	1		2.619	0.837
27-00-018-QRY															
Created On: 04/25/16		Updated On:													
HAEF	P	SW	NE	19	18N	8W	Trempealeau	0-162-19-2014		0.0	0.0	1		2.607	0.960
55-61-007-PIT															
Created On: 05/15/14		Updated On:													
HAEF	P	SW	NE	19	18N	8W	Trempealeau	0-223-30-2019		0.0	0.0	1		2.603	0.929
55-61-007-PIT															
Created On: 04/09/19		Updated On:													
HALQUIST NORTH LAKE	P		SE	9	8N	18E	Waukesha	0-223-49-2018		0.0	0.0	1		2.666	1.204
55-67-032-PIT															
Created On: 06/28/18		Updated On:													
HANSON	P		SE	28	34N	11W	Barron	0-162-14-2016		0.0	0.0	3		2.629	0.898
55-03-022-PIT															
Created On: 01/05/16		Updated On:													

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS				LA Wear (%)	Sp. Gravity		Absorp. %	
											100	500	Crse	Fine	Crse	Fine
HARTMAN SPRING LAKE	P	SE	NE	3	12N	21E	Ozaukee	0-223-38-2019		0.0	0.0	1			2.734	0.705
55-45-004-PIT Created On: 05/01/19 Updated On:																
HASTINGS	P	S	SE	11	114N	17W	Dakota	0-162-58-2016		0.0	0.0	1			2.639	0.735
27-00-029-PIT Created On: 10/12/16 Updated On:																
HELENA	P	NE	NE	16	8N	4E	Iowa	0-162-2-2012		0.0	0.0	1			2.654	0.594
55-25-013-PIT Created On: 01/11/12 Updated On:																
HELENA	P	NE	NE	16	8N	4E	Iowa	0-223-33-2019		0.0	0.0	1			2.638	0.311
55-25-013-PIT Created On: 04/18/19 Updated On:																
HELLICKSON	P	SE	NW	34	7N	11E	Dane	0-162-24-2012		0.0	0.0	1			2.674	0.573
55-13-031-PIT Created On: 04/23/12 Updated On:																
HELLICKSON	P	SE	NW	34	7N	11E	Dane	0-223-20-2017		0.0	0.0				2.658	1.010
55-13-031-PIT Created On: 04/13/17 Updated On:																
HERFEL	P	S	SE	28	6N	8E	Dane	0-223-51-2019		0.0	0.0	1			2.655	0.513
55-13-033-PIT Created On: 09/03/19 Updated On:																

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS				LA Wear (%)	Sp. Gravity		Absorp. %	
											100	500	Crse	Fine	Crse	Fine
HEYN	P	W	NE	22	19N	8E	Waushara	0-162-36-2016		0.0	0.0	1			2.689	0.725
55-69-006-PIT Created On: 04/07/16 Updated On:																
HIGH POINT	P	SW	NW	36	39N	7E	Oneida	0-223-37-2019		0.0	0.0	1			2.614	0.867
55-43-010-PIT Created On: 04/25/19 Updated On:																
HILGER	P			8	30N	8W	Chippewa	0-223-15-2018		0.0	0.0	1			2.659	0.908
55-09-031-PIT Created On: 02/15/18 Updated On:																
HILGER	P			8	30N	8W	Chippewa	0-223-10-2019		0.0	0.0				2.660	0.725
55-09-031-PIT Created On: 01/02/19 Updated On:																
HILLSIDE	P		SE	7	2N	19E	Racine	0-162-16-2014		0.0	0.0	1			2.631	1.071
55-51-010-PIT Created On: 04/07/14 Updated On:																
HILLSIDE	P		SE	7	2N	19E	Racine	0-223-22-2019		0.0	0.0	1			2.651	1.082
55-51-010-PIT Created On: 02/25/19 Updated On:																
HOLDER PIT	P	NW	SE	30	12N	11E	Columbia	0-223-12-2017		0.0	0.0	1			2.670	0.806
55-11-017-PIT Created On: 02/14/17 Updated On:																

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%)		Sp. Gravity		Absorp. %		
												100	500	Crse	Fine	Crse	Fine	
HOLLATZ	P	NE	NW	17	16N	14E	Fond Du Lac	0-162-7-2011		0.0	0.0	1			2.685		0.381	
55-20-017-PIT																		
Created On: 01/05/11		Updated On:																
HOLST	P		W	33	25N	18W	Pierce	0-223-56-2018		0.0	0.0	1			2.628		0.878	
55-47-010-PIT																		
Created On: 09/06/18		Updated On:																
HOWE SAND	P	SW	NW	19	18N	8W	Trempealeau	0-162-3-2014		0.0	0.0	1			2.556		0.664	
55-61-008-PIT																		
Created On: 01/02/14		Updated On:																
HOWE SAND	P	SW	NW	19	18N	8W	Trempealeau	0-223-20-2018		0.0	0.0	2			2.623		0.735	
55-61-008-PIT																		
Created On: 03/14/18		Updated On:																
HUGHES	Q		SW	15	28N	14W	Dunn	0-162-11-2014		0.0	0.0	1			2.685		0.130	
55-17-015-QRY																		
Created On: 02/17/14		Updated On:																
HURD PIT	P	NW	SW	15	4N	12E	Rock	0-162-14-2015		0.0	0.0	1			2.633		1.368	
55-53-017-PIT																		
Created On: 04/01/15		Updated On:																
HURD PIT	P	NW	SW	15	4N	12E	Rock	0-162-42-2016		0.0	0.0	1			2.613		1.502	
55-53-017-PIT																		
Created On: 04/14/16		Updated On:																

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric			
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
HURD PIT	P	NW	SW	15	4N	12E	Rock	0-223-43-2018		0.0	0.0			2.620	1.286
55-53-017-PIT															
Created On: 06/08/18		Updated On:													
INDIAN LAKE	P	E	NE	6	38N	10E	Oneida	0-162-54-2016		0.0	0.0	1		2.609	0.857
55-43-006-PIT															
Created On: 08/08/16		Updated On:													
J + R SAND PIT	P	SW	NE	24	8N	3W	Grant	0-162-1-2014		0.0	0.0	1		2.653	0.180
55-22-027-PIT															
Created On: 01/02/14		Updated On:													
J + R SAND PIT	P	SW	NE	24	8N	3W	Grant	0-223-52-2019		0.0	0.0	1		2.650	0.432
55-22-027-PIT															
Created On: 09/30/19		Updated On:													
JACOBSEN	P		SW	20	3N	16E	Walworth	0-223-40-2019		0.0	0.0	1		2.621	1.204
55-64-054-PIT															
Created On: 05/16/19		Updated On:													
JADIN	P	NE	SE	31	25N	25E	Kewaunee	0-162-29-2015		0.0	0.0	1		2.691	1.245
55-31-006-PIT															
Created On: 06/25/15		Updated On:													
JANESVILLE SAND & GRAVEL	P	SE	SW	24	3N	12E	Rock	0-162-4-2012		0.0	0.0	1		2.630	0.725
55-53-018-PIT															
Created On: 01/13/12		Updated On:													

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine		
JANESVILLE SAND & GRAVEL	P	SE	SW	24	3N	12E	Rock		0-162-8-2015		0.0	0.0	1		2.626	0.969
55-53-018-PIT																
Created On: 03/02/15 Updated On:																
JENNEMAN	P		NE	6	30N	8W	Chippewa		0-223-14-2018		0.0	0.0	1		2.638	1.010
55-09-032-PIT																
Created On: 02/14/18 Updated On:																
JENNEMAN	P		NE	6	30N	8W	Chippewa		0-223-11-2019		0.0	0.0	1		2.660	0.746
55-09-032-PIT																
Created On: 01/02/19 Updated On:																
JOHNSON - GENESEE CTH C	P		SW	6	6N	18E	Waukesha		0-162-28-2013		0.0	0.0	1		2.608	1.554
55-67-014-PIT																
Created On: 05/22/13 Updated On:																
JOHNSON - GENESEE CTH C	P		SW	6	6N	18E	Waukesha		0-223-28-2018		0.0	0.0	1		2.627	0.929
55-67-014-PIT																
Created On: 04/03/18 Updated On:																
JOHNSON S&G BOWERS ROAD	P		NE	2	3N	17E	Walworth		0-162-46-2016		0.0	0.0	1		2.619	1.338
55-64-015-PIT																
Created On: 05/04/16 Updated On:																
JOHNSON S&G BOWERS ROAD	P		NE	2	3N	17E	Walworth		0-223-34-2019		0.0	0.0	1		2.651	1.194
55-64-015-PIT																
Created On: 04/18/19 Updated On:																

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric			
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
JOHNSON S&G-MAINKA-CTH J	P		SW	4	3N	18E	Walworth	0-162-27-2016		0.0	0.0	1		2.633	1.204
55-64-020-PIT		Created On: 03/09/16 Updated On:													
K & N	P		S	9	8N	19E	Waukesha	0-223-18-2019		0.0	0.0	1		2.651	1.092
55-67-019-PIT		Created On: 02/13/19 Updated On:													
* K AND N	P		S	9	8N	19E	Waukesha	0-162-5-2014		0.0	0.0	1		2.663	0.817
55-67-019-PIT		Created On: 01/02/14 Updated On:													
KAPINUS	P			12	7N	7W	Crawford	0-223-53-2019		0.0	0.0	1		2.623	0.533
55-12-026-PIT		Created On: 09/30/19 Updated On:													
KEIPE - PETERSON	P	SW	NW	35	16N	12E	Green Lake	0-162-20-2013		0.0	0.0	1		2.686	0.604
55-24-003-PIT		Created On: 05/06/13 Updated On:													
KEIPE - PETERSON	P	SW	NW	35	16N	12E	Green Lake	0-223-33-2018		0.0	0.0	1		2.671	0.898
55-24-003-PIT		Created On: 05/02/18 Updated On:													
KING	Q	NW	NW	19	38N	10E	Oneida	0-162-36-2011		0.0	0.0	1		2.638	0.452
55-43-008-QRY		Created On: 06/27/11 Updated On:													

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%)		Sp. Gravity		Absorp. %		
												100	500	Crse	Fine	Crse	Fine	
KING	Q	NW	NW	19	38N	10E	Oneida	0-162-16-2013		0.0	0.0	1			2.583		0.381	
55-43-008-QRY																		
Created On: 04/22/13		Updated On:																
KLEGIN	P	SW	NW	11	23N	13E	Waupaca	0-162-35-2014		0.0	0.0	1			2.633		0.543	
55-68-015-PIT																		
Created On: 08/07/14		Updated On:																
KLEGIN	P	SW	NW	11	23N	13E	Waupaca	0-223-16-2019		0.0	0.0	1			2.650		0.351	
55-68-015-PIT																		
Created On: 01/29/19		Updated On:																
LADYSMITH EAST	P	S	NW	15	35N	6W	Rusk	0-162-38-2014		0.0	0.0	1			2.660		0.858	
55-54-012-PIT																		
Created On: 09/08/14		Updated On:																
LAFARGE COLGATE	P	S	NW	3	8N	19E	Waukesha	0-162-16-2011		0.0	0.0	1			2.672		0.675	
55-67-021-PIT																		
Created On: 03/17/11		Updated On:																
LAFARGE COLGATE	P	S	NW	3	8N	19E	Waukesha	0-162-1-2016		0.0	0.0	1			2.674		1.163	
55-67-021-PIT																		
Created On: 01/04/16		Updated On:																
LAFARGE COLGATE	P	S	NW	3	8N	19E	Waukesha	0-223-26-2018		0.0	0.0	1			2.662		1.410	
55-67-021-PIT																		
Created On: 03/23/18		Updated On:																

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS	LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
LAFARGE-DYER LAKE	P		W	29	2N	19E	Kenosha	0-162-2-2016		0.0	0.0	1		2.655	1.235
55-30-004-PIT Created On: 01/04/16 Updated On:															
LAFARGE-DYER LAKE	P		W	29	2N	19E	Kenosha	0-223-25-2018		0.0	0.0	1		2.648	1.133
55-30-004-PIT Created On: 03/23/18 Updated On:															
LAFARGE-DYER LAKE	P		W	29	2N	19E	Kenosha	0-223-38-2018		0.0	0.0	1		2.640	1.399
55-30-004-PIT Created On: 05/17/18 Updated On:															
LAGRANGE	P	W	SE	20	4N	16E	Walworth	0-162-7-2014		0.0	0.0	1		2.588	0.482
55-64-024-PIT Created On: 01/02/14 Updated On:															
LAGRANGE	P	W	SE	20	4N	16E	Walworth	0-223-34-2017		0.0	0.0	1		2.637	1.194
55-64-024-PIT Created On: 08/10/17 Updated On:															
LAGRANGE	P	W	SE	20	4N	16E	Walworth	0-223-19-2019		0.0	0.0	1		2.645	1.266
55-64-024-PIT Created On: 02/13/19 Updated On:															
LAKELAND	P	SE	SE	27	29N	20W	Washington	0-162-10-2013		0.0	0.0	1		2.660	0.371
27-00-021-PIT Created On: 02/21/13 Updated On:															

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS				LA Wear (%)	Sp. Gravity		Absorp. %	
											100	500	Crse	Fine	Crse	Fine
LAKELAND	P	SE	SE	27	29N	20W	Washington	0-223-36-2017		0.0	0.0	1			2.652	0.513
27-00-021-PIT																
Created On: 09/13/17 Updated On:																
LANNON LISBON PIT	P		SW	24	8N	19E	Waukesha	0-162-4-2015		0.0	0.0	1			2.710	1.031
55-67-024-PIT																
Created On: 01/16/15 Updated On:																
LANNON LISBON PIT	P		SW	24	8N	19E	Waukesha	0-162-16-2016		0.0	0.0	1			2.668	0.543
55-67-024-PIT																
Created On: 01/06/16 Updated On:																
LANNON STONE - JACKSON	Q		NE	12	10N	20E	Washington	0-162-8-2013		0.0	0.0	1			2.726	0.878
55-66-012-QRY																
Created On: 02/20/13 Updated On:																
LATHER	P	NW	NW	16	1N	13E	Rock	0-162-37-2015		0.0	0.0	1			2.625	1.031
55-53-022-PIT																
Created On: 08/21/15 Updated On:																
LATHER	P	NW	NW	16	1N	13E	Rock	0-162-40-2016		0.0	0.0	1			2.613	1.225
55-53-022-PIT																
Created On: 04/14/16 Updated On:																
LATHER	P	NW	NW	16	1N	13E	Rock	0-223-13-2018		0.0	0.0	1			2.614	1.215
55-53-022-PIT																
Created On: 01/24/18 Updated On:																

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric					
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS	LA Wear (%)	Sp. Gravity	Absorp. %		
											100	500	Crse	Fine	Crse	Fine
LATHER	P	NW	NW	16	1N	13E	Rock	0-223-7-2019		0.0	0.0	1			2.635	1.031
55-53-022-PIT Created On: 01/02/19 Updated On:																
LAWIN	P		NE	18	30N	8W	Chippewa	0-162-10-2011		0.0	0.0	1			2.623	1.061
55-09-039-PIT Created On: 01/20/11 Updated On:																
LAWIN	P		NE	18	30N	8W	Chippewa	0-162-2-2015		0.0	0.0	1			2.654	0.807
55-09-039-PIT Created On: 01/16/15 Updated On:																
LAWRY	P			17	5N	9E	Dane	0-223-19-2017		0.0	0.0				2.598	1.235
55-13-052-PIT Created On: 04/13/17 Updated On:																
LEATHERBERRY	P	E	NW	26	12N	6E	Sauk	0-162-55-2016		0.0	0.0	1			2.657	0.482
55-56-017-PIT Created On: 08/08/16 Updated On:																
LEE	P	SE	NW	3	12N	6E	Sauk	0-223-42-2018		0.0	0.0	1			2.663	0.594
55-56-018-PIT Created On: 05/29/18 Updated On:																
LENA	P		SE	20	29N	21E	Oconto	0-162-43-2016		0.0	0.0	1			2.663	0.888
55-42-036-PIT Created On: 04/21/16 Updated On:																

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	Crse	Fine	Crse	Fine
LEVIS PINES	P			6	21N		Jackson	0-223-47-2018		0.0	0.0	1			2.616	0.817
55-27-013-PIT Created On: 06/27/18 Updated On:																
LINCOLN CTH W	P	E	SW	33	31N	7E	Lincoln	0-223-6-2017		0.0	0.0	1			2.625	0.888
55-35-041-PIT Created On: 02/13/17 Updated On:																
LIND	P	SE	NE	20	23N	13E	Waupaca	0-162-23-2013		0.0	0.0	1			2.656	0.200
55-68-021-PIT Created On: 05/15/13 Updated On:																
LIND	P	SE	NE	20	23N	13E	Waupaca	0-223-15-2019		0.0	0.0	1			2.638	0.583
55-68-021-PIT Created On: 01/29/19 Updated On:																
LINDBERG AND SONS	P	NW	SW	5	40N	30W	Dickerson	0-162-35-2011		0.0	0.0	1			2.679	0.432
26-00-001-PIT Created On: 06/27/11 Updated On:																
LINDBERG AND SONS	P	NW	SW	5	40N	30W	Dickerson	0-223-3-2019		0.0	0.0	1			2.661	0.796
26-00-001-PIT Created On: 01/02/19 Updated On:																
LITCHFIELD	P	SW	SE	34	27N	10W	Eau Claire	0-162-26-2016		0.0	0.0	1			2.629	0.614
55-18-008-PIT Created On: 02/29/16 Updated On:																

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric			
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
LUND / RIOPEL	P	SW	SW	6	36N	8E	Oneida	0-162-30-2013		0.0	0.0	1		2.644	0.685
55-43-013-PIT															
Created On: 06/13/13		Updated On:													
LUTZKE	P	SE	SE	20	18N	22E	Manitowoc	0-162-36-2012		0.0	0.0	1		2.709	0.381
55-36-022-PIT															
Created On: 06/28/12		Updated On:													
LUTZKE	P	SE	SE	20	18N	22E	Manitowoc	0-223-4-2017		0.0	0.0	1		2.761	0.786
55-36-022-PIT															
Created On: 02/13/17		Updated On:													
MADISON SAND AND GRAVEL	P	NW	SE	22	9N	9E	Dane	0-162-44-2012		0.0	0.0	1		2.688	0.533
55-13-056-PIT															
Created On: 10/03/12		Updated On:													
MADISON SAND AND GRAVEL	P	NW	SE	22	9N	9E	Dane	0-223-24-2017		0.0	0.0	1		2.675	0.817
55-13-056-PIT															
Created On: 05/15/17		Updated On:													
MANCHESTER	P		SW	10	88N	5W	Delaware	0-162-33-2015		0.0	0.0	1		2.592	0.837
19-00-001-PIT															
Created On: 08/05/15		Updated On:													
MANTHEY EAST	P			26	17N	7E	Adams	0-162-37-2016		0.0	0.0	1		2.652	0.462
55-01-004-PIT															
Created On: 04/13/16		Updated On:													

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric			
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
MARIBEL	P	NE	NW	28	21N	22E	Manitowoc	0-223-37-2017		0.0	0.0	1		2.691	1.051
55-36-44-PIT	Created On: 10/11/17 Updated On:														
MARION AGGREGATES	P	SW	NW	5	25N	13E	Waupaca	0-162-15-2011		0.0	0.0	1		2.647	0.331
55-68-022-PIT	Created On: 03/16/11 Updated On:														
MARION AGGREGATES	P	SW	NW	5	25N	13E	Waupaca	0-162-15-2016		0.0	0.0	1		2.642	0.583
55-68-022-PIT	Created On: 01/06/16 Updated On:														
* MATTRISCH PIT	P			4	31N	19E	Marinette	0-162-37-2014		0.0	0.0	1		2.645	1.051
55-38-019-PIT	Created On: 09/08/14 Updated On:														
MCCLAIN	P	SW	NE	9	35N	13W	Barron	0-162-20-2015		0.0	0.0	1		2.660	0.898
55-03-027-PIT	Created On: 04/27/15 Updated On:														
* MCCUSKY	P		N	23	45N	12W	Douglas	0-162-39-2012		0.0	0.0	2		2.631	0.553
55-16-012-PIT	Created On: 07/09/12 Updated On:														
* MCCUSKY	P		N	23	45N	12W	Douglas	0-162-31-2014		0.0	0.0	4		2.611	0.715
55-16-012-PIT	Created On: 07/30/14 Updated On:														

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric					
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS	Plate	LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
MEDINA	P		SW	19	21N	16E	Outagamie	0-223-52-2018		0.0	0.0	1		2.701	0.513	
55-44-016-PIT		Created On: 07/05/18 Updated On:														
MERRILLAN-734 (PIT)	P	NW	SW	13	23N	3W	Clark	0-162-17-2013		0.0	0.0	1		2.631	0.786	
55-10-019-PIT		Created On: 04/22/13 Updated On:														
MERRILLAN-734 (PIT)	P	NW	SW	13	23N	3W	Clark	0-223-6-2018		0.0	0.0	1		2.643	0.695	
55-10-019-PIT		Created On: 01/03/18 Updated On:														
MEYER MATERIAL MCHENRY	P			29	45N	8E	Mchenry	0-223-50-2018		0.0	0.0	1		2.707	1.307	
17-00-011-PIT		Created On: 06/28/18 Updated On:														
* MEYER/DYERLAKE	P		W	29	2N	19E	Kenosha	0-162-13-2011		0.0	0.0	1		2.656	0.473	
55-30-004-PIT		Created On: 02/16/11 Updated On:														
MICHELS - MISHICOT	P	SE	SE	27	21N	23E	Manitowoc	0-162-25-2013		0.0	0.0	1		2.694	0.868	
55-36-025-PIT		Created On: 05/15/13 Updated On:														
MICHELS - MISHICOT	P	SE	SE	27	21N	23E	Manitowoc	0-162-3-2015		0.0	0.0	1		2.709	0.675	
55-36-025-PIT		Created On: 01/16/15 Updated On:														

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS	LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
MICHELS BECKER	P	SW	SW	27	11N	18E	Washington	0-162-23-2015		0.0	0.0	1		2.641	1.041
55-66-016-PIT															
Created On: 05/13/15		Updated On:													
MICHELS KELLING	P	N	NW	2	13N	20E	Sheboygan	0-162-42-2012		0.0	0.0	1		2.695	0.918
55-59-012-PIT															
Created On: 08/31/12		Updated On:													
MICHELS KELLING	P	N	NW	2	13N	20E	Sheboygan	0-223-1-2017		0.0	0.0	2		2.680	0.867
55-59-012-PIT															
Created On: 02/13/17		Updated On:													
MICHELS MANCHESTER	P	SW	SE	16	14N	12E	Green Lake	0-162-31-2015		0.0	0.0	1		2.634	1.000
55-24-010-PIT															
Created On: 07/14/15		Updated On:													
MICHELS MEYERS	P	NW	NW	36	20N	9E	Waushara	0-162-23-2011		0.0	0.0	1		2.676	0.301
55-69-012-PIT															
Created On: 05/05/11		Updated On:													
MICHELS MEYERS	P	NW	NW	36	20N	9E	Waushara	0-162-5-2016		0.0	0.0	1		2.625	1.605
55-69-012-PIT															
Created On: 01/04/16		Updated On:													
MICHELS MEYERS	P	NW	NW	36	20N	9E	Waushara	0-223-8-2017		0.0	0.0	1		2.654	0.523
55-69-012-PIT															
Created On: 02/13/17		Updated On:													

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	Crse	Fine	Crse	Fine
MILAS	P	SE	NW	3	29N	3W	Clark	0-162-1-2015		0.0	0.0	1			2.646	0.918
55-10-020-PIT Created On: 01/16/15 Updated On:																
MILESTONE RIEKEMANN PIT #222	P	SE	SW	4	26N	10W	Eau Claire	0-223-29-2019		0.0	0.0	1			2.626	0.654
55-18-011-PIT Created On: 04/09/19 Updated On:																
MILLIS	P	SE	NE	32	21N	4W	Jackson	0-223-28-2017		0.0	0.0	1			2.614	0.918
55-27-012-PIT Created On: 06/05/17 Updated On:																
MILLIS	P	SE	NE	32	21N	4W	Jackson	0-223-48-2018		0.0	0.0	1			2.635	0.533
55-27-012-PIT Created On: 06/27/18 Updated On:																
MITCH KING	P	SW	NE	6	26N	9E	Marathon	0-162-53-2016		0.0	0.0	1			2.619	0.472
55-37-051-PIT Created On: 08/03/16 Updated On:																
MORGAN	P	SE	SW	35	29N	5E	Marathon	0-162-34-2014		0.0	0.0	1			2.624	0.817
55-37-052-PIT Created On: 08/07/14 Updated On:																
MORGAN	P	SE	SW	35	29N	5E	Marathon	0-223-28-2019		0.0	0.0	1			2.594	0.959
55-37-052-PIT Created On: 04/08/19 Updated On:																

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine		
MORRISON	Q	SE	NW	35	25N	18W	Pierce		0-162-22-2013		0.0	0.0	1		2.702	0.746
55-47-018-QRY																
Created On: 05/13/13		Updated On:														
MROCZINSKI	P	SW	NW	16	29N	5E	Marathon		0-162-13-2013		0.0	0.0	1		2.626	1.062
55-37-054-PIT																
Created On: 03/25/13		Updated On:														
MURPHY	P	NW	NW	6	21N	4W	Jackson		0-162-29-2013		0.0	0.0	2		2.626	0.654
55-27-007-PIT																
Created On: 06/06/13		Updated On:														
MURPHY	P	NW	NW	6	21N	4W	Jackson		0-223-35-2018		0.0	0.0	1		2.615	0.908
55-27-007-PIT																
Created On: 05/09/18		Updated On:														
MURRAY	P	NE	SE	26	26N	23E	Door		0-162-17-2015		0.0	0.0	1		2.657	1.000
55-15-017-PIT																
Created On: 04/20/15		Updated On:														
MUSKEGO	P	SW	SW	18	5N	20E	Waukesha		0-223-8-2018		0.0	0.0	1		2.644	1.000
55-67-029-PIT																
Created On: 01/05/18		Updated On:														
MYKLEBUST	P		NE	26	13N	6E	Sauk		0-162-56-2016		0.0	0.0	1		2.673	0.503
55-56-023-PIT																
Created On: 08/08/16		Updated On:														

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	Crse	Fine	Crse	Fine
NEECK READY MIX	P	NW	NW	31	39N	1E	Price	0-162-15-2014			0.0	0.0	1			2.560	1.071
55-50-016-PIT																	
Created On: 03/28/14		Updated On:															
NEECK READY MIX	P	NW	NW	31	39N	1E	Price	0-223-2-2019			0.0	0.0	1			2.665	1.174
55-50-016-PIT																	
Created On: 01/02/19		Updated On:															
NEILLSVILLE	Q	SE	SW	10	24N	2W	Clark	0-223-32-2018			0.0	0.0	1			2.559	0.614
55-10-035-QRY																	
Created On: 04/25/18		Updated On:															
NELSON	P	SW	NW	12	13N	6E	Columbia	0-162-22-2015			0.0	0.0	1			2.613	0.959
55-11-029-PIT																	
Created On: 05/06/15		Updated On:															
NELSON MINE	P	NW	NW	13	28N	9W	Chippewa	0-162-5-2015			0.0	0.0	5			2.596	1.358
55-09-046-PIT																	
Created On: 01/16/15		Updated On:															
NEUMAN	P	NE	SE	28	32N	1E	Taylor	0-162-31-2012			0.0	0.0	1			2.684	1.041
55-60-018-PIT																	
Created On: 06/06/12		Updated On:															
NEUMAN	P	NE	SE	28	32N	1E	Taylor	0-223-31-2017			0.0	0.0	1			2.651	1.327
55-60-018-PIT																	
Created On: 06/29/17		Updated On:															

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric			
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
NLC MERCER	P	S	NW	6	42N	4E	Iron	0-162-29-2011		0.0	0.0	1		2.692	1.174
55-26-024-PIT															
Created On: 05/24/11		Updated On:													
NLC MERCER	P	S	NW	6	42N	4E	Iron	0-162-47-2016		0.0	0.0	1		2.680	1.092
55-26-024-PIT															
Created On: 05/04/16		Updated On:													
NLC PHILLIPS	P	SW	SW	5	37N	1E	Price	0-162-33-2014		0.0	0.0	2		2.652	0.705
55-50-019-PIT															
Created On: 08/07/14		Updated On:													
NLC WOODRUFF	P	NW	SE	14	40N	6E	Vilas	0-162-31-2013		0.0	0.0	1		2.657	0.634
55-63-013-PIT															
Created On: 06/13/13		Updated On:													
NLC WOODRUFF	P	NW	SE	14	40N	6E	Vilas	0-223-31-2018		0.0	0.0	1		2.657	0.806
55-63-013-PIT															
Created On: 04/16/18		Updated On:													
NOLL	P	NW	SW	8	30N	21E	Marinette	0-162-27-2015		0.0	0.0	1		2.657	1.184
55-38-022-PIT															
Created On: 06/18/15		Updated On:													
NORWAY GROVE	P	NW	SW	14	9N	9E	Dane	0-162-16-2015		0.0	0.0	1		2.673	0.847
55-13-068-PIT															
Created On: 04/16/15		Updated On:													

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS	LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
NORWAY GROVE	P	NW	SW	14	9N	9E	Dane	0-223-48-2019		0.0	0.0	1		2.674	0.817
55-13-068-PIT															
Created On: 07/15/19		Updated On:													
OLSON	P	NW	SW	14	41N	9W	Sawyer	0-162-15-2012		0.0	0.0	1		2.648	0.422
55-57-017-PIT															
Created On: 04/04/12		Updated On:													
OLSON	P	NW	SW	14	41N	9W	Sawyer	0-223-15-2017		0.0	0.0	1		2.657	0.685
55-57-017-PIT															
Created On: 02/24/17		Updated On:													
OLYNICK (@ JUMP RIVER)	P	NE	SE	14	33N	4W	Taylor	0-162-23-2014		0.0	0.0	1		2.681	0.867
55-60-016-PIT															
Created On: 06/02/14		Updated On:													
OLYNICK (@ JUMP RIVER)	P	NE	SE	14	33N	4W	Taylor	0-223-7-2018		0.0	0.0	1		2.653	1.031
55-60-016-PIT															
Created On: 01/03/18		Updated On:													
OPELT PIT	P	NE	NW	8	23N	2W	Clark	0-162-14-2012		0.0	0.0	1		2.638	0.960
55-10-023-PIT															
Created On: 03/30/12		Updated On:													
OPELT PIT	P	NE	NW	8	23N	2W	Clark	0-223-21-2017		0.0	0.0	1		2.630	1.061
55-10-023-PIT															
Created On: 05/01/17		Updated On:													

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric			
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
OREGON	P	NW	SE	36	5N	9E	Dane	0-223-50-2019		0.0	0.0	1		2.617	1.482
55-13-112-PIT															
Created On: 09/03/19		Updated On:													
P&D HONEY CREEK	P		NW	6	3N	19E	Racine	0-223-9-2018		0.0	0.0	1		2.658	1.286
55-51-020-PIT															
Created On: 01/05/18		Updated On:													
PADDOCK	P	E	SE	1	3N	16E	Walworth	0-162-19-2013		0.0	0.0	1		2.649	0.878
55-64-028-PIT															
Created On: 05/06/13		Updated On:													
PADDOCK	P	E	SE	1	3N	16E	Walworth	0-223-30-2018		0.0	0.0	1		2.647	1.071
55-64-028-PIT															
Created On: 04/13/18		Updated On:													
PAFFEL	P	NE	NE	21	39N	12W	Washburn	0-162-10-2014		0.0	0.0	1		2.652	1.004
55-65-010-PIT															
Created On: 02/10/14		Updated On:													
PALMER	P		SW	6	35N	17W	Polk	0-162-19-2016		0.0	0.0	1		2.645	0.725
55-48-020-PIT															
Created On: 01/25/16		Updated On:													
PAYNE AND DOLAN DOUSMAN	P		NE	1	6N	17E	Waukesha	0-162-4-2013		0.0	0.0	1		2.657	0.695
55-67-036-PIT															
Created On: 01/10/13		Updated On:													

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS	LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
PAYNE AND DOLAN DOUSMAN 55-67-036-PIT Created On: 01/05/18	P		NE	1	6N	17E	Waukesha	0-223-10-2018		0.0	0.0	1		2.633	1.092
Updated On:															
PELICAN PROJECT 55-52-020-PIT Created On: 09/30/11	P			32	9N	2E	Richland	0-162-43-2011		0.0	0.0	1		2.643	0.361
Updated On:															
PELICAN PROJECT 55-52-020-PIT Created On: 01/04/16	P			32	9N	2E	Richland	0-162-3-2016		0.0	0.0	1		2.628	0.442
Updated On:															
PETERS-WUSSOW 55-58-030-PIT Created On: 01/04/16	P			20	26N	18E	Shawano	0-162-12-2016		0.0	0.0	1		2.630	1.082
Updated On:															
PETERSON 55-09-052-PIT Created On: 01/03/18	P	NE	SW	32	29N	5W	Chippewa	0-223-1-2018		0.0	0.0	1		2.621	1.133
Updated On:															
PHILLIPS 55-50-019-PIT Created On: 07/18/16	P	SW	SW	5	37N	1E	Price	0-162-52-2016		0.0	0.0	1		2.637	1.061
Updated On:															
PINE LAKE MATERIALS 55-51-025-PIT Created On: 01/05/11	P		NE	35	3N	19E	Racine	0-162-4-2011		0.0	0.0	1		2.670	0.827
Updated On:															

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric					
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS	Plate	LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
PINE LAKE MATERIALS	P		NE	35	3N	19E	Racine	0-162-31-2016		0.0	0.0	1		2.634	1.502	
55-51-025-PIT		Created On: 03/28/16 Updated On:														
PINE VALLEY	Q		NW	21	24N	2W	Clark	0-162-21-2015		0.0	0.0	1		2.616	0.392	
55-10-027-QRY		Created On: 05/06/15 Updated On:														
PLOVER	P	SW	SW	5	22N	9E	Portage	0-162-12-2012		0.0	0.0	1		2.647	0.392	
55-49-019-PIT		Created On: 03/23/12 Updated On:														
PLOVER	P	SW	SW	5	22N	9E	Portage	0-223-16-2017		0.0	0.0			2.640	0.412	
55-49-019-PIT		Created On: 03/06/17 Updated On:														
PLOVER	P	SW	SW	5	22N	9E	Portage	0-223-34-2018		0.0	0.0	1		2.633	0.644	
55-49-019-PIT		Created On: 05/02/18 Updated On:														
PRAGER	P		N	SW	7	4N	19E	Racine	0-162-6-2014		0.0	0.0	1		2.678	0.472
55-51-026-PIT		Created On: 01/02/14 Updated On:														
PRAGER	P		N	SW	7	4N	19E	Racine	0-223-17-2019		0.0	0.0	1		2.649	1.276
55-51-026-PIT		Created On: 02/13/19 Updated On:														

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS Plate	LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
PRAIRIE AVE CONCRETE	P		SW 6		1N	13E	Rock	0-162-26-2012		0.0	0.0	1			0.503
55-53-030-PIT Created On: 05/17/12 Updated On:															
PRAIRIE AVE CONCRETE	P		SW 6		1N	13E	Rock	0-162-21-2016		0.0	0.0	1		2.623	0.949
55-53-030-PIT Created On: 02/17/16 Updated On:															
PRAVECHEK	P	W	SW 31		24N	24E	Kewaunee	0-162-30-2016		0.0	0.0	1		2.633	1.451
55-31-014-PIT Created On: 03/23/16 Updated On:															
PREFERRED SANDS - BLAIR	P	NE	NW 8		21N	7W	Trempealeau	0-162-22-2016		0.0	0.0	1		2.636	0.110
55-61-016-PIT Created On: 02/17/16 Updated On:															
R. THOMPSON	P		NE 4		37N	6W	Sawyer	0-162-28-2015		0.0	0.0	2		2.623	1.010
55-57-022-PIT Created On: 06/25/15 Updated On:															
RANDS	P	SE	NW 16		35N	6W	Rusk	0-162-12-2015		0.0	0.0	1		2.650	1.194
55-54-022-PIT Created On: 03/23/15 Updated On:															
REESE	P	SW	SW 22		17N	21E	Manitowoc	0-223-47-2019		0.0	0.0	1		2.749	0.766
55-36-034-PIT Created On: 07/01/19 Updated On:															

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS	LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
REESMAN CO. - BOLTON	P		SW 4	3N	18E	Walworth	0-162-27-2013		0.0	0.0	1		2.632	0.959	
55-64-020-PIT		Created On: 05/22/13 Updated On:													
REESMAN CO. - BOLTON	P		SW 4	3N	18E	Walworth	0-223-18-2018		0.0	0.0	1		2.643	1.174	
55-64-020-PIT		Created On: 02/21/18 Updated On:													
REESMAN CO. - RFD-2	P		SW 9	2N	19E	Racine	0-162-26-2013		0.0	0.0	1		2.564	2.135	
55-51-013-PIT		Created On: 05/22/13 Updated On:													
REESMAN CO. - RFD-2	P		SW 9	2N	19E	Racine	0-223-17-2018		0.0	0.0	1		2.637	0.929	
55-51-013-PIT		Created On: 02/21/18 Updated On:													
REUCKERTS	P		NE 21	26N	17E	Shawano	0-162-13-2015		0.0	0.0	1		2.677	0.725	
55-58-032-PIT		Created On: 04/01/15 Updated On:													
REYNOLDS PIT	P		SE 19	8N	2W	Grant	0-162-26-2011		0.0	0.0	1		2.637	0.140	
55-22-043-PIT		Created On: 05/13/11 Updated On:													
REYNOLDS PIT	P		SE 19	8N	2W	Grant	0-223-26-2017		0.0	0.0	1		2.621	0.371	
55-22-043-PIT		Created On: 05/25/17 Updated On:													

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS	LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
REYNOLDS PIT	P		SE	19	8N	2W	Grant	0-223-33-2017		0.0	0.0	1		2.625	0.523
55-22-043-PIT															
Created On: 08/02/17		Updated On:													
RIB RIVER	P	NW	SW	36	29N	5E	Marathon	0-162-9-2011		0.0	0.0	1		2.627	0.929
55-37-068-PIT															
Created On: 01/20/11		Updated On:													
RIB RIVER	P	NW	SW	36	29N	5E	Marathon	0-162-38-2011		0.0	0.0	1		2.645	0.503
55-37-068-PIT															
Created On: 07/20/11		Updated On:													
RIB RIVER	P	NW	SW	36	29N	5E	Marathon	0-162-40-2012		0.0	0.0	1		2.618	1.000
55-37-068-PIT															
Created On: 07/25/12		Updated On:													
RIB RIVER	P	NW	SW	36	29N	5E	Marathon	0-162-25-2016		0.0	0.0	1		2.610	1.133
55-37-068-PIT															
Created On: 02/29/16		Updated On:													
RICHMOND	P	NW	NW	15	3N	15E	Walworth	0-162-17-2016		0.0	0.0	1		2.635	2.354
55-64-035-PIT															
Created On: 01/07/16		Updated On:													
RILEY	P	NW	SW	19	14N	7E	Adams	0-162-18-2015		0.0	0.0	1		2.648	0.644
55-01-007-PIT															
Created On: 04/22/15		Updated On:													

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric			
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
RISNER	P	S	SW	16	30N	20E	Marinette	0-223-44-2018		0.0	0.0	1		2.679	0.705
55-38-029-PIT															
Created On: 06/18/18		Updated On:													
RIVARD	Q	SE	NE	12	30N	20W	St. Croix	0-162-34-2016		0.0	0.0	1		2.628	0.867
55-55-012-QRY															
Created On: 03/30/16		Updated On:													
RIVARD	Q	SE	NE	12	30N	20W	St. Croix	0-223-4-2018		0.0	0.0	1		2.623	0.847
55-55-012-QRY															
Created On: 01/03/18		Updated On:													
ROBERTSON	P	NW	SW	11	52N	17W	St Louis	0-162-28-2016		0.0	0.0	1		2.710	1.163
27-00-014-PIT															
Created On: 03/16/16		Updated On:													
* ROFFERS	Q	NE	NW	18	45N	11W	Douglas	0-162-49-2016		0.0	0.0	1		2.701	2.566
55-16-024-QRY															
Created On: 05/11/16		Updated On:													
ROGERS	P		SW	9	46N	2E	Winnebago II	0-223-41-2019		0.0	0.0	1		2.620	1.174
17-00-013-PIT															
Created On: 05/31/19		Updated On:													
ROLLMAN	P	NE	NW	11	35N	8E	Lincoln	0-223-36-2019		0.0	0.0	1		2.643	1.020
55-99-001-PIT															
Created On: 04/25/19		Updated On:													

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric						
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%)		Sp. Gravity		Absorp. %		
												100	500	Crse	Fine	Crse	Fine	
ROSE STONE	Q	SE	SE	30	35N	10W	Barron	0-162-25-2015		0.0	0.0	1			2.617		0.070	
55-03-032-QRY																		
Created On: 05/19/15		Updated On:																
ROSENBAUM	P	SW	NE	18	5N	11E	Dane	0-162-42-2011		0.0	0.0	1			2.645		0.533	
55-13-078-PIT																		
Created On: 09/16/11		Updated On:																
ROSENBAUM	P	SW	NE	18	5N	11E	Dane	0-162-24-2016		0.0	0.0	1			2.631		1.122	
55-13-078-PIT																		
Created On: 02/19/16		Updated On:																
SAFFERT 795	P	SW	SW	1	34N	11W	Barron	0-162-27-2011		0.0	0.0	1			2.639		0.392	
55-03-034-PIT																		
Created On: 05/13/11		Updated On:																
SAFFERT 795	P	SW	SW	1	34N	11W	Barron	0-162-51-2016		0.0	0.0	1			2.629		0.806	
55-03-034-PIT																		
Created On: 06/30/16		Updated On:																
SAMBS STONE	P	NW	NW	11	30N	11E	Langlade	0-162-10-2015		0.0	0.0	1			2.669		0.513	
55-34-022-PIT																		
Created On: 03/20/15		Updated On:																
SCHADLER	P	NE	SE	10	8N	6E	Dane	0-162-36-2013		0.0	0.0	1			2.639		0.735	
55-13-081-PIT																		
Created On: 07/11/13		Updated On:																

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine		
SCHADLER	P	NE	SE	10	8N	6E	Dane	0-223-2-2018		0.0	0.0	1		2.629	0.827	
55-13-081-PIT		Created On: 01/03/18 Updated On:														
SCHREINER	P		SE	1	32N	2E	Taylor	0-223-5-2018		0.0	0.0	1		2.661	1.010	
55-60-022-PIT		Created On: 01/03/18 Updated On:														
SCHRICKER	P	NE	SW	4	38N	12W	Washburn	0-162-39-2014		0.0	0.0	1		2.644	0.817	
55-65-013-PIT		Created On: 10/22/14 Updated On:														
SCHRICKER	P	NE	SW	4	38N	12W	Washburn	0-223-31-2019		0.0	0.0	1		2.638	0.959	
55-65-013-PIT		Created On: 04/09/19 Updated On:														
* SILVER LAKE	P	SE	NE	11	42N	10E	Vilas	0-162-17-2014		0.0	0.0	1		2.658	0.583	
55-63-019-PIT		Created On: 04/09/14 Updated On:														
SMITH	P	NE	SE	20	22N	3W	Jackson	0-162-5-2012		0.0	0.0	1		2.627	0.402	
55-27-011-PIT		Created On: 01/19/12 Updated On:														
SMITH	P	NE	SE	20	22N	3W	Jackson	0-162-27-2012		0.0	0.0	1		2.638	0.220	
55-27-011-PIT		Created On: 05/17/12 Updated On:														

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric			
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
SMITH	P	NE	SE	20	22N	3W	Jackson	0-223-26-2019		0.0	0.0	1		2.640	0.381
55-27-011-PIT Created On: 03/27/19 Updated On:															
SPILE	P		N	17	6N	11E	Dane	0-162-28-2014		0.0	0.0	1		2.653	1.061
55-13-085-PIT Created On: 07/17/14 Updated On:															
SPILE	P		N	17	6N	11E	Dane	0-162-36-2015		0.0	0.0	1		2.642	1.061
55-13-085-PIT Created On: 08/13/15 Updated On:															
SPILE	P		N	17	6N	11E	Dane	0-223-22-2017		0.0	0.0	1		2.618	1.041
55-13-085-PIT Created On: 05/01/17 Updated On:															
STELTER	P	SW	SW	5	30N	8W	Chippewa	0-223-17-2017		0.0	0.0	1		2.653	1.133
55-09-065-PIT Created On: 03/29/17 Updated On:															
STEWART	P	NW	SE	16	40N	17W	Burnett	0-162-35-2016		0.0	0.0	1		2.624	0.594
55-07-013-PIT Created On: 03/30/16 Updated On:															
STIEBS	P	S	SE	36	23N	12E	Waupaca	0-162-24-2013		0.0	0.0	1		2.654	0.170
55-68-027-PIT Created On: 05/15/13 Updated On:															

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	Crse	Fine	Crse	Fine
STIEBS	P	S	SE	36	23N	12E	Waupaca	0-223-23-2017		0.0	0.0	1			2.640		0.381
55-68-027-PIT																	
Created On: 05/04/17		Updated On:															
STORR'S	P	E	SW	25	4N	13E	Rock	0-223-29-2017		0.0	0.0	1			2.593		1.719
55-53-037-PIT																	
Created On: 06/07/17		Updated On:															
STOUGHTON	P	E	NW	10	5N	11E	Dane	0-223-1-2019		0.0	0.0	1			2.648		1.092
55-13-001-PIT																	
Created On: 01/02/19		Updated On:															
STRENKE	P	NW	NW	5	35N	15W	St Croix	0-162-9-2015		0.0	0.0	1			2.662		0.888
55-55-002-PIT																	
Created On: 03/20/15		Updated On:															
* STUCZYNSKI (DUFFEK)	P	NE	NW	4	23N	9E	Portage	0-162-18-2012		0.0	0.0	1			2.632		0.604
55-49-024-PIT																	
Created On: 04/10/12		Updated On:															
SUPER AGGREGATE - BURGETT LAKES	P		SE	1	46N	7E	Mchenry	0-162-23-2016		0.0	0.0	1			2.633		1.215
17-00-007-PIT																	
Created On: 02/19/16		Updated On:															
SUPER AGGREGATE / WATERFORD	P	SW	SE	28	4N	19E	Racine	0-162-4-2014		0.0	0.0	1			2.640		0.776
55-51-028-PIT																	
Created On: 01/02/14		Updated On:															

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%)		Sp. Gravity		Absorp. %
											100	500	Crse	Fine	Crse	Fine
SUPER AGGREGATE / WATERFORD	P	SW	SE	28	4N	19E	Racine	0-223-20-2019		0.0	0.0	1			2.623	1.031
55-51-028-PIT																
Created On: 02/14/19 Updated On:																
SUPER AGGREGATE-SUGAR CREEK	P	SE	NW	9	3N	16E	Walworth	0-162-29-2014		0.0	0.0	1			2.633	1.204
55-64-037-PIT																
Created On: 07/23/14 Updated On:																
SUPER AGGREGATE-SUGAR CREEK	P	SE	NW	9	3N	16E	Walworth	0-223-21-2019		0.0	0.0	1			2.640	0.827
55-64-037-PIT																
Created On: 02/14/19 Updated On:																
SWAGEL	P		N	29	23N	24E	Kewaunee	0-162-29-2016		0.0	0.0	1			2.672	1.389
55-31-017-PIT																
Created On: 03/23/16 Updated On:																
SWAGEL	P		N	29	23N	24E	Kewaunee	0-223-38-2017		0.0	0.0	1			2.674	1.358
55-31-017-PIT																
Created On: 11/08/17 Updated On:																
TAGGE	P		NE	31	27N	26E	Door	0-162-1-2012		0.0	0.0	1			2.626	1.000
55-15-023-PIT																
Created On: 01/11/12 Updated On:																
TAGGE	P		NE	31	27N	26E	Door	0-223-3-2017		0.0	0.0	1			2.690	1.143
55-15-023-PIT																
Created On: 02/13/17 Updated On:																

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%)		Sp. Gravity		Absorp. %	
												100	500	Crse	Fine	Crse	Fine
THEILER	P	NE	SE	2	34N	6E	Lincoln	0-162-18-2016		0.0	0.0	1			2.635		0.949
	55-35-035-PIT Created On: 01/07/16 Updated On:																
* THELEN S & G	P			9	46N	9E	Lake	0-162-12-2011		0.0	0.0	1			2.620		0.786
	17-00-002-PIT Created On: 02/16/11 Updated On:																
* THELEN S & G	P			9	46N	9E	Lake	0-162-25-2014		0.0	0.0	1			2.641		0.990
	17-00-002-PIT Created On: 06/13/14 Updated On:																
THELEN-ANTIOCH	P			9	46N	9E	Lake	0-223-36-2018		0.0	0.0	1			2.621		1.317
	17-00-002-PIT Created On: 05/10/18 Updated On:																
THELEN-LANGE ROAD	P	SE	SE	32	1N	18E	Walworth	0-162-24-2014		0.0	0.0	1			2.664		0.817
	55-64-025-PIT Created On: 06/13/14 Updated On:																
THELEN-LANGE ROAD	P	SE	SE	32	1N	18E	Walworth	0-223-37-2018		0.0	0.0	1			2.643		1.082
	55-64-025-PIT Created On: 05/10/18 Updated On:																
THIEL	P	NE	NW	5	22N	13E	Waupaca	0-162-15-2013		0.0	0.0	1			2.654		0.371
	55-68-028-PIT Created On: 04/19/13 Updated On:																

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric			
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
THOMPSON BARRON	P	S	SE	35	36N	13W	Barron	0-162-33-2011		0.0	0.0	1		2.673	0.583
55-03-037-PIT Created On: 06/16/11 Updated On:															
THOMPSON BARRON	P	S	SE	35	36N	13W	Barron	0-223-25-2017		0.0	0.0	1		2.657	0.735
55-03-037-PIT Created On: 05/25/17 Updated On:															
TIMBERLANE S & G	P	NW	SW	19	6N	14E	Jefferson	0-162-11-2012		0.0	0.0	1		2.668	0.746
55-28-015-PIT Created On: 03/23/12 Updated On:															
TIMBERLANE S & G	P	NW	SW	19	6N	14E	Jefferson	0-223-29-2018		0.0	0.0	1		2.648	0.634
55-28-015-PIT Created On: 04/11/18 Updated On:															
TOWER	P	W	NE	34	31N	20E	Marinette	0-162-5-2011		0.0	0.0	1		2.690	0.574
55-38-036-PIT Created On: 01/05/11 Updated On:															
TOWNLINE	P	NE	NE	1	1N	12E	Rock	0-162-7-2013		0.0	0.0	1		2.651	0.594
55-53-038-PIT Created On: 01/25/13 Updated On:															
TOWNLINE	P	NE	NE	1	1N	12E	Rock	0-162-41-2016		0.0	0.0	1		2.612	1.184
55-53-038-PIT Created On: 04/14/16 Updated On:															

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric			
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
TOWNLINE	P	NE	NE	1	1N	12E	Rock	0-223-12-2018		0.0	0.0	1		2.617	1.061
55-53-038-PIT															
Created On: 01/24/18		Updated On:													
TOWNLINE	P	NE	NE	1	1N	12E	Rock	0-223-6-2019		0.0	0.0	1		2.621	1.000
55-53-038-PIT															
Created On: 01/02/19		Updated On:													
TURNER	P	NW	SW	27	3N	5W	Grant	0-223-27-2019		0.0	0.0	1		2.641	0.553
55-22-053-PIT															
Created On: 03/27/19		Updated On:													
TWIN PORTS	P		NE	3	50N	16W	St Louis	0-162-45-2016		0.0	0.0	1		2.681	1.523
27-00-016-PIT															
Created On: 04/25/16		Updated On:													
UNION	P	SW	NW	36	26N	23E	Door	0-162-32-2015		0.0	0.0	1		2.662	0.857
55-15-024-PIT															
Created On: 07/15/15		Updated On:													
UTECHT	P	NE	NE	21	30N	18W	St. Croix	0-162-6-2015		0.0	0.0	1		2.648	0.847
55-55-018-PIT															
Created On: 01/16/15		Updated On:													
VEUM	P	NE	NW	35	28N	10W	Chippewa	0-223-12-2019		0.0	0.0	1		2.565	1.051
55-09-068-PIT															
Created On: 01/02/19		Updated On:													

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric			
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS Plate				LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
VOGHT	P	NE	NE	18	1N	2W	Grant	0-162-22-2014		0.0	0.0	1		2.638	0.594
55-22-057-PIT															
Created On: 05/15/14		Updated On:													
VOGHT	P	NE	NE	18	1N	2W	Grant	0-223-35-2019		0.0	0.0			2.597	1.020
55-22-057-PIT															
Created On: 04/19/19		Updated On:													
VOLENBERG	P		NW	19	6N	12E	Dane	0-162-23-2012		0.0	0.0	1		2.609	1.606
55-13-100-PIT															
Created On: 04/23/12		Updated On:													
VOLENBERG	P		NW	19	6N	12E	Dane	0-162-7-2016		0.0	0.0	1		2.626	1.225
55-13-100-PIT															
Created On: 01/04/16		Updated On:													
WABASHA SAND & GRAVEL	P			32	11N	10W	Wabasha	0-162-29-2012		0.0	0.0	1		2.617	0.624
27-00-020-PIT															
Created On: 05/24/12		Updated On:													
WABASHA SAND & GRAVEL	P			32	11N	10W	Wabasha	0-162-9-2014		0.0	0.0	1		2.644	0.624
27-00-020-PIT															
Created On: 02/10/14		Updated On:													
WABASHA SAND & GRAVEL	P			32	11N	10W	Wabasha	0-223-23-2019		0.0	0.0	1		2.634	0.725
27-00-020-PIT															
Created On: 03/25/19		Updated On:													

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description								Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric					
	P/Q	Qrt	Qrt	Sect	Town	Range	County	% Test SDS				LA Wear (%)	Sp. Gravity	Absorp. %			
												100	500	Crse	Fine	Crse	Fine
WAUCOUSTA RADEMANN	P	S	SW	33	14N	19E	Fond Du Lac	0-162-19-2011		0.0	0.0	1			2.701		1.112
55-20-049-PIT																	
Created On: 04/19/11 Updated On:																	
WAUCOUSTA RADEMANN	P	S	SW	33	14N	19E	Fond Du Lac	0-162-57-2016		0.0	0.0	1			2.804		0.898
55-20-049-PIT																	
Created On: 08/08/16 Updated On:																	
WEILAND	P		W	9	6N	8E	Dane	0-223-21-2018		0.0	0.0	1			2.629		1.225
55-13-118-PIT																	
Created On: 03/14/18 Updated On:																	
WEST BEND S & G	P	SW	SE	8	11N	19E	Washington	0-162-13-2014		0.0	0.0	1			2.710		0.583
55-66-020-PIT																	
Created On: 03/27/14 Updated On:																	
WEST BEND S & G	P	SW	SE	8	11N	19E	Washington	0-223-25-2019		0.0	0.0	1			2.704		0.796
55-66-020-PIT																	
Created On: 03/27/19 Updated On:																	
WICKERT	P	NE	NW	24	22N	14E	Waupaca	0-223-23-2018		0.0	0.0	1			2.629		0.725
55-68-034-PIT																	
Created On: 03/23/18 Updated On:																	
WIESER	Q	E	NE	9	25N	16W	Pierce	0-223-30-2017		0.0	0.0	1			2.604		0.908
55-47-033-QRY																	
Created On: 06/14/17 Updated On:																	

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric					
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS	Plate	LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
WIESER	P		NE	9	25N	16W	Pierce	0-223-43-2019		0.0	0.0	1		2.625	0.857	
55-47-033-PIT		Created On: 06/10/19 Updated On:														
WILBER	P	NW	SW	19	18N	8W	Trempealeau	0-223-42-2019		0.0	0.0	1		2.627	0.594	
55-61-022-PIT		Created On: 06/10/19 Updated On:														
WIMMIE	P		NW	28	23N	9E	Portage	0-162-14-2011		0.0	0.0	1		2.639	0.271	
55-49-026-PIT		Created On: 03/16/11 Updated On:														
WIMMIE	P		NW	28	23N	9E	Portage	0-162-13-2016		0.0	0.0	1		2.648	0.412	
55-49-026-PIT		Created On: 01/04/16 Updated On:														
* WINGRA (WEILAND-MARTY)	Q	NW	SW	9	6N	8E	Dane	0-162-20-2014		0.0	0.0	1		2.644	0.888	
55-13-103-QRY		Created On: 05/15/14 Updated On:														
WINONA SAND & GRAVEL	P		SE	12	107N	8W	Winona	0-162-28-2012		0.0	0.0	1		2.685	0.381	
27-00-025-PIT		Created On: 05/24/12 Updated On:														
WINONA SAND & GRAVEL	P		SE	12	107N	8W	Winona	0-223-27-2017		0.0	0.0	1		2.633	0.634	
27-00-025-PIT		Created On: 05/26/17 Updated On:														

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric				
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS	LA Wear (%) 100 500	Sp. Gravity Crse Fine	Absorp. % Crse Fine	
WINONA SAND & GRAVEL	P		SE	12	107N	8W	Winona	0-223-16-2018		0.0	0.0	1		2.627	0.573
27-00-025-PIT															
Created On: 02/15/18		Updated On:													
WINONA SAND & GRAVEL	P		SE	12	107N	8W	Winona	0-223-24-2019		0.0	0.0	1		2.637	0.523
27-00-025-PIT															
Created On: 03/25/19		Updated On:													
WISSOTA RUGBY S&G	P	SE	NE	34	10N	19E	Washington	0-162-12-2014		0.0	0.0	1		2.679	0.817
55-66-021-PIT															
Created On: 02/17/14		Updated On:													
WISSOTA RUGBY S&G	P	SE	NE	34	10N	19E	Washington	0-223-5-2019		0.0	0.0	1		2.686	0.746
55-66-021-PIT															
Created On: 01/02/19		Updated On:													
WOLF	P		E	6	6N	18E	Waukesha	0-223-18-2017		0.0	0.0	1		2.649	1.031
55-67-043-PIT															
Created On: 04/05/17		Updated On:													
ZANDER	P	NW	SW	11	7N	7E	Dane	0-162-33-2013		0.0	0.0	1		2.688	0.553
55-13-109-PIT															
Created On: 07/10/13		Updated On:													
ZANDER	P	NW	SW	11	7N	7E	Dane	0-223-22-2018		0.0	0.0	1		2.650	0.664
55-13-109-PIT															
Created On: 03/14/18		Updated On:													

APPROVED FINE AGGREGATE SOURCE Sorted by Source Name

Date Printed: 10/01/2019

Report Date Range 2011 AND 2019 For Site 0

* = Not Certified

Source Name	Location Description							Test Number	% Light weight Pieces	Freeze Thaw %	Colorimetric			Sp. Gravity		Absorp. %		
	P/Q	Qrt	Qrt	Sect	Town	Range	County				% Test SDS Plate	LA Wear (%) 100	LA Wear (%) 500	Crse	Fine	Crse	Fine	
ZANDER	P	NW	SW	11	7N	7E	Dane	0-223-4-2019		0.0	0.0	1			2.663		1.000	
55-13-109-PIT																		
Created On: 01/02/19		Updated On:																
* ZILLGES	P	SE	SW	20	18N	14E	Winnebago	0-162-30-2014		0.0	0.0	1			2.680		0.604	
55-70-037-PIT																		
Created On: 07/23/14		Updated On:																

Prepared by:

Wisconsin Department of Transportation
 Bureau of Highway Construction
 Quality Management Section