



# Wisconsin Department of Transportation

April 3, 2019

## Division of Transportation Systems Development

Bureau of Project Development  
4822 Madison Yards Way, 4<sup>th</sup> Floor South  
Madison, WI 53705

Telephone: (608) 266-1631  
Facsimile (FAX): (608) 266-8459

### NOTICE TO ALL CONTRACTORS:

<p><b>Proposal #21: 1009-42-70</b>  <b>Regionwide Culvert Replacement</b>  <b>Wood County Culverts</b>  <b>Var Hwy</b>  <b>Wood County</b></p>	<p><b>6841-00-60, WISC 2019 229</b>  <b>Fremont – Appleton</b>  <b>Wolf River Bridge B-68-31</b>  <b>STH 110</b>  <b>Waupaca County</b></p>	<p><b>1009-42-73</b>  <b>Regionwide Culvert Replacement</b>  <b>Waupaca County Culverts</b>  <b>Var Hwy</b>  <b>Waupaca County</b></p>
--	---	--

### Letting of April 9, 2019

This is Addendum No. 02, which provides for the following:

#### Special Provisions:

Added Special Provisions	
Article No.	Description
37	Cleaning Parapets, Item 509.9050.S

The responsibility for notifying potential subcontractors and suppliers of these changes remains with the prime contractor.

Sincerely,

*Mike Coleman*

Proposal Development Specialist  
Proposal Management Section

**ADDENDUM NO. 02**  
**1009-42-70, 1009-42-73, 6841-0060**  
**April 3, 2019**

**Special Provisions**

**37. Cleaning Parapets, Item 509.9050.S.**

**A Description**

This special provision describes cleaning the inside faces and top surface of the concrete parapet as the plans show and as the engineer directs.

**B (Vacant)**

**C Construction**

**C.1 Blast Cleaning Operation**

Blast clean the inside face and top surface of the concrete parapet according to SSPC SP-13 and ASTM D4259 for an abrasive blast cleaning to a surface roughness and finish as the engineer directs. Before abrasive blast cleaning operations are to begin for the entire bridge parapet, prepare a representative trial area on the parapet concrete surface, and have the method of blast cleaning approved by the engineer.

**C.2 Water Cleaning Operation**

After abrasive blast cleaning operations are completed, clean the prepared parapet surface with water according to ASTM D4258. Remove with this water cleaning all dust and loose material from the parapet inside face and top that is to be coated with pigmented surface sealer. Provide an adequate drying time of the parapet inside face and top surface of at least 24 hours before coating with the pigmented surface sealer. Remove all loose concrete, dirt, dust, or blast material that remains on the bridge deck, as the engineer directs.

**D Measurement**

The department will measure Cleaning Parapets in length by the linear foot of parapet, acceptably cleaned.

**E Payment**

The department will pay for measured quantities at the contract unit price under the following bid item:

ITEM NUMBER	DESCRIPTION	UNIT
509.9050.S	Cleaning Parapets	LF

Payment is full compensation for abrasive blast cleaning; for water cleaning; and for all additional clean up of the concrete surface and surrounding bridge deck area.

stp-509-050 (20151210)

END OF ADDENDUM