

February 19, 2021

NOTICE TO ALL CONTRACTORS:

Proposal #27: 8080-02-61, WISC 2021 108 City of Hudson, Second Street Front Street to Vine Street STH 35 St. Croix County

> 8080-02-71, WISC 2021 109 City of Hudson, Second Street Coulee Rd/Buckeye St Intersection STH 35 St. Croix County

8080-05-70, WISC 2021 110 V North Hudson, 6th Street Lake Mallalieu Bridge – Sommers St STH 35 St. Croix County

8080-07-70, WISC 2021 112 City of Hudson, Second Street Vine Street to Willow River STH 35 St. Croix County Division of Transportation Systems Development Bureau of Project Development 4822 Madison Yards Way, 4th Floor South Madison, WI 53705

Telephone: (608) 266-1631 Facsimile (FAX): (608) 266-8459

8080-02-60 C Hudson, Second Street Front Street to Vine Street STH 35 St. Croix County

8080-02-73, WISC 2021 110 V North Hudson, 6th Street North Sommers Street to North End Road STH 35 St. Croix County

8080-05-7 V North Hudson, 6th Street Lake Mallalieu Bridge – Sommers St STH 35 St. Croix County

8080-07-72 City of Hudson, Second Street Vine Street to Willow River STH 35 St. Croix County

Letting of March 9, 2021

This is Addendum No. 01, which provides for the following:

Special Provisions

Revised Special Provisions		
Article	Description	
No.	Description	
22	Concrete Pavement	

The responsibility for notifying potential subcontractors and suppliers of these changes remains with the prime contractor.

Sincerely,

Mike Coleman

Proposal Development Specialist Proposal Management Section

ADDENDUM NO. 01

8080-02-60. 8080-02-61, 8080-07-72, 8080-02-73, 8080-05-70, 8080-05-72, 8080-07-70 & 8080-07-72 February 19, 2021

Special Provisions

22. Concrete Pavement.

Replace entire article language with the following:

Supplement standard spec 715.2 with the following:

- If the geological composition of the coarse aggregate is primarily igneous or metamorphic materials, modify and supplement standard spec 415, standard spec 710, and standard spec 715 with the following:
 - 1. Concrete placed after September 30 will meet the following requirements: for binary mixes use up to 15% fly ash or slag, except for slip-formed work the contractor may use up to 20% slag and for ternary mixes use up to 25% fly ash and slag in combination. Replacement values are in percent by weight of the total cementitious material in the mix.
 - 2. One hundred percent (100%) of the aggregate shall pass the 1 1/4-inch sieve.
 - 3. Ninety-five percent (95%) of the aggregate shall pass the 1-Inch sieve.
- Use of recycled concrete for coarse aggregate will not be allowed.

END OF ADDENDUM